

INTERNATIONAL STANDARD

**ISO
3387**

Second edition
1994-06-01

Rubber — Determination of crystallization effects by hardness measurements

iTe Standards
Caoutchouc — Détermination des effets de la cristallisation au moyen de
mesurages de dureté
(<https://standards.iteh.ai>)
Document Preview

[ISO 3387:1994](#)

<https://standards.iteh.ai/catalog/standards/iso/7da30443-6610-49d3-a435-4ec8a33c388/iso-3387-1994>



Reference number
ISO 3387:1994(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 3387 was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 2, *Physical and degradation tests*.

This second edition cancels and replaces the first edition (ISO 3387:1978), of which it constitutes a minor revision.

[ISO 3387:1994](https://standards.iteh.ai/iso-3387-1994)

<https://standards.iteh.ai/catalog/standards/iso/7da30443-6610-49d3-a435-4ec8a33c38f8/iso-3387-1994>

© ISO 1994

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization
Case Postale 56 • CH-1211 Genève 20 • Switzerland

Printed in Switzerland

Rubber — Determination of crystallization effects by hardness measurements

1 Scope

This International Standard specifies a test based on hardness measurements for determining the progressive stiffening of rubber with time, caused by crystallization. It is limited to materials having an initial hardness at test temperature of 10 IRHD to 85 IRHD.

The method is applicable to raw, unvulcanized (compounded), and vulcanized rubber. It is mainly of interest for rubber with a marked crystallization tendency at temperatures experienced in cold climates, such as, for instance, chloroprene and natural rubber.

The method is not applicable to fast-crystallizing materials which crystallize to a considerable degree within the time-span of 15 min used for conditioning at test temperature.

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this International Standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 48:1994, *Rubber, vulcanized or thermoplastic — Determination of hardness (hardness between 10 IRHD and 100 IRHD)*.

ISO 471:—¹⁾, *Rubber — Times, temperatures and humidities for conditioning and testing*.

ISO 1826:1981, *Rubber, vulcanized — Time-interval between vulcanization and testing — Specification*.

ISO 3383:1985, *Rubber — General directions for achieving elevated or subnormal temperatures for test purposes*.

ISO 4661-1:1993, *Rubber, vulcanized or thermoplastic — Preparation of samples and test pieces — Part 1: Physical tests*.

3 Principle

One of the following measurements is made on a test piece stored at the desired temperature:

- the increase in hardness after a specified storage time;
- the time required for a specified increase in hardness to occur.

Tests may be carried out on test pieces of different thicknesses. These do not necessarily give the same values of hardness readings. Tests intended to be comparable shall be made on test pieces of the same thickness.

The different methods of calculating data to be reported may give somewhat different values. Comparisons of values obtained with different methods shall be avoided.

1) To be published. (Revision of ISO 471:1983)

4 Apparatus

4.1 Cold chamber, in accordance with ISO 3383, capable of being maintained within ± 1 °C of the specified temperature and using a gaseous heat-transfer medium.

As all final handling and measurements are to be made within the cold chamber, it shall be possible to perform these operations while the test piece temperature remains within the permissible variations. This may be done by providing suitable equipment which permits manipulation of materials within the chamber from the outside (for example by means of handholes and gloves through the door or wall of the cabinet).

4.2 Hardness gauges, in accordance with ISO 48. Lubricants, if used, shall be of a type not causing friction in the instrument at test temperature.

4.3 Tweezers or tongs, for handling of the test pieces.

4.4 Gloves, for handling of the test equipment.

4.5 Heated press, for the preparation of raw and unvulcanized (compounded) test pieces.

5 Test pieces

5.1 Dimensions

The test piece shall have its upper and lower surfaces flat, smooth and parallel to one another. The standard test piece shall be 8 mm to 10 mm thick. Non-standard test pieces may be either thicker or thinner, but in no case shall the test piece be thinner than 4 mm for hardnesses between 35 IRHD and 100 IRHD, or thinner than 6 mm for hardnesses between 10 IRHD and 35 IRHD. The lateral dimensions of both standard and non-standard test pieces shall be such that no test is made at a distance from the edge of the test piece less than the appropriate distance shown in table 1.

Table 1

Dimensions in millimetres

Total thickness of test piece	Minimum distance from point of contact to edge of test piece
4	7,0
6	8,0
8	9,0
10	10,0
15	11,5
25	13,0

5.2 Preparation — Vulcanized rubber

Test pieces of vulcanized rubber shall be prepared in accordance with ISO 4661-1. To obtain the necessary thickness, it is permissible to superimpose two pieces of rubber (but no more than two) provided that these have flat, parallel surfaces.

5.3 Preparation — Raw and unvulcanized rubber

Test pieces of raw and of unvulcanized (compounded) rubber shall be prepared by placing a suitable quantity in a preheated mould and then applying heat and pressure for a suitable time (see 4.5).

The mould, still under pressure, shall be cooled to standard temperature (see ISO 471). After 15 min, the pressure shall be released and the test piece removed. It shall be free from blisters and porosity.

Values of mould temperature and time of application of pressure required to produce a suitable test piece depend upon the type of rubber. A temperature of 150 °C applied for 10 min has been found suitable for many raw rubbers, whilst a temperature of 120 °C applied for 3 min has been found satisfactory for many compounded rubbers. However, for some materials, longer times or higher mould temperatures may be found necessary to ensure a smooth and flat test piece surface. Under no circumstances shall conditions be used that cause incipient cure or degradation.

5.4 Conditioning

5.4.1 Time-interval between vulcanization and testing

When appropriate, the time-interval between

vulcanization and testing shall be in accordance with ISO 1826.

5.4.2 Decrystallization and conditioning

Test pieces of vulcanized rubber or test pieces moulded from raw or unvulcanized (compounded) rubber kept for more than 8 h after moulding before testing shall be decrystallized immediately before testing by heating them in an oven at 70 °C for 45 min. They shall then be conditioned at standard temperature (see ISO 471) for at least 30 min and no more than 60 min before testing.

6 Procedure

6.1 Hardness measurement

Carry out hardness measurement in accordance with ISO 48. Make one measurement at either three or five different points distributed over the test piece and take the median of the results. Make each reading at a point at least 4 mm away from points where any previous readings have been made.

The same hardness gauge shall be used throughout any one test, the appropriate gauge being determined from the initial hardness at test temperature. For initial hardnesses between 10 IRHD and 30 IRHD, the instrument specified for method L of ISO 48:1994 shall be used, for initial hardnesses between 30 IRHD and 80 IRHD the instrument specified for method N of ISO 48:1994 shall be used and for hardnesses over 80 IRHD, the instrument specified for method H of ISO 48:1994 shall be used. If the hardness increase gives values above 35 IRHD for method L, the hardness readings shall be determined from an extension to table 5 of ISO 48:1994, calculated using the equation given in annex A of that standard.

6.2 Original hardness

First measure the hardness with the test piece and test equipment conditioned at the standard temperature (see ISO 471). This measurement gives additional information but is not used in the calculation of crystallization effects and may be omitted for highly plastic samples of unvulcanized rubber.

6.3 Initial hardness at test temperature

Condition the hardness gauge (4.2) and the tweezers or tongs (4.3) in the cold chamber (4.1) at the desired test temperature for at least 60 min.

Place the test piece in the cold chamber at the desired test temperature. After 15 min \pm 1 min, take the first hardness reading, using the tweezers or tongs for handling the test piece and the gloves (4.4) for handling the test equipment. If the initial hardness reading is above 85 IRHD, the method is not applicable.

NOTE 1 The hardness gauge used in this test procedure is normally conditioned and operated inside the cold chamber. Alternatively, a special device may be used where the body of the hardness gauge is placed outside the cold chamber and connected with the indentor in the cold chamber by means of a rod with low heat-conductive capacity, and constructed to avoid the introduction of additional friction.

6.4 Hardness increase due to crystallization

Repeat the hardness measurements, as specified in 6.1, after the specified times of storage at test temperature.

NOTE 2 After all measurements have been completed, it is advisable to dry all apparatus by warming it with circulating air to approximately 40 °C.

7 Temperature and duration of test

7.1 Temperature

The test shall be carried out at one of the following temperatures (see ISO 471):

+ 23 °C \pm 2 °C (standard temperature)

+ 27 °C \pm 2 °C (standard temperature)

+ 10 °C \pm 1 °C

0 °C \pm 1 °C

- 10 °C \pm 1 °C

- 25 °C \pm 1 °C

- 40 °C \pm 1 °C

- 55 °C \pm 1 °C

- 70 °C \pm 1 °C

If not specified for special reasons, the test shall be carried out at the temperature which is closest to the one where the crystallization rate is at its maximum, whenever this is known.

NOTE 3 Generally crystallization rates are known to have their maxima at the following approximate temperatures:

Rubber polymer	Temperature of maximum crystallization	
	rate	°C
Chloroprene rubber	—	— 10
Polyurethane rubber	—	— 10
Natural rubber (1,4-cis-polyisoprene)	—	— 25
Dimethyl silicone rubber	—	— 55
1,4-cis-polybutadiene	—	— 55

7.2 Duration

Hardness measurements are generally taken after (24 $^{+0}_{-0,5}$) h and (168 $^{+0}_{-2}$) h of storage at the test temperature. Intermediate times of reading that enable the hardness to be plotted against time shall be used (48 h and 96 h are suggested). Longer times of storage may be used if hardness is still increasing at 168 h.

If the hardness increase after (24 $^{+0}_{-0,5}$) h is more than 10 IRHD above the reading of initial hardness, the test shall be repeated using shorter times of storage (1 h, 2 h, 4 h and 8 h are suggested).

8 Expression of results

ISO 3387:1994

<https://standards.iteh.ai/catalog/standards/iso/7da30443-6610-49d3-a435-4ec8a33c3818/iso-3387-1994>

8.1 For specification purposes, the hardness increase between the initial hardness reading and the reading taken after (168 $^{+0}_{-2}$) h storage shall be calculated and stated in the test report (see figure 1, graph A). If this hardness increase is greater than 10 IRHD, the readings at different times shall be plotted against time (time on logarithmic scale) and a smooth curve fitted to the points. From the curve, the time corresponding to a hardness increase of 10 IRHD shall be obtained by interpolation (see figure 1, graph B).

The same procedure is applied, using the shorter time scale, when the hardness increase after (24 $^{+0}_{-0,5}$) h exceeds 10 IRHD.

The increase in hardness after a specified time or the time for a specified increase in hardness may also be used for reporting of data to comply with requirements in certain specifications (see figure 1, graph C).

8.2 For scientific purposes, the time for half the hardness increase to occur between initial and final hardness may be given (see figure 1, graph D), using the smooth curve of hardness versus time. This assumes that hardness measurements are extended in time to secure the level of final hardness.

9 Test report

The test report shall include the following information:

- Sample details:
 - a full description of the sample and its origin;
 - compound preparation details, and cure time and temperature, where appropriate;
 - method of preparation of test pieces from sample;
 - thickness of test piece and whether made up of one or two pieces.
- Test method and test details:
 - number of this International Standard;
 - method by which the hardness measurements were carried out;
 - any special data concerning the apparatus;
 - the particular standard temperature used;
 - temperature of test;
 - time of storage at test temperature;
 - decrystallization and conditioning prior to test, if carried out.
- Test results:
 - original hardness at standard temperature;
 - initial hardness at test temperature;
 - hardness increase after (168 $^{+0}_{-2}$) h of storage at the test temperature;

or

time, in hours, to reach an increase of 10 IRHD from initial hardness at test temperature;