



Designation: **C807—08 C807 – 13**

## Standard Test Method for Time of Setting of Hydraulic Cement Mortar by Modified Vicat Needle<sup>1</sup>

This standard is issued under the fixed designation C807; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope\*

1.1 This test method covers the determination of the time of setting of hydraulic cement mortar by means of the modified Vicat needle.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use. (Warning—Fresh hydraulic cementitious mixtures are caustic and may cause chemical burns to skin and tissue upon prolonged exposure.<sup>2</sup>The use of gloves, protective clothing, and eye protection is recommended. Wash contact area with copious amounts of water after contact. Wash eyes for a minimum of 15 min. Avoid exposure of the body to clothing saturated with the liquid phase of the unhardened material. Remove contaminated clothing immediately after exposure.)*

1.4 The text of this standard references notes and footnotes which provide explanatory material. These notes and footnotes (excluding those in tables and figures) shall not be considered as requirements of the standard.

### 2. Referenced Documents

2.1 *ASTM Standards:*<sup>3</sup>

**C109/C109M** Test Method for Compressive Strength of Hydraulic Cement Mortars (Using 2-in. or [50-mm] Cube Specimens)

**C183** Practice for Sampling and the Amount of Testing of Hydraulic Cement

**C187** Test Method for Amount of Water Required for Normal Consistency of Hydraulic Cement Paste

**C219** Terminology Relating to Hydraulic Cement

**C305** Practice for Mechanical Mixing of Hydraulic Cement Pastes and Mortars of Plastic Consistency

**C511** Specification for Mixing Rooms, Moist Cabinets, Moist Rooms, and Water Storage Tanks Used in the Testing of Hydraulic Cements and Concretes

**C670** Practice for Preparing Precision and Bias Statements for Test Methods for Construction Materials

**C778** Specification for Sand

**C845** Specification for Expansive Hydraulic Cement

**C1005** Specification for Reference Masses and Devices for Determining Mass and Volume for Use in the Physical Testing of Hydraulic Cements

**D1193** Specification for Reagent Water

### 3. Terminology

3.1 Terms used in this standard are defined in Terminology **C219**.

### 4. Summary of Test Method

4.1 A mortar is prepared with the cement to be tested, using stipulated quantities of cement and water, and sufficient standard sand to produce a required consistency as determined by a stipulated penetration using the plunger of the modified Vicat apparatus.

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee **C01** on Cement and is the direct responsibility of Subcommittee **C01.30** on Time of Set. Current edition approved June 1, 2008Dec. 1, 2013. Published July 2008January 2014. Originally approved in 1975. Last previous edition approved in 20052008 as **C807 – 05-C807 – 08**. DOI: 10.1520/C0807-08.10.1520/C0807-13.

<sup>2</sup> See the section on Safety, Manual of Cement Testing, *Annual Book of ASTM Standards*, Vol 04.01.

<sup>3</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

\*A Summary of Changes section appears at the end of this standard

Mortar of the proper consistency is then tested for time of setting, using the needle of the modified Vicat apparatus for the determination of a stipulated penetration. The time required to obtain the stipulated penetration of the modified Vicat needle is the time of setting.

## 5. Significance and Use

5.1 The purpose of this test method is to establish whether or not a cement complies with a specification limit on time of setting. It has been found to be particularly applicable for the determination of the setting time of expansive cements (see Specification C845).

## 6. Apparatus

6.1 *Tamper and Trowel*, conforming to the requirements of Test Method C109/C109M. In addition, the edges of the trowel when placed on a plane surface shall not depart from straightness by more than 1 mm.

6.2 *Vicat Apparatus*, conforming to the requirements of Test Method C187, with the following modifications:

6.2.1 For consistency determination, the plunger end of the movable rod shall be  $17.5 \pm 0.5$  mm in diameter instead of 10 mm, and the total mass of the movable rod (including the 17.5-mm plunger) shall be  $400 \pm 0.5$  g.

6.2.2 For time of setting determination, a  $2 \pm 0.05$ -mm stainless steel needle shall be substituted for the 1-mm needle. The total mass of the movable rod with the 2-mm needle shall be  $300 \pm 0.5$  g.

6.3 *Mold for Consistency and Setting Time*—A smooth cylindrical brass ring  $76 \pm 0.5$  mm inside diameter (3-in. brass tubing) by  $40 \pm 1$  mm deep, cemented to a plane, non-absorptive plate, or smooth cylindrical brass cups having the above dimensions.

6.4 *Mixer, Bowl, Paddle, and Scraper*, conforming to the requirements of Practice C305.

6.5 *Glass Graduates*, conforming to the requirements of Specification C1005.

6.6 *Masses and Mass Determining Devices*, conforming to the requirements of Specification C1005. The devices for determining mass shall be evaluated for precision and accuracy at a total load of 1000 g.

## 7. Reagents and Materials

7.1 *Graded Standard Sand*, conforming to the requirements of Specification C778.

7.2 *Mixing Water*—Potable water is satisfactory for routine tests. For all referee and cooperative tests, reagent water conforming to the requirements of Specification D1193 for Type III or Type IV grade of reagent water shall be used.

## 8. Sampling

8.1 When the test is part of acceptance testing, sample the cement in accordance with Practice C183.

## 9. Conditioning

9.1 Maintain the temperature of the room, dry materials, paddle, bowl, and molds at  $23.0 \pm 3.0$  °C.

9.2 Maintain the temperature of the mixing water at  $23.0 \pm 2.0$  °C

9.3 The relative humidity of the mixing room shall not be less than 50 %.

9.4 The moist closet or moist room shall be in accordance with Specification C511.

## 10. Procedure

10.1 *Preparation of Mortar*:

10.1.1 Mix 750 g of cement, 375 mL of water, and the quantity of graded standard sand required to give the consistency specified below under “Test for Consistency” in accordance with the mortar mixing procedure described in Practice C305.

10.1.2 Upon completion of mixing, place a layer of mortar about 20 mm in thickness in the mold and puddle with the tamper. Hold the tamper with the 25-mm side parallel to the radius of the mold for 14 strokes spaced equally around the outside of the mold. Apply an additional four strokes to the center of the specimen with the longitudinal axis of the tamper at the center of the mold and rotate the tamper 45° between each stroke. Then fill the mold to overflowing with mortar and puddle as specified for the first layer. Cut off the mortar to a plane surface flush with the top of the mold in two operations. First, with the trowel held at about a 20° angle, start at one side of the mold, 10 mm above the mold, and finish the stroke by cutting the mortar off the top of the mold at the opposite side. Second, starting from the opposite direction, cut the mortar flush with the top of the mold by drawing the straight edge of the trowel (held nearly perpendicular to the mold) with a sawing motion across the top of the mold.

10.2 *Test for Consistency*—Center the mortar confined in the mold under the movable rod of the modified Vicat apparatus described above. Bring the plunger in contact with the surface of the mortar and tighten the setscrew. Then set the movable indicator to the upper zero mark on the scale, or take an initial reading, and release the rod 35 to 50 s after starting to fill the mold. The mortar shall have the desired consistency when the rod settles to a point  $20 \pm 4$  mm below the original surface 30 s after being