



**International
Standard**

ISO 17246

Coal and coke — Proximate analysis

Charbon et coke — Analyse immédiate

**Third edition
2024-04**

iTeh Standards
(<https://standards.itih.ai>)
Document Preview

[ISO 17246:2024](https://standards.itih.ai/catalog/standards/iso/9906c5e3-be0e-4b70-a316-8e64926d0221/iso-17246-2024)

<https://standards.itih.ai/catalog/standards/iso/9906c5e3-be0e-4b70-a316-8e64926d0221/iso-17246-2024>

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

ISO 17246:2024

<https://standards.iteh.ai/catalog/standards/iso/9906c5e3-be0e-4b70-a316-8e64926d0221/iso-17246-2024>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2024

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword.....	iv
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 Principle.....	2
5 Preparation of sample.....	2
6 Test methods.....	2
7 Expression of results.....	2
8 Test report.....	3
Annex A (informative) Example of a proximate analysis.....	4
Bibliography.....	5

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[ISO 17246:2024](https://standards.iteh.ai/catalog/standards/iso/9906c5e3-be0e-4b70-a316-8e64926d0221/iso-17246-2024)

<https://standards.iteh.ai/catalog/standards/iso/9906c5e3-be0e-4b70-a316-8e64926d0221/iso-17246-2024>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 27, *Coal and coke*, Subcommittee SC 5, *Methods of analysis*.

This third edition cancels and replaces the second edition (ISO 17246:2010), which has been technically revised.

The main change is as follows:

- the scope has been widened to include coke.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Coal and coke — Proximate analysis

1 Scope

This document establishes a practice for the proximate analysis of coal and coke. It is intended for general utilization by the coal industry to provide a basis for comparison of coals and coke and for the determination of fixed carbon.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 562, *Hard coal and coke — Determination of volatile matter*

ISO 579, *Coke — Determination of total moisture*

ISO 589, *Hard coal — Determination of total moisture*

ISO 687, *Coke — Determination of moisture in the general analysis test sample*

ISO 1171, *Coal and coke — Determination of ash*

ISO 1213-2, *Solid mineral fuels — Vocabulary — Part 2: Terms relating to sampling, testing and analysis*

ISO 5068-1, *Brown coals and lignites — Determination of moisture content — Part 1: Indirect gravimetric method for total moisture*

ISO 5068-2, *Brown coals and lignites — Determination of moisture content — Part 2: Indirect gravimetric method for moisture in the analysis sample*

ISO 5071-1, *Brown coals and lignites — Determination of the volatile matter in the analysis sample — Part 1: Two-furnace method*

ISO 11722, *Solid mineral fuels — Hard coal — Determination of moisture in the general analysis test sample by drying in nitrogen*

ISO 20360, *Brown coals and lignites — Determination of the volatile matter in the analysis sample: one furnace method*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 1213-2 apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

4 Principle

Coal or coke is analysed for its mass fraction of moisture, ash and volatile matter. The fixed carbon is calculated and the results are reported, to the preferred basis, as a proximate analysis.

5 Preparation of sample

Prepare the sample in accordance with the requirements of the various test methods specified in [Table 1](#).

6 Test methods

Carry out the determination in accordance with the test methods specified in [Table 1](#).

Table 1 — Standard test methods for proximate analysis

Parameter	Test method		
	Coke	Hard coal	Brown coal and lignites
Total moisture (if an “as received” reporting basis is required)	ISO 579	ISO 589	ISO 5068-1
Moisture in air-dried sample	ISO 687	ISO 11722	ISO 5068-2
Volatile matter	ISO 562		ISO 5071-1 or ISO 20360
Ash	ISO 1171		

7 Expression of results

The fixed carbon mass fraction $C_{\text{fix,ad}}$, calculated to air-dried basis and expressed as per cent, is given by [Formula \(1\)](#):

$$C_{\text{fix,ad}} = 100 - (w_{\text{H}_2\text{O,ad}} + w_{\text{A,ad}} + w_{\text{V,ad}}) \quad \text{ISO 17246:2024} \quad (1)$$

where

- $w_{\text{H}_2\text{O,ad}}$ is the moisture mass fraction in the air-dried sample, expressed as per cent;
- $w_{\text{A,ad}}$ is the ash mass fraction, calculated to an air-dried basis and expressed as per cent;
- $w_{\text{V,ad}}$ is the volatile matter mass fraction, calculated to an air-dried basis and expressed as per cent;
- 100 is the conversion factor from mass fraction in units of dimension one, to per cent.

The result is reported to the nearest 0,1 % mass fraction.

The fixed carbon may also be calculated to other bases using the formulae in [Table 2](#).

Table 2 — Formulae for calculating the results to different bases

Basis of value given	Basis of value wanted		
	As received ^a (ar)	Air-dried (ad)	Dry ^a (d)
Parameter, P (moisture, ash or volatiles)	$P_{\text{ar}} = P_{\text{ad}} \times \frac{100 - w_{\text{H}_2\text{O,ar}}}{100 - w_{\text{H}_2\text{O,ad}}}$	—	$P_{\text{d}} = P_{\text{ad}} \times \frac{100}{100 - w_{\text{H}_2\text{O,ad}}}$
^a Where $w_{\text{H}_2\text{O}}$ is the moisture mass fraction.			