



Designation: E1794 – 13

# Standard Specification for Adhesive for Bonding Foam Cored Sandwich Panels (200°F Elevated Humidity Service), Type II Panels<sup>1</sup>

This standard is issued under the fixed designation E1794; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the U.S. Department of Defense.*

## 1. Scope

1.1 This specification covers two-part adhesives for bonding foam core sandwich panels. The adhesive may be used for new production or depot maintenance. The adhesive should be suitable for forming bonds that can withstand long-term exposure to temperatures from  $-55$  to  $93^{\circ}\text{C}$  ( $-67$  to  $200^{\circ}\text{F}$ ) and also withstand combinations of stress, temperature, and humidity expected to be encountered in service. The adhesives shall be used for bonding aluminum alloy facing to foam core, inserts, internal aluminum framing members, and other components of a foam cored sandwich panel.

1.2 The values stated in SI units are to be regarded as the standard where only SI units are given or where SI units are given first followed by inch-pound units; where inch-pound units are given first followed by SI units, the inch-pound units are to be regarded as the standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

### 2.1 ASTM Standards:<sup>2</sup>

[B209 Specification for Aluminum and Aluminum-Alloy Sheet and Plate](#)

[D1002 Test Method for Apparent Shear Strength of Single-Lap-Joint Adhesively Bonded Metal Specimens by Tension Loading \(Metal-to-Metal\)](#)

[E631 Terminology of Building Constructions](#)

[E864 Practice for Surface Preparation of Aluminum Alloys to Be Adhesively Bonded in Honeycomb Shelter Panels](#)  
[E1749 Terminology Relating to Rigid Wall Relocatable Shelters](#)

2.2 *Military Standard:*<sup>3</sup>

[MIL-STD-202F Test Methods for Electronic and Electrical Component Parts](#)

2.3 *Federal Specification:*<sup>3</sup>

[QQ-A-250/11d Aluminum Alloy 6061 T6 Plate and Sheet](#)

## 3. Terminology

3.1 *Definitions*—See Terminologies [E631](#) and [E1749](#) for definitions of terms used in this specification.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *adhesive life*—the maximum time that an adhesive, when mixed in a prescribed quantity can set at a designated temperature, after which the adhesive, when used to prepare specimens, will deliver the required properties.

## 4. Requirements

4.1 *Material*—The adhesive shall be a two-part thermosetting epoxy paste containing no asbestos and, when tested using the test methods described in Section 6, shall meet the requirements of Section 4. The adhesive shall not have a deleterious effect on the components being bonded over the range of temperatures at which the adhesive will be used.

4.2 *Working Characteristics:*

4.2.1 *Application*—The adhesive shall be suitable for application to facings and foam core materials. The adhesive shall be suitable for spray application to faying surfaces.

4.2.2 *Curing*—The time, temperature, and pressure used to cure the adhesive shall be within the range specified herein.

4.2.2.1 *Curing Time and Temperature*—The adhesive, when mixed in accordance with the manufacturer's instructions, shall meet the requirements of this specification when cured at a temperature of not more than  $99^{\circ}\text{C}$  ( $210^{\circ}\text{F}$ ) for 60 min, or  $107^{\circ}\text{C}$  ( $225^{\circ}\text{F}$ ) for 45 min. The timing of the cure shall start when the panel skins have reached the specified temperature.

<sup>3</sup> Available from DLA Document Services, Building 4/D, 700 Robbins Avenue, Philadelphia, PA 19111-5094, <http://quicksearch.dla.mil/>.

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee E06 on Performance of Buildings and is the direct responsibility of Subcommittee E06.53 on Materials and Processes for Durable Rigidwall Relocatable Structures.

Current edition approved Oct. 1, 2013. Published February 2014. Originally approved in 1996. Last previous edition approved in 2008 as E1794 – 08. DOI: 10.1520/E1794-13.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.