



# FINAL DRAFT International Standard

## ISO/FDIS 13909-5

### Coal and coke — Mechanical sampling —

#### Part 5: Sampling of coke from moving streams

ISO/TC 27/SC 4

Secretariat: **SABS**

Voting begins on:  
**2025-04-09**

Voting terminates on:  
**2025-06-04**

Standards  
(<https://standards.iteh.ai>)  
Document Preview

ISO/FDIS 13909-5

<https://standards.iteh.ai/catalog/standards/iso/73d954ce-47da-4851-889b-ec071bc6aa97/iso-fdis-13909-5>

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

iTeh Standards  
(<https://standards.iteh.ai>)  
Document Preview

ISO/FDIS 13909-5

<https://standards.iteh.ai/catalog/standards/iso/73d954ce-47da-4851-889b-ec071bc6aa97/iso-fdis-13909-5>



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2025

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

Page

<b>Foreword</b>	<b>v</b>
<b>1 Scope</b>	<b>1</b>
<b>2 Normative references</b>	<b>1</b>
<b>3 Terms and definitions</b>	<b>1</b>
<b>4 Establishing a sampling scheme</b>	<b>1</b>
4.1 General	1
4.2 Design of the sampling scheme	2
4.2.1 Material to be sampled	2
4.2.2 Parameters to be determined on samples	2
4.2.3 Division of lots	2
4.2.4 Basis of sampling	2
4.2.5 Precision of sampling	3
4.2.6 Bias of sampling	3
4.3 Precision of results	3
4.3.1 Precision and total variance	3
4.3.2 Primary increment variance	4
4.3.3 Preparation and testing variance	5
4.3.4 Number of sub-lots and number of increments in each sub-lot	5
4.4 Minimum mass of sample	8
4.5 Mass of primary increment	9
4.6 Size analysis	10
<b>5 Methods of sampling</b>	<b>10</b>
5.1 General	10
5.2 Time-basis sampling	10
5.2.1 Method of taking primary increments	10
5.2.2 Sampling interval	11
5.2.3 Mass of increment	11
5.3 Stratified random sampling	11
5.3.1 General	11
5.3.2 Time-basis stratified random sampling	11
5.4 Reference sampling	11
<b>6 Design of mechanical samplers</b>	<b>12</b>
6.1 Safety	12
6.2 Sampling system	12
6.2.1 General	12
6.2.2 Checking for precision and bias	12
6.2.3 Operation of sampler	13
6.3 Location of sampling equipment	13
6.4 General requirements for designing mechanical samplers	13
6.5 Design of falling-stream-type samplers	13
6.5.1 General	13
6.5.2 Cutter velocity	16
6.6 Cross-belt-type primary samplers	16
6.6.1 Operation	16
6.6.2 Design of cross-belt samplers	17
6.6.3 Maintenance of sampling equipment	18
<b>7 Handling and storage of samples</b>	<b>19</b>
<b>8 Sample preparation</b>	<b>20</b>
<b>9 Minimization of bias</b>	<b>20</b>
9.1 General	20
9.2 Spacing of increments	20
9.3 Incorrectly extracted increments	20

## ISO/FDIS 13909-5:2025(en)

9.4	Preservation of integrity of sample .....	20
9.4.1	General .....	20
9.4.2	Precautions to reduce bias .....	21
<b>10</b>	<b>Verification .....</b>	<b>21</b>
	<b>Bibliography .....</b>	<b>22</b>

**iTeh Standards**  
**(<https://standards.iteh.ai>)**  
**Document Preview**

[ISO/FDIS 13909-5](https://standards.iteh.ai/catalog/standards/iso/73d954ce-47da-4851-889b-ec071be6aa97/iso-fdis-13909-5)

<https://standards.iteh.ai/catalog/standards/iso/73d954ce-47da-4851-889b-ec071be6aa97/iso-fdis-13909-5>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at [www.iso.org/patents](http://www.iso.org/patents). ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 27, *Coal and coke*, Subcommittee SC 4, *Sampling*.

This third edition cancels and replaces the second edition (ISO 13909-5:2016), which has been technically revised.

The main changes are as follows:

- the title has been modified and aligned with the rest of the ISO 13909 series;

A list of all parts in the ISO 13909 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).



# Coal and coke — Mechanical sampling —

## Part 5: Sampling of coke from moving streams

### 1 Scope

This document specifies procedures and requirements for the design and establishment of sampling schemes for the mechanical sampling of coke from moving streams and the methods of sampling used.

The diversity of types of equipment for sampling and the conditions under which mechanical sampling is performed make it inappropriate to specify standard designs for samplers which will be applicable to all situations.

### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 13909-1:—<sup>1)</sup>, *Coal and coke — Mechanical sampling — Part 1: General introduction*

ISO 13909-6, *Coal and coke — Mechanical sampling — Part 6: Preparation of test samples of coke*

ISO 13909-7, *Coal and coke — Mechanical sampling — Part 7: Methods for determining the precision of sampling, sample preparation and testing*

ISO 13909-8, *Coal and coke — Mechanical sampling — Part 8: Methods of testing for bias*

ISO 21398, *Hard coal and coke — Guidance to the inspection of mechanical sampling systems*

### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 13909-1 apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

### 4 Establishing a sampling scheme

#### 4.1 General

The general procedure for establishing a sampling scheme is as follows:

- a) define the quality parameters to be determined and the types of samples required;
- b) define the lot;

---

1) Under preparation. Stage at the time of publication: ISO/FDIS 13909-1:2025.

- c) define or assume the precision required (see [4.3.1](#));
  - d) determine the method of combining the increments into a sample, or number of sub-lot samples, and the method of sample preparation (see ISO 13909-6);
  - e) determine or assume the variability of the coke (see [4.3.2](#)) and the variance of preparation and testing (see [4.3.3](#)). Methods for determining variability and the variance of preparation and testing are given in ISO 13909-7;
  - f) establish the number of sub-lots and the number of increments per sub-lot required to attain the desired precision (see [4.3.4](#));
  - g) define the sampling interval (see [Clause 5](#));
  - h) ascertain the nominal top size of the coke for the purpose of determining the minimum mass of sample (see [4.4](#) and [Table 1](#));
- NOTE The nominal top size may initially be ascertained by consulting the consignment details, or by visual estimation, and may be verified, if necessary, by preliminary test work.
- i) determine the minimum average increment mass (see [4.5](#)).

## 4.2 Design of the sampling scheme

### 4.2.1 Material to be sampled

The first stage in the design of the scheme is to identify the cokes to be sampled. Samples can be required for technical evaluation, process control, quality control, and for commercial reasons by both the producer and the customer. It is essential to ascertain exactly at what stage in the coke-handling process the sample is required and, as far as practicable, design the scheme accordingly.

### 4.2.2 Parameters to be determined on samples

The samples for moisture and physical tests may be collected separately or as one sample, which is then divided. In this document, a sample which is collected for the determination of moisture (and possibly also for general analysis) is referred to as the moisture sample; a sample which is collected for physical tests only is referred to as the physical sample. If a sample is used for the determination of moisture and for physical tests, it is referred to as a common sample.

In mechanical sampling of coke, the only sample which can, in certain circumstances (see [4.2.6](#)), be processed automatically beyond the divided-increment stage is the moisture sample.

In order to achieve the desired precision, it may be necessary to take different numbers of increments for the moisture and physical samples. Where a common sample is taken, the greater number of increments shall be used.

### 4.2.3 Division of lots

A lot may be sampled as a whole or as a series of sub-lots, e.g. coke despatched or delivered over a period of time, a ship load, a train load, a wagon load, or coke produced in a certain period, e.g. a shift.

It can be necessary to divide a lot into a number of sub-lots in order to improve the precision of the results.

For lots sampled over long periods, it can be expedient to divide the lot into a series of sub-lots, obtaining a sample for each.

### 4.2.4 Basis of sampling

Sampling may be carried out on either a time-basis or a mass-basis.



In time-basis sampling, increments are taken at fixed time intervals with an increment mass, collected with a fixed speed cutter, which is proportional to the flow rate at the time of extraction.

In mass-basis sampling, increments are taken at fixed mass intervals, using a belt weigher/mass integrator, and fixed mass increments are extracted using a variable speed cutter or sample preparation system which produces a fixed mass divided increment.

The conditions under which mass-basis sampling can seem to offer the advantage of consistent increment mass, for example highly variable flow rates, are those in which it is most difficult to implement in practice.

Time-basis sampling is by far the simplest to implement and is the basis of this document.

#### 4.2.5 Precision of sampling

The required precision for a lot for each parameter to be measured shall be decided. The number of sub-lots and minimum number of increments per sub-lot collected shall then be determined as described in [4.3.4](#), and the average mass of primary increments shall be determined as described in [4.5](#).

For single lots, the quality variation shall be assumed as the worst case (see [4.3.2](#)). The precision of sampling achieved may be measured using the procedure of replicate sampling (see ISO 13909-7).

At the start of regular sampling of unknown cokes, the worst-case quality variation shall be assumed. When sampling is in operation, a check shall be carried out to confirm that the desired precision has been achieved using the procedure of duplicate sampling as described in ISO 13909-7.

If any subsequent change in precision is required, the number of sub-lots and increments shall be changed as determined in [4.3.4](#) and the precision attained shall be rechecked. The precision shall also be checked if there is any reason to suppose that the variability of the coke being sampled has increased. The number of increments determined in [4.3.4](#) applies to the precision of the result when the sampling errors are large relative to the testing errors, e.g. moisture content. However, in some tests, e.g. Micum Index, the testing errors are themselves large. In this case, it may be necessary to prepare two or more test portions from the same sample (see [4.3.4.3](#)) and use the mean of the determinations to give a better precision.

#### 4.2.6 Bias of sampling

It is of particular importance in sampling to ensure, as far as possible, that the parameter to be measured is not altered by the sampling and sample preparation process or by subsequent storage prior to testing. For example, care shall be taken to avoid breakage of coke intended for physical testing and loss of moisture from the moisture sample during storage. This may require, in some circumstances, a limit on the minimum mass of primary increment (see [4.5](#) and [Clause 8](#)).

When collecting samples for moisture determination from lots over an extended period, it can be necessary to limit the standing time of samples by dividing the lot into a number of sub-lots (see [4.3.4](#)).

The use of on-line crushing and division of the moisture sample for moisture determination shall be treated with caution because of the risk of bias caused by loss of moisture in the processing (see [6.2.2](#)). In particular, the crushing of hot coke is not recommended. If the bias is unacceptable, the sample shall be left in the uncrushed state and the sample preparation carried out by manual methods. However, some bias is inevitable, whether due to breakage or loss of moisture from hot coke. The object, therefore, shall be to restrict such degradation or moisture loss to a minimum.

When a coke-sampling scheme is implemented, it shall be checked for bias in accordance with the methods given in ISO 13909-8.

### 4.3 Precision of results

#### 4.3.1 Precision and total variance

In all methods of sampling, sample preparation and analysis, errors are incurred and the experimental results obtained from such methods for any given parameter will deviate from the true value of that

parameter. While the absolute deviation of a single result from the “true” value cannot be determined, it is possible to make an estimate of the precision of the experimental results. This is the closeness with which the results of a series of measurements made on the same coke agree among themselves, and the deviation of the mean of the results from an accepted reference value, i.e. the bias of the results (see ISO 13909-8).

It is possible to design a sampling scheme by which, in principle, an arbitrary level of precision can be achieved.

NOTE The required overall precision for a lot is normally agreed between the parties concerned.

The theory of the estimation of precision is given in ISO 13909-7. [Formula \(1\)](#) is derived:

$$P_L = 2\sqrt{\frac{\frac{V_I}{n} + V_{PT}}{m}} \quad (1)$$

where

- $P_L$  is the estimated index of overall precision of sampling, sample preparation and testing for the lot at a 95 % confidence level, expressed as a percentage absolute;
- $V_I$  is the primary increment variance;
- $V_{PT}$  is the preparation and testing variance;
- $n$  is the number of increments taken per sub-lot;
- $m$  is the number of sub-lots in the lot.

If the quality of a coke of a type not previously sampled is required, then, in order to devise a sampling scheme, assumptions shall be made about the variability (see [4.3.2](#)). The precision actually achieved for a particular lot by the scheme devised can be measured by the procedures given in ISO 13909-7.

If the same type of coke is sampled regularly, sampling schemes can be laid down using data derived from previous sampling. The procedures given in ISO 13909-7 can be used to devise the optimum scheme, thus keeping the sampling costs to a minimum.

#### 4.3.2 Primary increment variance

The primary increment variance,  $V_I$ , depends upon the type and nominal top size of coke, the degree of pre-treatment and mixing, the absolute value of the parameter to be determined and the mass of increment taken.

The variability for moisture is usually higher than that for ash and hence, for the same precision, the number of increments for moisture is adequate for ash. If, however, a higher precision is required for ash, the relevant primary increment variance shall be applied for each sample.

The value of the primary increment variance,  $V_I$ , required for the calculation of the precision using [Formula \(1\)](#) can be obtained by either

- a) direct determination on the coke to be sampled using one of the methods described in ISO 13909-7; or
- b) assuming a value determined for a similar coke from a similar coke handling and sampling system.

If neither of these values is available, a value of  $V_I = 5$  can be assumed initially and checked, after the sampling has been carried out, using one of the methods described in ISO 13909-7.

### 4.3.3 Preparation and testing variance

The value of the preparation and testing variance,  $V_{PT}$ , required for the calculation of the precision using [Formula \(1\)](#) can be obtained by either:

- a) direct determination on the coke to be sampled using one of the methods described in ISO 13909-7; or
- b) assuming a value determined for a similar coke from a similar sample-preparation scheme.

If neither of these values is available, a value of  $V_{PT} = 0,2$  can be assumed initially and checked, after the preparation and testing has been carried out, using one of the methods described in ISO 13909-7.

### 4.3.4 Number of sub-lots and number of increments in each sub-lot

#### 4.3.4.1 General

The number of increments taken from a lot in order to achieve a particular precision is a function of the variability of the quality of the coke in the lot, irrespective of the mass of the lot. The lot may be sampled as a whole resulting in one sample, or divided into a number of sub-lots resulting in a sample from each. Such division may be necessary in order to achieve the required precision.

There may be other practical reasons for dividing the lot, such as:

- a) for convenience when sampling over a long period;
- b) to keep sample masses manageable;
- c) to maintain the integrity of the sample, i.e. to avoid bias after taking the increment, particularly in order to minimize loss of moisture due to standing. The need to do this division is dependent on factors such as the time taken to collect samples, ambient temperature and humidity conditions, the ease of keeping the sample in sealed containers during collection, and the particle size of the coke. It is recommended that, if moisture loss is suspected, a bias test is carried out to compare the quality of a reference sample immediately after extraction with the sample after standing for the normal time. If bias is found, the sample standing time shall be reduced by collecting samples more frequently, i.e. increasing the number of sub-lots.

The quality of the lot shall be calculated as the weighted average of the values found for the sub-lots.

As stated in [4.3.1](#), the precision is determined by the variability of the coke, the number of increments and sub-lots and the preparation and testing variance. By transposing [Formula \(1\)](#), it can be shown that the number of increments per sub-lot for a desired precision for a lot can be estimated from [Formula \(2\)](#):

$$n = \frac{4V_L}{mP_L^2 - 4V_{PT}} \quad (2)$$

Determine the number of sub-lots required for practical reasons and then estimate the number of increments in each for the desired precision using [Formula \(2\)](#). If  $n$  is a practicable number, the initial scheme is established. However, if  $n$  is less than 10, take 10 increments per sub-lot.

A value of infinity or a negative number indicates that the errors of preparation and testing are such that the required precision cannot be achieved with this number of sub-lots. If  $n$  is impracticably large, increase the number of sub-lots using one of the following methods:

- a) increase  $m$  to a number corresponding to a convenient mass or time, recalculate  $n$  and repeat this process until  $n$  is a practicable number;
- b) decide on the maximum practicable number of increments per sub-lot,  $n_1$ , and calculate  $m$  from [Formula \(3\)](#):