

# Standard Specification for Nonferrous Nuts for General Use [Metric]<sup>1</sup>

This standard is issued under the fixed designation F 467M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

## 1. Scope

1.1 This specification covers the requirements for commercial wrought nonferrous nuts in nominal thread diameters M6 to M36 inclusive in a number of alloys in common use and intended for general service applications.

1.2 Applicable bolts, cap screws, and studs for use with nuts covered by this specification are covered by Specification F 468M.

NOTE 1—This specification is the metric companion of Specification F 467.

## 2. Referenced Documents

- 2.1 ASTM Standards:
- B 154 Test Method for Mercurous Nitrate Test for Copper and Copper Alloys<sup>2</sup>
- D 3951 Practice for Commercial Packaging<sup>3</sup>
- E 18 Test Methods for Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials<sup>4</sup>
- E 29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications<sup>5</sup>
- E 34 Test Methods for Chemical Analysis of Aluminum and Aluminum Base Alloys<sup>6</sup>
- E 38 Methods for Chemical Analysis of Nickel-Chromium and Nickel-Chromium-Iron Alloys<sup>7</sup>
- E 53 Test Methods for Chemical Analysis of Copper<sup>6</sup>
- E 54 Test Methods for Chemical Analysis of Special Brasses and Bronzes<sup>6</sup>
- E 55 Practice for Sampling Wrought Nonferrous Metals and Alloys for Determination of Chemical Composition<sup>6</sup>

- <sup>4</sup> Annual Book of ASTM Standards, Vol 03.01.
- <sup>5</sup> Annual Book of ASTM Standards, Vol 14.02.
- <sup>6</sup> Annual Book of ASTM Standards, Vol 03.05.

- E 62 Test Methods for Chemical Analysis of Copper and Copper Alloys (Photometric Methods) $^{6}$
- E 75 Test Methods for Chemical Analysis of Copper-Nickel and Copper-Nickel-Zinc Alloys<sup>6</sup>
- E 76 Test Methods for Chemical Analysis of Nickel–Copper Alloys<sup>6</sup>
- $E\,92\,$  Test Method for Vickers Hardness of Metallic Materials  $^4$
- E 101 Test Method for Spectrographic Analysis of Aluminum and Aluminum Alloys by the Point-to-Plane Technique<sup>8</sup>
- E 120 Test Methods for Chemical Analysis of Titanium and Titanium Alloys<sup>6</sup>
- E 165 Practice for Liquid Penetrant Inspection Method<sup>9</sup>
- E 227 Test Method for Optical Emission Spectrometric Analysis of Aluminum and Aluminum Alloys by the Point-to-Plane Technique<sup>6</sup>
- E 354 Test Methods for Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron,
- Nickel, and Cobalt Alloys<sup>6</sup> 2d60c0/astm-f467m-01a
- E 478 Test Methods for Chemical Analysis of Copper Alloys<sup>6</sup>
- E 1409 Test Method for Determination of Oxygen in Titanium and Titanium Alloys by the Inert Gas Fusion Technique<sup>6</sup>
- F 468M Specification for Nonferrous Bolts, Hex Cap Screws, and Studs for General Use [Metric]<sup>10</sup>
- F 606M Test Methods for Determining the Mechanical Properties of Externally and Internally Threaded Fasteners, Washers, and Rivets [Metric]<sup>10</sup>
- F 1470 Guide for Fastener Sampling for Specified Mechanical Properties and Performance Inspection<sup>10</sup>
- 2.2 ASME Standards:

Copyright © ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States.

<sup>&</sup>lt;sup>1</sup> This specification is under the jurisdiction of ASTM Committee F16 on Fasteners and is the direct responsibility of Subcommittee F16.04 on Nonferrous Fasteners.

Current edition approved Oct. 10, 2001. Published December 2001. Originally published as F 467M – 79. Last previous edition F 467M – 98.

<sup>&</sup>lt;sup>2</sup> Annual Book of ASTM Standards, Vol 02.01.

<sup>&</sup>lt;sup>3</sup> Annual Book of ASTM Standards, Vol 15.09.

<sup>&</sup>lt;sup>7</sup> Discontinued 1989; *Replaced by E 350.* 

<sup>&</sup>lt;sup>8</sup> Discontinued; see 1995 Annual Book of ASTM Standards, Vol 03.05.

<sup>&</sup>lt;sup>9</sup> Annual Book of ASTM Standards, Vol 03.03.

<sup>&</sup>lt;sup>10</sup> Annual Book of ASTM Standards, Vol 01.08.

NOTICE: This standard has either been superceded and replaced by a new version or discontinued. Contact ASTM International (www.astm.org) for the latest information.

邰财 F 467M

B 1.13M Metric Screw Threads<sup>11</sup>

B 18.2.4.1MMetric Hex Nuts, Style 1<sup>11</sup>

## 3. Ordering Information

3.1 Orders for nuts under this specification shall include the following information:

3.1.1 Quantity (numbers of pieces of each item and size);

3.1.2 Name of item;

3.1.3 Nominal thread diameter and thread pitch;

3.1.4 Alloy number (Table 1);

3.1.5 Stress relieving, if required (4.2.3);

3.1.6 "Shipment lot" testing, as required (Section 9);

3.1.7 Source inspection, if required (Section 14);

3.1.8 Certificate of compliance or test report, if required (Section 16);

3.1.9 Additional requirements, if any, to be specified on the purchase order (4.2.1, 7.2, 8.2, 11.1, and 12.1),

3.1.10 Supplementary requirements, if any; and

3.1.11 ASTM specification and year of issue.

NOTE 2—A typical ordering description is as follows: 10 000 pieces, Hex Nut, M8  $\times$  1.25 Alloy 270, Furnish Certificate of Compliance, Supplementary Requirement S1, ASTM Specification F 467M – XX.

### 4. Materials and Manufacture

4.1 Materials:

4.1.1 The nuts shall be manufactured from material having a chemical composition conforming to the requirements in Table 1 and capable of developing the required mechanical properties for the specified alloy in the nut.

4.1.2 The starting condition of the raw material shall be at the discretion of the fastener manufacturer but shall be such that the nuts conform to all the specified requirements.

4.2 Manufacture:

4.2.1 *Forming*—Unless otherwise specified, the nuts shall be hot pressed, cold formed, or machined from suitable

material at the option of the manufacturer.

4.2.2 *Condition*—Except as provided in 4.2.3, the nuts shall be furnished in the condition specified below:

Alloy	Condition
Copper (all alloys)	As formed or stress relieved at manufacturer's option
Nickel alloys 400 and	As formed or stress relieved at manufacturer's option
405	
Nickel alloy 500	Solution annealed and aged
Aluminum alloys:	
2024-T4	Solution treated and naturally aged
6061-T6	Solution treated and artificially aged
6262-T9	Solution treated, artificially aged, and cold worked
Titanium	As formed

4.2.3 *Stress Relieving*—When required, stress relieving shall be specified by the purchaser for all copper alloys and nickel alloys 400 and 405.

### 5. Chemical Composition

5.1 *Chemical Composition*—The nuts shall conform to the chemical composition specified in Table 1 for the specified alloy.

5.2 Manufacturer's Analysis:

5.2.1 Except as provided in 5.2.2, when test reports are required on the inquiry or purchase order (3.1.8), the manufacturer shall make individual analyses of randomly selected nuts from the product to be shipped and report the results to the purchaser. Alternatively, if heat and lot identities have been maintained, the analysis of the raw material from which the nuts have been manufacturered may be reported instead of product analysis.

5.2.2 For aluminum nuts, instead of 5.2.1, the manufacturer may furnish a certificate of conformance certifying compliance with the chemical composition specified in Table 1.

5.3 Product Analysis:

5.3.1 Product analyses may be made by the purchaser from nuts representing each lot. The chemical composition thus determined shall conform to the requirements in Table 1.

5.3.2 In the event of disagreement, a referee chemical analysis of samples from each lot shall be made in accordance with 11.1 and 12.1.

<sup>&</sup>lt;sup>11</sup> Available from Global Engineering Documents, 15 Inverness Way East, Englewood, CO 80112.

		1	I	41
			Arsenic, max	0 13
			Ţ	0.5–1.0 0.5–1.0 4.2–5.8 0.20 max 0.20 max 0.20 max
			Lead, max	0.10 0.20 0.05 0.05 0.05 0.05 0.05 0.05 0.0
TABLE 1 Chemical Requirements			Zinc, max <sup>A</sup>	balance balance balance 0.30 1.5 1.5 1.5 1.00 1.00 1.00
			Silicon	0.25 max 1.5-2.2 ° 0.8-3.8 2.8-3.5 2.5 2.8-3.5 2.5 2.8-3.5 2.5 2.8-3.5 2.5 2.5 2.5 2.5 2.5 2.5 2.5 2.5 2.5 2
			Phos- phorus	0.03-0.35 iron does not e:
		Copper and Copper-Base Alloys	Nickel, max	0.6 0.6 0.6 0.25 0.25 0.25 0.25 0.25 0.25 0.25 0.25
	Composition, %	per and Copp	Man- ganese, max	amed elements
	Co	Copp	lron, max	0.07 0.07 0.07 0.10 0.10 0.10 0.10 0.10
	90		Copper, min	99.9 63.0-68.5 63.0-68.5 62.0-68.5 62.0-68.5 balance <sup>A</sup> 88.0 <sup>B</sup> 98.0 <sup>B</sup> 94.0 <sup>B</sup> 94.0 <sup>B</sup> 94.0 <sup>B</sup> 94.0 <sup>B</sup> 57.0-60.0 74.0 <sup>B</sup> 65.0 <sup>B</sup> 65.0 <sup>B</sup> e sum of all the
			Alumi- num	6.0-8.0 9.0-11.0 6.3-7.6 6.3-7.6 6.3-7.6 6.3-7.6 f. ax 0.25 max
			General Name	Current FTP Mask
			Alloy	110 110 110 614 651 651 651 655 661 710 710 710 710 0ntaining
		NNS	Designa- tion Number	C 11000 C 11000 C 464200 C 464200 C 464200 C 661400 C 661400 C 661400 C 66100 C 665100 C 711500 C 7115000 C 711500 C 71500 C 71500 C 71500 C 71500 C 715000 C 715000 C 715000 C 715000

# NOTICE: This standard has either been superceded and replaced by a new version or discontinued. Contact ASTM International (www.astm.org) for the latest information.

∰ F 467M

NOTICE: This standard has either been superceded and replaced by a new version or discontinued. Contact ASTM International (www.astm.org) for the latest information.

3.0-4.4

∰ F 467M

3.0-4.5

0.2–0.4 0.35 max

0.030 0.030 0.024 0.025-0.060 0.01 0.01 0.02 max

Tungsten

Vanadium

Sulfur, max

TABLE 1 Continued

Nickel and Nickel-Base Alloys

https://standards.iteh.ai/catalog/standards/s

Molyb- denum	26.0-30.0	15.0-17.0				15.0-17.0		
Co balt, max		2.50	В	В	В			
Tita- nium					0.35-0.85	0.02-0.25		
Sili- con, max	1.00	0.08	0.5	0.5	0.5	0.08	max	
Phos- pho- rus, max		0.040		2	1	0.04	max	a
Nickel			63.0-70.0			-		
Man- ga- nese, max	1.0	1.00	2.0	2.0	1.5	0.75	max	re
rds/sist/27	4.0-6.0	4.0-7.0	2.5	2.5	2.0	5.0 0.75	max	<u>1a</u> -4(
Copper <sup>A</sup>				balance	balance			
Chro- mium	1.0 max	14.5-16.5				19.0–23.0		
Car- bon, max	0.05	0.02	0.3	0.3	0.25	0.010	тах	
Alumi- num					2.30-3.15			
General Name	Ni-Mo	Ni-Mo-Cr	Ni-Cu Class A	Ni-Cu Class B	Ni-Cu-Al	Ni-Cr-Mo-W	_	
Al- loy	335		400			686		
UNS Designa- tion Num- ber	N10001	N10276	N04400	N04405	N05500	N06686		

<sup>A</sup> Elements shown as balance shall be arithmetically computed by deducting the sum of the other named elements from 100. <sup>B</sup> Cobalit is to be counted as nickel.

5c-9bd3-8e1f312d60c0/astm-f467m-01a