

Designation: C14 - 11 C14 - 14

Standard Specification for Nonreinforced Concrete Sewer, Storm Drain, and Culvert Pipe¹

This standard is issued under the fixed designation C14; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

- 1.1 This covers nonreinforced concrete pipe intended to be used for the conveyance of sewage, industrial wastes, storm water, and for the construction of culverts.
- 1.2 A complete metric companion to Specification C14 has been developed—C14M; therefore, no metric equivalents are presented in this specification.

Note 1-This specification is a manufacturing and purchase specification only and does not include requirements for bedding, backfill, or the relationship between field load conditions and the strength classification of pipe. However, experience has shown that the successful performance of this product depends upon the proper selection of the class of pipe, type of bedding and backfill, and care that the installation conforms to the construction specifications. The owner is cautioned that he must correlate the field requirements with the class of pipe specified and provide for or require inspection at the construction site.

2. Referenced Documents

2.1 ASTM Standards:²

C33 Specification for Concrete Aggregates

C150 Specification for Portland Cement S / S12110 2 T 0 S 11 C h C309 Specification for Liquid Membrane-Forming Compounds for Curing Concrete

C443 Specification for Joints for Concrete Pipe and Manholes, Using Rubber Gaskets

C494 Specification for Chemical Admixtures for Concrete

C497 Test Methods for Concrete Pipe, Manhole Sections, or Tile

C595 Specification for Blended Hydraulic Cements

C618 Specification for Coal Fly Ash and Raw or Calcined Natural Pozzolan for Use in Concrete f3743e/astm-c14-14

C822 Terminology Relating to Concrete Pipe and Related Products

C989 Specification for Slag Cement for Use in Concrete and Mortars

C1116 Specification for Fiber-Reinforced Concrete and Shotcrete

3. Terminology

3.1 Definitions—For definitions of terms relating to concrete pipe, see Terminology C822.

4. Classification

4.1 Pipe manufactured according to this specification shall be of three classes identified as "Class 1 Nonreinforced Concrete Pipe," "Class 2 Nonreinforced Concrete Pipe," and "Class 3 Nonreinforced Concrete Pipe." The corresponding strength requirements are prescribed in Table 1.

5. Basis of Acceptance

5.1 The acceptability of the pipe shall be determined by the results of the test prescribed in this section, when required, and by inspection to determine whether the pipe conforms to this specification as to design and freedom from defects.

¹ This specification is under the jurisdiction of ASTM Committee C13 on Concrete Pipe and is the direct responsibility of Subcommittee C13.01 on Non-Reinforced Concrete Sewer, Drain and Irrigation Pipe.

Current edition approved Sept. 1, 2011Feb. 1, 2014. Published October 2011February 2014. Originally approved in 1917. Last previous edition approved in 20072011 as C14 - 07.C14 - 11. DOI: 10.1520/C0014-11.10.1520/C0014-14.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.

TABLE 1 Physical and Dimensional Requirements for Nonreinforced Concrete Pipe^A

Triber in Tryological and Dimonological Hodgenomics for Homolinologic Control in the								
Internal Designated	Class 1		Class 2		Class 3			
	Minimum	Minimum Three-Edge	Minimum	Minimum Three-Edge	Minimum	Minimum Three-Edge		
Diameter, in.	Thickness of Wall,	Bearing Strength,	Thickness of Wall,	Bearing Strength,	Thickness of Wall,	Bearing Strength,		
	in.	lbf/linear ft	in.	lbf/linear ft	in.	lbf/linear ft		
-4	<u>5/8</u>	1500	3/4	2000	3/4	2400		
-6	5/8	1500	3/4	2000	7/8	2400		
-8	3/4	1500	7/8	2000	11/8	2400		
10	7/8	1600	1	2000	11/4	2400		
12	4	1800	13/8	2250	13/4	2600		
15	11/4	2000	15/8	2600	17/8	2900		
18	1½	2200	2	3000	21/4	3300		
21	13/4	2400	21/4	3300	23/4	3850		
24	21/8	2600	3	3600	3¾	4400		
27	31/4	2800	33/4	3950	3¾	4600		
30	31/2	3000	41/4	4300	41/4	4750		
33	3¾	3150	4½	4400	4½	4875		
36	4	3300	43/4	4500	43/4	5000		

TABLE 1 Physical and Dimensional Requirements for Nonreinforced Concrete Pipe^A

	Cla	iss 1	Class 2		Class 3	
Internal Designated	Minimum	Minimum Three-Edge	Minimum	Minimum Three-Edge	Minimum	Minimum Three-Edge
Diameter, in.	Thickness of Wall,	Bearing Strength,	Thickness of Wall,	Bearing Strength,	Thickness of Wall,	Bearing Strength,
	in.	lbf/linear ft	<u>in.</u>	lbf/linear ft	<u>in.</u>	lbf/linear ft
_4	<u>5/8</u>	<u>1500</u>	3/4	2000	3/4	2400
_6	<u>5/8</u>	<u>1500</u>	3/4	2000	<u>7/8</u>	2400
8	3/4	1500	7/8	2000	11/8	2400
10	7/8	1600	<u>1</u>	2000	11/4	2400
<u>12</u>	1	1800	13/8	2250	<u>1¾</u>	2600
<u>15</u>	<u>11/4</u>	<u>2000</u>	<u>15/8</u>	<u>2600</u>	1 7⁄8	<u>2900</u>
<u>18</u>	11/2	2200	2	3000	21/4	3300
<u>21</u>	<u>1¾</u>	2400	21/4	3300	23/4	<u>3850</u>
24	21/8	2600	<u>3</u>	3600	<u>3%</u>	<u>4400</u>
27	31/4	2800	33/4	3950	33/4	4600
30	31/2	3000	41/4	4300	41/4	4750
<u>33</u>	33/4	3150	41/2	4400	41/2	<u>4875</u>
36	4	3300	$4\frac{3}{4}$	4500	43/4	5000

^A Subject to tolerances in Section 11.

Document Preview

- 5.2 Acceptance as to Strength Properties—Pipe shall be acceptable under the strength tests when they have met the requirements as prescribed in 10.3.
- 5.3 Acceptance as to Absorption Properties—Pipe shall be acceptable under the absorption test when they have met the requirements as prescribed in 10.4.
- 5.4 Acceptance as to Permeability Properties—Pipe shall be acceptable under the permeability test when they have met the requirements as prescribed in 10.5.
 - Note 2—Prior to purchase, the owner has the option to specify the hydrostatic test prescribed in 10.610.6 instead of the permeability test.
- 5.5 Acceptance as to Hydrostatic Properties—Pipe shall be acceptable under the hydrostatic test when they have met the requirements as prescribed in 10.6.

6. Materials

- 6.1 Concrete—The concrete shall consist of cementitious materials, mineral aggregates, and water.
- 6.2 Cementitious Materials:
- 6.2.1 *Cement*—Cement shall conform to the requirements for portland cement of Specification C150 or shall be portland blast-furnace slag cement or slag modified portland cement, or portland-pozzolan cement conforming to the requirements of Specification C595, except that the pozzolan constituent in the Type IP portland–pozzolan cement shall be fly ash.
 - 6.2.2 Fly Ash—Fly ash shall conform to the requirements of Specification C618, Class F or Class C.
- 6.2.3 Ground Granulated Blast Furnace Slag (GGBFS)—GGBFS shall conform to the requirements of Grade 100 or 120 of Specification C989.
- 6.2.4 *Allowable Combinations of Cementitious Materials*—The combination of cementitious materials used in the concrete shall be one of the following:
 - 6.2.4.1 Portland cement only,
 - 6.2.4.2 Portland blast furnace slag cement only,
 - 6.2.4.3 Slag modified portland cement only,
 - 6.2.4.4 Portland pozzolan cement only,