



Designation: C172/C172M – 14

Standard Practice for Sampling Freshly Mixed Concrete¹

This standard is issued under the fixed designation C172/C172M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This practice covers procedures for obtaining representative samples of fresh concrete as delivered to the project site on which tests are to be performed to determine compliance with quality requirements of the specifications under which the concrete is furnished (Note 1). The practice includes sampling from stationary, paving and truck mixers, and from agitating and nonagitating equipment used to transport central-mixed concrete and from continuous mixing equipment as described in Specification C685/C685M.

1.2 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

NOTE 1—Composite samples are required by this practice, unless specifically excepted by procedures governing the tests to be performed such as tests to determine uniformity of consistency and mixer efficiency. Procedures used to select the specific test batches are not described in this practice, but it is recommended that random sampling be used to determine overall specification compliance.

1.3 This practice also covers the procedures to be used for preparing a sample of concrete for further testing where it is desirable or necessary to remove the aggregate larger than a designated size. This removal of larger aggregate particles is preferably accomplished by wet-sieving.

1.4 The text of this standard references notes and footnotes which provide explanatory material and shall not be considered as requirements of the practice.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* (Warning—Fresh

hydraulic cementitious mixtures are caustic and may cause chemical burns to skin and tissue upon prolonged exposure.²)

2. Referenced Documents

2.1 *ASTM Standards*:³

E11 Specification for Woven Wire Test Sieve Cloth and Test Sieves

C685/C685M Specification for Concrete Made by Volumetric Batching and Continuous Mixing

3. Significance and Use

3.1 This practice is intended to provide standard requirements and procedures for sampling freshly mixed concrete from different containers used in the production or transportation of concrete. The detailed requirements as to materials, mixtures, air content, temperature, number of specimens, slump, interpretation of results, and precision and bias are in specific test methods.

4. Sampling

4.1 The elapsed time shall not exceed 15 min. between obtaining the first and final portions of the composite sample.

4.1.1 Transport the individual samples to the place where fresh concrete tests are to be performed or where test specimens are to be molded. They shall be combined and remixed with a shovel the minimum amount necessary to ensure uniformity and compliance with the maximum time limits specified in 4.1.2.

4.1.2 Start tests for slump, temperature, and air content within 5 min after obtaining the final portion of the composite sample. Complete these tests expeditiously. Start molding specimens for strength tests within 15 min after fabricating the composite sample. Expeditiously obtain and use the sample and protect the sample from the sun, wind, and other sources of rapid evaporation, and from contamination.

¹ This practice is under the jurisdiction of ASTM Committee C09 on Concrete and Concrete Aggregates and is the direct responsibility of Subcommittee C09.60 on Testing Fresh Concrete.

Current edition approved Feb. 1, 2014. Published February 2014. Originally approved in 1942. Last previous edition approved in 2010 as C172–10. DOI: 10.1520/C0172_C0172M-14.

² Section on Safety Precautions, Manual of Aggregate and Concrete Testing, *Annual Book of ASTM Standards*, Vol 04.02.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard