



Designation: **C1038/C1038M – 10 C1038/C1038M – 14**

Standard Test Method for Expansion of Hydraulic Cement Mortar Bars Stored in Water¹

This standard is issued under the fixed designation C1038/C1038M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

1. Scope*

1.1 This test method covers the determination of the expansion of mortar bars made using hydraulic cement, of which sulfate is an integral part.

1.2 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use. (Warning —Fresh hydraulic cementitious mixtures are caustic and may cause chemical burns to skin and tissue upon prolonged exposure.²)*

2. Referenced Documents

2.1 *ASTM Standards:*³

C109/C109M Test Method for Compressive Strength of Hydraulic Cement Mortars (Using 2-in. or [50-mm] Cube Specimens)

C305 Practice for Mechanical Mixing of Hydraulic Cement Pastes and Mortars of Plastic Consistency

C490 Practice for Use of Apparatus for the Determination of Length Change of Hardened Cement Paste, Mortar, and Concrete

C511 Specification for Mixing Rooms, Moist Cabinets, Moist Rooms, and Water Storage Tanks Used in the Testing of Hydraulic Cements and Concretes

C778 Specification for Sand

C1005 Specification for Reference Masses and Devices for Determining Mass and Volume for Use in the Physical Testing of Hydraulic Cements

C1437 Test Method for Flow of Hydraulic Cement Mortar

D1193 Specification for Reagent Water

3. Significance and Use

3.1 This test method is used to determine the amount of expansion of a mortar bar when it is stored in water. The amount of mortar-bar expansion may relate to the amount of sulfate in the cement; expansion may become excessive when the cement contains too much sulfate.

3.2 Some cement specifications limit the amount of sulfate contained in hydraulic cement by requiring that the amount of expansion in water not exceed a specified value.

4. Apparatus

4.1 *Reference Masses and Mass-Determining Devices*, conforming to the requirements of Specification **C1005**. Evaluate the device for precision and bias at a total load of 2 Kg.

4.2 *Glass Graduates, Molds, and Length Comparator*, conforming to the requirements of Specification **C490**.

¹ This test method is under the jurisdiction of ASTM Committee **C01** on Cement and is the direct responsibility of Subcommittee **C01.28** on Sulfate Content. Current edition approved June 15, 2010. Jan. 15, 2014. Published July 2010. March 2014. Originally approved in 1985. Last previous edition approved in 2004 as **C1038-04-10**. DOI: 10.1520/C1038-C1038M-10.10.1520/C1038_C1038M-14.

² Section on Safety, *Manual of Cement Testing, Annual Book of Standards*, Vol. 04.01.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard

- 4.3 *Moist Cabinet or Room*, conforming to the requirements of Specification **C511**.
- 4.4 *Mixer, Bowl, and Paddle*, conforming to the requirements of Practice **C305**.
- 4.5 *Trowel and Tamper*, conforming to the requirements of Test Method **C109/C109M**.

5. Temperature and Relative Humidity

5.1 *Molding Room, Dry Materials, and Mixing Water*—Maintain the temperature of the molding room, dry materials, and mixing water at 23.0 ± 4.0 °C [77.0 – 73.5 ± 7.0 °F], and maintain the relative humidity of the molding room at not less than 50 %.

6. Reagents and Materials

6.1 *Mixing Water*—Potable water is satisfactory for routine tests. For all cooperative tests and in case of dispute, use reagent water conforming to the numerical limits of Type III of Specification **D1193**.

6.2 *Graded Sand*—Sand for making the test specimens shall conform to the requirements for graded standard sand in Specification **C778**.

7. Procedure

7.1 *Number and Dimensions of Test Specimens*—Make four 25 by 25 by 285-mm [1 by 1 by 11¼-in.] test specimens for each cement. The effective gage length of these specimens is 250 mm [10 in.].

NOTE 1—In routine tests, 25 by 25 by 160-mm [1 by 1 by 6¼-in.] specimens may be used; however, in case of dispute, results obtained with 25 by 25 by 285-mm [1 by 1 by 11¼-in.] specimens shall govern. The effective gage length of this specimen is 125 mm [5 in.].

7.2 *Specimen Molds*—Prepare the specimen molds in accordance with the requirements of Specification **C490**, except cover the interior surfaces of the mold with a release agent. A release agent will be acceptable if it serves as a parting agent without affecting the setting of the cement and without leaving any residue which will reduce the penetration of water into the specimen.

NOTE 2—TFE-fluorocarbon tape complies with the requirements for a mold release agent.

7.3 *Proportioning, Consistency, and Mixing of Mortar:*

7.3.1 The quantity of dry materials required to prepare four 25 by 25 by 285-mm [1 by 1 by 11¼-in.] specimens is 500 g of cement and 1375 g of graded sand. Use an amount of mixing water that produces a flow of 110 ± 5 as determined by the flow table after 25 drops in 15 s as described in Test Method **C1437**. Record the amount of water used to the nearest millilitre.

7.3.2 Mix the mortar in accordance with the procedure described in Practice **C305**.

7.4 *Molding Test Specimens*—Immediately upon completion of mixing, remove the paddle and the bowl from the mixer and shake the excess mortar from the paddle into the bowl. Fill the mold in two layers, compacting each layer with the tamper. Work the mortar into the corners, around the gage studs, and along the surfaces of the mold with the tamper until a homogeneous specimen is obtained. After the top layer has been compacted, cut the mortar off flush with the top of the mold and smooth the surface with a few strokes of the trowel.

8. Storage of Test Specimens

8.1 *Initial Storage*—Immediately upon completion of molding, place the test specimens in the moist cabinet or moist room. Keep all test specimens in the molds in the moist cabinet or moist room for 22.5 ± 0.5 h with upper surfaces exposed to the moist air but protected from dripping water. After this time, remove the specimens from the molds, properly identify, and place in water or saturated lime water maintained at 23.0 ± 2.0 °C [77 – 73.5 ± 43.5 °F] for at least 30 min prior to making the initial measurement.

8.2 *Subsequent Storage*—After the initial measurement, store the test specimens in saturated lime water in a tank in the moist cabinet or moist room. Cover the specimens with at least 5-mm [¼-in.] of water during storage. Keep the storage water clean by changing as necessary. Use a tank and lime water conforming to the requirements of Specification **C511**.

9. Length Change Measurement

9.1 Remove the specimens from water storage, one at a time, and wipe only the gage studs with a damp cloth before measuring. Make length-comparator readings. The effective gage length of specimens is 250 mm [10 in.] for the standard mold size.

9.2 Make the first reading at the age of $24 \text{ h} \pm 15 \text{ min}$ from the time the cement and water are mixed together. Make additional length-comparator readings at the age of 14 days.

NOTE 3—Additional information of value may be obtained by making length-comparator readings of the specimens at ages earlier and later than 14 days.

10. Calculation and Report

10.1 Calculate the change in length of the specimen at 24 h and at 14 days to the nearest 0.001 % of the effective gage length and report as the expansion of the specimen at that period. Report the average length of change of the four specimens to the nearest 0.001 %.