



Designation: D1600 – 14

Standard Terminology for Abbreviated Terms Relating to Plastics¹

This standard is issued under the fixed designation D1600; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 The purpose of this terminology is to provide uniform contractions of terms relating to plastics. Abbreviated terminology has evolved through widespread common usage. This compilation has been prepared to avoid both the occurrence of more than one abbreviated term for a given plastics term and multiple meanings for abbreviated terms.

1.2 The scope of these abbreviated terms includes plastics terms pertaining to composition and relating to type or kind according to mode of preparation or principle distinguishing characteristics. Also included are abbreviated terms for terms relating to copolymers, blends and alloys of plastics, and additives such as plasticizers, fillers, etc.

NOTE 1—A code relating to the composition of rubbers is given in Practice D1418.

1.3 No attempt is made here to systematize formally a shorthand terminology for polymers. Terminology, including nomenclature, codes, symbols, and formula designations for use in scientific literature in the field of natural and synthetic polymers, are being studied and standardized by the International Union of Pure and Applied Chemistry.²

1.4 These abbreviated terms are by no means all-inclusive of plastics terminology. They represent, in general, those terms that have come into established use. Since it is recognized that abbreviated terms serve no useful purpose unless they are generally accepted and used, no attempt has been made to establish a rigorous code for devising standard abbreviated terms. This would result in awkward departures from established usage of existing and accepted abbreviated terms and lead to cumbersome combinations in the future, which would not be likely to receive widespread acceptance. The abbreviated terms now in use have grown naturally out of the need for convenient, readily comprehended shorthand for long chemical names. This process can be expected to continue along the

natural lines of least resistance and will serve as a basis for further standardization as the need arises. A general guide for the preparation of abbreviated terms appears desirable, however, to facilitate more organized and uniform standardization in the future. An appendix is attached, which suggests a uniform way to prepare abbreviated terms.

1.5 Note that the uppercase letter F should be used to designate phosphate and that other elements may also be designated F.

1.6 An abbreviated term (FR) and code numbers are provided to identify classes of materials used as flame retardants added to plastics. The system is provided for use in situations where marking of plastics products is desired.

NOTE 2—Many of the abbreviated terms, codes, numbers, and symbols in ISO 1043 parts 1 through 4 and in ISO/DIS 1043-4 are the same as the corresponding item in ASTM D1600. D1600 includes a number of abbreviated terms that are not in ISO 1043.

2. Referenced Documents

2.1 *ASTM Standards*:³

D883 Terminology Relating to Plastics

D1418 Practice for Rubber and Rubber Latices—Nomenclature

D1972 Practice for Generic Marking of Plastic Products (Withdrawn 2014)⁴

2.2 *ISO Standards*:⁵

ISO 472:1988 Plastics—Vocabulary

ISO 1043-1:2001 Plastics—Symbols—Part 1: Basic Polymers and Their Special Characteristics

ISO 1043-2:2000 Plastics—Symbols—Part 2: Fillers and Reinforcing Materials

ISO 1043-3:1996 Plastics—Symbols—Part 3: Plasticizers

ISO 1043-4:1998 Plastics—Symbols and Abbreviated Terms—Part 4: Flame Retardants

¹ This terminology is under the jurisdiction of ASTM Committee D20 on Plastics and is the direct responsibility of Subcommittee D20.92 on Terminology.

Current edition approved Feb. 1, 2014. Published March 2014. Originally approved in 1958. Last previous edition approved in 2013 as D1600 - 13. DOI: 10.1520/D1600-14.

² "Report on Nomenclature in the Field of Macromolecules," *Journal of Polymer Science*, Vol VIII, 1952, pp. 257–277.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

⁴ The last approved version of this historical standard is referenced on www.astm.org.

⁵ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

*A Summary of Changes section appears at the end of this standard

3. Terminology

3.1 Definitions:

3.1.1 For definitions of general terms, see Terminology D883.

3.2 Definitions of Terms Specific to This Standard:

3.2.1 *flame retardant, FR, n*—a substance that markedly retards the propagation of a flame. (See ISO 472.)

3.2.1.1 *Discussion*—Flame retardants may be incorporated in plastics as additives (external flame retardant) or as chemical groups in the base polymer by use of reactive intermediates in the polymerization process (internal flame retardant). The code numbers in this standard are restricted to external flame retardants.

4. Terms and Abbreviated Terms

4.1 Plastics and Resins:⁶

Term	Abbreviated Term	Term	Abbreviated Term
Acrylonitrile/butadiene plastics	AB	Epoxy, epoxide	EP
Acrylonitrile-butadiene-acrylate plastics	ABA	Ethyl cellulose	EC
Acrylonitrile-butadiene-styrene plastics	ABS	Ethylene acrylate	EA
Acrylonitrile-chlorinated polyethylene-styrene plastics	ACPES	Ethylene-chlorotrifluoroethylene copolymer	E-CTFE
Acrylonitrile-ethylene-styrene plastics	AES	Ethylene-ethyl acrylate plastics	EEA
Acrylonitrile-methyl acrylate-acrylonitrile-butadiene rubber	AMAB	Ethylene-methacrylic acid plastics	EMA
Acrylonitrile-methyl methacrylate plastics	AMMA	Ethylene-propylene polymer	EPM
Acrylonitrile-styrene-acrylate plastics	ASA	Ethylene-propylene-diene plastics	EPD
Acrylonitrile/ethylene-propylene-diene/styrene	AEPDMS	Ethylene-tetrafluoroethylene copolymer	ETFE
Aromatic polyester	ARP	Ethylene-vinyl acetate plastics	EVA
		Ethylene-vinyl alcohol copolymer	EVOH
Carboxymethyl cellulose	CMC	Fluorocarbon perfluoromethoxy	MPA
Casein	CS	Furan formaldehyde resin	FF
Caseine-formaldehyde resin	CSF	General purpose polystyrene	GPSS
Cellulose acetate	CA	High density polyethylene plastics	HDPE
Cellulose acetate-butyrate	CAB	High impact-resistant polystyrene	HIPS
Cellulose acetate propionate	CAP	Impact resistant polystyrene	IPS
Cellulose formaldehyde	CEF	Linear low density polyethylene plastics	LLDPE
Cellulose nitrate	CN	Linear medium density polyethylene plastics	LMDPE
Cellulose plastics, general	CE	Liquid crystal polymer	LCP
Cellulose propionate	CP	Low density polyethylene plastics	LDPE
Cellulose triacetate	CTA	Medium density polyethylene plastics	MDPE
Chlorinated poly(vinyl chloride)	CPVC	Melamine-formaldehyde resin	MF
Chlorinated polyethylene	CPE	Melamine/phenol-formaldehyde resin	MPF
Cresol-formaldehyde resin	CF	Methacrylate-butadiene-styrene plastics	MBS
		Methyl cellulose	MC
		Methyl methacrylate-acrylonitrile-butadiene-styrene resin	MMABS
		Nylon (see also polyamide)	PA
		Perfluoro(alkoxy alkane)	PFA
		Perfluoro(ethylene-propylene) copolymer	FEP
		Perfluoromethoxy resin	MFA
		Phenol-formaldehyde resin	PF
		Phenol-furfural resin	PFF
		Poly(acrylic acid)	PAA
		Poly(allyl diglycol carbonate)	PADC
		Poly(aryl ether ketone)	PAEK
		Poly(butyl acrylate)	PBA
		Poly(butylene adipate-co-succinate)	PBAS
		Poly(butylene adipate-co-terephthalate)	PBAT
		Poly(butylene succinate)	PBS
		Poly(butylene terephthalate)	PBT
		Poly(cyclohexylenedimethylene cyclohexandicarboxylate), glycoland acid comonomer	PCCE
		Poly(cyclohexylenedimethylene terephthalate)	PCT

⁶ To prevent any confusion with or misuse of the registered trademark, PET[®] Milk, the guidelines of 8.1 shall be followed.

Term	Abbreviated Term	Term	Abbreviated Term
Poly(cyclohexylenedimethylene terephthalate), acid comonomer	PCTA	Polyisobutylene	PIB
Poly(cyclohexylenedimethylene terephthalate), glycol	PCTG	Polyisocyanurate	PIR
Poly(diallyl phthalate)	PDAP	Polyketone	PK
Poly(ester urethane)	PAUR	Polymethacrylimide	PMI
Poly(ether block amide)	PEBA	Polyoxymethylene, polyacetal	POM
Poly(ether sulfone)	PES	Polyphenylene	PPH
Poly(ether urethane)	PEUR	Polyphthalamide	PPA
Poly(ethylene furanoate)	PEF	Polypropylene	PP
Poly(ethylene oxide)	PEOX	Homopolymer polypropylene	HPP
Poly(ethylene terephthalate)	PET ⁶	Random copolymer polypropylene	RPP
Poly(ethylene terephthalate) acid comonomer	PETA	Impact copolymer polypropylene	CPP
Poly(ethylene terephthalate) glycol comonomer	PETG	Polystyrene	PS
Poly(lactic acid)	PLA	Polysulfone	PSU
Poly(methyl methacrylate)	PMMA	Polytetrafluoroethylene	PTFE
Poly(methyl methacrylimide)	PMMI	Polyurethane	PUR
Poly(methyl- α -chloroacrylate)	PMCA	Saturated polyester plastic	SP
Poly(phenyl sulfone)	PPSU	Silicone plastics	SI
Poly(phenylene ether) (or Poly(phenylene oxide), a deprecated term)	PPE	Styrene- α -methylstyrene plastic	SMS
Poly(phenylene sulfide)	PPS	Styrene-acrylonitrile plastic	SAN
Poly(phenylene sulfone)	PPSU	Styrene-butadiene plastic	SB
Poly(propylene oxide)	PPOX	Styrene-butadiene-styrene block copolymer	SBS
Poly(vinyl acetate)	PVAC	Styrene-ethylene/butylene-styrene block copolymer	SEBS
Poly(vinyl alcohol)	PVOH	Styrene-ethylene/propylene-styrene block copolymer	SEPS
Poly(vinyl butyral)	PVB	Styrene-isoprene-styrene block copolymer	SIS
Poly(vinyl carbazole)	PVK	Styrene-maleic anhydride plastics	S/MA
Poly(vinyl chloride)	PVC	Styrene-rubber plastics	SRP
Poly(vinyl chloride-acetate)	PVCA	Thermoplastic elastomer	TPE
Poly(vinyl fluoride)	PVF	Thermoplastic elastomer, ether-ester	TEEE
Poly(vinyl formal)	PVFM	Thermoplastic elastomer, fully crosslinked elastomer alloy	FCEA
Poly(vinyl pyrrolidone)	PVP	Thermoplastic elastomer, highly crosslinked thermoplastic vulcanizate	HCTPV
Poly(vinylidene chloride)	PVDC	Thermoplastic elastomer, olefinic	TEO
Poly(vinylidene fluoride)	PVDF	Thermoplastic elastomer, polyether block amide	PEBA
Poly(ϵ -caprolactone)	PCL	Thermoplastic elastomer, styrenic	TES
Poly-4-methylpentene-1	PMP	Thermoplastic elastomer styrenic, saturated	TESS
Poly- α -methylstyrene	PMS	Thermoplastic elastomer styrenic, unsaturated	TESU
Poly-p-oxybenzoate	POB	Thermoplastic polyester	TPES
Polyacrylonitrile	PAN	Thermoplastic polyester:	
Polyamide (nylon)	PA	Copolyester [poly(aryl terephthalate)]	ARP
Polyamide 10	PA10	Polyarylate [poly(aryl terephthalate)]—liquid crystal	PAT
Polyamide 1010	PA1010		
Polyamide 11	PA11		
Polyamide 12	PA12		
Polyamide 1212	PA1212		
Polyamide 46	PA46		
Polyamide 410	PA410	Thermoplastic polyurethane	TPU
Polyamide 6	PA6	Thermoplastic polyurethane, reinforced	RTPU
Polyamide 610	PA610	Thermoplastic starch	TPS
Polyamide 612	PA612	Thermoset polyurethane	TSPU
Polyamide 66	PA66	Ultra-high molecular weight polyethylene	UHMWPE
Polyamide 69	PA69	Unsaturated polyester	UP
Polyamide 6I	PA6I	Urea-formaldehyde resin	UF
Polyamide 6T	PA6T		
Polyamide-imide	PAI	Vinyl chloride-ethylene resin	VCE
Polyarylate	PAR	Vinyl chloride-ethylene-methyl acrylate resin	VCEMA
Polyaryl amide	PARA	Vinyl chloride-ethylene-vinyl acetate resin	VCEVAC
Polyarylether	PAE	Vinyl chloride-methyl acrylate resin	VCMA
Polyarylsulfone	PAS	Vinyl chloride-methyl methacrylate resin	VCMAA
Polybutadiene-acrylonitrile	PBAN	Vinyl chloride-octyl acrylate resin	VCOA
Polybutadiene-styrene	PBS	Vinyl chloride-vinyl acetate resin	VCVAC
Polybutene-1	PB	Vinyl chloride-vinylidene chloride resin	VCVDC
Polycarbonate	PC	Vinylidene fluoride	VDF
Polychlorotrifluoroethylene	PCTFE		
Polyester alkyd (or polyacrylate)	PAK		
Polyetheretherketone	PEEK		
Polyetheretherketoneketone	PEEKK		
Polyetherketoneetherketoneketone	PEKEKK		
Polyetherketoneketone	PEKK		
Polyetherimide	PEI		
Polyetherketone	PEK		
Polyethylene	PE		
Poly(ethylene naphthalate)	PEN		
Polyhydroxy butyrate	PHB		
Polyimide	PI		
Polyimidesulfone	PISU		

4.2 Blends and Alloys of Plastics:

Term	Abbreviated Term
Acrylonitrile-butadiene-acrylate plastics + poly(methyl methacrylate)	ABA+PMMA
Acrylonitrile-butadiene-acrylate plastics+poly(vinyl chloride)	ABA+PVC
Acrylonitrile-butadiene-acrylate plastics+polycarbonate	ABA+PC
Acrylonitrile-butadiene-styrene plastics+poly(vinyl chloride)	ABS+PVC
Acrylonitrile-butadiene-styrene plastics+polyphenylene sulfone	ABS+PPSU

Term	Abbreviated Term	Term	Abbreviated Term
Acrylonitrile-butadiene-styrene plastics+polytetrafluoroethylene	ABS+PTFE	Diisohexyl phthalate	DIHXP
Acrylonitrile-butadiene-styrene plastics+styrene maleic anhydride	ABS+SMA	Diisononyl adipate	DINA
Acrylonitrile-butadiene-styrene plastics+thermoplastic polyurethane	ABS+TPU	Diisononyl phthalate	DINP
Acrylonitrile-butadiene-styrene plastics+polyamide	ABS+PA	Diisooctyl adipate	DIOA
Acrylonitrile-butadiene-styrene plastics+polycarbonate	ABS+PC	Diisooctyl phthalate	DIOP
Acrylonitrile-styrene-acrylate plastics+poly(methyl methacrylate)	ASA+PMMA	Diisopentyl phthalate	DIPP
Acrylonitrile-styrene-acrylate plastics+polycarbonate	ASA+PC	Diisotridecyl phthalate	DITDP
Fully crosslinked elastomeric alloy	FCEA	Dimethyl phthalate	DMP
Poly(butylene terephthalate)+poly(ethylene terephthalate)	PBT+PET ⁶	Dinonyl phthalate	DNP
Poly(butylene terephthalate)+rubber	Abbreviated PBT+RBR	Diocetyl adipate	DOA
Poly(ethylene naphthalate)	PEN	Diocetyl azelate	DOZ
Poly(ethylene terephthalate)+poly(methyl methacrylate)	PET ⁶ +PMMA	Diocetyl isophthalate (di-2-ethylhexyl isophthalate)	DOIP
Poly(ethylene terephthalate)+poly(phenylene sulfone)	PET ⁶ +PPSU	Diocetyl phthalate	DOP
Poly(ethylene terephthalate)+rubber	PET ⁶ +RBR	Diocetyl sebacate	DOS
Poly(phenylene ether)+impact resistant polystyrene	PPE+IPS	Diocetyl terephthalate (di-2-ethylhexyl terephthalate)	DOTP
Poly(phenylene sulfide)+polytetrafluoroethylene	PPS+PTFE	Diphenyl octyl phosphate	DPOF
Poly(vinyl chloride)+chlorinated polyethylene	PVC+CPE	Diphenyl cresyl phosphate	DPCF
Poly(vinyl chloride)+nitrile-butadiene rubber	PVC+NBR	Diphenyl 2-ethylhexyl phosphate	DPOF
Poly(vinyl chloride)+poly(methyl methacrylate)	PVC+PMMA	Diundecyl phthalate	DUP
Poly(vinyl chloride) plastics+polyurethane	PVC+PUR	Epoxidized linseed oil	ELO
Polyamide (amorphous) blend	PA +	Epoxidized soya bean oil	ESO
Polyamide plastics+ethylene-methacrylic acid (ionomer)	PA+EMA	Heptyl nonyl undecyl adipate	HNUA
Polyamide+poly(phenylene ether)	PA+PPE	Heptyl nonyl undecyl phthalate	HNUP
Polyamide+polyethylene	PA+PE	Hexyl octyl decyl adipate	HXODA
Polyamide+rubber	PA+RBR	Hexyl octyl decyl phthalate	HXODP
Polyamide+styrene-acrylonitrile plastics	PA+SAN	n-Octyl decyl trimellitate	ODTM
Polycarbonate+poly(butylene terephthalate)	PC+PBT	Nonyl undecyl adipate	NUA
Polycarbonate+poly(ethylene terephthalate)	PC+PET ⁶	Nonyl undecyl phthalate	NUP
Polycarbonate+polyethylene	PC+PE	Octyl decyl adipate	ODA
Polycarbonate+styrene-maleic anhydride	PC+SMA	Octyl decyl phthalate	ODP
Polycarbonate+thermoplastic polyurethane	PC+TPU	Tetraoctyl pyromellitate (tetra-2-ethylhexyl pyromellitate)	TOPM
Polyoxymethylene+polytetrafluoroethylene	POM+PTFE	Trichloroethyl phosphate	TCEF
Polyoxymethylene+rubber	POM+RBR	Tricresyl phosphate (or tritolyl phosphate)	TCF
Polyurethane+polyisocyanate	PUR+PIR	Triheptyl trimellitate	THTM
Styrene-maleic anhydride plastics+impact resistant polystyrene	SMA+IPS	Triisooctyl trimellitate	TIOTM
Thermoplastic elastomer-chlorinated ethylene alloy	TECEA	Triocetyl phosphate	TOF
		Triocetyl trimellitate (tri-2-ethylhexyl trimellitate)	TOTM
		Triphenyl phosphate	TPP
		Trixylyl phosphate	TXF

4.4 Monomers:

NOTE 3—In general, blends and alloys of plastics shall be identified as Abbreviation 1+ Abbreviation 2 + Abbreviation n, where abbreviation n represents the abbreviation for component n, and the percentage, by weight, of component 1 > the percentage, by weight of component 2 > the percentage, by weight of component n.

4.3 Plastic and Resin Additives:

Term	Abbreviated Term	Term	Abbreviated Term
Alkylsulfonic acid ester	ASE	Adipic acid	AA
Benzyl butyl phthalate	BBP	Allyl diglycol carbonate	ADC
Benzyl octyl adipate (benzyl 2-ethylhexyl adipate)	BOA	Butanediol	BD
Benzyl octyl phthalate (benzyl 2-ethylhexyl phthalate)	BOP	Chlorotrifluoroethylene	CTFE
Di-n-octyl phthalate	DNOP	Diallyl chlorendate (diallyl ester of 1,4,5,6,7,7-hexachlorobicyclo-(2,2,1)-5-heptene-2,3-dicarboxylic acid)	DAC
Dibutylphthalate	DBP	Diallyl fumarate	DAF
Dibutyl sebacate	DBS	Diallyl isophthalate	DAIP
Dicapryl phthalate	DCP	Diallyl maleate	DAM
Dicylohexyl phthalate	DCHP	Diallyl phthalate (diallyl orthophthalate)	DAP
Didecyl phthalate	DDP	Ethylene	ET
Diethyl phthalate	DEP	Ethylene Glycol	EG
Diheptyl phthalate	DHP	Lactic acid	LA
Dihexyl phthalate	DHXP	Methyl methacrylate	MMA
Diisobutyl phthalate	DIBP	Propylene	PR
Diisodecyl adipate	DIDA	Succinic acid	SA
Diisodecyl phthalate	DIDP	p-Terephthalic acid	PTA
Diisohexyl phthalate	DIHP		

Term	Abbreviated Term	Term	Abbreviated Term
Tetrafluoroethylene	TFE	Diallyl chlorendate (diallyl ester of 1,4,5,6,7,7-hexachloro-	DAC
Triallyl cyanurate	TAC	bicyclo-(2,2,1)-5-heptene-2,3-dicarboxylic acid)	

4.5 Miscellaneous Plastics Terms:

Term	Abbreviated Term	Term	Abbreviated Term
General purpose	GP	Diallyl fumarate	DAF
Single stage	SS	Diallyl isophthalate	DAIP
		Diallyl maleate	DAM
		Diallyl phthalate (diallyl orthophthalate)	DAP
		Dibutyl phthalate	DBP
		Dibutyl sebacate	DBS
		Dicapryl phthalate	DCP
		Dicyclohexyl phthalate	DCHP
		Didecyl phthalate	DDP
		Diethyl phthalate	DEP
		Diheptyl phthalate	DHP
		Dihexyl phthalate	DHXP
		Diisobutyl phthalate	DIBP
		Diisodecyl adipate	DIDA
		Diisodecyl phthalate	DIDP
		Diisoheptyl phthalate	DIHP
		Diisohexyl phthalate	DIHXP
		Diisononyl adipate	DINA
		Diisononyl phthalate	DINP
		Diisooctyl adipate	DIOA
		Diisooctyl phthalate	DIOP
		Diisopentyl phthalate	DIPP
		Diisotridecyl phthalate	DITDP
		Dimethyl phthalate	DMP
		Dinonyl phthalate	DNP
		Diocetyl adipate	DOA
		Diocetyl azelate	DOZ
		Diocetyl isophthalate (di-2-ethylhexyl isophthalate)	DOIP
		Diocetyl phthalate	DOP
		Diocetyl sebacate	DOS
		Diocetyl terephthalate (di-2-ethylhexyl terephthalate)	DOTP
		Diphenyl 2-ethylhexyl phosphate	DPOF
		Diphenyl cresyl phosphate	DPCF
		Diphenyl octyl phosphate	DPOF
		Diundecyl phthalate	DUP
		Epoxidized linseed oil	ELO
		Epoxidized soya bean oil	ESO
		Epoxy, epoxide	EP
		Ethyl cellulose	EC
		Ethylene	ET
		Ethylene acrylate	EA
		Ethylene-chlorotrifluoroethylene copolymer	E-CTFE
		Ethylene-ethyl acrylate plastics	EEA
		Ethylene Glycol	EG
		Ethylene-methacrylic acid plastics	EMA
		Ethylene-propylene polymer	EPM
		Ethylene-propylene-diene plastics	EPD
		Ethylene-tetrafluoroethylene copolymer	ETFE
		Ethylene-vinyl acetate plastics	EVA
		Ethlene-vinyl alcohol copolymer	EVOH
		Fluorocarbon perfluoromethoxy	MPA
		Fully crosslinked elastomeric alloy	FCEA
		Furan-formaldehyde resin	FF
		General purpose	GP
		General purpose polystyrene	GPPS
		Heptyl nonyl undecyl adipate	HNUA
		Heptyl nonyl undecyl phthalate	HNUP
		Hexyl octyl decyl adipate	HXODA
		Hexyl octyl decyl phthalate	HXODP
		High density polyethylene plastics	HDPE
		High impact-resistant polystyrene	HIPS
		Homopolymer polypropylene	HPP
		Impact copolymer polypropylene	CPP
		Impact resistant polystyrene	IPS
		Lactic acid	LA

NOTE 4—When listing one or more components, the order preferably should be in decreasing amount by mass. There are situations, however, where long standing usage indicates that this recommendation should not be followed. An example is ETFE.

5. Full List by Term and Abbreviated Term

Term	Abbreviated Term	Term	Abbreviated Term
Acrylonitrile-butadiene-acrylate plastics+poly(methyl methacrylate)	ABA+PMMA		
Acrylonitrile-butadiene-acrylate plastics+poly(vinyl chloride)	ABA+PVC		
Acrylonitrile-butadiene-acrylate plastics+polycarbonate	ABA+PC		
Acrylonitrile-butadiene-acrylate plastics	ABA		
Acrylonitrile-butadiene-styrene plastics+poly(vinyl chloride)	ABS+PVC		
Acrylonitrile-butadiene-styrene plastics+polyphenylene sulfone	ABS+PPSU		
Acrylonitrile-butadiene-styrene plastics+polytetrafluoroethylene	ABS+PTFE		
Acrylonitrile-butadiene-styrene plastics+styrene maleic anhydride	ABS+SMA		
Acrylonitrile-butadiene-styrene plastics+thermoplastic polyurethane	ABS+TPU		
Acrylonitrile-butadiene plastics	AB		
Acrylonitrile-butadiene-styrene plastics+polyamide	ABS+PA		
Acrylonitrile-butadiene-styrene plastics+polycarbonate	ABS+PC		
Acrylonitrile-chlorinated polyethylene-styrene plastics	ACPE		
Acrylonitrile-ethylene-styrene plastics	AES		
Acrylonitrile-methyl acrylate-acrylonitrile-butadiene rubber	AMAB		
Acrylonitrile-methyl methacrylate plastics	AMMA		
Acrylonitrile-styrene-acrylate plastics+poly(methyl methacrylate)	ASA+PMMA		
Acrylonitrile-styrene-acrylate plastics+poly(vinyl chloride)	ASA+PVC		
Acrylonitrile-styrene-acrylate plastics	ASA		
Acrylonitrile-styrene-acrylate plastics+polycarbonate	ASA+PC		
Acrylonitrile/ethylene-propylene-diene/styrene plastics	AEPDMS		
Adipic Acid	AA		
Alkylsulfonic acid ester	ASE		
Allyl diglycol carbonate	ADC		
Aromatic polyester	ARP		
Benzyl butyl phthalate	BBP		
Benzyl octyl adipate (benzyl 2-ethylhexyl adipate)	BOA		
Benzyl octyl phthalate (benzyl 2-ethylhexyl phthalate)	BOP		
Butanediol	BD		
Carboxymethyl cellulose	CMC		
Casein	CS		
Caseine-formaldehyde resin	CSF		
Cellulose acetate	CA		
Cellulose acetate-butyrate	CAB		
Cellulose acetate-propionate	CAP		
Cellulose formaldehyde	CEF		
Cellulose nitrate	CN		
Cellulose plastics, general	CE		
Cellulose propionate	CP		
Cellulose triacetate	CTA		
Chlorinated poly(vinyl chloride)	CPVC		
Chlorinated polyethylene	CPE		
Chlorotrifluoroethylene	CTFE		
Cresol-formaldehyde resin	CF		
Di-n-octyl phthalate	DNOP		

Term	Abbreviated Term	Term	Abbreviated Term
Linear low density polyethylene plastics	LLDPE	Poly(vinyl chloride)+nitrile-butadiene rubber	PVC+NBR
Linear medium density polyethylene plastics	LMDPE	Poly(vinyl chloride)+poly(methyl methacrylate)	PVC+PMMA
Liquid crystal polymer	LCP	Poly(vinyl chloride) plastics+polyurethane	PVC+PUR
Low density polyethylene plastics	LDPE	Poly(vinyl chloride-acetate)	PVCA
		Poly(vinyl fluoride)	PVF
Medium density polyethylene plastics	MDPE	Poly(vinyl formal)	PVFM
Melamine-formaldehyde resin	MF	Poly(vinyl pyrrolidone)	PVP
Melamine/phenol-formaldehyde resin	MPF	Poly(vinylidene chloride)	PVDC
Methacrylate-butadiene-styrene plastics	MBS	Poly(vinylidene fluoride)	PVDF
Methyl cellulose	MC	Poly(ϵ -caprolactone)	PCL
Methyl methacrylate	MMA	Poly-4-methyl pentene-1	PMP
Methyl methacrylate-acrylonitrile-butadiene-styrene resin	MMABS	Poly- α -methylstyrene	PMS
		Poly-p-oxybenzoate	POB
		Polyacrylonitrile	PAN
n-Octyl decyl trimellitate	ODTM	Polyamide (amorphous) blend	PA +
Nonyl undecyl adipate	NUA	Polyamide (nylon)	PA
Nonyl undecyl phthalate	NUP	Polyamide 10	PA10
Nylon (See also <i>polyamide</i>)	PA	Polyamide 1010	PA1010
		Polyamide 11	PA11
Octyl decyl adipate	ODA	Polyamide 12	PA12
Octyl decyl phthalate	ODP	Polyamide 1212	PA1212
		Polyamide 46	PA46
Perfluoro(alkoxy alkane)	PFA	Polyamide 6	PA6
Perfluoro(ethylene-propylene) copolymer	FEP	Polyamide 610	PA610
Perfluoromethoxy resin	MFA	Polyamide 612	PA612
Phenol-formaldehyde resin	PF	Polyamide 66	PA66
Phenol-furfural resin	PFF	Polyamide 69	PA69
Poly(acrylic acid)	PAA	Polyamide 6I	PA6I
Poly(allyl diglycol carbonate)	PADC	Polyamide 6T	PA6T
Poly(aryl ether ketone)	PAEK	Polyamide plastics+ethylene-methacrylic acid (ionomer)	PA+EMA
Poly(butyl acrylate)	PBA		
Poly(butylene terephthalate)	PBT	Polyamide+poly(phenylene ether)	PA+PPE
Poly(butylene terephthalate)+poly(ethylene terephthalate)	PBT+PET ⁶	Polyamide+polyethylene	PA+PE
		Polyamide+rubber	PA+RBR
Poly(butylene terephthalate)+poly(phenylene ether)	PBT+PPE	Polyamide+styrene-acrylonitrile plastics	PA+SAN
Poly(butylene terephthalate)+rubber	PBT+RBR	Polyamide-imide	PAI
Poly(cyclohexylenedimethylene cyclohexandicarboxylate), glycol and acid comonomer	PCCE	Polyarylate	PAR
		Polyaryl amide	PARA
Poly(cyclohexylenedimethylene terephthalate)	PCT	Polyarylether	PAE
Poly(cyclohexylenedimethylene terephthalate), acid comonomer	PCTA	Polyarylsulfone	PASU
		Polybutadiene-acrylonitrile	PBAN
Poly(cyclohexylenedimethylene terephthalate), glycol comonomer	PCTG	Polybutadiene-styrene	PBS
Poly(diallyl phthalate)	PDAP	Polybutene-1	PB
Poly(ester urethane)	PAUR	Polycarbonate	PC
Poly(ether block amide)	PEBA	Polycarbonate+poly(butylene terephthalate)	PC+PBT
Poly(ether sulfone)	PES	Polycarbonate+poly(ethylene terephthalate)	PC+PC+PET ⁶
Poly(ether urethane)	PEUR	Polycarbonate+polyethylene	PC+PE
Poly(ethylene furanoate)	PEF	Polycarbonate+styrene-maleic anhydride	PC+SMA
Poly(ethylene naphthalate)	PEN	Polycarbonate+thermoplastic polyurethane	PC+TPU
Poly(ethylene oxide)	PEOX	Polychlorotrifluoroethylene	PCTFE
Poly(ethylene terephthalate)	PET ⁶	Polyester alkyd (or polyacrylate)	PAK
Poly(ethylene terephthalate)+poly(methyl methacrylate)	PET ⁶ +PMMA	Polyester, thermoplastic; polyarylate [poly(aryl terephthalate)]—liquid crystal polymer	PAT
		Polyetheretherketone	PEEK
Poly(ethylene terephthalate)+poly(phenylene sulfone)	PET ⁶ +PPSU	Polyetheretherketoneketone	PEEKK
		Polyetherketoneetherketoneketone	PEKEKK
Poly(ethylene terephthalate) acid	PETA	Polyetherketoneketone	PEKK
Poly(ethylene terephthalate), glycol comonomer	PETG	Polyetherizimide	PEI
Poly(lactic acid)	PLA	Polyetherketone	PEK
Poly(methyl methacrylate)	PMMA	Polyethylene	PE
Poly(methyl methacrylimide)	PMMI	Polyhydroxy butyrate	PHB
Poly(methyl- α -chloroacrylate)	PMCA	Polyhydroxy butyrate-polyhydroxy valerate	PHBV
Poly(phenyl sulfone)	PPSU	Polyimide	PI
Poly(phenylene ether) (or poly(phenylene oxide), a deprecated term)	PPE	Polyimidesulfone	PISU
Poly(phenylene ether)+impact resistant polystyrene	PPE+IPS	Polyisobutylene	PIB
Poly(phenylene sulfide)	PPS	Polyisocyanurate	PIR
Poly(phenylene sulfide)+polytetrafluoroethylene	PPS+PTFE	Polyketone	PK
Poly(phenylene sulfone)	PPSU	Polymethacrylimide	PMI
Poly(propylene oxide)	PPOX	Polyoxymethylene+polytetrafluoroethylene	POM+PTFE
Poly(vinyl acetate)	PVAC	Polyoxymethylene+rubber	POM+RBR
Poly(vinyl alcohol)	PVOH	Polyoxymethylene, polyacetal	POM
Poly(vinyl butyral)	PVB	Polyphenylene	PPH
Poly(vinyl carbazole)	PVK	Polyphthalamide	PPA
Poly(vinyl chloride)	PVC	Polypropylene	PP
Poly(vinyl chloride)+chlorinated polyethylene	PVC+CPE	Homopolymer polypropylene	HPP