



Designation: **D2377 – 00 (Reapproved 2008) D2377 – 14**

Standard Test Method for Tack-Free Time of Caulking Compounds and Sealants¹

This standard is issued under the fixed designation D2377; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method describes the determination of the tack-free time property of caulking compounds and sealants. This test method is applicable to both gun and knife grades.

1.2 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

1.4 The committee with jurisdiction over this standard is not aware of any comparable standard published by other organizations.

2. Referenced Documents

2.1 *ASTM Standards:*²

[C717 Terminology of Building Seals and Sealants](#)

3. Terminology

3.1 *Definitions*—Refer to Terminology [C717](#) for definitions of the following terms: caulking compound, compound, sealant.

4. Apparatus

4.1 *Cabinet or Room*, capable of maintaining a temperature of $73.4 \pm 3.6^\circ\text{F}$ Standard Conditions as defined in Terminology [C717](#) ($23 \pm 2^\circ\text{C}$) at $50 \pm 5\%$ relative humidity for extended periods of time.

4.2 *Brass Sheet*, $\frac{3}{4}$ by $1\frac{1}{2}$ in. (19 by 38 mm), approximately $\frac{1}{4}$ in. (6.4 mm) thick.

4.3 *Template*—A rectangular template of steel or brass, $\frac{1}{8}$ in. (3.2 mm) thick, 1 by $3\frac{3}{4}$ in. (25.4 by 95.1 mm) inside, and approximately 2 by $4\frac{3}{4}$ in. (51 by 121 mm) outside.

4.4 *Steel Sheets*—Two rectangular tin-plated steel sheets, approximately 3 by 5 in. (76 by 127 mm), and of a convenient thickness.

4.5 *Plastic Strips*—Two, clear, low-density polyethylene strips, 1 by 5 in. (25.4 by 127 mm) by 0.004 ± 0.001 in. (0.1016 ± 0.0254 mm) thick.

4.6 *Spatula*, steel, having a 4 to 5-in. (102 to 127-mm) long narrow blade.

4.7 *Thin Knife Blade*.

5. Solvent

5.1 *Methyl Ethyl Ketone, Ethylene Dichloride*, or similar solvent.

¹ This test method is under the jurisdiction of ASTM Committee [C24](#) on Building Seals and Sealants and is the direct responsibility of Subcommittee [C24.20](#) on General Test Methods.

Current edition approved ~~May 1, 2008~~ Feb. 1, 2014. Published ~~June 2008~~ March 2014. Originally approved in 1965. Last previous edition approved in ~~2006~~ 2008 as D2377 – 00 (2006) (2008). DOI: ~~10.1520/D2377-00R08~~ 10.1520/D2377-14.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.