



Designation: D5208 – 14

# Standard Practice for Fluorescent Ultraviolet (UV) Exposure of Photodegradable Plastics<sup>1</sup>

This standard is issued under the fixed designation D5208; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope\*

1.1 This practice covers the specific procedures applicable for fluorescent Ultraviolet (UV) exposure of photodegradable plastics conducted in accordance with Practices [G151](#) and [G154](#). This practice also covers the preparation of test specimens and the evaluation of test results.

1.2 Practice [D4329](#) covers fluorescent UV exposures of plastics intended for long term use in outdoor applications.

1.3 The values stated in SI units are to be regarded as standard. The values given in parentheses are for information only.

1.4 *This standard does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

NOTE 1—There is no known ISO equivalent to this standard.

## 2. Referenced Documents

### 2.1 ASTM Standards:<sup>2</sup>

[D3826](#) Practice for Determining Degradation End Point in Degradable Polyethylene and Polypropylene Using a Tensile Test

[D4329](#) Practice for Fluorescent Ultraviolet (UV) Lamp Apparatus Exposure of Plastics

[D5870](#) Practice for Calculating Property Retention Index of Plastics

[E691](#) Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method

[G113](#) Terminology Relating to Natural and Artificial Weathering Tests of Nonmetallic Materials

<sup>1</sup> This practice is under the jurisdiction of ASTM Committee [D20](#) on Plastics and is the direct responsibility of Subcommittee [D20.96](#) on Environmentally Degradable Plastics and Biobased Products.

Current edition approved April 1, 2014. Published April 2014. Originally approved in 1991. Last previous edition approved in 2009 as D5208 - 09. DOI: 10.1520/D5208-14.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

[G141](#) Guide for Addressing Variability in Exposure Testing of Nonmetallic Materials

[G147](#) Practice for Conditioning and Handling of Nonmetallic Materials for Natural and Artificial Weathering Tests

[G151](#) Practice for Exposing Nonmetallic Materials in Accelerated Test Devices that Use Laboratory Light Sources

[G154](#) Practice for Operating Fluorescent Ultraviolet (UV) Lamp Apparatus for Exposure of Nonmetallic Materials

[G169](#) Guide for Application of Basic Statistical Methods to Weathering Tests

## 3. Terminology

3.1 The definitions given in Terminology [G113](#) are applicable to this practice.

## 4. Significance and Use

4.1 Materials made from photodegradable plastics are intended to show relatively rapid deterioration of chemical, physical, and mechanical properties when exposed to light, heat, and water after fulfilling their intended purpose. This practice is intended to induce property changes associated with conditions that might be experienced when the material is discarded as litter, including the effects of sunlight, moisture, and heat. The exposure used in this practice is not intended to simulate the deterioration caused by localized weather phenomena such as atmospheric pollution, biological attack, and salt water exposure.

4.2 *Cautions*—Variation in results can be expected when operating conditions are varied within the accepted limits of this practice. Therefore, no reference to the use of this practice shall be made unless accompanied by a report prepared in accordance with Section 9 that describes the specific operating conditions used. Refer to Practice [G151](#) for detailed information on the caveats applicable to use of results obtained in accordance with this practice.

NOTE 2—Additional information on sources of variability and on strategies for addressing variability in the design, execution and data analysis of laboratory accelerated exposure tests is found in Guide [G141](#).

4.3 Exposure of a similar material of known performance (a control) at the same time as the test specimens provides a standard for comparative purposes. Use of a control to rank the stability of test materials greatly improves agreement between

\*A Summary of Changes section appears at the end of this standard

different laboratories.<sup>3,4</sup> It is recommended that at least three replicates of each material evaluated be exposed to allow for statistical evaluation of results.

4.4 Test results will depend upon the care that is taken to operate the equipment in accordance with Practice **G154**. Significant factors include regulation of line voltage, temperature of the room in which the device operates, temperature control, and condition and age of the lamps, if exposure is conducted in a device without irradiance control.

## 5. Apparatus

5.1 Use of fluorescent UV apparatus that conform to the requirements defined in Practices **G151** and **G154** is required to conform to this practice.

5.2 The spectral power distribution of the fluorescent UV lamp shall conform to the requirements in Practice **G154** for a UVA 340 lamp.

### 5.3 Test Chamber Location:

5.3.1 Locate the apparatus in an area maintained between 18 and 27°C (65 and 80°F). Control of ambient temperature is particularly critical when one apparatus is stacked above another, because the heat generated from the lower unit can interfere with the operation of the units above.

5.3.2 Place the apparatus at least 300 mm from walls or other apparatus. Do not place the apparatus near a heat source such as an oven.

5.3.3 Ventilate the room in which the apparatus is located to remove heat and moisture.

## 6. Test Specimens

6.1 The size and shape of specimens to be exposed will be determined by the specifications of the particular test method used to evaluate the effects of the exposure on the specimens; the test method shall be determined by the parties concerned. Where practical, it is recommended that specimens be sized to fit specimen holders and racks supplied with the exposure apparatus. Unless supplied with a specific backing as an integral part of the test, specimens shall be mounted so that only the minimum specimen area required for support by the holder shall be covered. This unexposed surface must not be used as part of the test area.

6.2 For specimens of insulating materials, such as foams, maximum specimen thickness is 20 mm in order to allow for adequate heat transfer for condensation.

6.3 To provide rigidity, attach flexible specimens to a backing panel made of aluminum, 0.635 mm (0.025 mm) thick. Suggested aluminum alloys are 5052, 6061, or 3003.

6.4 Seal any holes in specimens larger than two mm and any openings larger than one mm around irregularly shaped speci-

mens to prevent loss of water vapor. Attach porous specimens to a solid backing such as aluminum that can act as a vapor barrier.

6.5 Unless otherwise specified, expose at least three replicate specimens of each test and control material.

6.6 Follow the procedures described in Practice **G147** for identification and conditioning and handling of specimens of test, control, and reference materials prior to, during, and after exposure.

6.7 Do not mask the face of a specimen for the purpose of showing on one panel the effects of various exposure times. Misleading results can be obtained by this method, since the masked portion of the specimen is still exposed to temperature and humidity cycles that, in many cases, will affect results.

6.8 Since the thickness of a specimen can markedly affect the results, thickness of test and control specimens shall be within  $\pm 10\%$  of the nominal dimensions.

NOTE 3—This is especially important when mechanical properties are being investigated.

6.9 Retain a supply of unexposed file specimens of all materials tested.

6.10 Specimens shall not be removed from the exposure apparatus for more than 24 h and then returned for additional tests, since this will not produce the same results on all materials as tests run without this type of interruption. Report any elapsed time as noted under Section 9.

NOTE 4—Since the stability of the file specimen can also be time-dependent, users are cautioned that over prolonged exposure periods, or where small differences in the order of acceptable limits are anticipated, comparison of exposed specimens with the file specimen are not necessarily valid. Instrumental measurements are recommended whenever possible.

## 7. Procedure

7.1 When the test and control specimens do not completely fill the specimen racks, fill all empty spaces with blank panels to maintain the test conditions within the chamber.

7.2 Unless otherwise specified, control irradiance at 0.89 W/(m<sup>2</sup> · nm) at 340 nm.

NOTE 5—In devices without irradiance control operated at  $50 \pm 3^\circ\text{C}$  uninsulated black panel temperature the typical irradiance at 340 nm is 0.89 W/(m<sup>2</sup> · nm). (See Note 1 of Table X2.1 in Practice **G154** for a full explanation of the current default irradiance.)

7.2.1 During equilibrium operation, the allowed deviation from the 340 nm set point is  $\pm 0.02$  W/(m<sup>2</sup> · nm). If the indicated irradiance is outside the tolerance, stop the test and correct the problem before continuing.

7.3 Unless otherwise specified, program the device to one of the following test cycles.

7.3.1 *Cycle A*—20 h UV (light only) with uninsulated black panel temperature controlled at 50°C.

4 h Dark/condensation with uninsulated black panel temperature controlled at 40°C.

Repeat this 24-hour cycle continuously until the desired total exposure is reached.

<sup>3</sup> Fischer, R., "Results of Round Robin Studies of Light- and Water-Exposure Standard Practices," *Accelerated and Outdoor Durability Testing of Organic Materials*, ASTM STP 1202, Warren D. Ketola and Douglas Grossman, Eds., American Society for Testing and Materials, Philadelphia, 1993.

<sup>4</sup> Ketola, W., and Fischer, R., "Characterization and Use of Reference Materials in Accelerated Durability Tests," VAMAS Technical Report No. 30. Available from NIST, Gaithersburg, MD.