



Designation: **A743/A743M – 13a A743/A743M – 13a<sup>ε1</sup>**

## Standard Specification for Castings, Iron-Chromium, Iron-Chromium-Nickel, Corrosion Resistant, for General Application<sup>1</sup>

This standard is issued under the fixed designation A743/A743M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the U.S. Department of Defense.*

---

<sup>ε1</sup> NOTE—Table 2 and Table S12.1 were editorially corrected in January 2014.

---

### 1. Scope\*

1.1 This specification covers iron-chromium and iron-chromium-nickel alloy castings for general corrosion-resistant application. The grades covered by this specification represent types of alloy castings suitable for broad ranges of application which are intended for a wide variety of corrosion environments.

NOTE 1—For alloy castings for severe corrosion-resistant service, reference should be made to Specification **A744/A744M**. For general heat-resistant alloy castings, reference should be made to Specification **A297/A297M**. For nickel alloy castings for corrosion-resistant service, reference should be made to Specification **A494/A494M**.

1.2 The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other. Combining values from the two systems may result in nonconformance with the specification. Inch-pound units are applicable for material ordered to Specification A743 and SI units for material ordered to Specification A743M.

### 2. Referenced Documents

#### 2.1 ASTM Standards:<sup>2</sup>

**A262** Practices for Detecting Susceptibility to Intergranular Attack in Austenitic Stainless Steels

**A297/A297M** Specification for Steel Castings, Iron-Chromium and Iron-Chromium-Nickel, Heat Resistant, for General Application

**A370** Test Methods and Definitions for Mechanical Testing of Steel Products

**A494/A494M** Specification for Castings, Nickel and Nickel Alloy

**A744/A744M** Specification for Castings, Iron-Chromium-Nickel, Corrosion Resistant, for Severe Service

**A781/A781M** Specification for Castings, Steel and Alloy, Common Requirements, for General Industrial Use

**A890/A890M** Specification for Castings, Iron-Chromium-Nickel-Molybdenum Corrosion-Resistant, Duplex (Austenitic/Ferritic) for General Application

**A957** Specification for Investment Castings, Steel and Alloy, Common Requirements, for General Industrial Use

### 3. General Conditions for Delivery

3.1 Except for investment castings, castings furnished to this specification shall conform to the requirements of Specification **A781/A781M**, including any supplementary requirements that are indicated on the purchase order. Failure to comply with the general requirements of Specification **A781/A781M** constitutes nonconformance with this specification. In case of conflict between the requirements of this specification and Specification **A781/A781M**, this specification shall prevail.

3.2 Steel investment castings furnished to this specification shall conform to the requirements of Specification **A957**, including any supplementary requirements that are indicated in the purchase order. Failure to comply with the general requirements of

---

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee **A01** on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee **A01.18** on Castings.

Current edition approved May 15, 2013. Published June 2013. Originally approved in 1977. Last previous edition approved in 2013 as A743/A743M – 13. DOI: [10.1520/A0743-A0743M-13A](https://doi.org/10.1520/A0743-A0743M-13A); [10.1520/A0743-A0743M-13AE01](https://doi.org/10.1520/A0743-A0743M-13AE01).

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

\*A Summary of Changes section appears at the end of this standard

Specification **A957** constitutes nonconformance with this specification. In case of conflict between the requirements of this specification and Specification **A957**, Specification **A957** shall prevail.

#### 4. Ordering Information

- 4.1 Orders for material to this specification should include the following, as required, to describe the material adequately:
- 4.1.1 Description of the casting by pattern number or drawing,
  - 4.1.2 Grade,
  - 4.1.3 Heat treatment,
  - 4.1.4 Options in the specification,
  - 4.1.5 Whether castings are to be produced using the investment casting process, and
  - 4.1.6 Supplementary requirements desired, including the standards of acceptance.

#### 5. Process

5.1 The steel shall be made by the electric furnace process with or without separate refining such as argon-oxygen decarburization (AOD).

#### 6. Heat Treatment

6.1 Castings shall be heat treated in accordance with the requirements in **Table 1**.

**TABLE 1 Heat Treatment Requirements**

Grade	Heat Treatment
CA6N	Heat to 1900°F [1040°C], air cool, reheat to 1500°F [815°C], air cool, and age at 800°F [425°C], holding at each temperature sufficient time to heat casting uniformly to temperature.
CA6NM	Heat to 1850°F [1010°C] minimum, air cool to 200°F [95°C] or lower prior to any optional intermediate temper and prior to the final temper. The final temper shall be between 1050°F [565°C] and 1150°F [620°C].
CA15, CA15M, CA40, CA40F	(1) Heat to 1750°F [955°C] minimum, air cool and temper at 1100°F [595°C] minimum, or (2) Anneal at 1450°F [790°C] minimum.
CA28MWW	(1) Heat to 1875–1925°F [1025–1050°C], quench in air or oil, and temper at 1150°F [620°C] minimum, or (2) Anneal at 1400°F [760°C] minimum.
CB30, CC50	(1) Heat to 1450°F [790°C] minimum, and air cool, or (2) Heat to 1450°F [790°C] minimum, and furnace cool.
CB6	Heat between 1800°F [980°C] and 1920°F [1050°C], forced air, cool to 120°F [50°C] maximum, and temper between 1100°F and 1160°F [595°C and 625°C].
CE30, CH10, CH20, CK20	Heat to 2000°F [1093°C] minimum, hold for sufficient time to heat casting to temperature, quench in water or rapid cool by other means.
CF3, CF3M, CF3MN	(1) Heat to 1900°F [1040°C] minimum, hold for sufficient time to heat casting to temperature, quench in water or rapid cool by other means. (2) As cast if corrosion resistance is acceptable.
CF8, CF8C, CF8M, CF16F, CF16Fa, CF20, CG3M, CG8M, CG12	Heat to 1900°F [1040°C] minimum, hold for sufficient time to heat casting to temperature, quench in water or rapid cool by other means.
CF10SMnN	Heat to 1950°F [1065°C] minimum, hold for sufficient time to heat casting to temperature, quench in water or rapid cool by other means.
CK3MCuN, CK35MN, CN3M, CN3MN	Heat to 2200°F [1200°C] minimum, hold for 4 hours minimum, quench in water or rapid cool by other means.
CG6MMN, CN7M	Heat to 2050°F [1120°C] minimum, hold for sufficient time to heat casting to temperature, quench in water or rapid cool by other means.
CN7MS	Heat to 2100°F [1150°C] minimum, 2150°F [1180°C] maximum, hold for sufficient time (2 h minimum) to heat casting to temperature and quench in water.
HG10MNN	As-cast

NOTE 2—Proper heat treatment of these alloys is usually necessary to enhance corrosion resistance and in some cases to meet mechanical properties. Minimum heat treat temperatures are specified; however, it is sometimes necessary to heat treat at higher temperatures, hold for some minimum time at temperature and then rapidly cool the castings in order to enhance the corrosion resistance and meet mechanical properties.

#### 7. Chemical Requirements

7.1 The chemical requirements are shown in **Table 2**.

**TABLE 2 Chemical Requirements**

Grade (UNS)	Type	Composition, %													
		Carbon, max	Manganese, max	Silicon, max	Phosphorus, max	Sulfur, max	Chromium	Nickel	Molybdenum	Columbium	Selenium	Copper	Tungsten, max	Vanadium, max	Nitrogen
CA6N	11 Chromium, 7 Nickel	0.06	0.50	1.00	0.02	0.02	10.5–12.5	6.0–8.0	...	...	...	...	...	...	...
CA6NM (J91540)	12 Chromium, 4 Nickel	0.06	1.00	1.00	0.04	0.03	11.5–14.0	3.5–4.5	0.40–1.0	...	...	...	...	...	...

**TABLE 2** *Continued*

Grade (UNS)	Type	Composition, %													
		Carbon, max	Man- ganese, max	Silicon, max	Phospho- rus, max	Sulfur, max	Chromium	Nickel	Molybde- num	Colum- bium	Sele- nium	Copper	Tung- sten, max	Vana- dium, max	Nitrogen
CA15 (J91150)	12 Chromium	0.15	1.00	1.50	0.04	0.04	11.5–14.0	1.00 max	0.50 max	...	...	...	...	...	...
CA15M (J91151)	12 Chromium	0.15	1.00	0.65	0.040	0.040	11.5–14.0	1.0 max	0.15–1.0	...	...	...	...	...	...
CA28MWV (J91422)	12 Chromium, with Molybdenum, Tungsten and Vanadium	0.20– 0.28	0.50– 1.00	1.0	0.030	0.030	11.0–12.5	0.50– 1.00	0.90–1.25	...	...	0.90– 1.25	0.20– 0.30	...	...
CA40 (J91153)	12 Chromium	0.20– 0.40	1.00	1.50	0.04	0.04	11.5–14.0	1.0 max	0.5 max	...	...	...	...	...	...
CA40F (J91154)	12 Chromium, Free Machining	0.20– 0.40	1.00	1.50	0.04	0.20– 0.40	11.5–14.0	1.0 max	0.5 max	...	...	...	...	...	...
CB6 (J91804)	16 Chromium, 4 Nickel	0.06	1.00	1.00	0.04	0.03	15.5–17.5	3.5–5.5	0.5 max	...	...	...	...	...	...
CB30 (J91803)	20 Chromium	0.30	1.00	1.50	0.04	0.04	18.0–21.0	2.00 max	...	...	<i>B</i>	...	...	...	...
CC50 (J92615)	28 Chromium	0.50	1.00	1.50	0.04	0.04	26.0–30.0	4.00 max	...	...	...	...	...	...	...
CE30 (J93423)	29 Chromium, 9 Nickel	0.30	1.50	2.00	0.04	0.04	26.0–30.0	8.0– 11.0	...	...	...	...	...	...	...
CF3 (J92500)	19 Chromium, 9 Nickel	0.03	1.50	2.00	0.04	0.04	17.0–21.0	8.0– 12.0	...	...	...	...	...	...	...
CF3M (J92800)	19 Chromium, 10 Nickel, with Molybdenum	0.03	1.50	1.50	0.04	0.04	17.0–21.0	9.0– 13.0	2.0–3.0	...	...	...	...	...	...
CF3MN (J92804)	19 Chromium, 10 Nickel, with Molybdenum, and Nitrogen	0.03	1.50	1.50	0.040	0.040	17.0–22.0	9.0– 13.0	2.0–3.0	...	...	...	...	...	0.10– 0.20
CF8 (J92600)	19 Chromium, 9 Nickel	0.08	1.50	2.00	0.04	0.04	18.0–21.0	8.0– 11.0	...	...	...	...	...	...	...
CF8C (J92710)	19 Chromium, 10 Nickel, with Columbium	0.08	1.50	2.00	0.04	0.04	18.0–21.0	9.0– 12.0	...	<i>A</i>	...	...	...	...	...
CF8M (J92900)	19 Chromium, 10 Nickel, with Molybdenum	0.08	1.50	2.00	0.04	0.04	18.0–21.0	9.0– 12.0	2.0–3.0	...	...	...	...	...	...
CF10SMnN (J92972)	17 Chromium, 8.5 Nickel with Nitrogen	0.10	7.00– 9.00	3.50– 4.50	0.060	0.030	16.0–18.0	8.0– 9.0	...	...	...	...	...	...	0.08– 0.18
CF16F (J92701)	19 Chromium, 9 Nickel, Free Machining	0.16	1.50	2.00	0.17	0.04	18.0–21.0	9.0– 12.0	1.50 max	...	0.20– 0.35	...	...	...	...
CF16Fa	19 Chromium, 9 Nickel, Free Machining	0.16	1.50	2.00	0.04	0.20– 0.40	18.0–21.0	9.0– 12.0	0.40–0.80	...	...	...	...	...	...
CF20 (J92602)	19 Chromium, 9 Nickel	0.20	1.50	2.00	0.04	0.04	18.0–21.0	8.0– 11.0	...	...	...	...	...	...	...
CG3M (J92999)	19 Chromium, 11 Nickel, with Molybdenum	0.03	1.50	1.50	0.04	0.04	18.0–21.0	9.0– 13.0	3.0–4.0	...	...	...	...	...	...

**TABLE 2 Continued**

Grade (UNS)	Type	Composition, %													
		Carbon, max	Manganese, max	Silicon, max	Phosphorus, max	Sulfur, max	Chromium	Nickel	Molybdenum	Columbium	Selenium	Copper	Tungsten, max	Vanadium, max	Nitrogen
CG6MMN (J93790)		0.06	4.00–6.00	1.00	0.04	0.03	20.5–23.5	11.5–13.5	1.50–3.00	0.10–0.30	...	...	...	0.10–0.30	0.20–0.40
CG8M (J93000)	19 Chromium, 11 Nickel, with Molybdenum	0.08	1.50	1.50	0.04	0.04	18.0–21.0	9.0–13.0	3.0–4.0	...	...	...	...	...	...
CG12 (J93001)	22 Chromium, 12 Nickel	0.12	1.50	2.00	0.04	0.04	20.0–23.0	10.0–13.0	...	...	...	...	...	...	...
CH10 (J93401)	25 Chromium, 12 Nickel	0.10	1.50	2.00	0.04	0.04	22.0–26.0	12.0–15.0	...	...	...	...	...	...	...
CH20 (J93402)	25 Chromium, 12 Nickel	0.20	1.50	2.00	0.04	0.04	22.0–26.0	12.0–15.0	...	...	...	...	...	...	...
CK35MN	23 Chromium, 21 Nickel, with Molybdenum and Nitrogen	0.035	2.00	1.00	0.035	0.020	22.0–24.0	20.0–22.0	6.0–6.8	...	...	0.40	...	...	0.21–0.32
CK3MCuN (J93254)	20 Chromium 18 Nickel, with Copper and Molybdenum	0.025	1.20	1.00	0.045	0.010	19.5–20.5	17.5–19.5	6.0–7.0	...	...	0.50–1.00	...	...	0.180–0.240
CK20 (J94202)	25 Chromium, 20 Nickel	0.20	2.00	2.00	0.04	0.04	23.0–27.0	19.0–22.0	...	...	...	...	...	...	...
CN3M (J94652)		0.03	2.0	1.0	0.03	0.03	20.0–22.0	23.0–27.0	4.5–5.5	...	...	...	...	...	...
CN3MN (J94651)	21 Chromium, 24 Nickel with Molybdenum and Nitrogen	0.03	2.00	1.00	0.040	0.010	20.0–22.0	23.5–25.5	6.0–7.0	...	...	0.75 max	...	...	0.18–0.26
CN7M (N08007)	20 Chromium, 29 Nickel, with Copper and Molybdenum	0.07	1.50	1.50	0.04	0.04	19.0–22.0	27.5–30.5	2.0–3.0	...	...	3.0–4.0	...	...	...
CN7MS (J94650)	19 Chromium, 24 Nickel, with Copper and Molybdenum	0.07	1.00	2.50–3.50	0.04	0.03	18.0–20.0	22.0–25.0	2.5–3.0	...	...	1.5–2.0	...	...	...
HG10MNN J92604	19 Chromium, 12 Nickel, 4 Manganese	0.07–0.11	3.0–5.0	0.70	0.040	0.030	18.5–20.5	11.5–13.5	0.25–0.45	<sup>c</sup>	...	0.50	...	...	0.20–0.30

<sup>A</sup> Grade CF8C shall have a columbium content of not less than eight times the carbon content and not more than 1.0%. If a columbium-plus-tantalum alloy in the approximate Cb:Ta ratio of 3:1 is used for stabilizing this grade, the total columbium-plus-tantalum content shall not be less than nine times the carbon content and shall not exceed 1.1%.

<sup>B</sup> For Grade CB30 a copper content of 0.90 to 1.20% is optional.

<sup>C</sup> Grade HG10MNN shall have a columbium content of not less than eight times the carbon, but not over 1.00 %.

## 8. Repair by Welding

8.1 Repair welding of Grade CA28MWV is not permitted unless by agreement between the manufacturer and the purchaser.

8.2 When methods involving high temperature are used in the removal of discontinuities, castings shall be preheated in accordance with **Table 3**. Weld repairs shall be subject to the same quality standards as are used to inspect the castings.

**TABLE 3 Minimum Preheat Temperatures**

Grade	Minimum Preheat Temperatures	
	°F	°C
CA15, CA15M CA28MWV, CA40	400	[205]
Others	50	[10]