



Designation: ~~D2318 – 98 (Reapproved 2013)~~ **D2318 – 14**

## Standard Test Method for Quinoline-Insoluble (QI) Content of Tar and Pitch<sup>1</sup>

This standard is issued under the fixed designation D2318; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope-~~Scope~~\*

- 1.1 This test method covers the determination of the quinoline-insoluble matter (QI) in tar and pitch.
- 1.2 Since this test method is empirical, strict adherence to all details of the procedure is necessary.
- 1.3 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.
- 1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* For hazards information, see Section 7.

### 2. Referenced Documents

#### 2.1 ASTM Standards:<sup>2</sup>

- D71 Test Method for Relative Density of Solid Pitch and Asphalt (Displacement Method)
- D95 Test Method for Water in Petroleum Products and Bituminous Materials by Distillation
- D329 Specification for Acetone
- D362 Specification for Industrial Grade Toluene (Withdrawn 1989)<sup>3</sup>
- D850 Test Method for Distillation of Industrial Aromatic Hydrocarbons and Related Materials
- D4296 Practice for Sampling Pitch
- E1 Specification for ASTM Liquid-in-Glass Thermometers
- E11 Specification for Woven Wire Test Sieve Cloth and Test Sieves

### 3. Summary of Test Method

- 3.1 The sample is digested in hot quinoline and filtered. The insoluble material is washed, dried, and weighed.

### 4. Significance and Use

- 4.1 This test method is useful in evaluating and characterizing tar and pitch, and as one element in establishing the uniformity of shipments and sources of supply.

### 5. Apparatus

- 5.1 *Filtering Crucibles*, porcelain, with fine-porosity bottom, 25 to 40-mL capacity, high-form, maximum pore diameter, 7  $\mu\text{m}$ .
- 5.2 *Filter Apparatus*—Filter flask and tube with crucible adapter.
- 5.3 *Sieves*—U. S. Standard 600- $\mu\text{m}$  (No. 30) and 250- $\mu\text{m}$  (No. 60), conforming to Specification E11.
- 5.4 *Electric Hot Plate or Water Bath*, maintained at  $75 \pm 5^\circ\text{C}$ .

### 6. Reagents and Materials

- 6.1 *Quinoline, Refined*, meeting the following requirements:

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D02 on Petroleum Products—~~Products, Liquid Fuels,~~ and Lubricants and is the direct responsibility of Subcommittee D02.05 on Properties of Fuels, Petroleum Coke and Carbon Material.

Current edition approved July 15, 2013 May 1, 2014. Published August 2013 May 2014. Originally approved in 1964. Last previous edition approved in 2008 2013 as D2318 – 98 (2008) (2013). DOI: 10.1520/D2318-98R13-10.1520/D2318-14.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> The last approved version of this historical standard is referenced on www.astm.org.

\*A Summary of Changes section appears at the end of this standard

6.1.1 The quinoline shall distill from 5 to 95 % within a range of 2°C that shall include the temperature of 237.4°C after corrections for barometric pressure and emergent stem have been applied. The distillation shall be carried out in accordance with Test Method **D850** using a total immersion thermometer with a range from 195 to 305°C, graduated in 0.5°C, and conforming to the requirements for Thermometer 69C as described in Specification **E1**. Temperature measuring devices such as precision thermocouples, resistance temperature detectors (RTDs), and liquid-in-glass thermometers with equal or better accuracies in the appropriate temperature range may be used.

6.1.2 The quinoline shall have a specific gravity at 15.5/15.5°C of 1.092 to 1.098, as determined by Test Method **D71**, or other method of equivalent accuracy.

6.1.3 The quinoline shall be clear and light in color and shall contain less than 0.5 volume % of water as determined by Test Method **D95**. If not, redistill the quinoline in all-glass apparatus, discarding the first 5 % and collecting the next 90 %. If the quinoline contains suspended matter but is clear, light in color, and contains less than 0.5 % water, filter the quinoline through a crucible containing 5 g of Celite Filter Aid.

6.1.4 Store the quinoline in a tightly closed, dark bottle.

6.2 *Toluene, Industrial Pure*, meeting Specification **D362**.

6.3 *Acetone*, meeting Specification **D329**.

6.4 *Concentrated Hydrochloric Acid*.

6.5 *Celite Analytical Filter Aid (CAFA)*—Dry to constant weight at 105°C, and store in tightly stoppered container.

6.5.1 Do not use any other grade of filter aid because filtration characteristics may differ. CAFA is manufactured only by Manville Co. and distributed through scientific supply houses.

## 7. Hazards

7.1 Fumes of the solvents should be removed by means of proper hoods from all working areas. The working area should be kept free of sparks and flames. Quinoline fumes should not be inhaled, and prolonged contact with the skin should be avoided. Toluene is toxic and flammable.

7.2 Observe proper laboratory procedures for handling hydrochloric and diluting acid.

## 8. Bulk Sampling

8.1 Samples from shipments shall be taken in accordance with Practice **D4296** and shall be free of foreign substances. Thoroughly mix the sample immediately before removing a representative portion for the determination or for dehydration.

## 9. Dehydration of Sample

9.1 *Hard Pitch*—If the solid bulk sample contains free water, air-dry a representative portion in a forced draft oven at 50°C.

9.2 *Soft Pitch*—If the presence of water is indicated by surface foam on heating, maintain a representative portion of the bulk sample at a temperature between 125 and 150°C in an open container until the surface is free of foam. Take care not to overheat, and remove heat source immediately when foam subsides.

9.3 *Tar*—A wet tar sample may either be dehydrated or used as received as long as conditions stated in **9.3.1** and **9.3.2** are met.

9.3.1 Dehydrate a representative portion of the bulk sample at atmospheric pressure using a simple side-arm distillation apparatus similar to the one in Test Method **D850** and stop the distillation when the temperature reaches 170°C. Separate any oil from the water that has distilled over (if crystals are present, warm sufficiently to ensure their solution) and thoroughly mix the oil with the residual tar in the still after the latter has cooled to a moderate temperature.

9.3.2 As an alternative to dehydration, the water content of the tar is determined by Test Method **D95**, and if the water content is less than 10 mass %, the QI content is corrected to a dry-tar basis (see **13.2**). This alternative test method applies only to stable emulsions of water in tar, that is, no water separates when the tar sample is left undisturbed for 24 h at room temperature.

## 10. Preparation of Working Sample

10.1 *Hard Pitch*—If the pitch can be crushed at room temperature, prepare a 20-g working sample by suitable crushing, mixing, and quartering of a representative portion of the dry sample. The crushing can be done with a small jaw crusher and a mullite mortar and pestle. No particle in the representative sample shall be larger than 5 mm in any dimension. Crush this sample so that *all of it* will pass the 250- $\mu$ m (No. 60) sieve but will have a minimum of fine particles. Store the sieved working sample in a tightly closed container and use within 24 h (see **10.4**).

10.2 *Soft Pitch*—If the pitch is too soft to grind and too sticky to mix, heat a representative portion of the dry sample to the lowest temperature that will permit passage through the 600- $\mu$ m (No. 30) sieve, taking care to avoid excessive loss of volatile matter. Do not exceed 10 min for this melting period. Pass the heated sample through the 600- $\mu$ m sieve to remove foreign matter.

10.3 *Tar*—Heat a representative portion of the dry tar to the lowest temperature that will permit passage through the 600- $\mu$ m (No. 30) sieve, then filter through this sieve to remove foreign matter.