



Designation: **C772 – 03 (Reapproved 2009) C772 – 03 (Reapproved 2014)**

Standard Test Method for Oil Migration or Plasticizer Bleed-Out of Preformed Tape Sealants¹

This standard is issued under the fixed designation C772; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers a laboratory procedure that can be used to determine the oil migration or plasticizer bleed-out of preformed tape sealants.

1.2 The values stated in acceptable metric units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 The subcommittee with jurisdiction is not aware of any similar ISO standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[C717 Terminology of Building Seals and Sealants](#)

[D2203 Test Method for Staining from Sealants](#)

[E145 Specification for Gravity-Convection and Forced-Ventilation Ovens](#)

3. Terminology

3.1 *Definitions*—The definitions of the following terms used in this test method are found in Terminology [C717](#): preformed tape sealant, sealant.

4. Summary of Test Method

4.1 The preformed tape sealant to be tested is placed on filter paper. The specimen is heat aged and examined for migration into the filter paper.

5. Significance and Use

5.1 Preformed tape sealants are tacky, deformable solids that are used under compression between two substrates in a variety of sealing applications. In general, oil migration or plasticizer bleed-out is not desirable. However, in some limited instances, a controlled amount of plasticizer migration is sometimes desired in order to improve the penetration of the tape into the interstices of porous substrates. This test method is designed to indicate whether or not a preformed tape sealant exhibits oil or plasticizer migration and, if so, to what extent.

6. Apparatus

6.1 *Vented Air Circulating Oven*, that complies with Specification [E145](#) and is capable of aging samples at $70 \pm 2^\circ\text{C}$ ($158 \pm 3.6^\circ\text{F}$) or $100 \pm 2^\circ\text{C}$ ($212 \pm 3.6^\circ\text{F}$).

¹ This test method is under the jurisdiction of ASTM Committee [C24](#) on Building Seals and Sealants and is the direct responsibility of Subcommittee [C24.20](#) on General Test Methods.

Current edition approved ~~Jan. 1, 2009~~ June 1, 2014. Published ~~March 2009~~ July 2014. Originally approved in 1974. Last previous edition approved in ~~2003~~ 2009 as [C772 – 03](#); [C772 – 03\(2009\)](#). DOI: ~~10.1520/C0772-03R09~~ 10.1520/C0772-03R14.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.