



Standard Specification for Isotropic and Near-isotropic Nuclear Graphites¹

This standard is issued under the fixed designation D7219; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers the classification, processing, and properties of nuclear grade graphite billets with dimensions sufficient to meet the designer's requirements for fuel elements, moderator or reflector blocks, in a high temperature gas cooled reactor. The graphite classes specified here would be suitable for reactor core applications where neutron irradiation induced dimensional changes are a significant design consideration.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard. (See [IEEE/ASTM SI 10](#).)

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

[C559 Test Method for Bulk Density by Physical Measurements of Manufactured Carbon and Graphite Articles](#)

[C709 Terminology Relating to Manufactured Carbon and Graphite](#)

[C781 Practice for Testing Graphite and Boronated Graphite Materials for High-Temperature Gas-Cooled Nuclear Reactor Components](#)

[C838 Test Method for Bulk Density of As-Manufactured Carbon and Graphite Shapes](#)

[C1233 Practice for Determining Equivalent Boron Contents of Nuclear Materials](#)

[D346 Practice for Collection and Preparation of Coke Samples for Laboratory Analysis](#)

[D2638 Test Method for Real Density of Calcined Petroleum Coke by Helium Pycnometer](#)

[IEEE/ASTM SI 10 American National Standard for Use of the International System of Units \(SI\): The Modern Metric System](#)

2.2 ASME Standard:

[NQA-1 Quality Assurance Program Requirements for Nuclear Facilities³](#)

3. Terminology

3.1 *Definitions*—Definitions relating to this specification are given in Terminology [C709](#).

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *baking/re-baking charge*—number of billets in a baking/re-baking furnace run.

3.2.2 *bulk density*—mass of a unit volume of material including both permeable and impermeable voids.

3.2.3 *extrusion forming lot*—number of billets of the same size extruded in an uninterrupted sequence.

3.2.4 *green batch*—mass of coke, recycle green mix, recycle graphite, and pitch that is required to produce a forming lot.

3.2.5 *green mix*—percentage of mix formulation, pitch and additives required for the forming lot, which is processed and ready to be formed.

¹ This specification is under the jurisdiction of ASTM Committee [D02](#) on Petroleum Products—Products, Liquid Fuels, and Lubricants and is the direct responsibility of Subcommittee [D02.F0](#) on Manufactured Carbon and Graphite Products.

Current edition approved ~~May 1, 2008~~ May 1, 2014. Published ~~July 2008~~ July 2014. Originally approved in 2005. Last previous edition approved in ~~2005~~ 2008 as [D7219D7219 – 08, 05](#). DOI: [10.1520/D7219-08](#); [10.1520/D7219-08R14](#).

² For referenced ASTM standards, visit the ASTM website, [www.astm.org](#), or contact ASTM Customer Service at [service@astm.org](#). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from American Society of Mechanical Engineers (ASME), ASME International Headquarters, Three Park Ave., New York, NY 10016-5990.

TABLE 1 ASTM Standard Classes of Nuclear Graphite

Class ^A	CTE Isotropy Ratio ^B (a_{AG}/a_{WG})	Purity		Bulk Density, ^C g/cm ³ (min)	Class Designation
		Ash Content, ^B ppm (max)	Boron Equivalent, ^D ppm (max)		
Isomolded, isotropic—High Purity	1.0-1.1	300	2	1.7	IIHP
Isomolded, isotropic—Low Purity	1.0-1.1	1000	10	1.7	IILP
Isomolded, near-isotropic—High Purity	1.1-1.15	300	2	1.7	INHP
Isomolded, near-isotropic—Low Purity	1.1-1.15	1000	10	1.7	INLP
Extruded, isotropic—High Purity	1.0-1.1	300	2	1.7	EIHP
Extruded, isotropic—Low Purity	1.0-1.1	1000	10	1.7	EILP
Extruded, near-isotropic—High Purity	1.1-1.15	300	2	1.7	ENHP
Extruded, near-isotropic—Low Purity	1.1-1.15	1000	10	1.7	ENLP
Molded, isotropic—High Purity	1.0-1.1	300	2	1.7	MIHP
Molded, isotropic—Low Purity	1.0-1.1	1000	10	1.7	MILP
Molded, near-isotropic—High Purity	1.1-1.15	300	2	1.7	MNHP
Molded, near-isotropic—Low Purity	1.1-1.15	1000	10	1.7	MNLP

^A These classes may be further modified by the grain size as defined in Terminology C709 (see Table 2).

^B Determined in accordance with Practice C781.

^C Determined in accordance with Test Method C559.

^D Determined in accordance with Practice C1233.

3.2.6 *graphite billet*—extruded, molded, or iso-molded graphite artifact with dimensions sufficient to meet the designer's requirements for reactor components.

3.2.7 *graphite grade*—designation given to a material by a manufacturer such that it is always reproduced to the same specification and from the same raw materials and mix formulation.

3.2.8 *graphitization charge*—number of billets of the same grade in a graphitizing furnace run.

3.2.9 *graphitizing furnace run*—total number of billets graphitized together in one graphitization furnace.

3.2.10 *high purity nuclear graphite*—nuclear graphite with an Equivalent Boron Content less than 2 ppm.

3.2.11 *impregnation charge*—number of billets in an autoclave cycle.

3.2.12 *isotropic nuclear graphite*—graphite in which the isotropy ratio based on the coefficient of thermal expansion is 1.00 to 1.10.

3.2.13 *low purity nuclear graphite*—nuclear graphite with an Equivalent Boron Content greater than 2 ppm but less than 10 ppm.

3.2.14 *mix formulation*—percentages of each specifically sized filler used to manufacture a graphite grade.

3.2.15 *molding forming lot*—number of billets molded from a molding powder lot.

3.2.16 *molding powder lot*—sufficient quantity of re-milled and blended green batch produced from an uninterrupted flow of raw materials, or produced in a sequence of identical materials batches, to produce a molding forming lot.

3.2.17 *near isotropic nuclear graphite*—graphite in which the isotropy ratio based on the coefficient of thermal expansion is 1.10 to 1.15.

3.2.18 *nuclear graphite class*—designation of a nuclear graphite based upon its forming method, isotropy, purity and density (see Table 1).

3.2.19 *production lot*—specified number of billets made in accordance with this specification and additional requirements determined by the purchaser.

3.2.20 *purification charge*—number of billets in a purification run.

3.2.21 *recycle green mix*—ground non-baked billets or non used green mix manufactured in compliance with the mix formulation specified here.

4. Significance and Use

4.1 The purpose of this specification is to document the minimum acceptable properties and levels of quality assurance and traceability for isotropic and near-isotropic nuclear grade graphites.

5. Materials and Manufacture

5.1 *Nuclear Graphite Classes*—See Table 1.

5.2 *Raw Materials:*

5.2.1 *Fillers:*

TABLE 2 ASTM Graphite Grain Size Definitions from Terminology C709

Graphite Designation	Definition of Grains in the Starting Mix that are: ^A
Medium Grained	Generally < 4 mm ^B
Fine Grained	Generally < 100 μm
Superfine Grained	Generally < 50 μm
Ultrafine Grained	Generally < 10 μm
Microfine Grained	Generally < 2 μm

^A Grain size as defined in Terminology C709.

^B For nuclear graphite, the maximum grain size is 1.68 mm in accordance with 5.2.1.6.

5.2.1.1 The filler shall consist of a near-isotropic or isotropic coke derived from a petroleum oil or coal tar.

5.2.1.2 The coke shall have a coefficient of linear thermal expansion (CTE), determined in accordance with Practice C781 and measured over the temperature range 25 to 500°C, of between 3.5×10^{-6} and $5.5 \times 10^{-6} \text{ } ^\circ\text{C}^{-1}$.

5.2.1.3 The coke shall be sampled and distributed as described in Table 3.

5.2.1.4 Graphite manufactured in compliance with this specification but failing to meet the property requirements of Sections 6 and 7 may be used as recycle material in the mix formulation.

5.2.1.5 Recycle green mix manufactured from raw materials in compliance with this specification may be used in the mix formulation.

5.2.1.6 The maximum filler particle size used in the mix formulation shall be 1.68 mm.

5.3 *Binder*—The binder(s) shall consist of coal tar pitch of the same grade from the same manufacturer. The specific binder(s) used shall be identified to the purchaser and be traceable through the forming lot.

5.4 *Impregnant*—The impregnant(s) shall consist of a petroleum or coal tar pitch of the same grade from the same manufacturer. The specific impregnant used shall be identified to the purchaser and be traceable through the impregnation steps.

5.5 *Manufacturing or Processing Additives*—Additives (for example, extrusion aids) may be used to improve the processing, quality and properties of the product, but only with the consent and approval of the purchaser, and they must be traceable through the forming lot.

5.6 *Manufacture:*

5.6.1 *Formulation*—The mix formulation (as defined in 3.2.14) and recycle green mix fraction (as defined in 3.2.21) in the filler shall be recorded. This information shall be reported to the purchaser if requested.

5.6.2 *Forming*—The green mix may be formed by extrusion, molding (including vibrationally molding), or iso-molding.

5.6.3 *Graphitization Temperature*—The graphitization temperature shall be determined on each billet using the procedure described in Practice C781. Each billet tested in accordance with Practice C781 shall have a Specific Electrical Resistivity (SER) corresponding to a graphitization temperature of at least 2700°C.

6. Chemical Properties

6.1 Each graphite production lot shall be sampled in accordance with Section 11. The chemical impurities to be measured shall be as agreed between the supplier and the purchaser. The minimum list of elements to be measured and used for the EBC calculation shall be B, Cd, Dy, Eu, Gd, and Sm.

6.2 The boron equivalent shall be calculated in accordance with Practice C1233. The acceptance limits for the boron equivalent, as well as for ash content, are given in Table 1.

6.3 Table X1.1 contains a list of chemical impurities that are typically measured depending on end-use requirements. The impurities are categorized as neutron absorbing impurities, oxidation promoting catalysts, activation relevant impurities, metallic corrosion relevant impurities, and fissile/fissionable elements.

7. Physical and Mechanical Properties

7.1 Each graphite production lot shall be sampled in accordance with Section 11 and shall conform to the requirements for physical properties prescribed in Table 1 and Table 4 for the appropriate nuclear graphite class, and to the additional requirements of the purchaser.

7.2 The bulk density of each graphite billet shall be measured as described in Test Method C838.

8. Other Requirements

8.1 The graphitized billets shall be handled and stored such that they are protected from contaminants other than ambient air.