



Designation: E514/E514M – 14a

Standard Test Method for Water Penetration and Leakage Through Masonry¹

This standard is issued under the fixed designation E514/E514M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This laboratory test method² provides a procedure for determining the resistance to water penetration and leakage through unit masonry subjected to wind-driven rain. This test method is not identical to and the results are not the same as field standard Test Method **C1601**. This test method measures through-wall water penetration, whereas Test Method **C1601** only measures surface water penetration.

1.2 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* For a specific hazard statement, see Section 6.

2. Referenced Documents

2.1 ASTM Standards:³

- C270** Specification for Mortar for Unit Masonry
- C1232** Terminology of Masonry
- C1601** Test Method for Field Determination of Water Penetration of Masonry Wall Surfaces

¹ This test method is under the jurisdiction of ASTM Committee **C15** on Manufactured Masonry Units and is the direct responsibility of Subcommittee **C15.04** on Research.

Current edition approved July 1, 2014. Published July 2014. Originally approved in 1974. Last previous edition approved in 2014 as E514/E514M – 14. DOI: 10.1520/E0514_E0514M-14A.

² This test method is based upon those used by the National Bureau of Standards and described in *NBS Report BMS7*, "Water Permeability of Masonry Walls," 1933, and *NBS Report BMS82*, "Water Permeability of Walls Built of Masonry Units," 1942.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

2.2 The Masonry Society Standards:⁴

- TMS 402/ACI 530/ASCE 5** Building Code Requirements for Masonry Structures
- TMS 602/ACI 530.1/ASCE 6** Specifications for Masonry Structures

3. Terminology

3.1 Definitions of Terms Specific to This Standard:

3.1.1 *dampness, n*—visual change in the appearance of a material due to the presence of water.

3.1.2 *surface water penetration, n*—passage of water through the exterior face of the masonry.

3.1.3 *through-wall water penetration, n*—passage of water through a wall and appearance of the water on the interior face of the masonry.

3.1.4 *water penetration, n*—water that passes into or through the masonry.

3.1.5 *wind-driven rain, n*—rain water that is directed against the surface of the wall by wind.

3.2 For definitions of other terms used in this test method, refer to Terminology **C1232**.

4. Significance and Use

4.1 This test method provides information that aids in evaluating the effect of four principal variables: materials, coatings, wall design, and workmanship.

4.2 Water penetration and leakage through masonry is significantly affected by air pressure in the test chamber. Data from tests made at different pressures are not comparable.

4.3 The performance of a masonry wall is a function of materials, construction, wall design, and maintenance. In service the performance will also depend on the rigidity of supporting structure and on the resistance of components to deterioration by various causes, such as corrosion, vibration, thermal expansion and contraction, curing, and others. It is impossible to simulate the complex conditions encountered in

⁴ Published by The Masonry Society, www.masonrysociety.org; American Concrete Institute, www.aci-int.org; and American Society of Civil Engineers, www.asce.org.

*A Summary of Changes section appears at the end of this standard

service, such as variations in wind velocity, negative pressure, and lateral or upward moving air and water. Factors such as location, exposure, and wall openings should be considered.

4.4 Given the complexity of variables noted above, this test method establishes comparative behavior between various masonry wall constructions in a given laboratory.

4.5 Even when a single laboratory tests the same wall design utilizing the same wall materials and the same construction practices, variables such as the level of skill of the mason building the specimen, the temperature and humidity in the laboratory at the time of construction, curing of the specimen, the moisture contents of the materials used to build the specimen, and even the use or lack of use of a lime and water wash on the back of the specimen can affect the results of the test making reliable comparisons dubious. For these reasons and the multi-variables listed in 4.1, 4.2, and 4.3, a meaningful, useful, absolute wall leakage rating standard is impractical and discouraged.

4.6 This test method is similar to but distinct from field Test Method C1601. This laboratory test method is designed to test laboratory fabricated wall specimens. Field Test Method C1601 is designed to test in-situ walls. This test method measures the water that has penetrated into and through the masonry specimen and is collected. Test Method C1601 determines water penetration of the masonry at its surface. Results from Test Method C1601 and Test Method E514/E514M are not the same.

5. Apparatus

5.1 Test Chamber—Use a test chamber similar to that shown in Fig. 1 and Fig. 2. Provide an opening with a minimum area of 1.08 m² [12 ft²]. For example, 900 mm [36 in.] wide and 1200 mm [48 in.] high is suitable. Line the edges of the chamber in contact with the specimen with a closed-cell compressible gasket material or appropriate sealant. Provide an observation port in the face of the chamber. Provide a 19.0-mm [³/₄-in.] diameter corrosion-resistant spray pipe with a single line of 1.0-mm [0.04-in.] diameter holes spaced 25.0 mm [1 in.] apart.

5.2 Fixtures and Appurtenances to Chamber—Fixtures and appurtenances to the chamber shall include an air line with manometer, a water line with valves, a flow meter and manometer and a water drain pipe at the bottom of the chamber. Position the water spray pipe so that the water impinges the specimen not more than 75.0 mm [3.00 in.] below the top of the test chamber.

NOTE 1—A drain pipe that discharges into a reservoir equipped with an adjustable depth air outlet pipe and top baffles has been found to reduce surge.

5.3 Manometer—Measure the air pressure in the chamber using a manometer or other device capable of measuring air pressures of at least 51 mm [2.0 in.] of water (71.7 kPa [10.4 psf]) to an accuracy of 2.5 mm [0.1 in.] or 3.6 kPa [0.52 psf]. Connect the manometer or other device to the chamber




FIG. 1 Isometric Projection of Testing Chamber