



Designation: **D6191 – 97 (Reapproved 2008)^{ε1} D6191 – 97 (Reapproved 2014)**

Standard Test Method for Measurement of Evolved Formaldehyde from Water Reducible Air-Dry Coatings¹

This standard is issued under the fixed designation D6191; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

^{ε1} NOTE—The precaution note was moved into subsection 6.2 editorially in November 2008.

1. Scope

1.1 This test method may be used to measure the amount of formaldehyde evolved from air-dry water reducible coatings utilizing latices, resin emulsions, or water reducible alkyds. The results may be used to define the “free” formaldehyde evolved from a sample under controlled laboratory conditions.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

- 2.1 *ASTM Standards:*²
[D2194 Test Method for Concentration of Formaldehyde Solutions](#)

3. Summary of Test Method

3.1 A sample of water reducible coating is placed on the walls of a test tube with a drawdown rod and purged with nitrogen. The evolved formaldehyde is collected in deionized water with tandem impingers and measured colorimetrically using acetylacetone at 412 nm.

4. Significance and Use

4.1 This test method measures the amount of formaldehyde that is released from a coating under laboratory conditions. The amount of formaldehyde available for release from a coating may vary depending on composition, and may decrease as the sample ages.

4.2 This test method may be used for typical air dried paints where water is the major volatile material. The useful range is estimated to be from 10 ppm to 1000 ppm formaldehyde in the sample.

4.3 Significant amounts of other volatile aldehydes, such as acetaldehyde, are reported to cause an interference with the determination of formaldehyde. This limitation is not expected to cause a problem for most common water reducible coatings.

4.4 Samples containing organic solvents as the major volatile component have not been evaluated and are not expected to be compatible with this test method.

5. Apparatus

5.1 *Formaldehyde Collection Apparatus*, assembled using a flowmeter to control the nitrogen flow at ~ 1.0 L/min, a 25 by 200 mm outside diameter long glass test tube, and two 30-mL midget impingers. Connections are made with glass tubes through a No. 4 two-hole rubber stopper and clear flexible tubing (see Fig. 1).

5.2 *Drawdown Bar*, stainless steel No. 22 wire-wound 6.4-mm rod.

¹ This test method is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.21 on Chemical Analysis of Paints and Paint Materials.

Current edition approved Nov. 1, 2008; July 1, 2014. Published November 2008. Originally approved in 1997. Last previous edition approved in 2003 as D6191 – 97 (2003) (2008)^{ε1}. DOI: 10.1520/D6191-97R08E01; 10.1520/D6191-97R14.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.