



Designation: D2950/D2950M – 14

# Standard Test Method for Density of Bituminous Concrete in Place by Nuclear Methods<sup>1</sup>

This standard is issued under the fixed designation D2950/D2950M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This test method describes a test procedure for determining the density of bituminous concrete by the attenuation of gamma radiation, where the source and detector(s) remain on the surface (Backscatter Method) or the source or detector is placed at a known depth up to 300 mm [12 in.] while the detector or source remains on the surface (Direct Transmission Method).

1.2 The density, in mass per unit volume of the material under test, is determined by comparing the detected rate of gamma emissions with previously established calibration data.

1.3 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* For specific warning statements see Section 6 and Note 5.

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

## 2. Referenced Documents

### 2.1 ASTM Standards:<sup>2</sup>

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D04 on Road and Paving Materials and is the direct responsibility of Subcommittee D04.21 on Specific Gravity and Density of Asphalt Mixtures.

Current edition approved June 1, 2014. Published August 2014. Originally approved in 1971. Last previous edition approved in 2011 as D2950/D2950M – 11. DOI: 10.1520/D2950\_D2950M-14.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

- [C670 Practice for Preparing Precision and Bias Statements for Test Methods for Construction Materials](#)
- [D1188 Test Method for Bulk Specific Gravity and Density of Compacted Bituminous Mixtures Using Coated Samples](#)
- [D1559 Test Method for Resistance to Plastic Flow of Bituminous Mixtures Using Marshall Apparatus \(Withdrawn 1998\)<sup>3</sup>](#)
- [D2041 Test Method for Theoretical Maximum Specific Gravity and Density of Asphalt Mixtures](#)
- [D2726 Test Method for Bulk Specific Gravity and Density of Non-Absorptive Compacted Asphalt Mixtures](#)
- [D3665 Practice for Random Sampling of Construction Materials](#)
- [D6752 Test Method for Bulk Specific Gravity and Density of Compacted Asphalt Mixtures Using Automatic Vacuum Sealing Method](#)
- [D7013 Guide for Calibration Facility Setup for Nuclear Surface Gauges](#)
- [D7759 Guide for Nuclear Surface Moisture and Density Gauge Calibration](#)

## 3. Significance and Use

3.1 The test method described is useful as a rapid, nondestructive technique for determining the in-place density of compacted bituminous mixtures.

3.2 With proper calibration and confirmation testing, the test method is suitable for quality control and acceptance testing of compacted bituminous concrete.

3.3 The test method can be used to establish the proper rolling effort and pattern to achieve the required density.

3.4 The non-destructive nature of the test allows repetitive measurements to be made at a single test location between roller passes and to monitor changes in density.

3.5 The density results obtained by this test method are relative. Correlation with other test methods such as D1188 or D2726 are required to convert the results obtained using this method to actual density. It is recommended that at least seven core densities and seven nuclear densities be used to establish

<sup>3</sup> The last approved version of this historical standard is referenced on www.astm.org.



a conversion factor. A new factor must be established at any time a change is made in the paving mixture or in the construction process.

#### 4. Interferences

4.1 The chemical composition of the material being tested may significantly affect the measurement and adjustments may be necessary. Certain elements with atomic numbers greater than 20 may cause erroneously high test values.

4.2 The test method exhibits spatial bias in that the instrument is most sensitive to the density of the material in closest proximity to the nuclear source.

4.2.1 When measuring the density of an overlay, it may be necessary to employ a correction factor if the underlying material varies in thickness, mineral composition or degree of consolidation at different points within the project. (See [Annex A1](#).)

4.2.2 The surface roughness of the material being tested may cause lower than actual density determination.

4.3 Oversize aggregate particles in the source-detector path may cause higher than actual density determination.

4.4 The sample volume being tested is approximately  $0.0028 \text{ m}^3$  [ $0.0989 \text{ ft}^3$ ] for the Backscatter Method and  $0.0056 \text{ m}^3$  [ $0.198 \text{ ft}^3$ ] for the Direct Transmission Method. The actual sample volume varies with the apparatus and the density of the material. In general, the higher the density the smaller the volume ([Note 1](#)).

**NOTE 1**—The volume of field compacted material represented by a test can be effectively increased by repeating the test at adjacent locations and averaging the results.

4.5 If samples of the measured material are to be taken for purposes of correlation with other test methods such as [D1188](#) or [D2726](#), the volume measured can be approximated by a 200 mm [8 in.] diameter cylinder located directly under the center line of the radioactive source and detector(s). The height of the cylinder to be excavated will be the depth setting of the source rod when using the Direct Transmission Method or approximately 75 mm [3 in.] when using the Backscatter Method ([Note 2](#)).

**NOTE 2**—If the layer of bituminous concrete to be measured is less than the depth of measurement of the instrument, corrections must be made to the measurements to obtain accurate results due to the influence of the density of the underlying material. (See [Annex A1](#) for the method used.)

#### 5. Apparatus

5.1 *Nuclear Device*—An electronic counting instrument, capable of being seated on the surface of the material under test, and which contains:

5.1.1 *Gamma Source*—A sealed high energy gamma source such as cesium or radium, and

5.1.2 *Gamma Detector*—Any type of gamma detector such as a Geiger-Mueller tube(s).

5.2 *Reference Standard*—A block of dense material used for checking instrument operation and to establish conditions for a reproducible reference-count rate.

5.3 *Site Preparation Device*—A metal plate, straightedge, or other suitable leveling tool which may be used to level the test site to the required smoothness using fine sand or similar material.

5.4 *Drive Pin*—A steel rod of slightly larger diameter than the rod in the Direct Transmission Instrument, to prepare a perpendicular hole in the material under test for inserting the rod. A drill may also be used.

#### 6. Hazards

6.1 This equipment utilizes radioactive materials which may be hazardous to the health of the users unless proper precautions are taken. Users of this equipment must become familiar with applicable safety procedures and government regulations.

6.2 Effective user instructions together with routine safety procedures, such as source leak tests, recording and evaluation of film badge data, etc. are a recommended part of the operational guidelines for the use of this instrument.

6.3 A regulatory agency radioactive materials license may be required to possess this equipment.

#### 7. Calibration

7.1 Calibrate the instrument in accordance with [Guide D7759](#) and [Guide D7013](#).

7.2 *Calibration Adjustments*—The calibration response shall be checked by the user prior to performing tests on materials that are distinctly different from the material types used in establishing the calibration. The calibration response shall also be checked on newly acquired or repaired apparatus. Take a sufficient number of measurements and compare them to other accepted methods (such as [Test Method D2726](#) or [Test Method D6752](#)) to establish a correlation.

#### 8. Standardization and Reference Check

8.1 Nuclear test devices are subject to long-term aging of the radioactive source, detectors, and electronic systems, which may change the relationship between count rate and material density. To offset this aging, the apparatus may be standardized as the ratio of the measured count rate to a count rate made on a reference standard. The reference count rate should be of the same order of magnitude as the measured count rate over the useful density range of the apparatus.

8.2 Standardization of equipment should be performed at the start of each day's work, and a permanent record of this data retained.

8.2.1 Perform the standardization with the apparatus located at least 10 m [33 ft] away from other sources of radioactivity and clear of large masses or other items which may affect the reference count rate.

**NOTE 3**—The user is advised that the value given in [section 8.2.1](#) is intended as a minimum distance for nuclear sources typical in surface moisture/density gauges. The user should consider requiring a greater distance if other nuclear sources of greater activity are present.

8.2.2 Turn on the apparatus prior to standardization and allow it to stabilize. Follow the manufacturer's recommendations in order to provide the most stable and consistent results.