



Designation: **D4114 – 02 (Reapproved 2008) D4114 – 14**

Standard Performance Specification for Woven Flat Lining Fabrics for Women's and Girls' Apparel¹

This standard is issued under the fixed designation D4114; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This performance specification covers woven flat fabrics comprised of any textile fiber or mixture of fibers to be used as linings for women's and girls' apparel.

1.2 This performance specification is not applicable to woven pile, woven fusible, fire-bonded fusible, sliver-knit pile, and sheepskin lining fabrics.

1.3 These requirements apply to the length and width directions for those properties where fabric direction is pertinent.

1.4 The following precautionary statement pertains only to the test methods portion, Section 7, of this performance specification. *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

[D123 Terminology Relating to Textiles](#)

[D434 Test Method for Resistance to Slippage of Yarns in Woven Fabrics Using a Standard Seam \(Withdrawn 2003\)³](#)

[D1336 Test Method for Distortion of Yarn in Woven Fabrics](#)

[D1424 Test Method for Tearing Strength of Fabrics by Falling-Pendulum \(Elmendorf-Type\) Apparatus](#)

[D2261 Test Method for Tearing Strength of Fabrics by the Tongue \(Single Rip\) Procedure \(Constant-Rate-of-Extension Tensile Testing Machine\)](#)

[D2262 Test Method for Tearing Strength of Woven Fabrics by the Tongue \(Single Rip\) Method \(Constant-Rate-of-Traverse Tensile Testing Machine\) \(Withdrawn 1995\)³](#)

[D2724 Test Methods for Bonded, Fused, and Laminated Apparel Fabrics](#)

[D5034 Test Method for Breaking Strength and Elongation of Textile Fabrics \(Grab Test\)](#)

[D7022 Terminology Relating to Apparel](#)

2.2 AATCC Test Methods:⁴

[8 Colorfastness to Crocking: AATCC-Crockmeter Method](#)

[15 Colorfastness to Perspiration](#)

[16.1.2 Colorfastness to Light: Carbon-Arc](#)

[16.3 Colorfastness to Light: Xenon-Arc](#)

[23 Colorfastness to Burnt Gas Fumes](#)

[61 Colorfastness to Washing, Domestic, and Laundering, Commercial: Laundering: Accelerated](#)

[116 Colorfastness to Crocking: Rotary Vertical Crockmeter Method](#)

[124 Smoothness Appearance of Durable Press Fabrics After Repeated Home Launderings](#)

[132 Colorfastness to Drycleaning](#)

[135 Dimensional Changes in Automatic Home Laundering of Woven or Knit Fabrics of Fabrics after Home Laundering](#)

[172 Colorfastness to Powdered Non-Chlorine Bleach in Home Laundering](#)

¹ This performance specification is under the jurisdiction of ASTM Committee D13 on Textiles and is the direct responsibility of Subcommittee D13.61 on Apparel. Current edition approved Aug. 1, 2008; July 1, 2014. Published October 2008; August 2014. Originally approved in 1982. Last previous edition approved in 2002 as D4114 – 02; D4114 – 02(2008). DOI: 10.1520/D4114-02R08; 10.1520/D4114-14.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

⁴ Available from American Association of Textile Chemists and Colorists (AATCC), P.O. Box 12215, Research Triangle Park, NC 27709, http://www.aatcc.org.

188 Colorfastness to Chlorine-Sodium Hypochlorite Bleach in Home Laundering
Evaluation Procedure No. 1 Gray Scale for Color Change
Evaluation Procedure No. 2 Gray Scale for Staining
Evaluation Procedure No. 38 AATCC 9-Step Chromatic Transference Scale
[A Glossary of AATCC Standard Terminology](#)

2.3 *Federal Standard*.⁵

16 [CFR CFR](#), Chapter II—Consumer Product Safety Commission Subchapter D—Flammable Fabrics Act Regulations

2.4 *Military Standard*.⁶

[MIL-STD-105D Sampling Procedures and Tables for Inspection by Attributes](#)

NOTE 1—Reference to test methods in this performance specification give only the permanent part of the designation of ASTM, AATCC, or other test methods. The current editions of each test method cited shall prevail.

3. Terminology

3.1 Definitions:

3.1.1 For terminology related to apparel see Terminology [D7022](#).

3.1.2 For definitions of textile terms used in this performance specification, refer to the individual ASTM and AATCC methods and to Terminology [D123](#).

3.2 Definitions found in a dictionary of common terms are suitable for this performance specification.

4. Specification Requirements

4.1 The properties of woven flat fabrics, to be used as linings in women's and girls' apparel, shall conform to the specification requirements in [Table 1](#).

5. Significance and Use

5.1 Upon agreement between the purchaser and the supplier, fabrics intended for this end use should meet all of the requirements listed in [Table 1](#) of this performance specification.

5.2 It is recognized that for purposes of fashion or aesthetics the ultimate consumer of articles made from these fabrics may find acceptable fabrics that do not conform to all of the requirements in [Table 1](#). Therefore, one or more of the requirements listed in [Table 1](#) may be modified upon agreement between the purchaser and the supplier.

5.2.1 In such cases, any references to the specification shall specify that: "This fabric meets ASTM Specification D4114 except for the following characteristic(s)."

5.3 Where no prepurchase agreement has been reached between the purchaser and the supplier, and in case of controversy, the requirements listed in [Table 1](#) are intended to be used as a guide only. As noted in [5.2](#), ultimate consumer demands dictate varying performance parameters for any particular style of fabric.

5.4 The uses and significance of particular properties and methods are discussed in the appropriate sections of the specified test methods.

6. Sampling

6.1 *Lot Sample*—As a lot sample for acceptance testing, take at random the number of rolls as directed in an applicable specification or other agreement between the purchaser and the supplier, such as an agreement to use MIL-STD-105D.

6.2 *Laboratory Sample*—From each roll or piece in the lot sample, cut two laboratory samples the full width of the fabric and at least 375 mm (15 in.) along the selvage.

7. Test Methods (See [Note 1](#))

7.1 *Breaking Force*—Determine the dry breaking force, in the standard atmosphere for testing textiles, as directed in Test Method [D5034](#), using a constant rate of traverse (CRT) tensile-testing machine with the speed of the pulling clamp at 300 ± 10 mm (12 ± 0.5 in.)/min.

NOTE 2—If preferred, the use of a constant-rate-of-extension (CRE) tensile-testing machine is permitted. The crosshead speed should be as agreed upon between the purchaser and the supplier. There may be no overall correlation between the results obtained with the CRT machine and with the CRE machine. Consequently, these two breaking-load testers cannot be used interchangeably. In case of controversy, the CRT method shall prevail.

7.2 *Resistance to Yarn Slippage*—Determine the resistance to yarn slippage as directed in Test Method [D434](#).

NOTE 3—The precision of Test Method [D434](#) is being established, and it may not be suitable for fabrics with a low number of warp (ends) and filling (picks) counts (see [5.2](#)).

⁵ Available from Superintendent of Documents, Government Printing Office, Washington, DC 20402.

⁶ Available from Standardization Documents Order Desk, Bldg. 4 Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094, Attn: NPODS.