



Designation: D4114 – 14

Standard Performance Specification for Woven Flat Lining Fabrics for Women's and Girls' Apparel¹

This standard is issued under the fixed designation D4114; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This performance specification covers woven flat fabrics comprised of any textile fiber or mixture of fibers to be used as linings for women's and girls' apparel.

1.2 This performance specification is not applicable to woven pile, woven fusible, fire-bonded fusible, sliver-knit pile, and sheepskin lining fabrics.

1.3 These requirements apply to the length and width directions for those properties where fabric direction is pertinent.

1.4 The following precautionary statement pertains only to the test methods portion, Section 7, of this performance specification. *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

D123 Terminology Relating to Textiles

D434 Test Method for Resistance to Slippage of Yarns in Woven Fabrics Using a Standard Seam (Withdrawn 2003)³

D1336 Test Method for Distortion of Yarn in Woven Fabrics

D1424 Test Method for Tearing Strength of Fabrics by Falling-Pendulum (Elmendorf-Type) Apparatus

D2261 Test Method for Tearing Strength of Fabrics by the Tongue (Single Rip) Procedure (Constant-Rate-of-Extension Tensile Testing Machine)

D2262 Test Method for Tearing Strength of Woven Fabrics by the Tongue (Single Rip) Method (Constant-Rate-of-

Traverse Tensile Testing Machine) (Withdrawn 1995)³

D2724 Test Methods for Bonded, Fused, and Laminated Apparel Fabrics

D5034 Test Method for Breaking Strength and Elongation of Textile Fabrics (Grab Test)

D7022 Terminology Relating to Apparel

2.2 AATCC Test Methods:⁴

8 Colorfastness to Crocking: Crockmeter Method

15 Colorfastness to Perspiration

16.2 Colorfastness to Light: Carbon-Arc

16.3 Colorfastness to Light: Xenon-Arc

23 Colorfastness to Burnt Gas Fumes

61 Colorfastness to Laundering: Accelerated

116 Colorfastness to Crocking: Rotary Vertical Crockmeter Method

124 Smoothness Appearance of Fabrics After Repeated Home Laundering

132 Colorfastness to Drycleaning

135 Dimensional Changes of Fabrics after Home Laundering

172 Colorfastness to Powdered Non-Chlorine Bleach in Home Laundering

188 Colorfastness to Sodium Hypochlorite Bleach in Home Laundering

Evaluation Procedure No. 1 Gray Scale for Color Change

Evaluation Procedure No. 2 Gray Scale for Staining

Evaluation Procedure No. 8 AATCC 9-Step Chromatic Transference Scale

A Glossary of AATCC Standard Terminology

2.3 Federal Standard:⁵

16 CFR, Chapter II—Consumer Product Safety Commission Subchapter D—Flammable Fabrics Act Regulations

2.4 Military Standard:⁶

MIL-STD-105D Sampling Procedures and Tables for Inspection by Attributes

NOTE 1—Reference to test methods in this performance specification give only the permanent part of the designation of ASTM, AATCC, or

¹ This performance specification is under the jurisdiction of ASTM Committee D13 on Textiles and is the direct responsibility of Subcommittee D13.61 on Apparel.

Current edition approved July 1, 2014. Published August 2014. Originally approved in 1982. Last previous edition approved in 2008 as D4114 – 02(2008). DOI: 10.1520/D4114-14.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

⁴ Available from American Association of Textile Chemists and Colorists (AATCC), P.O. Box 12215, Research Triangle Park, NC 27709, <http://www.aatcc.org>.

⁵ Available from Superintendent of Documents, Government Printing Office, Washington, DC 20402.

⁶ Available from Standardization Documents Order Desk, Bldg. 4 Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094, Attn: NPODS.

other test methods. The current editions of each test method cited shall prevail.

3. Terminology

3.1 Definitions:

3.1.1 For terminology related to apparel see Terminology **D7022**.

3.1.2 For definitions of textile terms used in this performance specification, refer to the individual ASTM and AATCC methods and to Terminology **D123**.

3.2 Definitions found in a dictionary of common terms are suitable for this performance specification.

4. Specification Requirements

4.1 The properties of woven flat fabrics, to be used as linings in women's and girls' apparel, shall conform to the specification requirements in **Table 1**.

5. Significance and Use

5.1 Upon agreement between the purchaser and the supplier, fabrics intended for this end use should meet all of the requirements listed in **Table 1** of this performance specification.

5.2 It is recognized that for purposes of fashion or aesthetics the ultimate consumer of articles made from these fabrics may find acceptable fabrics that do not conform to all of the requirements in **Table 1**. Therefore, one or more of the requirements listed in **Table 1** may be modified upon agreement between the purchaser and the supplier.

5.2.1 In such cases, any references to the specification shall specify that: "This fabric meets ASTM Specification D4114 except for the following characteristic(s)."

5.3 Where no prepurchase agreement has been reached between the purchaser and the supplier, and in case of controversy, the requirements listed in **Table 1** are intended to be used as a guide only. As noted in **5.2**, ultimate consumer demands dictate varying performance parameters for any particular style of fabric.

5.4 The uses and significance of particular properties and methods are discussed in the appropriate sections of the specified test methods.

6. Sampling

6.1 *Lot Sample*—As a lot sample for acceptance testing, take at random the number of rolls as directed in an applicable

TABLE 1 Specification Requirements^A

NOTE 1—Class for color change, color transfer, and SA rating is based on a numerical scale of 5 for negligible or no color change, color transfer, or wrinkle to 1 for severe color change, color transfer, or wrinkle.

Characteristic	Requirements	Section
Breaking strength (load)(CRT)	111 N (25 lbf), min	7.1
Yarn slippage	6.3-mm (¼-in.) separation at 67 N (15 lbf), min	7.2
Tongue-tear strength	6.7 N (1.5 lbf), min	7.3
Yarn distortion		7.4
Satis	2.5 mm (0.10 in.), max	7.4
All other	1 mm (0.05 in.), max	7.4
Dimensional change:		
After five launderings	3 %, max	7.5.1
After three dry cleanings	2% , max	7.5.2
Colorfastness:		
Burnt gas fumes—2 cycles:		7.6.1
Shade change, original fabric	Grade 4 ^B , min	
Shade change after one laundering or one dry cleaning	Grade 4 ^B , min	
Sodium Hypochlorite Bleach	Grade 4 ^B , min	7.6.7
Powdered Non-Chlorine Bleach	Grade 4 ^B , min	7.6.8
Laundering: ^F		7.6.2
Shade change	Grade 4 ^B , min	
Staining	Grade 3 ^C , min	
Dry cleaning:		7.6.3
Shade change	Grade 4 ^B , min	
Crocking: ^F		7.6.4
Dry	Grade 4 ^D , min	
Wet	Grade 3 ^D , min	
Perspiration: ^F		7.6.5
Shade change	Grade 4 ^B , min	
Staining	Grade 3 ^C , min	
Light (10 AATCC Fading Units)(xenon-arc)	Grade 4 ^B , min	7.6.6
Fabric smoothness appearance (see 7.7.1)	SA 3.5 ^E , min	7.7
Flammability	pass	7.8

^A There is more than one method that can be used to measure breaking strength (load), tear strength, and lightfastness. These methods cannot be used interchangeably since there may be no overall correlation between them (see **Note 2**, **Note 4**, and **Note 8**).

^B AATCC Gray Scale for Color Change.

^C AATCC Gray Scale for Staining.

^D AATCC Chromatic Transference Scale.

^E For durable-press fabrics only.

^F See **Note 7**.