



## Standard Specification for Rigid Poly(Vinyl Chloride) (PVC) Interior-Profile Extrusions<sup>1</sup>

This standard is issued under the fixed designation D3678; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

<sup>ε1</sup> NOTE—Editorial changes were made throughout in April 2008.

### 1. Scope\*

1.1 This specification establishes requirements for the material properties, including dimensional stability and extrusion quality, of rigid, poly(vinyl chloride) (PVC) interior-profile extrusions. Methods for identifying interior-profile extrusions that comply with the requirements of this specification are provided.

1.2 ~~Rigid~~ Use of rigid PVC recycled plastic may be used in this product in is permitted in accordance with the requirements in of Sections 6 and 7.

1.3 Rigid PVC compounds for interior building product applications are covered in Specification **D1784**.

1.4 Rigid PVC exterior profile extrusions for assembled windows and doors are covered in Specification **D4726**.

1.5 The text of this standard references notes and footnotes which provide explanatory material. These notes and footnotes (excluding those in Tables and Figures) shall not be considered as requirements of this standard.

1.6 The values stated in SI units are to be regarded as the standard. The values given in parentheses are given for information only.

NOTE 1—Information with regard to application should be obtained from the manufacturers of the profiles.

NOTE 2—There is no known ISO equivalent to this standard.

NOTE 1—Information with regard to application should be obtained from the manufacturers of the profiles.

NOTE 2—There is no known ISO equivalent to this standard.

1.7 The following precautionary caveat pertains only to the test method portion, Section 8, of this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

### 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

**D618 Practice for Conditioning Plastics for Testing**

**D696 Test Method for Coefficient of Linear Thermal Expansion of Plastics Between –30°C and 30°C with a Vitreous Silica Dilatometer**

**D883 Terminology Relating to Plastics**

**D1042 Test Method for Linear Dimensional Changes of Plastics Caused by Exposure to Heat and Moisture**

**D1600 Terminology for Abbreviated Terms Relating to Plastics**

**D1784 Specification for Rigid Poly(Vinyl Chloride) (PVC) Compounds and Chlorinated Poly(Vinyl Chloride) (CPVC) Compounds**

**D2152 Test Method for Adequacy of Fusion of Extruded Poly(Vinyl Chloride) (PVC) Pipe and Molded Fittings by Acetone Immersion**

**D3892 Practice for Packaging/Packing of Plastics**

**D4726 Specification for Rigid Poly(Vinyl Chloride) (PVC) Exterior-Profile Extrusions Used for Assembled Windows and Doors**

**D4968 Guide for Annual Review of Test Methods and Specifications for Plastics**

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee **D20** on Plastics and is the direct responsibility of Subcommittee **D20.24** on Plastic Building Products. Current edition approved ~~March 1, 2008~~ Aug. 1, 2014. Published ~~April 2008~~ August 2014. Originally approved in 1978. Last previous edition approved in ~~2004~~ 2008 as D3678 – 97 (2008)<sup>ε1</sup> (2001). DOI: 10.1520/D3678-97R08E01-10.1520/D3678-14.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

\*A Summary of Changes section appears at the end of this standard

### 3. Terminology

3.1 *General*—Definitions are in accordance with Terminology **D883** or Terminology **E631** and abbreviations with Terminology **D1600**, unless otherwise indicated.

### 4. Significance and Use

4.1 The purpose of this specification is to establish on a national basis, a recognized standard of quality for rigid poly(vinyl chloride) (PVC) interior-profile extrusions for interior use other than cellular products, piping, tubing, and window and door profiles used in finished building products. The information contained in this standard is intended to be helpful to producers, distributors, and users, and to promote understanding between buyers and sellers. It is also intended to serve as the basis for requirements on finished interior building products which are either made from or employ rigid PVC profile extrusions in their construction.

### 5. Classification

5.1 This standard covers three classes of rigid PVC interior-profile extrusions as follows:

*Class 1*—Normal impact

*Class 2*—Intermediate impact

*Class 3*—High impact

### 6. Materials and Manufacture

6.1 This specification covers profile extrusions made from plastics conforming to the requirements of Specification **D1784**. Class 1 extrusions shall meet the requirements specified in Specification **D1784** for Class 12454 compound. Class 2 extrusions shall meet the requirements for Class 14323 compound. Class 3 extrusions shall meet the requirements for Class 1-40031-54-0000 compound. Refer to Table 1 in Specification **D1784**.

6.2 ~~Rigid~~—Use of rigid PVC recycled plastic, as defined in Guide **D7209**, ~~may be used~~ is permitted in this product if all the requirements in the sections on Materials and Manufacture (Section 6), and on Physical Requirements (Section 7) are met by the extrusions containing PVC recycled plastic.

6.3 All Class compounds shall have a minimum coefficient of linear expansion of  $10 \times 10^{-5} \frac{\text{cm}}{\text{cm}} \frac{\text{cm}}{\text{cm}} \frac{1}{^{\circ}\text{C}}$  ( $5.5 \times 10^{-5} \frac{\text{in.}}{\text{in.}} \frac{1}{^{\circ}\text{F}}$ ); in./in./°F.

NOTE 3—Non-PVC materials may be used as a capstock.

6.4 *Rework Material*—Clean, homogeneous PVC rework material or rework material containing PVC capstock generated from the manufacturer's own production of the same class compound ~~may be used~~ is permitted for use by the same manufacturer ~~providing provided~~ that the extruded profiles meet all the requirements of this specification. Clean principally PVC rework material containing non-PVC capstock ~~may be used~~ is permitted for use only in the substrate of a capstocked product by the same manufacturer, providing that the extruded profiles meet all of the requirements of this specification.

6.5 The PVC compound in extruded section shall maintain uniform color and be free of any visual surface or structural changes, such as peeling, chipping, cracking, flaking, or pitting.

### 7. Physical Requirements

7.1 *Dimensions*—The size, thickness, and dimensional tolerances of the interior-profile extrusions shall be as agreed upon between the supplier and purchaser.

7.2 *Dimensional Stability*—The dimensional stability of the interior-profile extrusions shall be determined in the extrusion direction in accordance with 8.5. Extrusions over 1.02 mm (0.040 in.) in thickness shall have a maximum shrinkage of 2.2 %; those of 1.02-mm (0.040-in.) thickness or less shall have a 3.0 % maximum shrinkage.

7.3 *Extrusion Quality*—The extrusion quality of Class 1 extrusions shall be determined by immersion in anhydrous acetone in accordance with the requirements of 8.6. Specimens of extrusions having not more than 25 % surface attack shall be considered as adequately fused and of satisfactory quality. The extrusion qualities of Class 2 and Class 3 extrusions shall be as agreed upon between the supplier and purchaser.

### 8. Test Methods

8.1 *General*—Use the inspection and test procedures contained in this section to determine the conformance of products to the requirements of this specification. Each producer or distributor who represents his products as conforming to this specification may utilize statistically based sampling plans that are appropriate for each particular manufacturing process, but shall keep such