



Designation: D3596 – 14

## Standard Practice for Determination of Gels (Fisheyes) In General-Purpose Poly(Vinyl Chloride) (PVC) Resins<sup>1</sup>

This standard is issued under the fixed designation D3596; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reappraisal.

### 1. Scope\*

1.1 This practice provides a quantitative measure of the gels remaining in a flexible vinyl compound processed from general-purpose poly(vinyl chloride) (PVC) resins under a prescribed set of working conditions.

1.2 The values stated in SI units are to be regarded as the standard. The values in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

NOTE 1—There is no known ISO equivalent to this standard.

### 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

D883 Terminology Relating to Plastics

D1600 Terminology for Abbreviated Terms Relating to Plastics

### 3. Terminology

3.1 *General*—Definitions are in accordance with Terminology D883 and abbreviations with Terminology D1600, unless otherwise indicated.

### 4. Summary of Practice

4.1 A sample of PVC resin is mixed with calcium/zinc stabilizer, stearic acid, carbon black, and a plasticizer in a laboratory mixer. The dry blend is milled on a two-roll laboratory mill.

4.2 The milled sheet is press-polished and the gels counted using a bottom-lighted viewing box and a magnifying comparator.

<sup>1</sup> This practice is under the jurisdiction of ASTM Committee D20 on Plastics and is the direct responsibility of Subcommittee D20.15 on Thermoplastic Materials.

Current edition approved Aug. 1, 2014. Published September 2014. Originally approved in 1977. Last previous edition approved in 2013 as D3596 – 13. DOI: 10.1520/D3596-14.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

### 5. Significance and Use

5.1 The gel (fisheye) in PVC resins is generally recognized as a hard particle of resin which will not fuse when the plastic mass is subjected to set conditions of hot processing. The number of unfused particles present is related to the conditions used. The presence of an excess of such particles is detrimental to many applications.

### 6. Apparatus

6.1 *Laboratory Mixer*, with stainless steel mixing bowl.

6.2 *Two-Roll Mill*, 152.4 by 304.8 mm (6 by 12 in.), 263.5 mm (10.5 in.) between guides, differential speed ratio  $1.40 \pm 0.04$ , fast roll speed  $34 \pm 2$  rpm, with an adjustable temperature range of 120–205 °C (250–400 °F).

NOTE 2—If the mill available does not meet these criteria, the specifications of the mill used should be included in the report.

6.3 *Surface Pyrometer*

6.4 *Balance*, 0.1-g sensitivity.

6.5 *Hydraulic Press* having platens at least 203 by 203 mm (8 by 8 in.), rated at a minimum of 140 MPa (20 000 psi) ram pressure on a 100-mm (4-in.) ram, which has the capacity for heating to  $163 \pm 3$  °C ( $325 \pm 5$  °F) on the pressing surfaces and equipped with cooling water.

6.6 *Timer*, capable of being read in seconds.

6.7 *Cotton Gloves*.

6.8 *Mill Knife*.

6.9 *Plates or Mold*, two 203 by 203-mm (8 by 8-in.) chrome-plated ferro plates, or a chrome-plated mold with a 152 by 152 by 6.4-mm (6 by 6 by 0.25-in.) cavity.

6.10 *Backing Plates*, two 203 by 203 by 6.4 mm (8 by 8 by 0.250 in.).

6.11 *Brass Shims*, four, 0.51 by 13 by 203 mm (0.020 by 0.5 by 8.0 in.).

6.12 *Magnifying Comparator (optional)*, equipped with a transparent reticule (scale) showing circles from 0.03 to 1.27 mm (0.001 to 0.050 in.) in diameter.

6.13 *Bottom-Lighted Viewing Box*.

\*A Summary of Changes section appears at the end of this standard