This document is not an ASTM standard and is intended only to provide the user of an ASTM standard an indication of what changes have been made to the previous version. Because it may not be technically possible to adequately depict all changes accurately, ASTM recommends that users consult prior editions as appropriate. In all cases only the current version of the standard as published by ASTM is to be considered the official document.



## Designation: A610 - 79 (Reapproved 2009) A610 - 79 (Reapproved 2014)

# **Standard Test Methods for** Sampling and Testing Ferroalloys for Determination of Size<sup>1</sup>

This standard is issued under the fixed designation A610; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

#### 1. Scope

1.1 These test methods cover procedures for the sampling and testing of the various ferroalloys for sizing, either before or after shipment from the plants of the manufacturers.

1.2 They are designed to give results representative of each lot that will be comparable with the manufacturer's certified analysis for the same lot.

1.3 The purchaser may use any sampling procedure he desires, but the results obtained on such samples shall not be a basis for complaint or rejection, unless the procedure followed is of an accuracy equivalent to that prescribed in these test methods.

1.4 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.4.1 Exception—The SI units that correspond to mesh sizes in Table 1 are to be regarded as standard.

1.5 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

### 2. Referenced Documents

2.1 *ASTM Standards*:<sup>2</sup> E11 Specification for Woven Wire Test Sieve Cloth and Test Sieves

E32 Practices for Sampling Ferroalloys and Steel Additives for Determination of Chemical Composition

#### 3. Unit Quantities for Sampling and Testing

3.1 Each shipment, except as otherwise agreed upon by the purchaser and the manufacturer, shall constitute a unit for sampling and testing. It is recommended that shipments of any alloy exceeding 100 tons (91 000 kg) be divided into smaller lots for sampling according to some plan best adapted to the material and conditions, such as each cast, each carload, each ladleful or each binful. The division of samples should be in accordance with Practices E32.

#### 4. Sampling for Size Analysis

4.1 Lumps—Conformance of lump material to sizing standards normally shall be judged by visual examination. The inspection judgment shall be made on an increment selected at random. Unless otherwise required, the increment shall be the contents of a unit container of 2000 lb (910 kg) minimum quantity. When more precise data are required for checking on the visual examination, a sizing test shall be made on material from a unit container (usually 2000 to 3000 lb (910 to 1360 kg) of alloy) selected at random.

4.2 Crushed or Plates—Sampling for conformance of crushed or plates material to size requirements shall be in accordance with Practices E32 or by alternative methods which are demonstrated to yield equivalent results. A representative portion of the lot sample (before any reduction in particle size) shall be obtained for screen testing. If necessary, the percentage of sample taken shall be increased to provide sufficient sample in the half reserved for screen testing.

4.2.1 Table 1 lists the amount of material that is to be used for size analysis.

<sup>&</sup>lt;sup>1</sup> These test methods are under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and are the direct responsibility of Subcommittee A01.18 on Castings.

Current edition approved Oct. 1, 2009Oct. 1, 2014. Published January 2010October 2014. Originally approved in 1970. Last previous edition approved in 20042009 as A610 - 79 (2004).(2009). DOI: 10.1520/A0610-79R09.10.1520/A0610-79R14.

<sup>&</sup>lt;sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.