



Designation: ~~C467 – 97 (Reapproved 2008)~~ C467 – 14

Standard Classification of Mullite Refractories¹

This standard is issued under the fixed designation C467; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This classification covers refractory products consisting predominantly of mullite ($3\text{Al}_2\text{O}_3 \cdot 2\text{SiO}_2$) crystals that are formed by either converting any of the sillimanite group of minerals, or synthesizing from appropriate materials in a melt or sinter process.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

2. Referenced Documents

2.1 *ASTM Standards:*²

C16 Test Method for Load Testing Refractory Shapes at High Temperatures

NOTE 1—Chemical analysis of refractory products are determined by a combination of x-ray fluorescence (XRF) and inductively coupled plasma (ICP) using standard reference materials (SRM), including various types of minerals and refractory materials which are available from the National Institute of Standards and Technology and other appropriate sources.

C832 Test Method of Measuring Thermal Expansion and Creep of Refractories Under Load

3. Significance and Use

3.1 The mullite content of an alumina-silica refractory material has an important influence on volume stability, load bearing properties, and its satisfactory use in refractory applications. This classification is considered useful for purchase specifications and quality control.

4. Properties—Basis of Classification

4.1 The refractory products falling within the scope of this classification are classified by chemical and physical tests to meet the following requirements:

ASTM C467-14	
Alumina content, %	56 to 79
Impurities, ^A max, %	5
Deformation, ^B max, %	5

^A Impurities refer to metal oxides other than those of aluminum and silicon.

^B When tested in accordance with 6.1.2.

5. Test Specimens

5.1 Testing for compliance with this classification shall be performed on 9 by 4½ by 2½-in. (228 by 114 by 64-mm) rectangular brick as made, or on specimens of this size cut from larger shapes, utilizing existing plane surfaces as much as possible.

6. Test Methods

6.1 The properties enumerated in this classification shall be determined in accordance with the following ASTM methods:

6.1.1 *Alumina Content*—XRF and ICP.

6.1.2 *Load Test*—Schedule 6 of Table 1 in Test Method **C16**.

6.1.3 *Thermal Expansion and Creep*—Method **C832**.

¹ This classification is under the jurisdiction of the ASTM Committee **C08** on Refractories and is the direct responsibility of Subcommittee **C08.92** on The Joseph E. Kopanda Subcommittee for Editorial, Terminology and Classification.

Current edition approved Aug. 1, 2008; Sept. 1, 2014. Published September 2008. Originally approved in 1961. Last previous edition approved in 2002 as C467 – 97 (2002) (2008). DOI: 10.1520/C0467-97R08; 10.1520/C0467-14.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.