



Designation: **A632 – 04 (Reapproved 2009) A632 – 04 (Reapproved 2014)**

## Standard Specification for Seamless and Welded Austenitic Stainless Steel Tubing (Small-Diameter) for General Service<sup>1</sup>

This standard is issued under the fixed designation A632; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This specification covers grades of stainless steel tubing in sizes under  $\frac{1}{2}$  down to 0.050 in. (12.7 to 1.27 mm) in outside diameter and wall thicknesses less than 0.065 in. down to 0.005 in. (1.65 to 0.13 mm) for general corrosion-resisting and low- or high-temperature service, as designated in [Table 1](#).

NOTE 1—The grades of austenitic stainless steel tubing furnished in accordance with this specification have been found suitable for low-temperature service down to  $-325^{\circ}\text{F}$  ( $-200^{\circ}\text{C}$ ) in which Charpy notched-bar impact values of 15 ft-lbf (20 J), minimum, are required and these grades need not be impact tested.

1.2 Optional supplementary requirements are provided and, when desired, shall be so stated in the order.

1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

### 2. Referenced Documents

2.1 *ASTM Standards*:<sup>2</sup>

[A262 Practices for Detecting Susceptibility to Intergranular Attack in Austenitic Stainless Steels](#)

[A380 Practice for Cleaning, Descaling, and Passivation of Stainless Steel Parts, Equipment, and Systems](#)

[E165 Practice for Liquid Penetrant Examination for General Industry](#)

[E527 Practice for Numbering Metals and Alloys in the Unified Numbering System \(UNS\)](#)

2.2 *SAE Standard*:

[SAE J 1086 Practice for Numbering Metals and Alloys \(UNS\)](#)<sup>3</sup>

### 3. Ordering Information

3.1 Orders for product under this specification should include the following, as required, to describe the desired material adequately:

3.1.1 Quantity (feet or number of lengths),

3.1.2 Name of product (seamless or welded tubes),

3.1.3 Grade (see [Table 1](#)),

3.1.4 Size (only two of the following: outside diameter, inside diameter, and average wall),

3.1.5 Length (specific or random),

3.1.6 Optional requirements (check analysis, see [Section 7](#); hydrostatic, air underwater pressure test, or nondestructive electric test, see [Section 13](#)),

3.1.7 Test report required,

3.1.8 Specification designation, and

3.1.9 Special requirements or any supplementary requirements selected, or both.

### 4. General Requirements

4.1 Tubing furnished under this specification shall conform to the applicable requirements of the current edition of Specification [E165](#), unless otherwise provided herein.

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.10 on Stainless and Alloy Steel Tubular Products.

Current edition approved Oct. 1, 2009; Oct. 1, 2014. Published February 2010; October 2014. Originally approved in 1969. Last previous edition approved in 2004 as A632 – 04 – 04 (2009). DOI: 10.1520/A0632-04R09; 10.1520/A0632-04R14.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> Available from SAE International (SAE), 400 Commonwealth Dr., Warrendale, PA 15096-0001, <http://www.sae.org>.

**TABLE 1 Chemical Requirements**

Element	Composition, %									
	Grade	TP 304	TP 304L	TP 310	TP 316	TP 316L	TP 317	TP 321	TP 347	TP 348
	UNS Designation <sup>A</sup>	S30400	S30403	S31000	S31600	S31603	S31700	S32100	S34700	S34800
Carbon, max		0.08	0.030	0.15	0.08	0.030	0.08	0.08	0.08	0.08
Manganese max		2.00	2.00	2.00	2.00	2.00	2.00	2.00	2.00	2.00
Phosphorus, max		0.045	0.045	0.045	0.045	0.045	0.045	0.045	0.045	0.045
Sulfur, max		0.030	0.030	0.030	0.030	0.030	0.030	0.030	0.030	0.030
Silicon, max		0.75	0.75	0.75	0.75	0.75 <sup>B</sup>	0.75	0.75	0.75	0.75
Nickel		8.0–11.0	8.0–13.0	19.0–22.0	11.0–14.0 <sup>C</sup>	10.0–15.0	11.0–14.0	9.0–13.0	9.0–13.0	9.0–13.0
Chromium		18.0–20.0	18.0–20.0	24.0–26.0	16.0–18.0	16.0–18.0	18.0–20.0	17.0–20.0	17.0–20.0	17.0–20.0
Molybdenum		...	...	...	2.00–3.00	2.00–3.00	3.00–4.00	...	...	...
Titanium		...	...	...	...	...	...	<i>D</i>	...	...
Columbium + tantalum		...	...	...	...	...	...	...	<i>E</i>	<i>E</i>
Tantalum, max		...	...	...	...	...	...	...	...	0.10

<sup>A</sup> New designation established in accordance with Practice E527 and SAE J 1086, Practice for Numbering Metals and Alloys (UNS).

<sup>B</sup> For seamless TP316L tubes, the silicon maximum shall be 1.00 %.

<sup>C</sup> For welded TP 316 tubes, the nickel range shall be 10.0–14.0 %.

<sup>D</sup> Grade TP 321 shall have a titanium content of not less than five times the carbon content and not more than 0.60 %.

<sup>E</sup> Grades TP 347 and TP 348 shall have a columbium plus tantalum content of not less than ten times the carbon content and not more than 1.0 %.

## 5. Manufacture

5.1 *Manufacture*—The tubes shall be cold finished and shall be made by the seamless or welded process.

5.2 *Heat Treatment*—All material shall be furnished in the heat-treated condition. The heat-treatment procedure shall consist of heating the material to a minimum temperature of 1800°F (980°C) and quenching in water or rapidly cooling by other means.

## 6. Chemical Composition

6.1 The steel shall conform to the requirements as to chemical composition as specified in Table 1.

## 7. Product Analysis

7.1 When specified on the purchase order, an analysis of either one billet or one length of flat-rolled stock or one tube shall be made from each heat. The chemical composition thus determined shall conform to the specified requirements.

7.2 If the analysis made in accordance with 7.1 does not conform to the specified requirements, an analysis of each billet or length of flat-rolled stock or tube from the same heat may be made and all billets, stock, or tubes thus conforming to the requirements shall be accepted so far as chemical composition is concerned.

## 8. Mechanical Properties

8.1 *Tensile Requirements*—The material shall conform to the requirements as to tensile properties specified in Table 2. These mechanical properties apply to tubing 1/8 in. (3.2 mm) and larger in outside diameter by 0.015 in. (0.38 mm) in wall thickness and heavier. Smaller sizes are available meeting the minimum tensile strength specified in Table 2; however, yield strength is not generally determined on such sizes, and the minimum elongation shall be 25 %.

## 9. Permissible Variations in Dimensions

9.1 Variations in diameter and wall thickness from those specified shall not exceed the amounts specified in Table 3.

## 10. Surface Condition

10.1 The tubes shall be pickled free of scale. When bright annealing is used, pickling is not required.

**TABLE 2 Tensile Requirements**

Tensile strength, min, ksi (MPa)	75 <sup>A</sup> (515) <sup>A</sup>
Yield strength, min, ksi (MPa)	30 <sup>A,B</sup> (205) <sup>A,B</sup>
Elongation in 2 in. or 50 mm, min, %	35 <sup>B</sup>

<sup>A</sup> Grades TP 304L and TP 316L shall have a minimum tensile strength of 70 ksi (485 MPa) and a minimum yield strength of 25 ksi (170 MPa).

<sup>B</sup> Yield strength is not generally determined on tubing sizes smaller than 1/8 in. (3.2 mm) in outside diameter or thinner than 0.015 in. (0.38 mm) wall, so yield strength is not required on such sizes. Also, the minimum elongation required on these smaller or thinner sizes is 25 %.