



Designation: **C1038/C1038M – 14a** C1038/C1038M – 14b

Standard Test Method for Expansion of Hydraulic Cement Mortar Bars Stored in Water¹

This standard is issued under the fixed designation C1038/C1038M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

1. Scope*

1.1 This test method covers the determination of the expansion of mortar bars made using hydraulic cement, of which sulfate is an integral part.

1.2 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use. (Warning —Fresh hydraulic cementitious mixtures are caustic and may cause chemical burns to skin and tissue upon prolonged exposure.²)*

2. Referenced Documents

2.1 *ASTM Standards:*³

[C109/C109M Test Method for Compressive Strength of Hydraulic Cement Mortars \(Using 2-in. or \[50-mm\] Cube Specimens\)](#)

[C305 Practice for Mechanical Mixing of Hydraulic Cement Pastes and Mortars of Plastic Consistency](#)

[C490 Practice for Use of Apparatus for the Determination of Length Change of Hardened Cement Paste, Mortar, and Concrete](#)

[C511 Specification for Mixing Rooms, Moist Cabinets, Moist Rooms, and Water Storage Tanks Used in the Testing of Hydraulic Cements and Concretes](#)

[C778 Specification for Sand](#)

[C1005 Specification for Reference Masses and Devices for Determining Mass and Volume for Use in the Physical Testing of Hydraulic Cements](#)

[C1437 Test Method for Flow of Hydraulic Cement Mortar](#)

[D1193 Specification for Reagent Water](#)

3. Significance and Use

3.1 This test method is used to determine the amount of expansion of a mortar bar when it is stored in water. The amount of mortar-bar expansion may relate to the amount of sulfate in the cement; expansion may become excessive when the cement contains too much sulfate.

3.2 Some cement specifications limit the amount of sulfate contained in hydraulic cement by requiring that the amount of expansion in water not exceed a specified value.

4. Apparatus

4.1 *Reference Masses and Mass-Determining Devices*, conforming to the requirements of Specification [C1005](#). Evaluate the device for precision and bias at a total load of 2 ~~kg~~.kg.

4.2 *Glass Graduates, Molds, and Length Comparator*, conforming to the requirements of Specification [C490](#).

¹ This test method is under the jurisdiction of ASTM Committee [C01](#) on Cement and is the direct responsibility of Subcommittee [C01.28](#) on Sulfate Content. Current edition approved ~~June 15, 2014~~ Oct. 1, 2014. Published ~~July 2014~~ October 2014. Originally approved in 1985. Last previous edition approved in 2014 as [C1038/C1038M – 14a, 14](#). DOI: [10.1520/C1038-C1038M-14a.10.1520/C1038_C1038M-14B](#).

² Section on Safety, *Manual of Cement Testing, Annual Book of Standards, Vol. 04.01*, Vol. 04.01.

³ For referenced ASTM standards, visit the ASTM website, [www.astm.org](#), or contact ASTM Customer Service at [service@astm.org](#). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard