

Designation: A449 - 14

Standard Specification for Hex Cap Screws, Bolts and Studs, Steel, Heat Treated, 120/ 105/90 ksi Minimum Tensile Strength, General Use¹

This standard is issued under the fixed designation A449; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

- 1.1 This specification² covers quenched and tempered steel hex cap screws, bolts, and studs having a minimum tensile strength of 120 ksi for diameters 1.0 in. and smaller; 105 ksi for diameters over 1.0 in. to $1\frac{1}{2}$ in.; and 90 ksi for diameters $1\frac{3}{4}$ in. to 3.0 in. inclusive. The term "fasteners" in this specification denotes hex cap screws, bolts, and studs.
 - 1.2 The fasteners are intended for general engineering use.
- 1.3 The fasteners are furnished in diameters ½ to 3.0 in. inclusive. They are designated by type denoting chemical composition as follows:

Type	Description
Type I	Plain carbon steel, carbon boron steel, alloy steel, or alloy boron steel
Type 2	Withdrawn 2003
Type 3	Weathering steel

- 1.4 Terms used in this specification are defined in Terminology F1789 unless otherwise defined in this specification.
- 1.5 The values stated in inch-pound units are to be regarded as standard. No other units of measurement are included in this standard.
- 1.6 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

2. Referenced Documents

2.1 ASTM Standards:³

A563 Specification for Carbon and Alloy Steel Nuts

A751 Test Methods, Practices, and Terminology for Chemical Analysis of Steel Products

B695 Specification for Coatings of Zinc Mechanically Deposited on Iron and Steel

F436 Specification for Hardened Steel Washers

F606 Test Methods for Determining the Mechanical Properties of Externally and Internally Threaded Fasteners, Washers, Direct Tension Indicators, and Rivets

F788/F788M Specification for Surface Discontinuities of Bolts, Screws, and Studs, Inch and Metric Series

F1470 Practice for Fastener Sampling for Specified Mechanical Properties and Performance Inspection

F1789 Terminology for F16 Mechanical Fasteners

F2329 Specification for Zinc Coating, Hot-Dip, Requirements for Application to Carbon and Alloy Steel Bolts, Screws, Washers, Nuts, and Special Threaded Fasteners

G101 Guide for Estimating the Atmospheric Corrosion Re-7 sistance of Low-Alloy Steels 49-14

2.2 ASME Standards:4

B 1.1 Unified Screw Threads

B 18.2.1 Square and Hex Bolts and Screws

B 18.24 Part Identifying Number (PIN) Code System Standard for B18 Fastener Products

3. Ordering Information

- 3.1 Orders for fasteners under this specification shall include the following:
 - 3.1.1 Quantity (number of pieces),
 - 3.1.2 Size, including nominal diameter and length,
 - 3.1.3 Name of product,
 - 3.1.4 Type, that is, Type 1, or Type 3 as required,

¹ This specification is under the jurisdiction of ASTM Committee F16 on Fastenersand is the direct responsibility of Subcommittee F16.02 on Steel Bolts, Nuts, Rivets and Washers.

Current edition approved Oct. 1, 2014. Published October 2014. Originally approved in 1963. Last previous edition approved in 2010 as A449-10. DOI: 10.1520/A0449-14.

² For ASME Boiler and Pressure Vessel Code applications see related Specifications SA-449 in Section II of that Code.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

⁴ Available from American Society of Mechanical Engineers (ASME), ASME International Headquarters, Three Park Ave., New York, NY 10016-5990, http://www.asme.org.



- 3.1.5 ASTM designation and year of issue, and
- 3.1.6 Other components such as nuts and washers if required.
- 3.1.7 Hot-Dip or Mechanically Deposited Zinc Coatings—For hot-dip or mechanically deposited zinc coatings covered by 5.1 and requiring over-tapped nuts, specify the zinc coating process required, that is, hot-dip, mechanically deposited, or no preference (see 5.1).
- 3.1.8 *Other Coatings*—Specify other protective coating if required (see 5.2).
- 3.1.9 Specify if inspection at point of manufacture is required.
 - 3.1.10 Test reports if required.
 - 3.1.11 Supplementary or special requirements.
- 3.1.12 For establishment of a part identifying system, see ASME B18.24.

Note 1—A typical ordering description follows: 1000 pieces ½ in. diameter × 4.0 in. long hex cap screw, Type 1, ASTM A449–XX, each with one finished hex nut ASTM A563, Grade DH. Each component mechanically zinc coated in accordance with B695, Class 5, Type II.

- 3.2 Suitable Nuts and Washers:
- 3.2.1 Suitable nuts are covered in Specification A563. Unless otherwise specified, the grade and style of nut shall be as follows:

Fastener Size and Surface Finish

Nut Grade and Style^A

1/4 to 11/2 in., plain (or with a coating of insufficient thickness to require over-tapped nuts)

Over 11/2 to 3 in., plain (or with a coating of insufficient thickness to require over-tapped nuts)

1/4 to 3 in., zinc-coated (or with a coating thickness requiring over-tapped nuts)

1/4 to 3 in., Type 3

C3, DH3, heavy hex

3.2.2 Unless otherwise specified, washers ordered with fasteners shall be furnished to the requirements of Specification F436, Type 1 or Specification F436, Type 3. Washers for A449 Type 3 fasteners shall conform to Specification F436 Type 3.

4. Materials and Manufacture

- 4.1 Heat Treatment:
- 4.1.1 Type 1 fasteners produced from medium carbon steel shall be quenched in a liquid medium from the austenitizing temperature.
- 4.1.2 Type 1 fasteners produced from medium carbon steel to which chromium, nickel, molybdenum, or boron were intentionally added, and Type 3 fasteners, shall be quenched in oil from the austenitizing temperature.
- 4.1.3 Type 1 and Type 3 fasteners, regardless of the steel used, shall be tempered by reheating to not less than 800°F.
 - 4.2 Threading—Threads shall be rolled, cut, or ground.
- 4.3 Secondary Processing—If any processing which can affect the mechanical properties of the fasteners is performed after the initial testing, the fasteners shall be retested for all specified mechanical properties affected by the reprocessing.

5. Protective Coatings

- 5.1 Zinc, Hot Dip, and Mechanically Deposited Requiring Over-tapped Nuts:
- 5.1.1 When zinc-coated fasteners are required, the purchaser shall specify the zinc-coating process, such as, hot-dip, mechanically deposited, or no preference.
- 5.1.2 When hot dip is specified, the fasteners shall be zinc coated by the hot-dip process in accordance with the requirements of Specification F2329.
- 5.1.3 When mechanically deposited is specified, the fasteners shall be zinc coated by the mechanical deposition process in accordance with the requirements of Class 55 of Specification B695.
- 5.1.4 When no preference is specified, the supplier may furnish either a hot-dip zinc coating in accordance with Specification F2329, or a mechanically deposited zinc coating in accordance with Specification B695, Class 55. Threaded components (bolts and nuts) shall be coated by the same zinc coating process, and the suppliers' option shall be limited to one process per item with no mixed processes in a lot.

Note 2—When the intended application requires that assembled tension exceeds 50 % of minimum bolt or stud proof load, an anti-galling lubricant may be needed. Application of such a lubricant to nuts and a test of the lubricant efficiency are provided in Supplementary Requirement S1 of Specification A563 and should be specified when required.

5.2 Other Coatings:

- 5.2.1 When other coatings are required, the purchaser shall specify the coating specification, including the classification codes or grade numbers to identify the coating material, thickness, supplemental treatments, or other requirements to define the coating. The fasteners shall be coated in accordance with and conform to the specified coating specification.
- 5.2.2 When a specification does not apply, the purchaser shall specify the desired coating, coating thickness, supplemental treatments, or other requirements to define the coating.

6. Chemical Composition

- 6.1 Type 1 fasteners shall be plain carbon steel, carbon boron steel, alloy steel, or alloy boron steels, at the manufacturers option, conforming to the requirements in Table 1.
- 6.2 Type 3 fasteners shall be weathering steel and shall conform to one of the chemical compositions specified in Table 2. The selection of the chemical composition, A, B, C, D, E or F, shall be a the option of the manufacturer. See Guide G101 for methods of estimating the atmospheric corrosion resistance of low alloy steel.
- 6.3 Product analyses made on finished fasteners representing each lot shall conform to the product analysis requirements specified in Table 1 or Table 2, as applicable.
- 6.4 Heats of steel to which bismuth, selenium, tellurium, or lead has been intentionally added shall not be permitted for bolts. Compliance shall be based on certification that heats of steel having any of the listed elements intentionally added were not used to produce the bolts.
- 6.5 Chemical analyses shall be performed in accordance with Test Methods, Practices, and Terminology A751.

^A Nuts of other grades and styles having specified proof load stresses (Specification A563, Table 3) greater than the specified grade and style of nut are suitable.