



Standard Specification for Forged or Rolled Alloy and Stainless Steel Pipe Flanges, Forged Fittings, and Valves and Parts for High-Temperature Service¹

This standard is issued under the fixed designation A182/A182M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This specification² covers forged low alloy and stainless steel piping components for use in pressure systems. Included are flanges, fittings, valves, and similar parts to specified dimensions or to dimensional standards, such as the ASME specifications that are referenced in Section 2.

1.2 For bars and products machined directly from bar (other than those directly addressed by this specification; see 6.4), refer to Specifications [A479/A479M](#) and [A739](#) for the similar grades available in those specifications. Products made to this specification are limited to a maximum weight of 10 000 lb [4540 kg]. For larger products and products for other applications, refer to Specifications [A336/A336M](#) and [A965/A965M](#) for the similar ferritic and austenitic grades, respectively, available in those specifications.

1.3 Several grades of low alloy steels and ferritic, martensitic, austenitic, and ferritic-austenitic stainless steels are included in this specification. Selection will depend upon design and service requirements. Several of the ferritic/austenitic (duplex) grades are also found in Specification [A1049/A1049M](#).

1.4 Supplementary requirements are provided for use when additional testing or inspection is desired. These shall apply only when specified individually by the purchaser in the order.

1.5 This specification is expressed in both inch-pound units and in SI units. However, unless the order specifies the applicable "M" specification designation (SI units), the material shall be furnished to inch-pound units.

1.6 The values stated in either SI units or inch-pound units are to be regarded separately as the standard. Within the text, the SI units are shown in brackets. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

2. Referenced Documents

2.1 In addition to the referenced documents listed in Specification [A961/A961M](#), the following list of standards apply to this specification.

2.2 ASTM Standards:³

[A262](#) Practices for Detecting Susceptibility to Intergranular Attack in Austenitic Stainless Steels

[A275/A275M](#) Practice for Magnetic Particle Examination of Steel Forgings

[A336/A336M](#) Specification for Alloy Steel Forgings for Pressure and High-Temperature Parts

[A388/A388M](#) Practice for Ultrasonic Examination of Steel Forgings

[A479/A479M](#) Specification for Stainless Steel Bars and Shapes for Use in Boilers and Other Pressure Vessels

[A484/A484M](#) Specification for General Requirements for Stainless Steel Bars, Billets, and Forgings

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.22 on Steel Forgings and Wrought Fittings for Piping Applications and Bolting Materials for Piping and Special Purpose Applications.

Current edition approved May 1, 2014/Oct. 1, 2014. Published June 2014/October 2014. Originally approved in 1935. Last previous edition approved in 2014 as A182/A182M-14-14a. DOI: 10.1520/A0182_A0182M-14A-10.1520/A0182_A0182M-14B.

² For ASME Boiler and Pressure Vessel Code applications see related Specification SA-182 in Section II of that Code.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard

A739 Specification for Steel Bars, Alloy, Hot-Wrought, for Elevated Temperature or Pressure-Containing Parts, or Both
A763 Practices for Detecting Susceptibility to Intergranular Attack in Ferritic Stainless Steels
A788/A788M Specification for Steel Forgings, General Requirements
A923 Test Methods for Detecting Detrimental Intermetallic Phase in Duplex Austenitic/Ferritic Stainless Steels
A961/A961M Specification for Common Requirements for Steel Flanges, Forged Fittings, Valves, and Parts for Piping Applications
A965/A965M Specification for Steel Forgings, Austenitic, for Pressure and High Temperature Parts
A1049/A1049M Specification for Stainless Steel Forgings, Ferritic/Austenitic (Duplex), for Pressure Vessels and Related Components
A1084 Test Method for Detecting Detrimental Phases in Lean Duplex Austenitic/Ferritic Stainless Steels
E92 Test Method for Vickers Hardness of Metallic Materials (Withdrawn 2010)⁴
E112 Test Methods for Determining Average Grain Size
E165 Practice for Liquid Penetrant Examination for General Industry
E340 Test Method for Macroetching Metals and Alloys
2.3 ASME Standards:⁵
B16.11 Forged Steel Fittings, Socket Welding, and Threaded
2.4 ASME Boiler and Pressure Vessel Code:⁵
Section IX
2.5 AWS Specifications⁶
A5.4/A5.4M Specification for Stainless Steel Electrodes for Shielded Metal Arc Welding
A5.5/A5.5M Specification for Low-Alloy Steel Electrodes for Shielded Metal Arc Welding
A5.9/A5.9M Specification for Bare Stainless Steel Welding Electrodes and Rods
A5.11/A5.11M Specification for Nickel and Nickel-Alloy Welding Electrodes for Shielded Metal Arc Welding
A5.14/A5.14M Specification for Nickel and Nickel-Alloy Bare Welding Electrodes and Rods
A5.23/A5.23M Specification for Low-Alloy Steel Electrodes and Fluxes for Submerged Arc Welding
A5.28/A5.28M Specification for Low-Alloy Steel Electrodes for Gas Shielded Arc Welding
A5.29/A5.29M Low-Alloy Steel Electrodes for Flux Cored Arc Welding

3. Terminology

3.1 *Definitions*—For definitions of terms used in this specification, refer to Specification A961/A961M.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *hardened condition, n*—for F23, the metallurgical condition achieved after normalizing and cooling to room temperature but prior to tempering.

4. Ordering Information

4.1 It is the purchaser's responsibility to specify in the purchase order information necessary to purchase the needed material. In addition to the ordering information guidelines in Specification A961/A961M, orders should include the following information:

4.1.1 Additional requirements (see 7.2.1, Table 2 footnotes, 9.3, and 19.2), and

4.1.2 Requirement, if any, that manufacturer shall submit drawings for approval showing the shape of the rough forging before machining and the exact location of test specimen material (see 9.3.1).

5. General Requirements

5.1 Product furnished to this specification shall conform to the requirements of Specification A961/A961M, including any supplementary requirements that are indicated in the purchase order. Failure to comply with the general requirements of Specification A961/A961M constitutes nonconformance with this specification. In case of conflict between the requirements of this specification and Specification A961/A961M, this specification shall prevail.

6. Manufacture

6.1 The low-alloy ferritic steels shall be made by the open-hearth, electric-furnace, or basic-oxygen process with the option of separate degassing and refining processes in each case.

6.2 The stainless steels shall be melted by one of the following processes: (a) electric-furnace (with the option of separate degassing and refining processes); (b) vacuum-furnace; or (c) one of the former followed by vacuum or electroslag-consumable remelting. Grade F XM-27Cb may be produced by electron-beam melting.

⁴ The last approved version of this historical standard is referenced on www.astm.org.

⁵ Available from American Society of Mechanical Engineers (ASME), ASME International Headquarters, Two Park Ave., New York, NY 10016-5990, <http://www.asme.org>.

⁶ Available from American Welding Society (AWS), 550 NW LeJeune Rd., Miami, FL 33126, <http://www.aws.org>.

6.3 A sufficient discard shall be made to secure freedom from injurious piping and undue segregation.

6.4 The material shall be forged as close as practicable to the specified shape and size.

6.4.1 Flanges of any type, elbows, return bends, tees, and header tees shall not be machined directly from bar stock.

6.4.2 Cylindrically-shaped parts may be machined from forged or rolled solution-annealed austenitic stainless steel bar without additional hot working.

6.4.3 Cylindrically-shaped low alloy, martensitic stainless, ferritic stainless, and ferritic-austenitic stainless steel parts, NPS-4 [DN 100] and under, may be machined from forged or rolled bar, without additional hot working.

6.5 Except as provided for in 6.4, the finished product shall be a forging as defined in the Terminology section of Specification [A788/A788M](#).

7. Heat Treatment⁷

7.1 After hot working, forgings shall be cooled to a temperature below 1000 °F [538 °C] prior to heat treating in accordance with the requirements of [Table 1](#).

7.2 *Low Alloy Steels and Ferritic and Martensitic Stainless Steels*—The low alloy steels and ferritic and martensitic stainless steels shall be heat treated in accordance with the requirements of 7.1 and [Table 1](#). When more than one heat treatment option is listed for a Grade in [Table 1](#), any one of the heat treatments listed shall be performed. The selection of the heat treatment shall be at the manufacturer's option, unless otherwise stated in the purchase order.

7.2.1 *Liquid Quenching*—Except as permitted in 7.2.2, for

F 1, F 2, and F 3, and in 7.2.3, for F 91, and when agreed to by the purchaser, liquid quenching followed by tempering shall be permitted provided the temperatures in [Table 1](#) for each grade are used.

7.2.1.1 *Marking*—Parts that are liquid quenched and tempered shall be marked “QT.”

7.2.2 Alternatively, Grade F 1, F 2, and F 12, Classes 1 and 2 may be given a heat treatment of 1200 °F [650 °C] minimum after final hot or cold forming.

7.2.3 Alternatively, Grade F 91 forged fittings having any section thickness greater than 3 in. [75 mm], at the time of heat treatment, shall be normalized and tempered or quenched and tempered at the manufacturer's option, provided that the temperatures in [Table 1](#) for F 91 are used.

7.3 *Austenitic and Ferritic-Austenitic Stainless Steels*—The austenitic and ferritic-austenitic stainless steels shall be heat treated in accordance with the requirements of 7.1 and [Table 1](#).

7.3.1 Alternatively, immediately following hot working, while the temperature of the forging is not less than the minimum solution annealing temperature specified in [Table 1](#), forgings made from austenitic grades (except grades F 304H, F 309H, F 310, F 310H, F 316H, F 321, F 321H, F 347, F 347H, F 348, F 348H, F 45, and F 56) may be individually rapidly quenched in accordance with the requirements of [Table 1](#).

7.3.2 See Supplementary Requirement S8 if a particular heat treatment method is to be employed.

7.4 *Time of Heat Treatment*—Heat treatment of forgings may be performed before machining.

7.5 *Forged or Rolled Bar*—Forged or rolled austenitic stainless bar from which cylindrically shaped parts are to be machined, as permitted by 6.4, and the parts machined from such bar, without heat treatment after machining, shall be furnished to the annealing requirements of Specification [A479/A479M](#) or this specification, with subsequent light cold drawing and straightening permitted (see Supplementary Requirement S3 if annealing must be the final operation).

8. Chemical Composition

8.1 A chemical heat analysis in accordance with Specification [A961/A961M](#) shall be made and conform to the chemical composition prescribed in [Table 2](#).

8.2 Grades to which lead, selenium, or other elements are added for the purpose of rendering the material free-machining shall not be used.

8.3 Starting material produced to a specification that specifically requires the addition of any element beyond those listed in [Table 2](#) for the applicable grade of material is not permitted.

8.4 Steel grades covered in this specification shall not contain an unspecified element, other than nitrogen in stainless steels, for the ordered grade to the extent that the steel conforms to the requirements of another grade for which that element is a specified element having a required minimum content. For this requirement, a grade is defined as an alloy described individually and identified by its own UNS designation or Grade designation and identification symbol in [Table 2](#).

⁷ A solution annealing temperature above 1950 °F [1065 °C] may impair the resistance to intergranular corrosion after subsequent exposure to sensitizing conditions in F 321, F 321H, F 347, F 347H, F 348, and F 348H. When specified by the purchaser, a lower temperature stabilization or resolution annealing shall be used subsequent to the initial high temperature solution anneal (see Supplementary Requirement S10).



TABLE 1 Heat Treating Requirements

Grade	Heat Treat Type	Austenitizing/Solutioning Temperature, Minimum or Range, °F [°C] ⁴	Cooling Media	Quenching Cool Below °F [°C]	Tempering Temperature, Minimum or Range, °F [°C]
Low Alloy Steels					
F 1	anneal	1650 [900]	furnace cool	<i>B</i>	<i>B</i>
	normalize and temper	1650 [900]	air cool	<i>B</i>	1150 [620]
F 2	anneal	1650 [900]	furnace cool	<i>B</i>	<i>B</i>
	normalize and temper	1650 [900]	air cool	<i>B</i>	1150 [620]
F 5, F 5a	anneal	1750 [955]	furnace cool	<i>B</i>	<i>B</i>
	normalize and temper	1750 [955]	air cool	<i>B</i>	1250 [675]
F 9	anneal	1750 [955]	furnace cool	<i>B</i>	<i>B</i>
	normalize and temper	1750 [955]	air cool	<i>B</i>	1250 [675]
F 10	solution treat and quench	1900 [1040]	liquid	500 [260]	<i>B</i>
F 91	normalize and temper	1900-1975 [1040-1080]	air cool	<i>B</i>	1350-1470 [730-800]
F 92	normalize and temper	1900-1975 [1040-1080]	air cool	<i>B</i>	1350-1470 [730-800]
F 122	normalize and temper	1900-1975 [1040-1080]	air cool	<i>B</i>	1350-1470 [730-800]
F 911	normalize and temper	1900-1975 [1040-1080]	air cool or liquid	<i>B</i>	1365-1435 [740-780]
F 11, Class 1, 2, 3	anneal	1650 [900]	furnace cool	<i>B</i>	<i>B</i>
	normalize and temper	1650 [900]	air cool	<i>B</i>	1150 [620]
F 12, Class 1, 2	anneal	1650 [900]	furnace cool	<i>B</i>	<i>B</i>
	normalize and temper	1650 [900]	air cool	<i>B</i>	1150 [620]
F 21, F 3V, and F 3VCb	anneal	1750 [955]	furnace cool	<i>B</i>	<i>B</i>
	normalize and temper	1750 [955]	air cool	<i>B</i>	1250 [675]
F 22, Class 1, 3	anneal	1650 [900]	furnace cool	<i>B</i>	<i>B</i>
	normalize and temper	1650 [900]	air cool	<i>B</i>	1250 [675]
F 22V	normalize and temper or quench and temper	1650 [900]	air cool or liquid	<i>B</i>	1250 [675]
F 23	normalize and temper	1900-1975 [1040-1080]	air cool	<i>B</i>	1350-1470 [730-800]
			accelerated cool		
F 24	normalize and temper	1800-1975 [980-1080]	air cool	<i>B</i>	1350-1470 [730-800]
			or liquid		
FR	anneal	1750 [955]	furnace cool	<i>B</i>	<i>B</i>
	normalize	1750 [955]	air cool	<i>B</i>	<i>B</i>
	normalize and temper	1750 [955]	air cool	<i>B</i>	1250 [675]
F 36, Class 1	normalize and temper	1650 [900]	air cool	<i>B</i>	1100 [595]
F 36, Class 2	normalize and temper	1650 [900]	air cool	<i>B</i>	1100 [595]
	quench and temper	1650 [900]	accelerated air cool or liquid		1100 [595]
Martensitic Stainless Steels					
F 6a Class 1	anneal	not specified	furnace cool	<i>B</i>	<i>B</i>
	normalize and temper	not specified	air cool	400 [205]	1325 [725]
	temper	not required		<i>B</i>	1325 [725]
F 6a Class 2	anneal	not specified	furnace cool	<i>B</i>	<i>B</i>
	normalize and temper	not specified	air cool	400 [205]	1250 [675]
	temper	not required		<i>B</i>	1250 [675]
F 6a Class 3	anneal	not specified	furnace cool	<i>B</i>	<i>B</i>
	normalize and temper	not specified	air cool	400 [205]	1100 [595]
F 6a Class 4	anneal	not specified	furnace cool	<i>B</i>	<i>B</i>
	normalize and temper	not specified	air cool	400 [205]	1000 [540]
F 6b	anneal	1750 [955]	furnace cool	<i>B</i>	<i>B</i>
	normalize and temper	1750 [955]	air cool	400 [205]	1150 [620]
F 6NM	normalize and temper	1850 [1010]	air cool	200 [95]	1040-1120 [560-600]
Ferritic Stainless Steels					
F XM-27 Cb	anneal	1850 [1010]	furnace cool	<i>B</i>	<i>B</i>
F 429	anneal	1850 [1010]	furnace cool	<i>B</i>	<i>B</i>
F 430	anneal	not specified	furnace cool	<i>B</i>	<i>B</i>
Austenitic Stainless Steels					
F 304	solution treat and quench	1900 [1040]	liquid	500 [260]	<i>B</i>
F 304H	solution treat and quench	1900 [1040]	liquid	500 [260]	<i>B</i>
F 304L	solution treat and quench	1900 [1040]	liquid	500 [260]	<i>B</i>
F 304N	solution treat and quench	1900 [1040]	liquid	500 [260]	<i>B</i>
F 304LN	solution treat and quench	1900 [1040]	liquid	500 [260]	<i>B</i>
F 309H	solution treat and quench	1900 [1040]	liquid	500 [260]	<i>B</i>
F 310	solution treat and quench	1900 [1040]	liquid	500 [260]	<i>B</i>
F 310H	solution treat and quench	1900 [1040]	liquid	500 [260]	<i>B</i>
F 310MoLN	solution treat and quench	1900-2010 [1050-1100]	liquid	500 [260]	<i>B</i>
F 316	solution treat and quench	1900 [1040]	liquid	500 [260]	<i>B</i>
F 316H	solution treat and quench	1900 [1040]	liquid	500 [260]	<i>B</i>
F 316L	solution treat and quench	1900 [1040]	liquid	500 [260]	<i>B</i>
F 316N	solution treat and quench	1900 [1040]	liquid	500 [260]	<i>B</i>
F 316LN	solution treat and quench	1900 [1040]	liquid	500 [260]	<i>B</i>
F 316Ti	solution treat and quench	1900 [1040]	liquid	500 [260]	<i>B</i>
F 317	solution treat and quench	1900 [1040]	liquid	500 [260]	<i>B</i>
F 317L	solution treat and quench	1900 [1040]	liquid	500 [260]	<i>B</i>
S31727	solution treat and quench	1975-2155 [1080-1180]	liquid	500 [260]	<i>B</i>



TABLE 1 Continued

Grade	Heat Treat Type	Austenitizing/Solutioning Temperature, Minimum or Range, °F [°C] ^A	Cooling Media	Quenching Cool Below °F [°C]	Tempering Temperature, Minimum or Range, °F [°C]
F 72	solution treat and quench	1975–2155 [1080–1180]	liquid	500 [260]	B
S32053	solution treat and quench	1975–2155 [1080–1180]	liquid	500 [260]	B
F 73	solution treat and quench	1975–2155 [1080–1180]	liquid	500 [260]	B
F 347	solution treat and quench	1900 [1040]	liquid	500 [260]	B
F 347H	solution treat and quench	2000 [1095]	liquid	500 [260]	B
F 347LN	solution treat and quench	1900 [1040]	liquid	500 [260]	B
F 348	solution treat and quench	1900 [1040]	liquid	500 [260]	B
F 348H	solution treat and quench	2000 [1095]	liquid	500 [260]	B
F 321	solution treat and quench	1900 [1040]	liquid	500 [260]	B
F 321H	solution treat and quench	2000 [1095]	liquid	500 [260]	B
F XM-11	solution treat and quench	1900 [1040]	liquid	500 [260]	B
F XM-19	solution treat and quench	1900 [1040]	liquid	500 [260]	B
F 20	solution treat and quench	1700–1850 [925–1010]	liquid	500 [260]	B
F 44	solution treat and quench	2100 [1150]	liquid	500 [260]	B
F 45	solution treat and quench	1900 [1040]	liquid	500 [260]	B
F 46	solution treat and quench	2010–2140 [1100–1140]	liquid	500 [260]	B
F 47	solution treat and quench	1900 [1040]	liquid	500 [260]	B
F 48	solution treat and quench	1900 [1040]	liquid	500 [260]	B
F 49	solution treat and quench	2050 [1120]	liquid	500 [260]	B
F 56	solution treat and quench	2050–2160 [1120–1180]	liquid	500 [260]	B
F 58	solution treat and quench	2085 [1140]	liquid	500 [260]	B
F 62	solution treat and quench	2025 [1105]	liquid	500 [260]	B
F 63	solution treat and quench	1900 [1040]	liquid	500 [260]	B
F 64	solution treat and quench	2010–2140 [1100–1170]	liquid	500 [260]	B
F 904L	solution treat and quench	1920–2100 [1050–1150]	liquid	500 [260]	B
F70	solution treat and quench	1900 [1040]	liquid^D	500 [260]	B
F 70	solution treat and quench	1900 [1040]	liquid ^D	500 [260]	B
Ferritic-Austenitic Stainless Steels					
F 50	solution treat and quench	1925 [1050]	liquid	500 [260]	B
F 51	solution treat and quench	1870 [1020]	liquid	500 [260]	B
F 52 ^C			liquid	500 [260]	B
F 53	solution treat and quench	1880 [1025]	liquid	500 [260]	B
F 54	solution treat and quench	1920–2060 [1050–1125]	liquid	500 [260]	B
F 55	solution treat and quench	2010–2085 [1100–1140]	liquid	500 [260]	B
F 57	solution treat and quench	1940 [1060]	liquid	175 [80]	B
F 59	solution treat and quench	1975–2050 [1080–1120]	liquid	500 [260]	B
F 60	solution treat and quench	1870 [1020]	liquid	500 [260]	B
F 61	solution treat and quench	1920–2060 [1050–1125]	liquid	500 [260]	B
F 65	solution treat and quench	1830–2100 [1000–1150]	liquid ^D	500 [260]	B
F 66	solution treat and quench	1870–1975 [1020–1080]	liquid	500 [260]	B
F 67	solution treat and quench	1870–2050 [1020–1120]	liquid	500 [260]	B
F 68	solution treat and quench	1700–1920 [925–1050]	liquid	500 [260]	B
F 69	solution treat and quench	1870 [1020]	liquid	500 [260]	B
F 71	solution treat and quench	1925–2100 [1050–1150]	liquid	500 [260]	B

^A Minimum unless temperature range is listed.

^B Not applicable.

^C Grade F 52 shall be solution treated at 1825 to 1875 °F [995 to 1025 °C] 30 min/in. of thickness and water quenched.

^D The cooling media for Grades F 65 and F70 shall be quenching in water or rapidly cooling by other means.

8.5 *Product Analysis*—The purchaser may make a product analysis on products supplied to this specification in accordance with Specification [A961/A961M](#).

9. Mechanical Properties

9.1 The material shall conform to the requirements as to mechanical properties for the grade ordered as listed in [Table 3](#).

9.2 Mechanical test specimens shall be obtained from production forgings, or from separately forged test blanks prepared from the stock used to make the finished product. In either case, mechanical test specimens shall not be removed until after all heat treatment is complete. If repair welding is required, test specimens shall not be removed until after post-weld heat treatment is complete, except for ferritic grades when the post-weld heat treatment is conducted at least 50 °F [30 °C] below the actual tempering temperature. When test blanks are used, they shall receive approximately the same working as the finished product. The test blanks shall be heat treated with the finished product and shall approximate the maximum cross section of the forgings they represent.

9.3 For normalized and tempered, or quenched and tempered forgings, the central axis of the test specimen shall be taken at least $\frac{1}{4} T$ from the nearest surface as-heat-treated, where T is the maximum heat-treated thickness of the represented forging. In addition, for quenched and tempered forgings, the mid-length of the test specimen shall be at least T from all other surfaces

TABLE 2 Chemical Requirements^A

Identifi- cation Symbol	UNS Desig- nation	Grade	Composition, %										
			Carbon	Manga- nese	Phos- phorus	Sulfur	Silicon	Nickel	Chromium	Molybde- num	Colum- bium	Titan- ium	Other Elements
Low Alloy Steels													
F-1	K12822	carbon-molybdenum	0.28	0.60–0.90	0.045	0.045	0.15–0.35	0.44–0.65
F-2 ^B	K12122	0.5% chromium, 0.5% molybdenum	0.05–0.21	0.30–0.80	0.040	0.040	0.10–0.60	...	0.50–0.81	0.44–0.65
F-5 ^C	K41545	4 to 6% chromium	0.15	0.30–0.60	0.030	0.030	0.50	0.50	4.0–6.0	0.44–0.65
F-5a ^C	K42544	4 to 6% chromium	0.25	0.60	0.040	0.030	0.50	0.50	4.0–6.0	0.44–0.65
F-9	K90941	9% chromium	0.15	0.30–0.60	0.030	0.030	0.50–1.00	...	8.0–10.0	0.90–1.10
F-10	S33100	20 nickel, 8 chromium	0.10–0.20	0.50–0.80	0.040	0.030	1.00–1.40	19.0–22.0	7.0–9.0
F-91	K90901	9% chromium, 1% molybdenum, 0.2% vanadium plus columbium and nitrogen	0.08–0.12	0.30–0.60	0.020	0.010	0.20–0.50	0.40	8.0–9.5	0.85–1.05	0.06–0.10	...	N 0.03–0.07 —Al 0.02 ^D —V 0.18–0.25 —Ti 0.01 ^D —Zr 0.01 ^D
F-92	K92460	9% chromium, 1.8% tungsten, 0.2% vanadium plus columbium	0.07–0.13	0.30–0.60	0.020	0.010	0.50	0.40	8.50–9.50	0.30–0.60	0.04–0.09	...	V 0.15–0.25 —N 0.030–0.070 —Al 0.02 ^D —W 1.50–2.00 —B 0.001–0.006 —Ti 0.01 ^D —Zr 0.01 ^D
F-122	K91271	11% chromium, 2% tungsten, 0.2% vanadium, plus molybdenum, columbium, copper, nickel, nitrogen, and boron	0.07–0.14	0.70	0.020	0.010	0.50	0.50	10.00–11.50	0.25–0.60	0.04– –0.10	...	—V 0.15–0.30 —B 0.005 —N 0.040–0.100 —Al 0.02 ^D —Cu 0.30–1.70 —W 1.50–2.50 —Ti 0.01 ^D —Zr 0.01 ^D
F-911	K91061	9% chromium, 1% molybdenum, 0.2% vanadium plus columbium and nitrogen	0.09–0.13	0.30–0.60	0.020	0.010	0.10–0.50	0.40	8.5–9.5	0.90–1.10	0.060–0.10	...	W 0.90–1.10 —Al 0.02 ^D —N 0.04–0.09 —V 0.18–0.25 —B 0.0003– 0.006 —Ti 0.01 ^D —Zr 0.01 ^D
F-11	K11597	1.25% chromium, 0.5% molybdenum	0.05–0.15	0.30–0.60	0.030	0.030	0.50–1.00	...	1.00–1.50	0.44–0.65
—Class 1	K11572	1.25% chromium, 0.5% molybdenum	0.10–0.20	0.30–0.80	0.040	0.040	0.50–1.00	...	1.00–1.50	0.44–0.65
—Class 2	K11572	1.25% chromium, 0.5% molybdenum	0.10–0.20	0.30–0.80	0.040	0.040	0.50–1.00	...	1.00–1.50	0.44–0.65
—Class 3	K11562	1% chromium, 0.5% molybdenum	0.05–0.15	0.30–0.60	0.045	0.045	0.50 max	...	0.80–1.25	0.44–0.65
F-12	K11562	1% chromium, 0.5% molybdenum	0.10–0.20	0.30–0.60	0.040	0.040	0.10–0.60	...	0.80–1.25	0.44–0.65
—Class 1	K11564	1% chromium, 0.5% molybdenum	0.10–0.20	0.30–0.60	0.040	0.040	0.10–0.60	...	0.80–1.25	0.44–0.65
—Class 2	K31545	chromium-molybdenum	0.05–0.15	0.30–0.60	0.040	0.040	0.50 max	...	2.7–3.3	0.80–1.06
F-21	K31830	3% chromium, 1% molybdenum, 0.25% vanadium plus boron and titanium	0.05–0.18	0.30–0.60	0.020	0.020	0.10	...	2.8–3.2	0.90–1.10	...	0.015– –0.035	—V 0.20–0.30 —B 0.001–0.003
F-3V	K31390	3% chromium, 1% molybdenum, 0.25% vanadium plus boron, columbium, and titanium	0.10–0.15	0.30–0.60	0.020	0.010	0.10	0.25	2.7–3.3	0.90–1.10	0.015–0.070	0.015	—V 0.20–0.30 —Cu 0.25 —Ca 0.0005– —0.0150
F-22	K21590	chromium-molybdenum	0.05–0.15	0.30–0.60	0.040	0.040	0.50	...	2.00–2.50	0.87–1.13
—Class 1	—	—	—	—	—	—	—	—	—	—	—	—	...
F-22	K21590	chromium-molybdenum	0.05–0.15	0.30–0.60	0.040	0.040	0.50	...	2.00–2.50	0.87–1.13
—Class 3	—	—	—	—	—	—	—	—	—	—	—	—	...
F-22V	K31835	2.25% chromium, 1% molybdenum, 0.25% vanadium	0.11–0.15	0.30–0.60	0.015	0.010	0.10	0.25	2.00–2.50	0.90–1.10	0.07	0.030	—Cu 0.20 —V 0.25–0.35 —B 0.002 —Ca 0.015 ^E
F-23	K41650	2.25% chromium, 1.6% tungsten, 0.25% vanadium, plus molybdenum, columbium, and boron	0.04–0.10	0.10–0.60	0.030	0.010	0.50	0.40	1.90–2.60	0.05–0.30	0.02– 0.08	0.005– 0.060 ^E	—V 0.20–0.30 —B 0.0010– —0.006 —N 0.015 ^E —Al 0.030 —W 1.45–1.75

as-heat-treated, exclusive of the *T* dimension surfaces. When the section thickness does not permit this positioning, the test specimen shall be positioned as near as possible to the prescribed location, as agreed to by the purchaser and the supplier.



TABLE 2 Continued

Identification Symbol	UNS Designation	Grade	Composition, %										
			Carbon	Manganese	Phosphorus	Sulfur	Silicon	Nickel	Chromium	Molybdenum	Columbium	Titanium	Other Elements
F-24	K30736	2.25% chromium, 1% molybdenum, 0.25% vanadium plus titanium and boron	0.05–0.10	0.30–0.70	0.020	0.010	0.15–0.45	...	2.20–2.60	0.90–1.10	...	0.06–0.10	V 0.20–0.30 —N 0.12 —Al 0.020 —B 0.0015–0.0070
FR F-36	K22035 K21001	2% nickel, 1% copper 1.15% nickel, 0.65% copper, molybdenum, and columbium	0.20 0.10–0.17	0.40–1.06 0.80–1.20	0.045 0.030	0.050 0.025	...	1.60–2.24 1.00–1.30	—Cu 0.75–1.25 —N 0.020 —Al 0.050 —Cu 0.50–0.80 —V 0.02
Martensitic Stainless Steels													
F-6a	S41000	13% chromium 410 ^G	0.15	1.00	0.040	0.030	1.00	0.50	11.5–13.5
F-6b	S41026	13% chromium, 0.5% molybdenum	0.15	1.00	0.020	0.020	1.00	1.00–2.00	11.5–13.5	0.40–0.60	—Cu 0.50
F-6NM	S41500	13% chromium, 4% nickel	0.05	0.50–1.00	0.030	0.030	0.60	3.5–5.5	11.5–14.0	0.50–1.00
Ferritic Stainless Steels													
F-XM- —27Cb	S44627	27 chromium, 1 molybdenum XM-27 ^G	0.010 ^H	0.40	0.020	0.020	0.40	0.50 ^H	25.0–27.5	0.75–1.50	0.05–0.20	...	—N 0.015 ^H —Cu 0.20 ^H
F-429	S42900	15 chromium 429 ^G	0.12	1.00	0.040	0.030	0.75	0.50	14.0–16.0
F-430	S43000	17 chromium 430 ^G	0.12	1.00	0.040	0.030	0.75	0.50	16.0–18.0
Austenitic Stainless Steels													
F-304	S30400	18 chromium, 8 nickel 304 ^G	0.08	2.00	0.045	0.030	1.00	8.0–11.0	18.0–20.0	—N 0.10
F-304H	S30409	18 chromium, 8 nickel 304H ^G	0.04–0.10	2.00	0.045	0.030	1.00	8.0–11.0	18.0–20.0
F-304L	S30403	18 chromium, 8 nickel, low carbon 304L ^G	0.030	2.00	0.045	0.030	1.00	8.0–13.0	18.0–20.0	—N 0.10
F-304N	S30451	18 chromium, 8 nickel, modified with nitrogen 304N ^G	0.08	2.00	0.045	0.030	1.00	8.0–10.5	18.0–20.0	—N 0.10–0.16
F-304LN	S30453	18 chromium, 8 nickel, modified with nitrogen 304LN ^G	0.030	2.00	0.045	0.030	1.00	8.0–10.5	18.0–20.0	—N 0.10–0.16
F-309H	S30909	23 chromium, 13.5 nickel 309H ^G	0.04–0.10	2.00	0.045	0.030	1.00	12.0–15.0	22.0–24.0
F-310	S31000	25 chromium, 20 nickel 310 ^G	0.25	2.00	0.045	0.030	1.00	19.0–22.0	24.0–26.0
F-310H	S31009	25 chromium, 20 nickel 310H ^G	0.04–0.10	2.00	0.045	0.030	1.00	19.0–22.0	24.0–26.0
F-310MoLN	S31050	25 chromium, 22 nickel, modified with molybdenum and nitrogen, low carbon 310MoLN ^G	0.030	2.00	0.030	0.015	0.40	21.0–23.0	24.0–26.0	2.00–3.00	N 0.10–0.16
F-316	S31600	18 chromium, 8 nickel, modified with molybdenum 316 ^G	0.08	2.00	0.045	0.030	1.00	10.0–14.0	16.0–18.0	2.00–3.00	N 0.10
F-316H	S31609	18 chromium, 8 nickel, modified with molybdenum 316H ^G	0.04–0.10	2.00	0.045	0.030	1.00	10.0–14.0	16.0–18.0	2.00–3.00
F-316L	S31603	18 chromium, 8 nickel, modified with molybdenum, low carbon 316L ^G	0.030	2.00	0.045	0.030	1.00	10.0–15.0	16.0–18.0	2.00–3.00	N 0.10
F-316N	S31651	18 chromium, 8 nickel, modified with molybdenum and nitrogen 316N ^G	0.08	2.00	0.045	0.030	1.00	11.0–14.0	16.0–18.0	2.00–3.00	N 0.10–0.16



TABLE 2 Continued

Identification Symbol	UNS Designation	Grade	Composition, %										
			Carbon	Manganese	Phosphorus	Sulfur	Silicon	Nickel	Chromium	Molybdenum	Columbium	Titanium	Other Elements
F-316LN	S31653	18-chromium, 8-nickel, modified with molybdenum and nitrogen 316LN ^G	0.030	2.00	0.045	0.030	1.00	11.0–14.0	16.0–18.0	2.00–3.00	N-0.10–0.16
F-316Ti	S31635	18-chromium, 8-nickel, modified with molybdenum and nitrogen 316Ti ^G	0.08	2.00	0.045	0.030	1.00	10.0–14.0	16.0–18.0	2.00–3.00	...	!	N-0.10-max
F-317	S31700	19-chromium, 13-nickel, 3.5-molybdenum 317 ^G	0.08	2.00	0.045	0.030	1.00	11.0–15.0	18.0–20.0	3.0–4.0
F-317L	S31703	19-chromium, 13-nickel, 3.5-molybdenum 317L ^G	0.030	2.00	0.045	0.030	1.00	11.0–15.0	18.0–20.0	3.0–4.0
S31727	S31727	18-chromium, 15-nickel, 4.5-molybdenum, 3.5-copper with nitrogen	0.030	1.00	0.030	0.030	1.00	14.5–16.5	17.5–19.0	3.8–4.5	Cu-2.8–4.0 N-0.15–0.21
F-70	S31730	18-chromium, 16-nickel, 4.5-copper, 3.5-molybdenum, with nitrogen	0.030	2.00	0.040	0.010	1.00	15–16.5	17.0–19.0	3.0–4.0	Cu-4.0–5.0 N-0.045
S32053	S32053	23-chromium, 25-nickel, 5.5-molybdenum, with nitrogen	0.030	1.00	0.030	0.010	1.00	24.0–28.0	22.0–24.0	5.0–6.0	N-0.17–0.22
F-321	S32100	18-chromium, 8-nickel modified with titanium 321 ^G	0.08	2.00	0.045	0.030	1.00	9.0–12.0	17.0–19.0	J	...
F-321H	S32109	18-chromium, 8-nickel, modified with titanium 321H ^G	0.04–0.10	2.00	0.045	0.030	1.00	9.0–12.0	17.0–19.0	K	...
F-347	S34700	18-chromium, 8-nickel modified with columbium 347 ^G	0.08	2.00	0.045	0.030	1.00	9.0–13.0	17.0–20.0	...	L
F-347H	S34709	18-chromium, 8-nickel, modified with columbium 347H ^G	0.04–0.10	2.00	0.045	0.030	1.00	9.0–13.0	17.0–20.0	...	M
F347LN	S34751	18-chromium, 8-nickel modified with columbium and nitrogen 347LN	0.005–0.020	2.00	0.045	0.030	1.00	9.0–13.0	17.0–19.0	...	0.20–0.50 ^N	...	N-0.06–0.10
F-348	S34800	18-chromium, 8-nickel modified with columbium 348 ^G	0.08	2.00	0.045	0.030	1.00	9.0–13.0	17.0–20.0	...	L	...	Co-0.20 Ta-0.10
F-348H	S34809	18-chromium, 8-nickel, modified with columbium 348H ^G	0.04–0.10	2.00	0.045	0.030	1.00	9.0–13.0	17.0–20.0	...	M	...	Co-0.20 Ta-0.10
F-XM-11	S21904	20-chromium, 6-nickel, 9-manganese XM-11 ^G	0.040	8.0–10.0	0.060	0.030	1.00	5.5–7.5	19.0–21.5	N-0.15–0.40
F-XM-19	S20910	22-chromium, 13-nickel, 5-manganese XM-19 ^G	0.06	4.0–6.0	0.040	0.030	1.00	11.5–13.5	20.5–23.5	1.50–3.00	0.10–0.30	...	N-0.20–0.40 V-0.10–0.30
F-20	N08020	35-nickel, 20-chromium, 3.5-copper, 2.5-molybdenum	.07	2.00	0.045	0.035	1.00	32.0–38.0	19.0–21.0	2.00–3.00	8xCmin–1.00	...	Cu-3.0–4.0
F-44	S31254	20-chromium, 18-nickel, 6-molybdenum, low-carbon	0.020	1.00	0.030	0.010	0.80	17.5–18.5	19.5–20.5	6.0–6.5	Cu-0.50–1.00 N-0.18–0.25
F-45	S30815	21-chromium, 11-nickel modified with nitrogen and cerium	0.05–0.10	0.80	0.040	0.030	1.40–2.00	10.0–12.0	20.0–22.0	N-0.14–0.20 Ce-0.03–0.08
F-46	S30600	18-chromium, 15-nickel, 4-silicon	0.018	2.00	0.020	0.020	3.7–4.3	14.0–15.5	17.0–18.5	0.20	Cu-0.50



TABLE 2 Continued

Identification Symbol	UNS Designation	Grade	Composition, %										
			Carbon	Manganese	Phosphorus	Sulfur	Silicon	Nickel	Chromium	Molybdenum	Columbium	Titanium	Other Elements
F-47	S31725	19 chromium, 15 nickel, 4 molybdenum 317LM [Ⓒ]	0.030	2.00	0.045	0.030	0.75	13.0–17.5	18.0–20.0	4.0–5.0	N-0.10
F-48	S31726	19 chromium, 15 nickel, 4 molybdenum 317LMN [Ⓒ]	0.030	2.00	0.045	0.030	0.75	13.5–17.5	17.0–20.0	4.0–5.0	N-0.10–0.20
F-49	S34565	24 chromium, 17 nickel, 6 manganese, 5 molybdenum	0.030	5.0–7.0	0.030	0.010	1.00	16.0–18.0	23.0–25.0	4.0–5.0	0.10	...	N-0.40–0.60
F-56	S33228	32 nickel, 27 chromium with columbium	0.04–0.08	1.00	0.020	0.015	0.30	31.0–33.0	26.0–28.0	...	0.6–1.0	...	Ce-0.05–0.10 Al-0.025
F-58	S31266	24 chromium, 20 nickel, 6 molybdenum, 2 tungsten with nitrogen	0.030	2.0–4.0	0.035	0.020	1.00	21.0–24.0	23.0–25.0	5.2–6.2	N-0.35–0.60 Cu-1.00–2.50 W-1.50–2.50
F-62	N08367	21 chromium, 25 nickel, 6.5 molybdenum	0.030	2.00	0.040	0.030	1.00	23.5–25.5	20.0–22.0	6.0–7.0	N-0.18–0.25 Cu-0.75
F-63	S32615	18 chromium, 20 nickel, 5.5 silicon	0.07	2.00	0.045	0.030	4.8–6.0	19.0–22.0	16.5–19.5	0.30–1.50	Cu-1.50–2.50
F-64	S30601	17.5 chromium, 17.5 nickel, 5.3 silicon	0.015	0.50–0.80	0.030	0.013	5.0–5.6	17.0–18.0	17.0–18.0	0.20	Cu-0.35, N-0.05
F-904L	N08904	21 chromium, 26 nickel, 4.5 molybdenum 904L [Ⓒ]	0.020	2.0	0.040	0.030	1.00	23.0–28.0	19.0–23.0	4.0–5.0	Cu-1.00–2.00 N-0.10
Ferritic-Austenitic Stainless Steels													
F-50	S31200	25 chromium, 6 nickel, modified with nitrogen	0.030	2.00	0.045	0.030	1.00	5.5–6.5	24.0–26.0	1.20–2.00	N-0.14–0.20
F-51	S31803	22 chromium, 5.5 nickel, modified with nitrogen	0.030	2.00	0.030	0.020	1.00	4.5–6.5	21.0–23.0	2.5–3.5	N-0.08–0.20
F-69	S32101	21.5 chromium, 1.5 nickel, modified with nitrogen	0.040	4.00–6.00	0.040	0.030	1.00	1.35–1.70	21.0–22.0	0.10–0.80	N-0.20–0.25 Cu-0.10–0.80
F-52	S32950	26 chromium, 3.5 nickel, 1.0 molybdenum	0.030	2.00	0.035	0.010	0.60	3.5–5.2	26.0–29.0	1.00–2.50	N-0.15–0.35
F-53	S32750	25 chromium, 7 nickel, 4 molybdenum, modified with nitrogen 2507 [Ⓒ]	0.030	1.20	0.035	0.020	0.80	6.0–8.0	24.0–26.0	3.0–5.0	N-0.24–0.32 Cu-0.50
F-54	S39274	25 chromium, 7 nickel, modified with nitrogen and tungsten	0.030	1.00	0.030	0.020	0.80	6.0–8.0	24.0–26.0	2.5–3.5	N-0.24–0.32 Cu-0.20–0.80 W-1.50–2.50
F-55	S32760	25 chromium, 7 nickel, 3.5 molybdenum, modified with nitrogen and tungsten	0.030	1.00	0.030	0.010	1.00	6.0–8.0	24.0–26.0	3.0–4.0	N-0.20–0.30 Cu-0.50–1.00 W-0.50–1.00 [Ⓒ]
F-57	S39277	26 chromium, 7 nickel, 3.7 molybdenum	0.025	0.80	0.025	0.002	0.80	6.5–8.0	24.0–26.0	3.0–4.0	Cu-1.20–2.00 W-0.80–1.20 N-0.23–0.33
F-59	S32520	25 chromium, 6.5 nickel, 4 molybdenum with nitrogen	0.030	1.50	0.035	0.020	0.80	5.5–8.0	24.0–26.0	3.0–5.0	N-0.20–0.35 Cu-0.50–3.00
F-60	S32205	22 chromium, 5.5 nickel, 3 molybdenum, modified with nitrogen 2205 [Ⓒ]	0.030	2.00	0.030	0.020	1.00	4.5–6.5	22.0–23.0	3.0–3.5	N-0.14–0.20
F-61	S32550	26 chromium, 6 nickel, 3.5 molybdenum with nitrogen and copper 255 [Ⓒ]	0.040	1.50	0.040	0.030	1.00	4.5–6.5	24.0–27.0	2.9–3.9	Cu-1.50–2.50 N-0.10–0.25
F-65	S32906	29 chromium, 6.5 nickel, 2 molybdenum with nitrogen	0.030	0.80–1.50	0.030	0.030	0.80	5.8–7.5	28.0–30.0	1.5–2.6	Cu-0.80 N-0.30–0.40
F-66	S32202	22 chromium, 2.0 nickel, 0.25 molybdenum with nitrogen	0.030	2.00	0.040	0.010	1.00	1.00–2.80	21.5–24.0	0.45	N-0.18–0.26
F-67	S32506	25 chromium, 6 nickel, 3 molybdenum, with nitrogen and tungsten	0.030	1.00	0.040	0.015	0.90	5.5–7.2	24.0–26.0	3.0–3.5	N-0.08–0.20 W-0.05–0.30
F-68	S32304	23 chromium, 4 nickel, with nitrogen	0.030	2.50	0.040	0.030	1.00	3.0–5.5	21.5–24.5	0.05–0.60	N-0.05–0.20 Cu-0.05–0.60



A182/A182M – 14b

TABLE 2 Continued

Identification Symbol	UNS Designation	Grade	Composition, %										
			Carbon	Manganese	Phosphorus	Sulfur	Silicon	Nickel	Chromium	Molybdenum	Columbium	Titanium	Other Elements
F74	S32808	27.5 chromium, 7.6 nickel, 1 molybdenum, 2.3 tungsten, with nitrogen	0.030	1.10	0.030	0.010	0.50	7.0–8.2	27.0–27.9	0.80–1.2	N 0.30–0.40 W 2.10–2.50

TABLE 2 Chemical Requirements^A

Grade/Identification Symbol	UNS Designation	Composition, %										
		Carbon	Manganese	Phosphorus	Sulfur	Silicon	Nickel	Chromium	Molybdenum	Columbium	Titanium	Other Elements
Low Alloy Steels												
F 1	K12822	0.28	0.60–0.90	0.045	0.045	0.15–0.35	0.44–0.65
F 2 ^B	K12122	0.05–0.21	0.30–0.80	0.040	0.040	0.10–0.60	...	0.50–0.81	0.44–0.65
F 5 ^C	K41545	0.15	0.30–0.60	0.030	0.030	0.50	0.50	4.0–6.0	0.44–0.65
F 5a ^C	K42544	0.25	0.60	0.040	0.030	0.50	0.50	4.0–6.0	0.44–0.65
F 9	K90941	0.15	0.30–0.60	0.030	0.030	0.50–1.00	...	8.0–10.0	0.90–1.10
F 10	S33100	0.10–0.20	0.50–0.80	0.040	0.030	1.00–1.40	19.0–22.0	7.0–9.0
F 91	K90901	0.08–0.12	0.30–0.60	0.020	0.010	0.20–0.50	0.40	8.0–9.5	0.85–1.05	0.06–0.10	...	N 0.03–0.07 Al 0.02 ^D V 0.18–0.25 Ti 0.01 ^D Zr 0.01 ^D
F 92	K92460	0.07–0.13	0.30–0.60	0.020	0.010	0.50	0.40	8.50–9.50	0.30–0.60	0.04–0.09	...	V 0.15–0.25 N 0.030–0.070 Al 0.02 ^D W 1.50–2.00 B 0.001–0.006 Ti 0.01 ^D Zr 0.01 ^D
F 122	K91271	0.07–0.14	0.70	0.020	0.010	0.50	0.50	10.00–11.50	0.25–0.60	0.04–0.10	...	V 0.15–0.30 B 0.005 N 0.040–0.100 Al 0.02 ^D Cu 0.30–1.70 W 1.50–2.50 Ti 0.01 ^D Zr 0.01 ^D
F 911	K91061	0.09–0.13	0.30–0.60	0.020	0.010	0.10–0.50	0.40	8.5–9.5	0.90–1.10	0.060–0.10	...	W 0.90–1.10 Al 0.02 ^D N 0.04–0.09 V 0.18–0.25 B 0.0003–0.0006 Ti 0.01 ^D Zr 0.01 ^D
F 11 Class 1	K11597	0.05–0.15	0.30–0.60	0.030	0.030	0.50–1.00	...	1.00–1.50	0.44–0.65
F 11 Class 2	K11572	0.10–0.20	0.30–0.80	0.040	0.040	0.50–1.00	...	1.00–1.50	0.44–0.65
F 11 Class 3	K11572	0.10–0.20	0.30–0.80	0.040	0.040	0.50–1.00	...	1.00–1.50	0.44–0.65
F 12 Class 1	K11562	0.05–0.15	0.30–0.60	0.045	0.045	0.50 max	...	0.80–1.25	0.44–0.65
F 12 Class 2	K11564	0.10–0.20	0.30–0.80	0.040	0.040	0.10–0.60	...	0.80–1.25	0.44–0.65
F 21	K31545	0.05–0.15	0.30–0.60	0.040	0.040	0.50 max	...	2.7–3.3	0.80–1.06
F 3V	K31830	0.05–0.18	0.30–0.60	0.020	0.020	0.10	...	2.8–3.2	0.90–1.10	...	0.015–0.035	V 0.20–0.30 B 0.001–0.003
F 3VCb	K31390	0.10–0.15	0.30–0.60	0.020	0.010	0.10	0.25	2.7–3.3	0.90–1.10	0.015–0.070	0.015	V 0.20–0.30 Cu 0.25 Ca 0.0005–0.0150
F 22 Class 1	K21590	0.05–0.15	0.30–0.60	0.040	0.040	0.50	...	2.00–2.50	0.87–1.13
F 22 Class 3	K21590	0.05–0.15	0.30–0.60	0.040	0.040	0.50	...	2.00–2.50	0.87–1.13
F 22V	K31835	0.11–0.15	0.30–0.60	0.015	0.010	0.10	0.25	2.00–2.50	0.90–1.10	0.07	0.030	Cu 0.20 V 0.25–0.35 B 0.002 Ca 0.015 ^F

iTeh Standards
(<https://standards.itih.ai>)
Document Preview

ASTM A182/A182M-14b

<https://standards.itih.ai/catalog/standards/sist/c40c4de-95db-46d6-b33f-7b33c43938bb/astm-a182-a182m-14b>