



Designation: **G114–07** G114 – 14

Standard Practices for Evaluating the Age Resistance of Polymeric Materials Used in Oxygen Service¹

This standard is issued under the fixed designation G114; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 These practices describe ~~several~~ procedures that are used to determine the age resistance of plastic, thermosetting, ~~and elastomeric~~ elastomeric, and polymer matrix composite materials exposed to oxygen-containing media.

1.2 While these practices focus on evaluating the age resistance of polymeric materials in oxygen-containing media prior to ignition and combustion testing, they also have relevance for evaluating the age resistance of ~~metals~~ metals, and nonmetallic oils and greases.

1.3 These practices address both established procedures that have a foundation of experience and new procedures that have yet to be validated. The latter are included to promote research and later elaboration in this practice as methods of the former type.

1.4 The results of these practices may not give exact correlation with service performance since service conditions vary widely and may involve multiple ~~factors~~ factors such as those listed in subsection 5.8.

1.5 Three procedures are described for evaluating the age resistance of polymeric materials depending on application and information sought.

1.5.1 *Procedure A: Natural Aging*—This procedure is used to simulate the effect(s) of one or more service stressors on a material's oxygen resistance, and is suitable for evaluating materials that experience continuous or intermittent exposure to elevated temperature during service.

1.5.2 *Procedure B: Accelerated Aging Comparative Oxygen Resistance*—This procedure is suitable for evaluating materials that are used in ambient temperature service, or at a temperature that is otherwise lower than the aging temperature, and is useful for developing oxygen compatibility rankings on a laboratory comparison basis.

1.5.3 *Procedure C: Accelerated Aging Lifetime Prediction*—This procedure is used to determine the relationship between aging temperature and a fixed level of property change, thereby allowing predictions to be made about the effect of prolonged service on oxidative degradation.

1.6 The values stated in SI units are to be regarded as the standard, however, all numerical values must~~shall~~ also be cited in the systems in which they were actually measured.

1.7 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* Specific precautionary statements are given in Section 10.

2. Referenced Documents

2.1 ASTM Standards:²

[D395 Test Methods for Rubber Property—Compression Set](#)

[D412 Test Methods for Vulcanized Rubber and Thermoplastic Elastomers—Tension](#)

[D638 Test Method for Tensile Properties of Plastics](#)

[D1349 Practice for Rubber—Standard Conditions for Testing](#)

[D1708 Test Method for Tensile Properties of Plastics by Use of Microtensile Specimens](#)

[D2240 Test Method for Rubber Property—Durometer Hardness](#)

¹ These practices are under the jurisdiction of ASTM Committee G04 on Compatibility and Sensitivity of Materials in Oxygen Enriched Atmospheres and is the direct responsibility of Subcommittee G04.02 on Recommended Practices.

Current edition approved March 15, 2007; Oct. 1, 2014. Published June 2007; November 2014. Originally approved in 1993. Last previous edition approved in 2006; 2007 as G114–06; G114–07. DOI: 10.1520/G0114-07; 10.1520/G0114-14.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

- D2512 Test Method for Compatibility of Materials with Liquid Oxygen (Impact Sensitivity Threshold and Pass-Fail Techniques)
- D2863 Test Method for Measuring the Minimum Oxygen Concentration to Support Candle-Like Combustion of Plastics (Oxygen Index)
- D3039 Test Method for Tensile Properties of Polymer Matrix Composite Materials
- D3045 Practice for Heat Aging of Plastics Without Load
- D4809 Test Method for Heat of Combustion of Liquid Hydrocarbon Fuels by Bomb Calorimeter (Precision Method)
- D5510 Practice for Heat Aging of Oxidatively Degradable Plastics (Withdrawn 2010)³
- G63 Guide for Evaluating Nonmetallic Materials for Oxygen Service
- G72 Test Method for Autogenous Ignition Temperature of Liquids and Solids in a High-Pressure Oxygen-Enriched Environment
- G74 Test Method for Ignition Sensitivity of Nonmetallic Materials and Components by Gaseous Fluid Impact
- G86 Test Method for Determining Ignition Sensitivity of Materials to Mechanical Impact in Ambient Liquid Oxygen and Pressurized Liquid and Gaseous Oxygen Environments
- G125 Test Method for Measuring Liquid and Solid Material Fire Limits in Gaseous Oxidants
- G126 Terminology Relating to the Compatibility and Sensitivity of Materials in Oxygen Enriched Atmospheres
- 2.2 ~~Federal~~CGA Standard:
~~Federal Specification BB-0-925~~CGA G-4.3 Type I QVL E Oxygen, Technical, Gas and Liquid Commodity Specification for Oxygen³
- 2.3 Military Standard:
~~MIL-O-27210~~EMIL-PRF-27210 Amendment 1—Oxygen, Aviator's Breathing, Liquid and Gas⁴

3. Terminology

3.1 Definitions of Terms Specific to This Standard:

- 3.1.1 *aging*—see Terminology G126.
- 3.1.2 *accelerated aging*—a type of artificial aging whereby the effect of prolonged exposure during service is simulated by aging at elevated temperature.
- 3.1.3 *artificial aging*—see Terminology G126.
- 3.1.4 *oxidative degradation*—physical or mechanical property changes occurring as a result of exposure to oxygen-containing media.
- 3.1.5 *oxygen-containing media*—air media containing greater than 21 mole % oxygen, or oxygen-enriched media containing greater than 25 mole % oxygen.
- 3.1.6 *oxygen resistance*—resistance of a material to ignite spontaneously, propagate by sustained combustion, or undergo oxidative degradation.
- 3.1.7 *oxygen service*—applications involving the production, storage, transportation, distribution, or use of oxygen-containing media.
- 3.1.8 *natural aging*—see Terminology G126.
- 3.1.9 *physical aging*—aging that occurs during normal storage and which is a function of time after production, molding or curing.

4. Summary of Practice

4.1 These practices can be used to evaluate systematically the effect of natural aging (Procedure A) or accelerated aging (Procedures B and C) on oxygen resistance. To apply its principle, the user first characterizes the material, then subjects the material to an aging stressor or stressors, followed by re-characterizing the material. Caution must be taken in interpreting results because interactions occurring in service may be different than from those simulated during aging.

4.2 It is always more accurate, although not always practical, to determine the effect of natural aging (Procedure A) without resorting to accelerated aging (Procedures B and C). Accelerated aging procedures are more useful for determining material rankings (Procedure B) or for making lifetime predictions (Procedure C).

4.3 Summary of Practice for Evaluating the Effect of Aging in Incident Studies:

4.3.1 In incident studies, in which initial characterization data are not available, historical or average property data may be used to draw coarser conclusions about the effect of aging on oxygen resistance.

4.4 Practices for Natural Aging (Procedure A) and Accelerated Aging for Comparative Oxygen Resistance (Procedure B):

³ The last approved version of this historical standard is referenced on www.astm.org. Available from Compressed Gas Association (CGA), 4221 Walney Rd., 5th Floor, Chantilly, VA 20151-2923, <http://www.cganet.com>.

⁴ Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098, <http://www.dodssp.daps.mil> <http://www.dsp.dla.mil>.