



Designation: ~~D5638 – 05 (Reapproved 2010)~~ **D5638 – 14**

## Standard Test Method for Chemical Resistance of Electrical Insulating Varnishes<sup>1</sup>

This standard is issued under the fixed designation D5638; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. ~~Scope~~ Scope\*

- 1.1 This test method covers the mechanical performance of insulating varnishes after exposure to various chemicals.
- 1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.
- 1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use. See 7.1.*

NOTE 1—There is no IEC/ISO equivalent.

### 2. Referenced Documents

- 2.1 *ASTM Standards*:<sup>2</sup>  
[D2519 Test Method for Bond Strength of Electrical Insulating Varnishes by the Helical Coil Test](#)

### 3. Terminology

- 3.1 See Test Method [D2519](#).

### 4. Summary of Test Method

4.1 Flexural strength tests are made on varnish-treated helical coils to determine the force required to break the coil under specified conditions both before and after exposure to liquid chemicals.

### 5. Significance and Use

- 5.1 This test method is useful for the evaluation of insulating varnish performance in chemical exposure.

### 6. Apparatus

- 6.1 *Tensile Testing Machine*—See Test Method [D2519](#).
- 6.2 *Test Fixture*—See Test Method [D2519](#).
- 6.3 *Chemical Containers*—Sealable ~~1000-mL~~ 1000-mL containers of suitable material and design for containing the chemicals to be used.

### 7. Safety Precautions

7.1 It is unsafe to use varnish at temperatures above the flash point without adequate ventilation, especially if the possibility exists that flames or sparks are present. Store varnish in sealed containers.

### 8. Test Specimen

8.1 Prepare a minimum of five test specimens for each chemical solution to be tested and a minimum of five to determine unconditioned bond strength in accordance with Test Method [D2519](#) using a wire mutually agreed upon by supplier and user.

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee [D09](#) on Electrical and Electronic Insulating Materials and is the direct responsibility of Subcommittee [D09.01](#) on Electrical Insulating Varnishes, Powders and Encapsulating Compounds.

Current edition approved ~~May 1, 2010~~ Nov. 1, 2014. Published ~~September 2010~~ November 2014. Originally approved in 1994. Last previous edition approved in ~~2005-2010~~ as ~~D5638~~ D5638 – 05 (2010), ~~05~~. DOI: ~~10.1520/D5638-05R10~~ 10.1520/D5638-14.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

\*A Summary of Changes section appears at the end of this standard