



Designation: **D1731 – 09 D1731 – 09 (Reapproved 2014)**

Standard Practices for Preparation of Hot-Dip Aluminum Surfaces for Painting¹

This standard is issued under the fixed designation D1731; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 These practices describe procedures for the preparation of hot-dip aluminum surfaces for painting.

1.2 *This standard may involve hazardous materials, operations, and equipment. This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[D609 Practice for Preparation of Cold-Rolled Steel Panels for Testing Paint, Varnish, Conversion Coatings, and Related Coating Products](#)

2.2 *Military Standards:*³

[MIL-DTL-5541 Chemical Conversion Coatings on Aluminum and Aluminum Alloys](#)

[MIL-C-15328 Specification for Acid Wash Primers](#)

[MIL-M-10578B Metal Conditioner and Rust Remover \(Phosphoric Acid Type\)](#)

3. Types of Surface Preparations

3.1 Two types of surface preparations are covered as follows:

3.1.1 Solvent Cleaning, and

3.1.2 Chemical Treatments.

3.2 These two types cover several methods as described in Section 5. Variations in surface treatment produce end conditions which differ and which do not necessarily yield identical results when paints are applied. Service conditions will dictate the type of surface preparation that should be selected.

4. Solvent Cleaning

4.1 The surfaces may be prepared for painting by any of the methods for solvent cleaning described in 4.2 and 4.3.

4.2 *Method 1*—Manual swabbing or dip washing with a solvent such as mineral spirits or high flask solvent naphtha. It is extremely difficult to produce a clean metal surface by this method. Accumulated contaminants in the solvent or on the swab are frequently redeposited on the surface being prepared.

4.3 *Method 2*—Solvent spray cleaning in accordance with Method A, Procedure 1 of Practice [D609](#).

4.4 *Method 3*—Vapor degreasing in special equipment in accordance with the latest revision of Method A, Procedure 2 of Practice [D609](#), employing trichlorethylene or perchlorethylene vapor. Solvent cleaning does not disturb the natural oxide film on the metal and may prove adequate for some applications.

5. Chemical Treatment

5.1 The surfaces may be prepared for painting by any of the methods for chemical treatment ([Note 1](#)) described in 5.2 to 5.9:

NOTE 1—Materials and procedures employed in these methods of treatment are available from a number of sources as proprietary compounds or

¹ These practices are under the jurisdiction of ASTM Committee B08 on Metallic and Inorganic Coatings and is the direct responsibility of Subcommittee B08.07 on Conversion Coatings.

Current edition approved April 15, 2009; Nov. 1, 2014. Published May 2009; November 2014. Originally approved in 1960. Last previous edition approved in 2003; 2009 as [D1731 – 03; D1731 – 09](#). DOI: [10.1520/D1731-09](#); [10.1520/D1731-09R14](#).

² For referenced ASTM standards, visit the ASTM website, [www.astm.org](#), or contact ASTM Customer Service at [service@astm.org](#). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098