



Standard Specification for Structural Bolts, Alloy Steel, Heat Treated, 150 ksi Minimum Tensile Strength¹

This standard is issued under the fixed designation A490; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This specification covers two types of quenched and tempered, alloy steel, heavy hex structural bolts having a tensile strength of 150 to 173 ksi.

1.2 These bolts are intended for use in structural connections. These connections are covered under the requirements of the Specification for Structural Joints Using Specification **A325** or **A490** bolts, approved by the Research Council on Structural Connections; endorsed by the American Institute of Steel Construction and by the Industrial Fastener Institute.²

1.3 The bolts are furnished in sizes $\frac{1}{2}$ to $1\frac{1}{2}$ in., inclusive. They are designated by type denoting chemical composition as follows:

Type	Description
Type 1	Medium carbon alloy steel
Type 2	Withdrawn in 2002
Type 3	Weathering steel

1.4 This specification provides that heavy hex structural bolts shall be furnished unless other dimensional requirements are specified on the purchase order.

1.5 Terms used in this specification are defined in Terminology **F1789** unless otherwise defined herein.

1.6 For metric bolts, see Specification **A490M** Classes 10.9 and 10.9.3

1.7 The values stated in inch-pound units are to be regarded as standard. No other units of measurement are included in this standard.

1.8 The following safety hazards caveat pertains only to the Test Methods portion, Section **12** of this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*³

A194/A194M Specification for Carbon and Alloy Steel Nuts for Bolts for High Pressure or High Temperature Service, or Both

A325 Specification for Structural Bolts, Steel, Heat Treated, 120/105 ksi Minimum Tensile Strength

A354 Specification for Quenched and Tempered Alloy Steel Bolts, Studs, and Other Externally Threaded Fasteners

A490M Specification for High-Strength Steel Bolts, Classes 10.9 and 10.9.3, for Structural Steel Joints (Metric)

A563 Specification for Carbon and Alloy Steel Nuts

A751 Test Methods, Practices, and Terminology for Chemical Analysis of Steel Products

¹ This specification is under the jurisdiction of ASTM Committee **F16** on Fasteners and is the direct responsibility of Subcommittee **F16.02** on Steel Bolts, Nuts, Rivets and Washers.

Current edition approved April 1, 2012; August 1, 2014. Published April 2012; December 2014. Originally approved in 1964. Last previous edition approved in 2011 as **A490 – 11; A490 – 12**. DOI: 10.1520/A0490-12.10.1520/A0490-14.

² Available from American Institute of Steel Construction (AISC), One E. Wacker Dr., Suite 700, Chicago, IL 60601-2001, <http://www.aisc.org>.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard

- D3951 Practice for Commercial Packaging
- E384 Test Method for Knoop and Vickers Hardness of Materials
- E709 Guide for Magnetic Particle Testing
- E1444 Practice for Magnetic Particle Testing
- F436 Specification for Hardened Steel Washers
- F606 Test Methods for Determining the Mechanical Properties of Externally and Internally Threaded Fasteners, Washers, Direct Tension Indicators, and Rivets
- F788/F788M Specification for Surface Discontinuities of Bolts, Screws, and Studs, Inch and Metric Series
- F959 Specification for Compressible-Washer-Type Direct Tension Indicators for Use with Structural Fasteners
- F1136 Specification for Zinc/Aluminum Corrosion Protective Coatings for Fasteners
- F1470 Practice for Fastener Sampling for Specified Mechanical Properties and Performance Inspection
- F1789 Terminology for F16 Mechanical Fasteners
- F2328 Test Method for Determining Decarburization and Carburization in Hardened and Tempered Threaded Steel Bolts, Screws, Studs, and Nuts
- F2833 Specification for Corrosion Protective Fastener Coatings with Zinc Rich Base Coat and Aluminum Organic/Inorganic Type
- G101 Guide for Estimating the Atmospheric Corrosion Resistance of Low-Alloy Steels
- 2.2 *ASME Standards*:⁴
 - B1.1 Unified Screw Threads
 - B18.2.6 Fasteners for Use in Structural Applications
 - B18.24 Part Identification Number (PIN) Code System Standard for B18 Fastener Products
- 2.3 *IFI Standard*:⁵
 - IFI 144 Test Evaluation Procedures for Coating Qualification Intended for Use on High-Strength Bolts

3. Ordering Information

- 3.1 Orders for heavy hex structural bolts under this specification shall include the following:
 - 3.1.1 Quantity (number of pieces of bolts and accessories);
 - 3.1.2 Size, including nominal bolt diameter, thread pitch, and bolt length. The thread length shall not be changed;
 - 3.1.3 Name of product: heavy hex structural bolts, or other such bolts as specified;
 - 3.1.4 Type of bolt (Type 1 or 3). When type is not specified, either Type 1 or Type 3 shall be furnished at the supplier's option;
 - 3.1.5 ASTM designation and year of issue,
 - 3.1.6 Other components such as nuts, washers, and washer-type direct tension indicators, if required;
 - 3.1.7 Test Reports, if required (see Section 15); and
 - 3.1.8 Protective coating per Specification F1136, Grade 3, if required. See 4.3.
 - 3.1.9 Protective coating per Specification F2833, Grade 1, if required. See 4.3.
 - 3.1.10 Special requirements.
 - 3.1.11 For establishment of a part identifying system, see ASME B18.24.

NOTE 1—A typical ordering description follows: 1000 pieces 1–8 in. dia × 4 in. long heavy hex structural bolt, Type 1, ASTM A490 – 02; each with two hardened washers, ASTM F436 Type 1; and one heavy hex nut, ASTM A563 Grade DH.

3.2 Recommended Nuts:

3.2.1 Nuts conforming to the requirements of Specification A563 are the recommended nuts for use with Specification A490 heavy hex structural bolts. The nuts shall be of the class and have a surface finish for each type of bolt as follows:

Bolt Type and Finish	Nut Class and Finish
1, plain (uncoated)	A563—DH, DH3 plain (uncoated)
1, coated in accordance with Specification F1136, Grade 3 or Specification F2833, Grade 1.	A563—coated in accordance with Specification F1136, Grade 5 or Specification F2833, Grade 1.
3, weathering steel	A563—DH3, weathering steel

3.2.2 Alternatively, nuts conforming to Specification A194/A194M Gr. 2H plain (uncoated) are considered a suitable substitute for use with Specification A490 Type 1 heavy hex structural bolts.

3.3 *Recommended Washers*—Washers conforming to Specification F436 are the recommended washers for use with Specification A490 heavy hex structural bolts. The washers shall have a surface finish for each type of bolt as follows:

⁴ Available from American Society of Mechanical Engineers (ASME), ASME International Headquarters, Three Park Ave., New York, NY 10016-5990, <http://www.asme.org>.

⁵ Available from Industrial Fastener Institute, (IFI), 6363 Oak Tree Boulevard, Independence, OH 44131. <http://www.industrial-fasteners.org>.

Bolt Type and Finish	Washer Finish
1, plain (uncoated)	plain (uncoated)
1, coated in accordance with F1136 , Grade 3 or F2833 , Grade 1.	plain, coated in accordance with F1136 , Grade 3 or F2833 , Grade 1.
3, weathering steel	weathering steel

3.4 *Other Accessories*—When compressible washer type direct tension indicators are specified to be used with these bolts, they shall conform to Specification **F959** Type 490.

4. Materials and Manufacture

4.1 *Heat Treatment*—Type 1 and Type 3 bolts shall be heat treated by quenching in oil from the austenitic temperature and then tempered by reheating to a temperature of not less than 800°F.

4.2 *Threading*—The threads shall be cut or rolled.

4.3 *Protective Coatings:*

4.3.1 When a protective coating is required and specified, the bolts shall be coated with Zinc/Aluminum Corrosion Protective Coatings in accordance with Specification **F1136**, Grade 3-3, both chromium and non-chromium versions, or Specification **F2833**, Grade 1. These coatings have been qualified based on the findings of an investigation founded on IFI 144.⁶

4.3.2 No other metallic coatings are permitted unless authorized by Committee F16. Future consideration of any coating will be based on results of testing performed in accordance with the procedures in IFI 144, and submitted to Committee F16 for review (See note 2).

NOTE 2—For more detail see the H. E. Townsend Report “Effects of Zinc Coatings on Stress Corrosion Cracking and Hydrogen Embrittlement of Low Alloy Steel,” published in Metallurgical Transactions, Vol. 6, April 1975.

5. Chemical Composition

5.1 Type 1 bolts shall be alloy steel conforming to the chemical composition specified in **Table 1**. The steel shall contain sufficient alloying elements to qualify it as an alloy steel (see **Table 1**, footnote A.).

⁶ Supporting data have been filed at ASTM International Headquarters and may be obtained by requesting Research Report Reports RR:F16-1001, RR:F16-1002, and RR:F16-1003.

TABLE 1 Chemical Requirements for Type 1 Bolts

Alloy Steel		
Element	Heat Analysis, %	Product Analysis, %
Carbon		
For sizes through 1 $\frac{1}{8}$ in.	0.30–0.48	0.28–0.50
For size 1 $\frac{1}{2}$ in.	0.35–0.53	0.33–0.55
Phosphorus, max	0.040	0.045
Manganese, min	0.60	0.57
Sulfur, max	0.040	0.045
Alloying Elements	A	A
Alloy Steel with Boron Addition		
Element	Heat Analysis, %	Product Analysis, %
Carbon		
For sizes through 1 $\frac{1}{8}$ in.	0.30–0.48	0.28–0.50
For size 1 $\frac{1}{2}$ in.	0.35–0.53	0.33–0.55
Manganese, min	0.60	0.57
Phosphorus, max	0.040	0.045
Sulfur, max	0.040	0.045
Boron	0.0005–0.003	0.0005–0.003
Alloying Elements	A	A

^ASteel, as defined by the American Iron and Steel Institute, shall be considered to be alloy when the maximum of the range given for the content of alloying elements exceeds one or more of the following limits: Manganese, 1.65 %; silicon, 0.60 %; copper, 0.60 % or in which a definite range or a definite minimum quantity of any of the following elements is specified or required within the limits of the recognized field of constructional alloy steels: aluminum, chromium up to 3.99 %, cobalt, columbium, molybdenum, nickel, titanium, tungsten, vanadium, zirconium, or any other alloying elements added to obtain a desired alloying effect.

5.2 Type 3 bolts shall be weathering steel conforming to the chemical composition requirements in **Table 2**. See Guide **G101** for methods of estimating the atmospheric corrosion resistance of low alloy steel.

5.3 Product analyses made on finished bolts representing each lot shall conform to the product analysis requirements specified in **Tables 1 and 2**, as applicable.

5.4 Heats of steel to which bismuth, selenium, tellurium, or lead has been intentionally added shall not be used for bolts furnished to this specification. Compliance with this requirement shall be based on certification that steels having these elements intentionally added were not used.

5.5 Chemical analyses shall be performed in accordance with Test Methods, Practices, and Terminology **A751**.

6. Mechanical Properties

6.1 *Hardness*—The bolts shall conform to the hardness specified in **Table 3**.

6.2 *Tensile Properties*:

6.2.1 Except as permitted in **6.2.1.1** for long bolts and **6.2.1.2** for short bolts, sizes 1.00 in. and smaller having a nominal length of $2\frac{1}{4}D$ and longer and sizes larger than 1.00 in. having a nominal length of $3D$ and longer shall be wedge tested full size and shall conform to the minimum and maximum wedge tensile load, and proof load or alternative proof load specified in **Table 4**. The load achieved during proof load testing shall be equal to or greater than the specified proof load.

6.2.1.1 When the length of the bolt makes full-size testing impractical, machined specimens shall be tested and shall conform to the requirements specified in **Table 5**. When bolts are tested by both full-size and machined specimen methods, the full-size test shall take precedence.

6.2.1.2 Sizes 1.00 in. and smaller having a nominal length shorter than $2\frac{1}{4}D$ down to $2D$, inclusive, that cannot be wedge tensile tested shall be axially tension tested full size and shall conform to the minimum tensile load and proof load or alternate proof load specified in **Table 4**. Sizes 1.00 in. and smaller having a nominal length shorter than $2D$ and sizes larger than 1.00 in. with nominal lengths shorter than $3D$ that cannot be axially tensile tested shall be qualified on the basis of hardness.

6.2.2 For bolts on which hardness and tension tests are performed, acceptance based on tensile requirements shall take precedence in the event of low hardness readings.

7. Carburization/Decarburization

7.1 This test is intended to evaluate the presence or absence of carburization and decarburization as determined by the difference in microhardness near the surface and core.

7.2 *Requirements*:

7.2.1 *Carburization*—The bolts shall show no evidence of a carburized surface when evaluated in accordance with **12.2**.

7.2.2 *Decarburization*—Hardness value differences shall not exceed the requirements set forth for decarburization in Test Method **F2328** materials when evaluated in accordance with **12.2**.

8. Dimensions

8.1 *Head and Body*:

8.1.1 Unless otherwise specified, bolts shall conform to the dimensions for heavy hex structural bolts specified in ASME B18.2.6.

8.1.2 The thread length shall not be changed from that specified in ASME B18.2.6 for heavy hex structural bolts. Bolts requiring thread lengths other than those required by this specification shall be ordered under Specification **A354 Gr. BD**.

8.2 *Threads*—Threads shall be the Unified Coarse Thread Series as specified in ASME B1.1 and shall have Class 2A tolerances.

9. Workmanship

9.1 The allowable limits, inspection, and evaluation of the surface discontinuities, quench cracks, forging cracks, head bursts, shear bursts, seams, folds, thread laps, voids, tool marks, nicks, and gouges shall be in accordance with Specification **F788/F788M**.

TABLE 2 Chemical Requirements for Type 3 Bolts

Element	Heat Analysis, %	Product Analysis, %
Carbon		
Sizes 0.75 in. and smaller	0.20–0.53	0.19–0.55
Sizes larger than 0.75 in.	0.30–0.53	0.28–0.55
Manganese, min	0.40	0.37
Phosphorus, max	0.035	0.040
Sulfur, max	0.040	0.045
Copper	0.20–0.60	0.17–0.63
Chromium, min	0.45	0.42
Nickel, min	0.20	0.17
or		
Molybdenum, min	0.15	0.14