



Designation: **D3493—13 D3493 – 14**

## Standard Test Method for Carbon Black—Oil Absorption Number of Compressed Sample (COAN)<sup>1</sup>

This standard is issued under the fixed designation D3493; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This test method covers the procedure for the mechanical compression of a carbon black sample and the determination of the oil absorption number of the compressed sample.

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

### 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

[D1765 Classification System for Carbon Blacks Used in Rubber Products](#)

[D1799 Practice for Carbon Black—Sampling Packaged Shipments](#)

[D1900 Practice for Carbon Black—Sampling Bulk Shipments](#)

[D2414 Test Method for Carbon Black—Oil Absorption Number \(OAN\)](#)

[D4821 Guide for Carbon Black—Validation of Test Method Precision and Bias](#)

[D4483 Practice for Evaluating Precision for Test Method Standards in the Rubber and Carbon Black Manufacturing Industries](#)

### 3. Summary of Test Method

3.1 A sample of carbon black is compressed four times in a compression cylinder at a pressure of 165 MPa (24 000 psi) and then tested in an absorptometer to determine the oil absorption number.

3.2 *n*-Dibutyl phthalate, paraffin, or EFA oil is added by means of a constant-rate buret to the compressed sample of carbon black in the mixer chamber of an absorptometer. As the sample absorbs the oil, the mixture changes from a free-flowing state to one of a semiplastic agglomeration, with an accompanying increase in viscosity. This increased viscosity is transmitted to the torque-sensing system of the absorptometer. When the viscosity of the mixture reaches a predetermined torque level, the absorptometer and buret will simultaneously shut off. The volume of oil added is read from the direct reading buret. The volume of oil per unit mass of carbon black is the oil absorption number. Either DBP, paraffin, or EFA oil is acceptable for use with many standard pelleted grades of N-series carbon blacks found in Classification [D1765](#). COAN testing using paraffin or EFA oil on some specialty blacks and powder blacks may result in significant differences when compared to COAN testing using DBP oil. Referee testing between suppliers and users should use DBP oil until such time that precision data is available for paraffin and EFA oils.

### 4. Significance and Use

4.1 The oil absorption number of a carbon black is related to the processing and vulcanizate properties of rubber compounds containing the carbon black.

4.2 The difference between the regular oil absorption number and the oil absorption number of compressed sample is some measure of the stability of the structure of the carbon black.

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee [D24](#) on Carbon Black and is the direct responsibility of Subcommittee [D24.11](#) on Carbon Black Structure. Current edition approved July 1, 2013; July 1, 2014. Published August 2013; December 2014. Originally approved in 1976. Last previous edition approved in 2009 as [D3493 – 09](#); [D3493 – 13](#). DOI: [10.1520/D3493-13](#); [10.1520/D3493-14](#).

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](#), or contact ASTM Customer Service at [service@astm.org](#). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

## 5. Apparatus<sup>3</sup>

- 5.1 *Balance*, analytical, 0.01-g sensitivity.
- 5.2 *Oven*, gravity-convection type, capable of maintaining 125°C ± 5°C.
- 5.3 *Carbon Black Press*, capable of compressing a 25-g sample to 165 MPa (24 000 psi).<sup>4</sup>
- 5.4 *Absorptometer*,<sup>5</sup> equipped with a constant-rate buret that delivers 67 ± 0.4 mm<sup>3</sup>/s (4 ± 0.024 cm<sup>3</sup>/min).
- 5.5 *Spatula*, rubber, 100 mm.
- 5.6 *Sieve*, 850 µm (U.S. No. 20), approximately 125-mm (5-in.) diameter with receiver pan.
- 5.7 *Brush*, approximately 40 mm (1.5 in.), stiff bristle.
- 5.8 *Desiccator*.

## 6. Reagent and Standards

6.1 *Purity of Reagents*—Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents shall conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society, where such specifications are available.<sup>6</sup> Other grades may be used, provided it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

6.2 *n-Dibutyl Phthalate*, having a density of 1.042 to 1.047 mg/m<sup>3</sup> at 25°C and a relative density of 1.045 to 1.050 at 25°C.

6.3 *Paraffin Oil*, having a kinematic viscosity of 10 to 34 mm<sup>2</sup>/s (cSt) at 40°C.<sup>7</sup>

6.4 *Epoxidized Fatty Acid Ester (EFA)*, meeting the specifications listed in Test Method **D2414**, Table 1. It is recommended to store the product at temperatures between 7 and 30°C. If stored in sealed original containers, the product is stable for at least 12 months. For handling and safety, please refer to safety data sheet.

6.5 *ASTM D24 Standard Reference Blacks, SRB*.<sup>8</sup>

## 7. Sampling

7.1 Samples shall be taken in accordance with Practices **D1799** and **D1900**.

## 8. Calibration and Standardization

8.1 See Test Method **D2414**.

NOTE 1—If values are not obtained within the acceptable range, it will be necessary to either vary the pressure of the hydraulic press until acceptable values are obtained or follow Guide **D4821**.

## 9. Procedure

9.1 Dry an adequate sample for 1 h in a specified oven set at 125°C. Cool the sample in a desiccator for a minimum of 30 min prior to testing.

9.2 Weigh a sample mass of either 25, 30, or 45 g depending on the sample mass requirement for oil absorption per Test Method **D2414**. The desired sample mass to be compressed will weigh 5 ± 0.1 g greater than the mass specified in subsection 9.2 of Test Method **D2414**.

9.3 Compress the sample using either the ~~Chandler~~ Chandler, Titan, or Titan ~~ISTCO~~ ISTCO press.

<sup>3</sup> Each apparatus is to be operated and maintained in accordance with the manufacturer's directions for optimum performance.

<sup>4</sup> ~~The sole source of supply of carbon black presses known to the committee at this time is Titan Specialties, Inc., P.O. Box 2316, Pampa, TX 79066-2316. carbon black press is available from two suppliers: Jaron Technologies, LLC, 2338 Duncan St., Pampa, TX 79065, <http://jarontech.com/>. ISTCO Engineering Works, K-1, 884/10 & 885/A, GIDC Industrial Estate, Makarpura, Vadodara-390010, Gujarat, India, <http://www.indiamart.com/istcoengineering/hydraulic-testingmachine.html>. If you are aware of alternative suppliers, please provide this information to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,<sup>1</sup> which you may attend.~~

<sup>5</sup> Available from C. W. Brabender Instruments, Inc., 50 E. Wesley St., South Hackensack, NJ 07606 and from HITEC Luxembourg, 5 Rue de l'Eglise, L-1458, Luxembourg. The sole source of supply of the apparatus known to the committee at this time is listed above. If you are aware of alternative suppliers, please provide this information to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,<sup>1</sup> which you may attend.

<sup>6</sup> *Reagent Chemicals, American Chemical Society Specifications*, American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see *Analar Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeia and National Formulary*, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD.

<sup>7</sup> The sole source of supply of paraffin oil (Marcol 82, which has been demonstrated to provide comparable results to DBP oil) known to the committee at this time is Exxon. If you are aware of alternative suppliers, please provide this information to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,<sup>1</sup> which you may attend.

<sup>8</sup> The sole source of supply of the ASTM standard reference blacks known to the committee at this time is Laboratory Standards and Technologies, 227 Somerset, Borger, TX 79007, <http://www.carbonstandard.com/>. If you are aware of alternative suppliers, please provide this information to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,<sup>1</sup> which you may attend.