



## Designation: **F1913–04 (Reapproved 2010) F1913 – 04 (Reapproved 2014)**

# Standard Specification for Vinyl Sheet Floor Covering Without Backing<sup>1</sup>

This standard is issued under the fixed designation F1913; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This specification covers sheet floor covering having a vinyl wear layer without backing. Products also may contain a clear specialty performance top layer(s).

1.2 This type of floor covering is intended for use in commercial and light commercial buildings. General information and performance characteristics, which determine serviceability and recommended use, are included in this specification.

1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

### 2.1 ASTM Standards:<sup>2</sup>

[F137 Test Method for Flexibility of Resilient Flooring Materials with Cylindrical Mandrel Apparatus](#)

[F141 Terminology Relating to Resilient Floor Coverings](#)

[F386 Test Method for Thickness of Resilient Flooring Materials Having Flat Surfaces](#)

[F410 Test Method for Wear Layer Thickness of Resilient Floor Coverings by Optical Measurement](#)

[F925 Test Method for Resistance to Chemicals of Resilient Flooring](#)

[F970 Test Method for Static Load Limit](#)

[F1514 Test Method for Measuring Heat Stability of Resilient Flooring by Color Change](#)

[F1515 Test Method for Measuring Light Stability of Resilient Flooring by Color Change](#)

[F1914 Test Methods for Short-Term Indentation and Residual Indentation of Resilient Floor Covering](#)

### 2.2 ANSI/ASQC Standard:

[ANS/ASQC Z1.4 Sampling Procedures and Tables for Inspection by Attributes](#)<sup>3</sup>

## 3. Terminology

3.1 *Definitions*— Terms used in this specification are defined in accordance with Terminology [F141](#).

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *wear layer, n*—the portion of a resilient floor covering that contains the pattern effect.

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee [F06](#) on Resilient Floor Coverings and is the direct responsibility of Subcommittee [F06.80](#) on Specifications.

Current edition approved ~~May 1, 2010~~ Nov. 1, 2014. Published ~~May 2010~~ December 2014. Originally approved in 1998. Last previous edition approved in ~~2004~~ 2010 as F1913 - 04:04(2010). DOI: ~~10.1520/F1913-04R10~~ 10.1520/F1913-04R14.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

### 3.2.1.1 Discussion—

The wear layer thickness and total thickness of through pattern unbacked sheet vinyl flooring are the same. A clear specialty performance top layer may be used to enhance specific properties and to protect the pattern effect and shall be counted as part of the wear layer. The wear layer does not include temporary finishes or maintenance coatings.



4. Significance and Use

4.1 The information in this specification is for use by specifiers as a reference when selecting unbacked resilient sheet vinyl flooring for areas within commercial and light commercial buildings.

5. Classification

5.1 Sheet Vinyl floor covering shall conform to the following.

5.1.1 The binder content of the PVC-pattern portion of the wear layer (vinyl resins, plasticizers, and stabilizers) shall be a minimum of 50 %. A clear specialty performance layer(s) used as the top layer is not described by binder limits.

PVC Binder Content  
Minimum %  
50 %

PVC Wear Layer Description  
The material shall be a vinyl compound consisting of a blended composition of pigments stabilized against heat and light deterioration. The design, color and pattern extends throughout the thickness of the wear layer.

PVC Binder Content  
Minimum %  
50 %

PVC Wear Layer Description  
The material shall be a vinyl compound consisting of a blended composition of pigments stabilized against heat and light deterioration. The design, color and pattern extends throughout the thickness of the wear layer.

5.1.1.1 All flooring may have a clear specialty performance top layer(s) with an average minimum total thickness of 0.0004 in. The specialty performance top layer(s) may consist of a single layer or multiple layers, which do not delaminate under normal use. Top layer(s) thinner than 0.0004 in. may be used but cannot be counted as part of the clear specialty performance top layer.

5.1.2 The total thickness is the sum of the PVC wear layer and the clear specialty top layer(s). The total thickness average minimum is 0.075 in. (1.9 mm).

6. Ordering Information

6.1 Sheet vinyl floor covering without backing shall be ordered according to characteristics important to the purchaser for the intended use as indicated by Table 1.

6.2 Intended Use— The following is a partial list providing generic guidance on typical applications of product use. For specific applications, refer to the manufacturers product recommendations.

6.2.1 LC (Light Commercial):

6.2.1.1 Multi-family Dwelling—Common Areas.

6.2.1.2 Hotel/Motel Guest Rooms.

6.2.2 C (Commercial):

6.2.2.1 Educational/Institutional.

6.2.2.2 Hospital/Health Care.

6.2.2.3 Retail/Mercantile.

6.2.2.4 Office

6.2.2.5 Hospitality.

6.3 The purchaser may wish to specify the following items:

6.3.1 Manufacturer,

6.3.2 Style name and number,

6.3.3 Minimum roll width (see 9.1),

6.3.4 Surface texture (see 7.1.3), and

6.3.5 Variation in list of chemicals used to demonstrate chemical resistance (see 12.7).

7. Material

7.1 Wear Layer:

TABLE 1 Total Thickness

Average Minimum in. (mm)	Intended Use
0.075 (1.9)	LC/G

TABLE 1 Total Thickness

Average Minimum in. (mm)	Intended Use
0.075 (1.9)	LC/C