



Designation: **C1777—13** **C1777 – 14**

Standard Test Method for Rapid Determination of the Methylene Blue Value for Fine Aggregate or Mineral Filler Using a Colorimeter¹

This standard is issued under the fixed designation C1777; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method provides a rapid test to determine the amount of methylene blue adsorbed by a specimen of fine aggregate or mineral filler and can be used both in the laboratory and in the field.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[C125 Terminology Relating to Concrete and Concrete Aggregates](#)

[C702 Practice for Reducing Samples of Aggregate to Testing Size](#)

[D75 Practice for Sampling Aggregates](#)

[E11 Specification for Woven Wire Test Sieve Cloth and Test Sieves](#)

2.2 *Other Standards:*

[AASHTO T330 Standard Method of Test for the Qualitative Detection of Harmful Clays of the Smectite Group in Aggregates Using Methylene Blue](#)³

[EN 933-9 Tests for geometrical properties of aggregates. Part 9: Assessment of fines – Methylene blue test](#)⁴

3. Terminology

3.1 *Definitions:*

3.1.1 For definitions of terms used in this standard, refer to Terminology [C125](#).

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *mineral filler, n*—a finely divided mineral product at least 65 % of which passes the 75- μ m sieve.

4. Summary of Test Method

4.1 A specimen of fine aggregate or mineral filler is combined with a methylene blue solution of known concentration and mixed for a prescribed period of time. The specimen adsorbs some of the methylene blue from solution. The resulting mixture is filtered and a portion of the filtered solution is diluted by a fixed amount. A colorimeter is used to determine the absorbance of the diluted solution, from which the concentration of methylene blue prior to dilution is calculated. The change in concentration of methylene blue before and after mixing with fine aggregate or mineral filler is converted to a methylene blue value and reported in units of mg/g.

¹ This test method is under the jurisdiction of ASTM Committee [C09](#) on Concrete and Concrete Aggregates and is the direct responsibility of Subcommittee [C09.20](#) on Normal Weight Aggregates.

Current edition approved Nov. 1, 2013/Dec. 15, 2014. Published November 2013/January 2015. Originally approved in 2013. Last previous edition approved in 2013 as C1777-13. DOI: [10.1520/C1777-13](#). [10.1520/C1777-14](#).

² For referenced ASTM standards, visit the ASTM website, [www.astm.org](#), or contact ASTM Customer Service at [service@astm.org](#). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from American Association of State Highway and Transportation Officials (AASHTO), 444 N. Capitol St., NW, Suite 249, Washington, DC 20001, [http://www.transportation.org](#).

⁴ Available from European Committee for Standardization, Avenue Marnix 17, B-1000 Brussels, Belgium.

5. Significance and Use

5.1 This test method is used to determine rapidly the amount of methylene blue adsorbed by a specimen of fine aggregate or mineral filler. The result is reported as a methylene blue value in units of mg of methylene blue adsorbed per g of fine aggregate or mineral filler. The methylene blue value is a function of the amount and characteristics of clay minerals present in the test specimen. High methylene blue values indicate increased potential for diminished fine aggregate or mineral filler performance in a cementitious mixture due to the presence of clays.

NOTE 1—Results from this test method are not expected to be correlated with those obtained using AASHTO T 330 or EN 933-9. These three test methods are likely to give very different numerical values even though the units are the same. The AASHTO T 330 test is performed only on the fraction of an aggregate passing the 75 μm sieve, the EN 933-9 test is performed only on the fraction finer than 2 mm, and this test is performed on the fraction finer than the 4.75 mm sieve. Therefore, when testing the same fine aggregate source, the AASHTO test method would give the highest methylene blue value because any clay present in the specimen would be concentrated in the fraction finer than the 75 μm sieve. The AASHTO and EN test methods do not take into account the amount of material passing the 75 μm sieve or 2 mm sieve, respectively. For example, a fine aggregate with high methylene blue value measured by the AASHTO method but low percentage passing the 75 μm sieve may have less effect on concrete performance than a fine aggregate with low methylene blue value measured by the AASHTO method but a high percentage passing the 75 μm sieve. In contrast, this test method expresses methylene blue value based on the entire fine aggregate or mineral filler specimen. Additionally, the AASHTO and EN test methods use titration to determine the amount of methylene blue of known concentration that is adsorbed by a specimen and require the operator to visually determine the end point of the test. In contrast, this test method uses a colorimeter to detect the change in concentration of methylene blue solution before and after being mixed with the fine aggregate or mineral filler specimen.

NOTE 2—Recommendations for maximum methylene blue values for specific applications are not provided in this test method. Maximum methylene blue values should be established based on successful performance of fine aggregate or mineral filler in the applications under consideration.

6. Interferences

6.1 Methylene blue will degrade when exposed to light. Store in darkness. No appreciable degradation occurs during the time it takes to complete the test method.

6.2 Methylene blue will stain glassware and plastic ware. Therefore, do not reuse such apparatus.

7. Apparatus

7.1 *4.75-mm sieve* conforming to E11.

7.2 *Mass Balance* having a capacity of 50 g or more and capable of measuring to the nearest 0.1 g or less.

7.3 *Micropipette* capable of measuring to the nearest 1 μL .

7.4 *Colorimeter* capable of reading absorbance of a specimen at a wavelength of 610 ± 1 nm at operating temperatures of at least 0 to 50°C. The colorimeter shall be able to read absorbance between zero and the absorbance associated with a 0.144 % mass concentration of methylene blue solution.

7.5 *Disposable items for each test*—two plastic 50-mL test tubes, one plastic 1-mL vial, one 3-mL syringe with Luer-Lok adapter, one 0.2- μm syringe filter, one colorimeter glass cuvette (or sample cell), one micropipette tip, and two transfer pipettes.

7.6 *Additional disposable items for confirming methylene blue starting concentration*—plastic 50-mL test tube, colorimeter glass cuvette, micropipette tip, and transfer pipette.

7.7 *Additional disposable items for standardizing the colorimeter*—plastic 50-mL test tube, colorimeter glass cuvette, micropipette tip, and transfer pipette.

7.8 *Drying Apparatus*—A ventilated oven capable of maintaining a uniform temperature of $110 \pm 5^\circ\text{C}$. Other suitable drying apparatuses shall be permitted, such as an electric hot plate or heat lamp. The temperature of the specimen shall not exceed 150°C. In cases where the fine aggregate or mineral filler itself is altered by temperature greater than 115°C, use a ventilated, controlled-temperature oven at $110 \pm 5^\circ\text{C}$.

NOTE 3—Drying by means other than a ventilated oven may be appropriate for field use.

8. Reagents and Materials

8.1 *Purity of Reagents*—reagent grade methylene blue shall be used in all tests.

8.2 *Purity of water*—references to water shall be understood to mean distilled or deionized water.

8.3 *Methylene blue test solution*—a 0.50 % mass concentration methylene blue solution based on mass of trihydrate methylene blue in water.

NOTE 4—Methylene blue is available in both anhydrous and trihydrate form and can also be obtained in solution form. This test is based on the mass of the trihydrate form.

9. Sampling, Test Specimens, and Test Units

9.1 Sample fine aggregate in accordance to Practice D75.

9.2 Thoroughly mix the sample and reduce it as necessary using the applicable procedures in Practice C702.