



Designation: **F90–09 F90 – 14**

Standard Specification for Wrought Cobalt-20Chromium-15Tungsten-10Nickel Alloy for Surgical Implant Applications (UNS R30605)¹

This standard is issued under the fixed designation F90; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers the requirements for wrought cobalt-20chromium-15tungsten-10nickel alloy used for surgical implants. The properties specified apply specifically to wrought bar, rod, wire, sheet, and strip, but do not apply to surgical fixation wire (see Specification **F1091**).

1.2 ~~The values stated in SI units in this standard are the primary units. Values in primary SI or secondary inch-pound units are to be regarded separately as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.~~ stated in each system may not be exact equivalents; therefore each system shall be used independent of the other. Combining values from the two systems may result in non-conformance with the specification.

2. Referenced Documents

2.1 ASTM Standards:²

A751 Test Methods, Practices, and Terminology for Chemical Analysis of Steel Products

E8E8/E8M Test Methods for Tension Testing of Metallic Materials

E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

E45 Test Methods for Determining the Inclusion Content of Steel

E354 Test Methods for Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt Alloys

F981 Practice for Assessment of Compatibility of Biomaterials for Surgical Implants with Respect to Effect of Materials on Muscle and Bone

F1091 Specification for Wrought Cobalt-20Chromium-15Tungsten-10Nickel Alloy Surgical Fixation Wire (UNS R30605)

F2527 Specification for Wrought Seamless and Welded and Drawn Cobalt Alloy Small Diameter Tubing for Surgical Implants (UNS R30003, UNS R30008, UNS R30035, UNS R30605, and UNS R31537)

IEEE/ASTM SI 10 American National Standard for Use of the International System of Units (SI): The Modern Metric System

2.2 Aerospace Material Specification:³

AMS 2269 Chemical Check Analysis Limits, Wrought Nickel Alloys and Cobalt Alloys

AMS 5759 Cobalt Alloy, Corrosion and Heat Resistant Bars, Forgings, and Rings, 52Co – 20 Cr – 10Ni – 15W, Solution Heat Treated

2.3 ISO Standards:⁴

ISO 5832-5 Wrought Cobalt-Chromium-Tungsten-Nickel Alloy

ISO 6892 Metallic Materials Tensile Testing at Ambient Temperature

ISO 9001 Quality System—Requirements

2.4 American Society for Quality (ASQ) Standard:

C1 Specification of General Requirements for a Quality Program⁵

¹ This specification is under the jurisdiction of ASTM Committee **F04** on Medical and Surgical Materials and Devices and is the direct responsibility of Subcommittee **F04.12** on Metallurgical Materials.

Current edition approved ~~June 1, 2009~~ Nov. 1, 2014. Published ~~July 2009~~ January 2015. Originally approved in 1968. Last previous edition approved in ~~2007~~ 2009 as **F90–07:F90–09**. DOI: ~~10.1520/F0090-09.10.1520/F0090-14.~~

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from Society of Automotive Engineers (SAE), 400 Commonwealth Dr., Warrendale, PA 15096-0001, <http://www.sae.org>.

⁴ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

⁵ Available from American Society for Quality (ASQ), 600 N. Plankinton Ave., Milwaukee, WI 53203, <http://www.asq.org>.

*A Summary of Changes section appears at the end of this standard

3. Classification

3.1 *Bar*—Round, rectangular, or other complex shaped product delivered straightened and cut to defined lengths, with a maximum cross-sectional area of 16 in.² (103 cm²).

3.2 *Wire*—Round, rectangular, or other complex shaped product produced and delivered in coils.

3.3 *Fine Wire*—Wire with diameter or major dimension less than 0.063 in. (1.6 mm).

4. Ordering Information

4.1 Inquiries and orders for material under this specification shall include the following information:

4.1.1 Quantity,

4.1.2 ASTM designation and date of issue,

4.1.3 Mechanical properties (see Section 7),

4.1.4 Form (bar, rod, wire, sheet, strip),

4.1.5 Applicable dimensions including size, thickness, width, and length (exact, random, or multiples) or drawing number,

4.1.6 Condition (see 5.1),

4.1.7 Finish (see 5.2),

4.1.8 Other requirements.

5. Materials and Manufacture

5.1 *Condition*—Bar, wire, sheet, and strip shall be furnished to the purchaser, as specified, in the annealed ~~or cold-worked~~ cold-worked, or cold worked and aged condition.

5.2 *Finish*:

5.2.1 Bar and wire shall be furnished bright annealed, cold drawn, pickled, ground, or ground and polished, as specified by the purchaser.

5.2.2 Sheet shall be furnished bright annealed, pickled, cold-rolled, or polished, as specified by the purchaser.

6. Chemical Requirements

6.1 The heat analysis shall conform to the chemical composition of Table 1. The supplier shall not ship material that is outside the limits specified in Table 1.

6.1.1 Requirements for the major and minor elemental constituents are listed in Table 1. Also listed are important residual elements. Analysis for elements not listed in Table 1 is not required to verify compliance with this specification.

6.2 *Product Analysis*—The product analysis is either for the purpose of verifying the composition of a heat or lot or to determine variations in the composition within the heat.

6.2.1 Acceptance or rejection of a heat or lot of material may be made by the purchaser on the basis of this product analysis.

6.2.2 Product analysis tolerances do not broaden the specified heat analysis requirements but instead cover variations between laboratories in the measurement of chemical content. Product analysis limits shall be as specified in Table 2.

6.3 For referee purposes, Test Methods E354 shall be used.

6.4 Methods and practices relating to chemical analysis required by this specification shall be in accordance with Test Methods A751.

TABLE 1 Chemical Requirements

Element	Composition, % (mass/mass)	
	min	max
Carbon	0.05	0.15
Manganese	1.00	2.00
Silicon	...	0.40
Phosphorus	...	0.040
Sulfur	...	0.030
Chromium	19.00	21.00
Nickel	9.00	11.00
Tungsten	14.00	16.00
Iron	...	3.00
Cobalt ^A	balance	balance

^A Approximately equal to the difference between 100 % and the sum percentage of the other specified elements. The percentage of the cobalt difference is not required to be reported.