



Designation: D1746 – 15

# Standard Test Method for Transparency of Plastic Sheeting<sup>1</sup>

This standard is issued under the fixed designation D1746; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the U.S. Department of Defense.*

## 1. Scope\*

1.1 This test method covers the measurement of the transparency of plastic sheeting in terms of regular transmittance ( $T_r$ ). Although generally applicable to any translucent or transparent material, it is principally intended for use with nominally clear and colorless thin sheeting.

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

NOTE 1—There is no known ISO equivalent to this standard.

NOTE 2—For additional information, see Terminology E284 and Practice E1164.

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

- D618 Practice for Conditioning Plastics for Testing
- D883 Terminology Relating to Plastics
- D1003 Test Method for Haze and Luminous Transmittance of Transparent Plastics
- E284 Terminology of Appearance
- E691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method
- E1164 Practice for Obtaining Spectrometric Data for Object-Color Evaluation
- E1316 Terminology for Nondestructive Examinations
- E1345 Practice for Reducing the Effect of Variability of Color Measurement by Use of Multiple Measurements
- E1347 Test Method for Color and Color-Difference Measurement by Tristimulus Colorimetry

surement by Tristimulus Colorimetry  
E1348 Test Method for Transmittance and Color by Spectrophotometry Using Hemispherical Geometry

## 3. Terminology

3.1 *Definitions:*

3.1.1 For definitions of terms used in this test method, refer to Terminologies D883, E284, and E1316.

## 4. Significance and Use

4.1 The attribute of clarity of a sheet, measured by its ability to transmit image-forming light, correlates with its regular transmittance. Sensitivity to differences improves with decreasing incident beam- and receptor-angle. If the angular width of the incident beam and of the receptor aperture (as seen from the specimen position) are of the order of  $0.1^\circ$  or less, sheeting of commercial interest have a range of transparency of about 10 to 90 % as measured by this test. Results obtained by the use of this test method are greatly influenced by the design parameters of the instruments; for example, the resolution is largely determined by the angular width of the receptor aperture. Caution should therefore be exercised in comparing results obtained from different instruments, especially for samples with low regular transmittance.

4.2 Regular transmittance data in accordance with this test method correlate with the property commonly known as “see-through,” which is rated subjectively by the effect of a hand-held specimen on an observer’s ability to distinguish clearly a relatively distant target. This correlation is poor for highly diffusing materials because of interference of scattered light in the visual test.

## 5. Apparatus

5.1 The apparatus shall consist of a light source, source aperture, lens system, specimen holder, receptor aperture, photoelectric detector, and an indicating or recording system, arranged to measure regular transmittance. The system shall meet the following requirements:

5.1.1 An incandescent or vapor-arc lamp, with a regulated power supply such that fluctuations in light intensity shall be less than  $\pm 1\%$ . If an arc lamp is used, an appropriate filter shall be used to limit light only to the spectral range from 540 to 560 nm.

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D20 on Plastics and is the direct responsibility of Subcommittee D20.40 on Optical Properties.

Current edition approved April 1, 2015. Published April 2015. Originally approved in 1960. Last previous edition approved in 2009 as D1746 – 09. DOI: 10.1520/D1746-15.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

\*A Summary of Changes section appears at the end of this standard

5.1.2 A system of apertures and lenses shall be used that will provide a symmetrical incident beam. When measured with the indicating or recording system of the apparatus, using a receptor aperture having a width or diameter subtending an angle of  $0.025 \pm 0.005^\circ$  at the plane of the specimen, the incident beam shall meet the following requirements:

Angle, °	Maximum Relative Intensity
0	100
0.05	10
0.1	1
0.3	0.1

The source aperture may be circular or a rectangular slit having a length-to-width ratio of at least 10.

5.1.3 A holder shall be provided that will secure the specimen so that its plane is normal to the axis of the incident beam at a fixed distance from the receptor aperture. Provision must be made for rotating the specimen if slit optics are used. Provision for transverse motion may be provided to facilitate replication of measurements.

5.1.4 An aperture shall be provided over the receptor so that its diameter or width subtends an angle, at the plane of the specimen, of  $0.1 \pm 0.025^\circ$ . The image of the source aperture with no specimen in place shall be the same shape as the receptor aperture centered on and entirely within it.

5.1.5 A photoelectric detector shall be provided such that the indicated or recorded response to incident light shall be substantially a linear function and uniform over the entire range from the unobstructed beam ( $I_o$ ) to  $0.01 I_o$  or less.

5.1.6 Means shall be provided for relatively displacing the receptor or the image of the source aperture (in the plane of the receptor aperture) by at least  $1^\circ$  from the optical axis of the undeviated incident beam; for circular apertures, in two directions at right angles to each other; for slit optics, in the direction of the short dimension of the slit.

NOTE 3—This provision is necessary for checking the geometry of the incident beam (5.1.2) and for readjusting for maximum light intensity in the event that the beam is deviated by a specimen with nonparallel surfaces.

NOTE 4—Apparatus meeting these requirements has been described in the literature,<sup>3</sup> and commercial versions are available.<sup>4</sup>

## 6. Reference Materials

6.1 Since no regular transmittance standards are known to be available, it is recommended that specimens of glass or other material(s) maintaining constant light transmission properties with time be selected that yield different regular transmittance values for use as reference materials.

6.2 Measure the regular transmittance value of each specimen, and label it with the value obtained.

6.3 Keep these reference materials for checking any changes in instrument performance over time.

<sup>3</sup> Webber, Alfred C., "Method for the Measurement of Transparency of Sheet Materials," *Journal of the Optical Society of America*, JOSAA, Vol 47, No. 9, September 1957, pp. 785–789.

<sup>4</sup> The sole source of supply of the Clarity Meter known to the committee at this time is Zebedee, P.O. Box 395, Landrum, SC 29356, (800) 462-1804. If you are aware of alternative suppliers, please provide this information to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,<sup>1</sup> which you may attend.

## 7. Test Specimens

7.1 All specimens should preferably be colorless (see Note 5) and transparent to translucent, have essentially plane parallel surfaces, and be free of surface or internal contamination.

NOTE 5—Transparency of colored or highly reflective materials may be measured by the ratio of  $T_r/T_t$ , where  $T_t$  is the total luminous transmittance (see Test Method D1003, E1347, or E1348).

7.2 A suitable holder shall be used for nonrigid specimens so that they are flat and free from wrinkles.

7.3 A minimum of three test specimens shall be prepared for each material unless otherwise specified in the applicable product specification.

NOTE 6—Practice E1345 provides procedures for reducing variability in test results to meet stated tolerance limits by using measurements of multiple specimens (or multiple measurements on a single specimen).

## 8. Conditioning

8.1 *Conditioning*—Condition the test specimens at  $23 \pm 2^\circ\text{C}$  ( $73.4 \pm 3.6^\circ\text{F}$ ) and  $50 \pm 10\%$  relative humidity for not less than 40 h prior to test in accordance with Procedure A of Practice D618 unless otherwise specified by contract or the relevant ASTM material specification. In cases of disagreement, the tolerances shall be  $1^\circ\text{C}$  ( $1.8^\circ\text{F}$ ) and  $\pm 5\%$  relative humidity.

8.2 *Test Conditions*—Conduct the tests at the same temperature and humidity used for conditioning with tolerances in accordance with Section 7 of Practice D618, unless otherwise specified by contract or the relevant ASTM material specification. In cases of disagreement, the tolerances shall be  $1^\circ\text{C}$  ( $1.8^\circ\text{F}$ ) and  $\pm 5\%$  relative humidity.

## 9. Instrument Adjustment

9.1 Turn the instrument on and allow it to come to a stable operating temperature.

9.2 With the light beam blocked at sample position, set the reading to zero.

9.3 With the light beam unblocked, adjust the reading to a maximum by moving the receptor aperture so that the receptor receives the maximum intensity from the light. Either set this value to 100 or record it as  $I_o$ .

9.4 Check for changes in instrument performance by reading the reference materials prepared in Section 6.

## 10. Procedure

10.1 Turn the instrument on and allow it to come to a stable operating temperature.

10.2 With the light beam blocked at sample position, set the reading to zero.

10.3 With the light beam unblocked, set the reading to 100 and record it as  $I_o$ .

10.4 Mount a test specimen in the instrument so that it is neither wrinkled nor stretched, but centered and normal to the light beam. Record the reading as  $I_r$ . Rotate the specimen  $90^\circ$  to measure the directionality of the specimen and record the