



SLOVENSKI STANDARD
SIST EN 1186-6:2002

01-september-2002

BUXca Yý U
SIST ENV 1186-6:1997

A UYf]U]']b]nXY_]j`gh_i`n`y]j]]]!'Dc`]a Yfb]a UYf]U]']!* "XY.`DfYg_i gbY`a YtcXY`nU
Wf`c]bc`a][fUY`c`j`c`]j bc`c`^Y`n]j fY`_c

Materials and articles in contact with foodstuffs - Plastics - Part 6: Test methods for overall migration into olive oil using a pouch

Werkstoffe und Gegenstände in Kontakt mit Lebensmitteln - Kunststoffe - Teil 6: Prüfverfahren für die Gesamtmigration in Olivenöl unter Verwendung eines Beutels

Matériaux et objets en contact avec les denrées alimentaires - Matière plastique - Partie 6: Méthodes d'essai pour la migration globale dans l'huile d'olive à l'aide d'un sachet

Ta slovenski standard je istoveten z: EN 1186-6:2002

ICS:

67.250 Materiali in predmeti v stiku z živili Materials and articles in contact with foodstuffs

SIST EN 1186-6:2002 en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 1186-6:2002](#)

<https://standards.iteh.ai/catalog/standards/sist/0cfc8f01-bc11-45d2-a2ee-aeb2c879be64/sist-en-1186-6-2002>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 1186-6

April 2002

ICS 67.250

Supersedes ENV 1186-6:1994

English version

**Materials and articles in contact with foodstuffs - Plastics - Part
6: Test methods for overall migration into olive oil using a pouch**

Matériaux et objets en contact avec les denrées
alimentaires - Matière plastique - Partie 6: Méthodes
d'essai pour la migration globale dans l'huile d'olive à l'aide
d'un sachet

Werkstoffe und Gegenstände in Kontakt mit Lebensmitteln
- Kunststoffe - Teil 6: Prüfverfahren für die
Gesamtmigration in Olivenöl unter Verwendung eines
Beutels

This European Standard was approved by CEN on 4 January 2002.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

(standards.iteh.ai)

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

[SIST EN 1186-6:2002](https://standards.iteh.ai/catalog/standards/sist/0cfc8f01-bc11-45d2-a2ee-aeb2c879be64/sist-en-1186-6-2002)

<https://standards.iteh.ai/catalog/standards/sist/0cfc8f01-bc11-45d2-a2ee-aeb2c879be64/sist-en-1186-6-2002>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

	page
Foreword.....	3
1 Scope	5
2 Normative references	5
3 Principle	5
4 Reagents	6
5 Apparatus	7
6 Preparation of test specimens.....	9
7 Procedure	10
8 Expression of results	16
9 Test report	18
Annex A (normative) Determination of the suitability of olive oil as the fatty food simulant and of triheptadecanoin as the internal standard	19
Annex B (normative) Determination of the need for sample conditioning	21
Annex C (normative) Determination of the need for sample conditioning and determination of the mass of moisture sensitive test specimens, by vacuum drying	22
Annex D (normative) Determination of change in moisture content of test specimens by measurement of the transfer of water to, or from olive oil by Karl Fischer titration	24
Annex E (informative) Pouch holder, typical chromatograms and calibration graph	26
Annex F (informative) Precision data	30
Annex ZA (informative) Relationship of this European Standard with Council Directive 89/109/EEC and Commission Directive 90/128/EEC and associated Directives	31
Bibliography	33

Foreword

This document EN 1186-6:2002 has been prepared by Technical Committee CEN/TC 194 "Utensils in contact with food", the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 2002, and conflicting national standards shall be withdrawn at the latest by October 2002.

This document supersedes ENV 1186-6:1994.

This European Standard is one of a series of methods of test for plastics materials and articles in contact with foodstuffs.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of EC Directive(s).

For relationship with EC Directive(s), see informative annex ZA, which is an integral part of this document.

At the time of preparation and publication of this standard the European Union legislation relating to plastics materials and articles intended to come into contact with foodstuffs is incomplete. Further Directives and amendments to existing Directives are expected which could change the legislative requirements which this standard supports. It is therefore strongly recommended that users of this standard refer to the latest relevant published Directive(s) before commencement of any of the test or tests described in this standard.

EN 1186-6:2002 should be read in conjunction with EN 1186-1:2002.

Further Parts of this standard have been prepared, and others are in preparation, concerned with the determination of overall migration from plastics materials into food simulants.

Their titles are as follows:

EN 1186 Materials and articles in contact with foodstuffs- Plastics-

- | | |
|---------|--|
| Part 1 | Guide to the selection of conditions and test methods for overall migration |
| Part 2 | Test methods for overall migration into olive oil by total immersion |
| Part 3 | Test methods for overall migration into aqueous food simulants by total immersion |
| Part 4 | Test methods for overall migration into olive oil by cell |
| Part 5 | Test methods for overall migration into aqueous food simulants by cell |
| Part 7 | Test methods for overall migration into aqueous food simulants using a pouch |
| Part 8 | Test methods for overall migration into olive oil by article filling |
| Part 9 | Test methods for overall migration into aqueous food simulants by article filling |
| Part 10 | Test methods for overall migration into olive oil (modified method for use in cases where incomplete extraction of olive oil occurs) |
| Part 11 | Test methods for overall migration into mixtures of ¹⁴ C-labelled synthetic triglyceride |

EN 1186-6:2002 (E)

Part 12	Test methods for overall migration at low temperatures
Part 13	Test methods for overall migration at high temperatures
Part 14	Test methods for 'substitute tests' for overall migration from plastics intended to come into contact with fatty foodstuffs using test media iso-octane and 95 % ethanol
Part 15	Alternative test methods to migration into fatty food simulants by rapid extraction into iso-octane and/or 95 % ethanol

Annexes A, B, C and D to this standard are normative where applicable. Annexes E and F are informative.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

iTeh STANDARD PREVIEW **(standards.iteh.ai)**

[SIST EN 1186-6:2002](https://standards.iteh.ai/catalog/standards/sist/0cfc8f01-bc11-45d2-a2ee-aeb2c879be64/sist-en-1186-6-2002)

<https://standards.iteh.ai/catalog/standards/sist/0cfc8f01-bc11-45d2-a2ee-aeb2c879be64/sist-en-1186-6-2002>

1 Scope

This Part of this European Standard specifies test methods for the determination of the overall migration into fatty food simulants from one surface only of plastics in the form of film or sheet, which is intended to come into contact with foodstuffs, by forming the plastics film or sheet into standard pouches and exposing them by filling at temperatures above 20 °C and up to, but not including, 100 °C for selected times.

A standard pouch is a pouch with dimensions as defined in 6.3.

This method is most suitable for plastics in the form of films and sheets, which are sealable by heat or pressure, but it is particularly applicable to those materials consisting of more than one layer, which has to be tested with the food simulant in contact only with the surface which is intended to come into contact with the foodstuffs.

NOTE This test method has been written for use with the fatty food simulant, olive oil. The test method can also be used with appropriate modifications with 'other fatty food simulants' called simulant D - a synthetic mixture of triglycerides, sunflower oil and corn oil. These other fatty food simulants will produce different chromatograms for the simulant methyl esters to those of the methyl esters of olive oil. Select suitable chromatogram peaks of the methyl esters of the other fatty food simulants for the quantitative determination of the simulant extracted from the test specimens.

The test method described is applicable to most types of plastics, although there are some plastics for which it is known not to be applicable.

iTeh STANDARD PREVIEW (standards.iteh.ai)

2 Normative references

This European Standard incorporates by dated and undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text, and the publications are listed hereafter. For dated references, subsequent amendments to and revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

EN 1186-1:2002, *Materials and articles in contact with food – Plastics – Part 1: Guide to the selection of conditions and test methods for overall migration.*

ISO 648, *Laboratory glassware - One mark pipettes.*

ISO 4788, *Laboratory glassware - Graduated measuring cylinders.*

3 Principle

The overall migration from a sample of the plastics is determined as the loss in mass per unit of surface area intended to come into contact with foodstuffs.

The selection of the conditions of test will be determined by the conditions of use, see clauses 4, 5 and 6 of EN 1186-1:2002.

Test specimens of known mass and in the form of pouches are filled with olive oil for the exposure time, at temperatures above 20 °C and below 100 °C, then the olive oil is removed, the pouches cut open and the olive oil adhering to the surface is removed by blotting. The cut portion of each pouch is then reweighed,

The specimens will usually retain absorbed olive oil which is extracted and determined quantitatively by means of gas chromatography after conversion to methyl esters. Methylation is carried out by reacting a boron trifluoride/methanol complex with fatty acids formed by hydrolysing the oil with potassium hydroxide. An internal standard, triheptadecanoin, is added prior to the extraction of the absorbed olive oil from the test specimens. This ensures that any active or extractable components of the plastics react with the internal standard, as well as with

EN 1186-6:2002 (E)

the extracted olive oil. The internal standard is also subjected to the hydrolysis and methylation reactions, providing compensation for any inefficiencies in the hydrolysis and methylation processes.

Migration into the olive oil is calculated by subtracting the mass of olive oil retained by the test specimen from the mass of the test specimen after removal from the olive oil, then subtracting this mass from the initial mass of the specimen.

The total loss in mass is expressed in milligrams per square decimetre of surface area of the specimen and the overall migration is reported as the mean of a minimum of three determinations on separate test specimens.

To allow for inaccuracies which may arise during the procedure and which may be difficult to detect, due for example to contamination or loss of oil during the sample handling stages, four determinations are carried out on the sample allowing for the result from one specimen to be discarded.

This method includes variations that are applicable to certain plastics.

NOTE Before starting a migration exercise, the test sample should be examined for the presence of components interfering in the determination of the amount of olive oil extracted, see 7.1. If an unacceptable amount of interference is present then suitability of one of the 'other fatty food simulants' should be examined, see annex A and 9.3 and 9.5 of EN 1186-1:2002. If an interference is present which would interfere with the triheptadecanoic internal standard an alternative internal standard should be used, see annex A, and 9.3 of EN 1186-1:2002.

4 Reagents

NOTE All reagents should be of recognized analytical quality, unless otherwise specified.

4.1 Olive oil, simulant D, as specified in 5.2 of EN 1186-1:2002.

4.2 Extraction solvent (see 10.1 of EN 1186-1:2002).

4.2.1 For non-polar plastics, such as polyethylene and polypropylene:

- Pentane 98 % boiling point 36 °C.

For polar plastics, such as polyamide and polyacetal:

- 95/5 by volume azeotropic mixture of pentane 98 % and ethanol 99 %.

NOTE 1 Pentane is a very volatile and highly flammable solvent. Care should therefore be taken when handling this solvent to prevent contact with sources of ignition. Ethanol is also a flammable solvent. It is not recommended that extractions with either pentane or the pentane/ethanol mixture be left unattended, particularly overnight.

NOTE 2 Due to the low boiling points of these solvents, cooled condenser water can be required to prevent undue loss of the solvent from the condenser.

or

4.2.2 Other suitable solvent.

NOTE 1 In previous methods for determining overall migration into olive oil the extraction solvent used has been 1,1,2-trichloro-trifluoroethane. For environmental reasons the use of this solvent should be avoided where possible, see 9.1 of EN 1186-1:2002. Experience has shown that this solvent, although effective for most plastics requires longer periods of extraction.

NOTE 2 Some solvents can contain non-volatile substances which, after hydrolysis and methylation processes, produce gas chromatography peaks with retention times similar to the retention times of olive oil methyl esters and methyl heptadecanoate from the internal standard. Solvents found to contain such substances should be redistilled before use.

- 4.3** Internal standard, triheptadecanoin (glyceryl trimargarate) CAS No. 2438-40-6¹⁾ of a quality such that the products from hydrolysis and methylation processes do not contain substances giving detectable gas chromatography peaks (see 9.3 of EN 1186-1:2002) with similar retention times to the olive oil methyl ester peaks. Prepared as a solution containing 2,0 mg/ml in cyclohexane.
- 4.4** Potassium hydroxide solution, 11,0 g/l in methanol.
- 4.5** Boron trifluoride, methanol complex, approximately 150 g/l BF₃.
- 4.6** n -Heptane.
- 4.7** Sodium sulfate.
- 4.7.1** Sodium sulfate, anhydrous, Na₂SO₄.
- 4.7.2** Sodium sulfate, saturated solution.
- 4.8** Diethyl ether.
- 4.9** Karl Fischer solvent, commercially prepared, methanol and chloroform based, water capacity of 5 mg/ml.
- 4.10** Karl Fischer titrant (for volumetric apparatus only), commercially prepared, water capacity of 2 mg/ml.

5 Apparatus

iTeh STANDARD PREVIEW

- 5.1** Cutting slab, clean smooth glass, metal or plastics slab of sufficient area to prepare test specimens, 250 mm × 250 mm is suitable.
- 5.2** Tweezers, stainless steel, blunt nosed.
- 5.3** Cutting implement, scalpel, scissors, sharp knife or other suitable device.
- 5.4** Metal templates (120 mm ± 1 mm) × (120 mm ± 1 mm) (square).
- 5.5** Rule, graduated in mm, and with an accuracy of 0,1 mm.
- 5.6** Analytical balance capable of determining a change in mass of 0,1 mg.
- 5.7** Pouch holder, as shown in Figure E.1 has been shown to be suitable, constructed from aluminium or other suitable material or an equivalent holder, plus clips to secure corners of pouches.
- 5.8** Conditioning containers, for conditioning test specimens at 50 % ± 5 % relative humidity and 80 % ± 5 % relative humidity at 20 °C ± 5 °C.

NOTE For 50 % relative humidity, 43 % w/v sulphuric acid solution in water is suitable and for 80 % relative humidity, 27 % w/v sulphuric acid solution is suitable. The solutions should be freshly prepared by adding a weighed amount of acid to a suitable volume of water, cooling to room temperature and making up to the required volume.

It is recommended that relative humidity and temperature be maintained during the conditioning period. Therefore the containers should be placed in a thermostatically controlled room or oven, at a temperature of approximately 20 °C, the set temperature should not vary by more than ± 1 °C.

¹⁾ The source of this is the Chemical Abstracts published by the American Chemical Society.

EN 1186-6:2002 (E)

5.9 Glass tubes, ground neck and stoppers, for retaining the olive oil and test specimens. Tubes with an internal diameter of approximately 35 mm and length in the range of 100 mm to 200 mm, excluding the ground neck, see 7.2 of EN 1186-1:2002, have been found to be satisfactory.

5.10 Thermostatically controlled oven or incubator capable of maintaining the set temperature, within the tolerances specified in Table B.2 of EN 1186-1:2002.

5.11 Filter paper, lint-free.

5.12 Anti-bumping beads.

5.13 Soxhlet type extractors, capable of holding test specimens on the supports, with 250 ml or 500 ml round bottom flasks to fit.

NOTE Alternative extractors capable of satisfactorily extracting absorbed olive oil from the test specimens can be used.

5.14 Water bath, capable of holding the flasks of soxhlet type extractors (5.15).

5.15 Rotary evaporator or distillation apparatus, for evaporation and collection of the extraction solvent.

NOTE Artificially cooled water can be necessary for efficient condensation of a low boiling point solvent.

5.16 Steam bath or water bath.

5.17 Flasks, 50 ml, long neck with condensers to fit, for methyl ester preparations.

5.18 Measuring cylinders, complying with the minimum requirements of ISO 4788, 500 ml, 250 ml, 100 ml, 25 ml, and 10 ml. A 10 ml graduated syringe may be used in place of the 10 ml measuring cylinder.

5.19 Pipettes, complying with the minimum requirements of ISO 648, 5 ml and 10 ml.

5.20 Glass beads, 2 mm to 3 mm in diameter or glass rods, 2 mm to 3 mm in diameter and approximately 100 mm long (see 7.2 of EN 1186-1:2002).

5.21 Gas chromatograph, with flame ionisation detector equipped with an appropriate column. When using a polar column, the major peaks of olive oil, such as C16:0, methyl hexadecanoate (methyl palmitate), C16:1, methyl 9-hexadecenoate (methyl palmitoate), C18:0, methyl octadecanoate (methyl stearate), C18:1, methyl 9-octadecenoate (methyl oleate), C18:2, methyl 9,12-octadecadienoate (methyl linoleate) and the internal standard C17:0, methyl heptadecanoate (methyl margarate) shall demonstrate baseline separation. Optionally, a non-polar column can be used which shall give baseline separation of the methyl esters with 16 and 18 carbon numbers and the internal standard with 17 carbon number.

NOTE The following columns have been found to be suitable:

- Column 1, polar column, WCOT fused silica column, length 50 m, internal diameter 0,25 mm, coated with a 0,21 micrometre film of cyanopropyl silicone;
- Column 2, non polar column, BP1, length 25 m, internal diameter 0,32 mm, with a 1 micron film thickness;
- Column 3, polar column, stainless steel column 2 mm to 3 mm internal diameter and 2 m to 3 m length with a packing of 10 % to 20 % by mass of polyester succinate on a stationary phase of diatomaceous earth 80 mesh to 100 mesh.

5.22 Heat or pressure sealing device, for use in forming pouches

5.23 Glass tubes with ground glass necks and stoppers, of a volume of approximately 10 ml, for storing the heptane layer if necessary.

5.24 Vacuum oven or vacuum desiccator, capable of maintaining a temperature of $60\text{ }^{\circ}\text{C} \pm 2\text{ }^{\circ}\text{C}$. The vacuum oven or vacuum desiccator shall be equipped with or connected to a vacuum pump capable of achieving a vacuum

of 1,3 kPa or less. The vacuum pump shall be provided with a time controller to switch on the vacuum pump every hour for 15 min.

NOTE If a vacuum oven is not available, a vacuum desiccator placed in an oven at 60 °C can be used.

5.25 Desiccator containing self indicating silica gel or anhydrous calcium chloride.

5.26 Balance, capable of determining a change of mass of 10 mg.

5.27 Disposable plastic syringes with luer fitting. 1 ml or 10 ml size.

5.28 Wide gauge luer needles (80 mm × 1,2 mm).

5.29 Karl Fischer apparatus, either an automated volumetric titrator, or an automated coulometric titrator. The Karl Fischer titrator shall be capable of measuring the water content of the simulant with a precision (standard deviation) of 10 mg/kg or less (equivalent to 1 mg/dm² plastic). An automated volumetric or coulometric instrument shall be used. Manual titration procedures do not give the required accuracy or precision.

6 Preparation of test specimens

6.1 General

It is essential that test specimens are clean and free from surface contamination (many plastics can readily attract dust due to static charges). Before preparing test specimens, remove any surface contamination from the sample by gently wiping it with a lint-free cloth, or by brushing with a soft brush. Under no circumstances wash the sample with water or solvent. If it is specified in the instructions for use of the article that it should be washed or cleaned before use see 8.1 of EN 1186-1:2002. Minimise handling of the samples and, where necessary, wear cotton gloves.

[SIST EN 1186-6:2002](https://standards.iteh.ai/catalog/standards/sist/0cfc8f01-bc11-45d2-a2ee-aeb2c879bc64/sist-en-1186-6-2002)

[https://standards.iteh.ai/catalog/standards/sist/0cfc8f01-bc11-45d2-a2ee-](https://standards.iteh.ai/catalog/standards/sist/0cfc8f01-bc11-45d2-a2ee-aeb2c879bc64/sist-en-1186-6-2002)

6.2 Number of test specimens [aeb2c879bc64/sist-en-1186-6-2002](https://standards.iteh.ai/catalog/standards/sist/0cfc8f01-bc11-45d2-a2ee-aeb2c879bc64/sist-en-1186-6-2002)

Seven test specimens are required. These test specimens are utilized as follows:

- a) four test specimens for the migration test;
- b) two test specimens to check for possible loss of volatiles;
- c) one test specimen to determine the suitability of olive oil as the fatty food simulant and triheptadecanoin as the internal standard (see annex A);

If the conditioning test in annex C is used, one additional test specimen is required.

NOTE The two test specimens, b), are used to check whether the sample loses mass from the evaporation of volatiles, such as solvents, during the test period. If the vacuum drying procedure in annex C is used these test specimens are not required as during the vacuum drying any volatiles will have been removed from the test specimens.

If previous testing has established that interference in the gas chromatography procedure is unlikely and annex A is omitted, one fewer test specimen will be required.

A minimum of three valid test results is required to calculate the mean. Testing in triplicate is allowed but in this case if one test result is invalid repeat the entire procedure.

6.3 Cutting and preparation of test specimens

Lay the sample on the cutting slab (5.1) with the surface to be in contact with the olive oil uppermost and cut and cut test pieces using the 120 mm × 120 mm template (5.4). Two test pieces are required for each test specimen.

EN 1186-6:2002 (E)

Place pairs of the test pieces together with the surfaces to be in contact with the olive oil facing. Using the heat or pressure sealer (5.22), join to form pouches with four seals parallel to all four edges, 10 mm from the edge. Measure the distances between the inner edges of the seals to the nearest 1 mm and calculate the total surface area of the test specimen which will be exposed to olive oil, to the nearest 0,01 dm². This shall be approximately 2 dm². Using the cutting implement, remove excess film from the sealed area (to reduce the area of film not directly exposed to olive oil) whilst leaving enough to withstand the test conditions without leaking.

Measure and record the surface area of the pouch which will be in contact with the simulant and the total external area of the pouch after trimming excess material.

Mark each pouch for identification. Cut off one corner of the pouch to leave a hole sufficiently large to insert a 100 ml pipette.

7 Procedure**7.1 General**

Determine the applicability of the method by carrying out the procedure described in annex A. If prior tests have established that the method is applicable then annex A may be omitted.

Before weighing, discharge any build up of static electricity with an antistatic gun or other suitable means.

7.2 Initial weighing of test specimens

7.2.1 Determine the need for conditioning of the test specimens by carrying out the procedure described in annex B or in annex C. If prior tests have established that sample conditioning is not required then annex B and annex C may be omitted. If prior tests have established that the procedure described in annex D is applicable to the sample, then annex B or annex C may be omitted.

7.2.2 If the tests described in annex B or annex C show that conditioning is not necessary, determine and record the mass of each test specimen.

7.2.3 If the tests described in annex B or annex C show that conditioning is necessary, follow the directions in the relevant annex to determine the initial mass of the sample.

7.2.4 If the tests described in annex B show that conditioning is necessary, but constant mass cannot be achieved within five days then carry out the conditioning procedure described in C.3.1 or annex D.

NOTE 1 Long conditioning periods are not satisfactory due to oxidation of the olive oil which can occur upon prolonged conditioning.

NOTE 2 The conditioning procedures described in annex C and annex D can be used if it has been established that these procedures are more suited to the polymer type under test.

7.3 Exposure to food simulant

Take five of the glass tubes (5.9), measure 100 ml \pm 5 ml of olive oil (4.1) into each tube by measuring cylinder (5.18) and stopper the tube.

NOTE 1 The pouch holder (5.7) should be cleaned before use, if necessary, using solvents, such as acetone and or detergents. For difficult to remove olive oil, use propriety solvent mixtures.

WARNING Proprietary solvent mixtures usually contain caustic substances and also volatile solvents. Handle with care, using protective gloves and eye protection, in a fume cupboard. Information regarding sources of the proprietary mixtures specified in this European Standard are available from National Standards Bodies.

NOTE 2 If the procedure described in annex D is used, it can be necessary to dry all of the olive oil used for the migration test, see D.3.2.