This document is not an ASTM standard and is intended only to provide the user of an ASTM standard an indication of what changes have been made to the previous version. Because it may not be technically possible to adequately depict all changes accurately, ASTM recommends that users consult prior editions as appropriate. In all cases only the current version of the standard as published by ASTM is to be considered the official document.



# Designation: A1044/A1044M - 05 (Reapproved 2010) A1044/A1044M - 15

# Standard Specification for Steel Stud Assemblies for Shear Reinforcement of Concrete<sup>1</sup>

This standard is issued under the fixed designation A1044/A1044M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\varepsilon$ ) indicates an editorial change since the last revision or reapproval.

# 1. Scope-Scope\*

1.1 This specification covers steel stud assemblies for shear reinforcement of concrete. Stud assemblies consist of either single-headed studs attached to a steel base rail by welding, or double-headed studs mechanically crimped into a steel shape.

NOTE 1—The configuration of the studs for stud assemblies is much different than the configuration of the headed-type studs prescribed in Section 7, Figure 7.1 of AWS D1.1/D1.1M. Ratios of the cross-sectional areas of the head-to-shank of the AWS D1.1/D1.1M studs range from about 2.5 to 4. In contrast, this specification requires the area of the head of the studs for stud assemblies to be at least 10 times the area of the shank. Thus, the standard headed-type studs in Section 7, Figure 7.1 of AWS D1.1/D1.1M do not conform to the requirements of this specification for use as stud assemblies for shear reinforcement.

1.2 This specification is applicable for orders in either inch-pound units or in SI units.

1.3 The values stated either in inch-pound or SI units are to be regarded as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other. Combining values from the two systems may result in nonconformance with this specification.

#### 2. Referenced Documents

2.1 ASTM Standards:<sup>2</sup>

A29/A29M Specification for General Requirements for Steel Bars, Carbon and Alloy, Hot-Wrought A36/A36M Specification for Carbon Structural Steel A370 Test Methods and Definitions for Mechanical Testing of Steel Products

2.2 AWS Standard:<sup>3</sup>

- AWS D1.1/D1.1M-2004 Structural Welding Code—Steel
- 2.3 U.S. Military Standards:<sup>4</sup>

MIL-STD-129 Marking for Shipment and Storage MA1044/A1044M-15

MIL-STD-163 Steel Mill Products Preparation for Shipment and Storage 85bf-6802fdf16254/astm-a1044-a1044m-15 2.4 U.S. Federal Standard:<sup>4</sup>

Fed. Std. No. 123 Marking for Shipment (Civil Agencies)

## 3. Terminology

- 3.1 Definitions of Terms Specific to This Standard:
- 3.1.1 headed stud, n-a steel bar used in the reinforcement of concrete that has a head formed at one or both ends.
- 3.1.2 base rail, n—the steel shape or plate that a group of headed studs is attached to by welding or other means.

#### 3.1.2.1 Discussion-

Stud assemblies comprised of single-headed studs require a base rail; the base rail acts as a structural element to provide anchorage

\*A Summary of Changes section appears at the end of this standard

Copyright © ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959. United States

<sup>&</sup>lt;sup>1</sup> This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.05 on Steel Reinforcement.

Current edition approved Nov. 1, 2010 March 1, 2015. Published November 2010 March 2015. Originally approved in 2005. Last previous edition approved in 2005 2010 as  $\frac{1044/A1044M - 05.A1044/A1044M - 05(2010)}{10.1520/A1044 - A1044M - 05(2010)}$ . DOI:  $\frac{10.1520/A1044 - A1044M - 05(2010)}{10.1520/A1044 - A1044M - 15}$ .

<sup>&</sup>lt;sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>&</sup>lt;sup>3</sup> Available from The-American Welding Society (AWS), 550 NW LeJeune Rd., 8669 NW 36 Street, #130, Miami, FL 33126:33166-6672, http://www.aws.org.

<sup>&</sup>lt;sup>4</sup> Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098; 19111-5098, http://dodssp.daps.dla.mil.

# 🕼 A1044/A1044M – 15

to the concrete. For stud assemblies in which double-headed studs are mechanically crimped into a base rail, for example, into a steel channel, the base rail is not required to provide anchorage to the concrete; the purpose of the base rail is to hold the studs in the appropriate location, direction, and spacing until the concrete is cast.

## 4. Ordering Information

4.1 It shall be the responsibility of the purchaser to specify all requirements that are necessary for material ordered to this specification. Such requirements shall include but are not limited to the following:

- 4.1.1 Name of product: stud assemblies for shear reinforcement of concrete,
- 4.1.2 Quantity of studs by diameter,
- 4.1.3 Number of heads per stud,
- 4.1.4 Dimensions of base rail, if included,
- 4.1.5 Overall height of stud assembly,
- 4.1.6 Number of studs per each assembly and their spacing (see Note 2),
- 4.1.7 Packaging, and
- 4.1.8 ASTM designation and year of issue.

Note 2-In the case of ordering studs rather than assemblies, the length of the studs should be specified such that the appropriate height of the stud assembly is achieved.

# 5. Materials and Manufacture

5.1 Headed studs shall be manufactured from steel conforming to Specification A29/A29M, Grades 1010 through 1020. The stud material shall conform to the requirements for tensile properties prescribed in Table 1.

# 5.2 Base Rails:

5.2.1 For stud assemblies in which the stude are welded to a base rail, the base rail material shall conform to 5.2.1.1, 5.2.1.2, or 5.2.1.3.

5.2.1.1 The base rail material, except for tensile properties, shall conform to Specification A36/A36M or equivalent. The base rail material shall conform to the requirements for tensile properties prescribed in Table 2.

5.2.1.2 Base rail material conforming to the minimum required tensile properties in Specification A36/A36M shall be permitted provided the base rail thickness is increased by a factor equal to the minimum yield strength specified in Table 2 divided by the minimum yield strength required by Specification A36/A36M.

5.2.1.3 Base rail material selected by the manufacturer shall be permitted subject to agreement with the purchaser. The manufacturer shall furnish documentation to the purchaser in the form of test reports that confirms the suitability of the selected base rail material for: (1) manufacturing stud assemblies; and (2) structural adequacy of the stud assemblies for the intended application.

5.2.2 For stud assemblies in which double-headed studs are mechanically crimped into a steel shape, the steel shape shall be sufficiently stiff to hold the studs in appropriate location, direction, and spacing.

5.3 For stud assemblies in which the studs are attached to base rails by stud welding, the stud welding shall conform to AWS D1.1/D1.1M, including the provisions for production control, and fabrication and verification requirements.

## 5.4 Dimensions:

5.4.1 Minimum dimensions of headed studs and plate base rails shall conform to Table 3.

NOTE 3-The configurations of stud assemblies are shown in Fig. 1.

5.4.2 Headed studs with heads that have variable thickness shall be permitted, provided they meet the tensile requirements of this specification.

## 6. Tensile Tests

6.1 At periodic intervals, tensile tests of the headed stud with a single or double head formed at one or both ends of the shank or welded to the base rail shall be performed as specified in the quality assurance program of the manufacturer and agreed upon by the purchaser. Tensile tests on the studs shall be conducted by the assembly manufacturer, or an inspection agency, or the stud supplier.

6.2 Tensile testing shall be performed in accordance with the requirements described in Test Methods and Definitions A370. Tensile testing of headed studs shall be performed using a test fixture as described in Section 7.3.2 of AWS D1.1/D1.1M.

**TABLE 1 Tensile Requirements—Stud Material** 

	otaa matoriai
Tensile strength, min, psi [MPa]	65 000 [450]
Yield strength, min, psi [MPa]	51 000 [350]
Elongation in 2 in. [50 mm], min, %	20
Reduction of area, min, %	50



TABLE 2 Tensile Requirements—Base Rail Material<sup>A</sup>

Tensile strength, min, psi [MPa] Yield strength, min, psi [MPa]	65 000 [450] 44 000 [300]
Elongation in 8 in. [200 mm], min, %	20
A Stude welded to been roll	

<sup>A</sup> Studs welded to base rail

## 7. Acceptance Criteria

7.1 In addition to meeting the strength requirements of 5.1 and 5.2, no observed partial or total fracture of the head, the stud weld, or other stud-base rail connection shall be permitted. The failure shall occur either in the stud material a minimum of one-half shank diameter from the head-to-shank or stud-to-base rail connection, or by tearing a hole in the base rail. Failure of the head or stud-to-base rail connection within the attachment region shall be cause for rejection. The tensile force at which failure occurs shall exceed the minimum yield strength of the stud.

## 8. Number of Tests

8.1 A minimum of two tensile tests shall be conducted during a production shift or period. It shall be permissible to test separate base rail material of the same thickness, chemical composition, and configuration of the base rails used in production. One test at the start and one test at the end of each 8-h production shift or less than 8-h production period, or at random intervals during the production period, shall be conducted.

8.2 In the event different heats of stud or base rail material within the same material specification are used to produce stud assemblies during a production run, a minimum of two tensile tests in accordance with Section 6 shall be conducted to verify the production method, product quality, and weldability of the heats of materials prior to continuing production.

8.3 Any identified procedural or performance deficiencies shall be corrected and testing repeated until the tensile test results meet the requirements of this specification.

#### 9. Retests

9.1 If the tension test fails before meeting the specified minimum yield strength of the headed stud material per in accordance with Table 1, but is within 2000 psi [14 MPa] of the required tensile strength, and if the fracture is not located within one-half shank diameter from the head-to-shank or stud-to-base rail connection, then a retest shall be allowed. Two specimens taken at random from the production lot shall be tested during a retest. Both assembled specimens shall pass the minimum yield strength requirements of Section 6 or the lot shall be rejected.

9.2 If any test specimen fails because of mechanical reasons such as failure of the testing equipment or from flaws caused by specimen preparation, shipment or other damage unrelated to fabrication or testing, it shall be discarded and another specimen from the same production lot substituted.

#### https://standards.iteh.ai/catalog/standards/sist/1fc0d7e0-dc38-4175-85bf-6802fdf16254/astm-a1044-a 10. Finish

10.1 Finished studs shall be of uniform quality and condition, free of discontinuous laps, seams, fins, or other discontinuities that would adversely affect welding or structural strength of the studs. Radial cracks or bursts in the head(s) of the studs shall not be cause for rejection provided that the length of cracks or bursts do not exceed the value 0.25 times (head diameter – shank diameter), or using the notation in Fig. 1: 0.25 (D - d). Surface rust and mill scale shall not be cause for rejection provided they do not adversely affect welding or structural strength of the stud assembly.

NOTE 4—Heads of studs are subject to cracks or bursts, which are terms for the same thing. Cracks or bursts designate an abrupt interruption of the periphery of the stud head by radial separation of the metal.

#### 11. Inspection

11.1 The inspector representing the purchaser shall have free entry while work on the contract of the purchaser is being performed, to the parts of the manufacturer's facilities that concern manufacture of the material ordered. The manufacturer shall afford the inspector reasonable access to the facilities to satisfy the inspector that the materials and procedures are in accordance with this specification. Inspection at the place of manufacture shall be conducted so as not to interfere unnecessarily with the operation of the manufacturer's facilities.

11.2 For Government Procurement Only—Except as otherwise specified in the contract, the manufacturer shall be responsible for the performance of inspection and test requirements specified herein, unless otherwise agreed by the purchaser at the time of purchase, and shall use his/her own or other suitable facilities for the performance of the inspection and test requirements specified herein.

#### 12. Rejection

12.1 The purchaser shall have the right to perform any of the inspections and tests as set forth in this specification as deemed necessary. Unless otherwise specified, any rejection based on tests made in accordance with this specification shall be reported to the manufacturer within five working days from the receipt of samples by the purchaser.