



Designation: D2054 – 99 (Reapproved 2015)

Standard Test Method for Colorfastness of Zipper Tapes to Crocking¹

This standard is issued under the fixed designation D2054; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the determination of the degree of color that may be transferred from the textile tape of zippers of all fibers to other surfaces by rubbing under wet or dry conditions, or both.

1.2 The values stated in either SI units or inch-pound units are to be regarded separately as the standard. Within the text, the inch-pound units are shown in parentheses. The values stated in each system are not exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in nonconformance with this test method.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D123 Terminology Relating to Textiles

D1776 Practice for Conditioning and Testing Textiles

D2050 Terminology Relating to Fasteners and Closures

Used with Textiles

2.2 *AATCC Methods:*³

Method 8 Colorfastness to Crocking;

AATCC Crockmeter Method

AATCC Chromatic Transference Scale

3. Terminology

3.1 *Definitions*—For definitions of zipper terms used in this standard, refer to Terminology D2050. For definitions of other

¹ This test method is under the jurisdiction of ASTM Committee D13 on Textiles and is the direct responsibility of Subcommittee D13.54 on Subassemblies. This test method was developed in cooperation with the Slide Fastener Association, Inc.

Current edition approved Feb. 1, 2015. Published April 2015. Originally approved in 1961. Last previous edition approved in 2010 as D2054 – 99(2010). DOI: 10.1520/D2054-99R15.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Technical Manual of the American Association of Textile Chemists and Colorists, P. O. Box 12215, Research Triangle Park, NC 27709.

textile terminology used in this standard, refer to Terminology D123.

4. Summary of Test Method

4.1 A specimen of the zipper tape fastened to the base of a crockmeter is rubbed with white crock test cloth under controlled conditions. Color transferred to the white test cloth is assessed by a comparison with the AATCC Chromatic Transference Scale.

5. Significance and Use

5.1 This test method is considered satisfactory for acceptance testing of commercial shipments because the method has been used extensively in the trade for acceptance testing.

5.1.1 If there are differences of practical significance between reported test results for two laboratories (or more), comparative tests should be performed to determine if there is a statistical bias between them, using competent statistical assistance. As a minimum, the test samples should be used that are as homogeneous as possible, that are drawn from the material from which the disparate test results were obtained, and that are randomly assigned in equal numbers to each laboratory for testing. Other materials with established test values may be used for this purpose. The test results from the two laboratories should be compared using a statistical test for unpaired data, at a probability level chosen prior to the testing series. If a bias is found, either its cause must be found and corrected, or future test results must be adjusted in consideration of the known bias.

6. Apparatus

6.1 *Apparatus*, as specified in AATCC Test Method 8.

6.2 *Smooth Cardboard Cards*, 50 by 200 mm (2 by 8 in.) approximating index card weight.

7. Sampling and Test Specimens

7.1 *Primary Sampling Unit*—Consider individual containers from each shipping carton to be the primary sampling units

7.2 *Laboratory Sampling Unit*—As a laboratory sampling unit, take at random one zipper from each primary sampling unit.

7.3 *Test Specimens*—Consider the laboratory sample as the test specimen.