



Designation: B937 – 15

Standard Specification for Copper-Beryllium Seamless Tube (UNS Nos. C17500 and C17510)¹

This standard is issued under the fixed designation B937; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification establishes the requirements for copper-beryllium alloy seamless tube in straight lengths. Copper-cobalt-beryllium alloy UNS No. C17500 and copper-nickel-beryllium alloy UNS No. C17510 will be the alloys furnished whenever this specification is specified.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 The following safety hazard caveat pertains only to the test method(s) described in this specification. *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and to determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 The following documents of the issue in effect on date of material purchase form a part of this specification to the extent referenced herein:

2.2 *ASTM Standards*:²

B193 Test Method for Resistivity of Electrical Conductor Materials

B194 Specification for Copper-Beryllium Alloy Plate, Sheet, Strip, and Rolled Bar

B251 Specification for General Requirements for Wrought Seamless Copper and Copper-Alloy Tube

B601 Classification for Temper Designations for Copper and Copper Alloys—Wrought and Cast

B846 Terminology for Copper and Copper Alloys

¹ This specification is under the jurisdiction of ASTM Committee B05 on Copper and Copper Alloys and is the direct responsibility of Subcommittee B05.04 on Pipe and Tube.

Current edition approved May 1, 2015. Published May 2015. Originally approved in 2004. Last previous edition approved in 2010 as B937 – 04 (2010). DOI: 10.1520/B0937-15.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

E8/E8M Test Methods for Tension Testing of Metallic Materials

E255 Practice for Sampling Copper and Copper Alloys for the Determination of Chemical Composition

E1004 Test Method for Determining Electrical Conductivity Using the Electromagnetic (Eddy-Current) Method

3. General Requirements

3.1 The following sections of Specification B251 (as noted) constitute a part of this specification:

3.1.1 Terminology,

3.1.2 Test Specimens,

3.1.3 Significance of Numerical Limits,

3.1.4 Inspection,

3.1.5 Rejection and Rehearing,

3.1.6 Certification,

3.1.7 Packaging and Package Marking, and

3.1.8 Mill Test Report.

4. Terminology

4.1 For definitions of terms related to copper and copper alloys, refer to Terminology B846.

4.2 *Definitions of Terms Specific to This Standard*:

4.2.1 *average diameter (for round tubes only), n*—the average of the maximum and minimum outside diameters, or maximum and minimum inside diameters, whichever is applicable, as determined at any one cross section of the tube.

4.2.2 *lengths, n*—straight pieces of the product

4.2.2.1 *ends, n*—straight pieces, shorter than the nominal length, left over after cutting the product into mill lengths, stock lengths, or specific lengths. They are subject to minimum length and maximum weight requirements.

4.2.2.2 *specific, adj*—straight lengths that are uniform in length, as specified, and subject to established length tolerances.

4.2.2.3 *specific with ends, adj*—specific lengths, including ends.

4.2.2.4 *stock, n*—straight lengths that are mill cut and stored in advance of orders. They are usually 8, 10, 12, or 20 ft (2.44, 3.05, 3.66, or 6.10 m) and subject to established length tolerances.

*A Summary of Changes section appears at the end of this standard

4.2.2.5 *stock with ends, adj*—stock lengths, including ends.

4.2.3 *tube, n*—a hollow product of round or any other cross section having a continuous periphery.

4.2.3.1 *tube, seamless, adj*—a tube produced with a continuous periphery in all stages of the operations.

5. Ordering Information

5.1 Include the following information in orders for product under this specification, as applicable:

- 5.1.1 ASTM designation and year of issue,
- 5.1.2 Copper Alloy UNS designation (1.1),
- 5.1.3 Temper (see Section 8),
- 5.1.4 Quantity, pounds or number of pieces,
- 5.1.5 Dimensions, including length if applicable. For tube or pipe specify either OD/ID, OD/wall, or ID/wall,
- 5.1.6 How furnished: stock lengths with or without ends, specific lengths with or without ends,
- 5.1.7 When product is purchased for ASME Boiler and Pressure Vessel Code Application, and
- 5.1.8 When product is purchased for agencies of the U.S. government,
- 5.1.9 Special tests or exceptions, if any,
- 5.1.10 Tensile strength test, if required,
- 5.1.11 Special marking or packaging, if required,
- 5.1.12 Inspection, if required (see Specification B251),
- 5.1.13 Certification (see Specification B251),
- 5.1.14 Mill test report, if required (see Specification B251).

5.2 When material is purchased for agencies of the U.S. government, the material shall conform to the Supplementary Requirements as defined in the current issue of Specification B251.

6. Materials and Manufacture

6.1 *Materials:*

6.1.1 The material of manufacture shall be UNS Alloy No. C17500 or C17510, cast and worked into tubular form, and of such purity and soundness as to be suitable for processing into the products prescribed herein.

6.1.2 The tube shall have heat traceable identity.

6.2 *Manufacture:*

6.2.1 The product shall be manufactured by a combination of hot working or cold working, or both; annealing; or

TABLE 1 Chemical Composition

Element	Concentration, %	
	Copper Alloy UNS No. C17500	Copper Alloy UNS No. C17510
Beryllium	0.4-0.7	0.2-0.6
Cobalt	2.4-2.7	0.3 max
Nickel	...	1.4-2.2
Iron, max	0.10	0.10
Aluminum, max	0.20	0.20
Silicon, max	0.20	0.20
Copper	Remainder	Remainder

precipitation heat treatment, or both, as to produce a uniform wrought structure in the finished product, to meet the temper specified.

7. Chemical Composition

7.1 The material shall conform to the chemical composition requirements in Table 1 for the copper alloy designated in the ordering information.

7.2 These composition limits do not preclude the presence of other elements. By agreement between the manufacturer and purchaser, limits may be established and analysis required for unnamed elements

7.3 For alloys in which copper is listed as “Remainder,” copper is the difference between the sum of results of all elements determined and 100 %. When all elements in Table 1 are determined, the sum of results shall be 99.5 % min.

8. Temper

8.1 Tempers, as described in Classification B601, available under this specification are: TB00 (solution treated (A)), TF00 (precipitation hardened (AT)), TD04 (solution heat-treated and cold worked: hard (H)), and TH04 (hard and precipitation heat-treated (HT)). These products meet property requirements in Table 2.

9. Precipitation Heat Treatment

9.1 When material is purchased in the TB00 (A) or the TD04 (H) tempers, the precipitation heat treatment is performed by the purchaser.

TABLE 2 Tensile Strength and Rockwell Hardness Requirements^A

Temper Designation		As Supplied				
Standard	Former	Tensile Strength ksi ^B (MPa ^C)	Yield Strength ksi (MPa) min	Rockwell Hardness, B Scale	Elongation min, %	Electrical Conductivity IACS min, %
TB00	A	35-55 (240-380)		50 max		20
TD04	H	65-80 (450-550)		60-80		20
After Precipitation Heat Treatment						
TF00	AT	100-130 (690-895) ^D	80 (550)	92-100	10	45
TH04	HT	110-140 (760-965) ^D		95-102		48

^A These values apply to mill products. See Section 11 for exceptions in end products.

^B ksi = 1000 psi.

^C See Appendix.

^D The upper limits in the tensile strength column are for design guidance only.