



Designation: **B62—09 B62 – 15**

## Standard Specification for Composition Bronze or Ounce Metal Castings<sup>1</sup>

This standard is issued under the fixed designation B62; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the U.S. Department of Defense.*

### 1. Scope\*

1.1 This specification<sup>2</sup> establishes requirements for an alloy having a composition of copper, tin, lead, and zinc, used for component castings of valves, flanges, and fittings. The common trade name of this alloy is 85-5-5; the correct identification is Copper Alloy UNS No. C83600.<sup>3</sup>

1.2 The castings covered are used in products that may be manufactured in advance and supplied from stock from the manufacturer or other dealer.

1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

### 2. Referenced Documents

2.1 *ASTM Standards*:<sup>4</sup>

[B208 Practice for Preparing Tension Test Specimens for Copper Alloy Sand, Permanent Mold, Centrifugal, and Continuous Castings](#)

[B824 Specification for General Requirements for Copper Alloy Castings](#)

[E527 Practice for Numbering Metals and Alloys in the Unified Numbering System \(UNS\)](#)

2.2 *MSS Standards*:<sup>5</sup>

[SP-25 Standard Marking System for Valves, Fittings, Flanges and Unions](#)

### 3. General Requirements

3.1 The following sections of Specification [B824](#) form a part of this specification. In the event of a conflict between this specification and Specification [B824](#), the requirements of this specification shall take precedence.

3.1.1 Terminology (Section 3),

3.1.2 Other Requirements (Section 7),

3.1.3 Dimensions, Mass, and Permissible Variations (Section 8),

3.1.4 Workmanship, Finish, and Appearance (Section 9),

3.1.5 Sampling (Section 10),

3.1.6 Number of Tests and Retests (Sections 11 and 13),

3.1.7 Specimen Preparation (Section 12),

3.1.8 Test Methods (Section 13),

3.1.9 Significance of Numerical Limits (Section 14),

3.1.10 Inspection (Section 15),

3.1.11 Rejection and Rehearing (Section 16),

<sup>1</sup> This practice is under the jurisdiction of ASTM Committee [B05](#) on Copper and Copper Alloys and is the direct responsibility of Subcommittee [B05.05](#) on Castings and Ingots for Remelting.

Current edition approved ~~April 1, 2009~~ ~~May 1, 2015~~ ~~May 2009~~ ~~May 2015~~. Originally approved in 1926. ~~Discontinued June 2002 and reinstated as B62—02.~~ Last previous edition approved in ~~2002~~ ~~2009~~ as ~~B62—02~~ ~~B62 – 09~~. DOI: ~~10.1520/B0062-09~~ ~~10.1520/B0062-15~~.

<sup>2</sup> For *ASME Boiler and Pressure Vessel Code* applications see related Specification SB-61 of that Code.

<sup>3</sup> The UNS system for copper and copper alloys (see Practice [E527](#)) is a simple expansion of the former standard designation system accomplished by the addition of a prefix “C” and a suffix “00”. The suffix can be used to accommodate composition variations of the base alloy.

<sup>4</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards*, ~~Standards Vol 02.01~~ volume information, refer to the standard’s Document Summary page on the ASTM website.

<sup>5</sup> Available from Manufacturers Standardization Society (MSS) of the Valve and Fittings Industry, 127 Park ~~Street~~ ~~St.~~, NE, Vienna, VA ~~22180-4602~~ ~~22180-4602~~, <http://www.msshq.org>.

\*A Summary of Changes section appears at the end of this standard

- 3.1.12 Certification (Section 17),
- 3.1.13 Test Report (Section 18),
- 3.1.14 Product Marking (Section 19), and
- 3.1.15 Packaging and Package Marking (Section 20)

#### 4. Terminology

4.1 For definitions of terms relating to copper and copper alloys, refer to Terminology B846.

#### 5. Ordering Information

5.1 Include the following information when placing orders for castings under this specification:

- 5.1.1 Quantity of castings required,
- 5.1.2 Copper Alloy UNS No. (Table 1),
- 5.1.3 Specification title, number, and year of issue,
- 5.1.4 Pattern or drawing number and condition (as-cast, machined),
- ~~5.1.5 Chemical analysis of residual elements, if specified in the purchase order (Specification B824),~~
- 5.1.5 Pressure test requirements, if specified in the purchase order (Specification B824),
- 5.1.6 Soundness requirements, if specified in the purchase order (Specification B824),
- 5.1.7 Certification, if specified in the purchase order (Specification B824),
- 5.1.8 Foundry test report, if specified in the purchase order (Specification B824),
- 5.1.9 Witness inspection, if specified in the purchase order (Specification B824),
- 5.1.10 ASME Boiler and Pressure Vessel application (Section 10), and
- 5.1.11 Product marking, if specified in the purchase order (Specification B824 and Section 11).

5.2 When material is purchased for agencies of the U.S. Government, specify the Supplementary Requirements in Specification B824.

#### 6. Chemical Composition

6.1 The alloy shall conform to the requirements specified in Table 1.

6.2 These specification limits do not preclude the presence of other elements. Limits may be established for unnamed elements by agreement between manufacturer or supplier and purchaser. Copper or zinc may be given as remainder and may be taken as the difference between the sum of all elements analyzed and 100 %. When all named elements in Table 1 are analyzed, their sum shall be as follows:

Copper Plus Named Elements, 99.3 % Minimum (1)

~~6.3 It is recognized that residual elements may be present in cast copper base alloys. Analysis shall be made for residual elements only when specified in the purchase order (Specification B824).~~

#### 7. Mechanical Property Requirements

7.1 Mechanical properties shall be determined from separately cast test bars and shall meet the requirements shown in Table 2.

**TABLE 1 Chemical Requirements Copper Alloy UNS No. C83600**

| Major-Elements          | Composition, % max<br>(Except as Indicated) |
|-------------------------|---|
| Copper                  | 84.0–86.0                                   |
| Tin                     | 4.0–6.0                                     |
| Lead                    | 4.0–6.0                                     |
| Zinc                    | 4.0–6.0                                     |
| Nickel incl Cobalt      | 1.0 <sup>A</sup>                            |
| Nickel including Cobalt | 1.0 <sup>A</sup>                            |
| Residual-Elements       | Composition, % max<br>(Except as Indicated) |
| Iron                    | 0.30  |
| Antimony                | 0.25  |
| Sulfur                  | 0.08  |
| Phosphorus <sup>B</sup> | 0.05  |
| Aluminum                | 0.005                                       |
| Silicon                 | 0.005                                       |

<sup>A</sup> In determining copper minimum, copper may be calculated as copper plus nickel.

<sup>B</sup> For continuous castings, Phosphorus shall be 1.5 % max.