



Designation: **C660 – 81 (Reapproved 2010) C660 – 81 (Reapproved 2015)**

Standard Practices for Production and Preparation of Gray Iron Castings for Porcelain Enameling¹

This standard is issued under the fixed designation C660; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

INTRODUCTION

Porcelain-enameled gray iron is a composite of a vitreous or glassy inorganic coating, bonded to a casting by fusion at temperatures above 800 °F (425 °C). Porcelain enamels are a family of coatings available in a wide variety of compositions and properties, but all are characterized by their glass-like nature. Selection of an appropriate porcelain enamel must be made on the basis of the end-use requirements. Certain casting design features and processing considerations can facilitate the application and efficient use of the selected enamel.

Two general types of enamels are available for use on cast iron. These are commonly referred to as wet-process and dry-process enamels (see Terminology **C286**). In wet-process enameling, a slurry of wet-ground materials is dipped or sprayed on the casting, the water removed by drying, and the coating matured by heating in a furnace for sufficient time to bring about fusion of the glassy particles. In dry-process enameling, dry-powdered glassy material is applied by dusting onto a redhot casting that has been ground-coated by the wet process prior to firing. The partially matured dusted coating is returned to the furnace to complete the fusion process. In general, wet-process enamels are thinner over-all than dry-process enamels.

1. Scope

1.1 These practices are intended to indicate certain casting characteristics and pre-enameling practices which will facilitate finishing by the wet- or dry-process methods of porcelain enameling. All of the listed recommendations are based on experiences with gray iron casting and enameling.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

A48/A48M Specification for Gray Iron Castings

A74 Specification for Cast Iron Soil Pipe and Fittings

A126 Specification for Gray Iron Castings for Valves, Flanges, and Pipe Fittings

A278/A278M Specification for Gray Iron Castings for Pressure-Containing Parts for Temperatures Up to 650°F (350°C)

C286 Terminology Relating to Porcelain Enamel and Ceramic-Metal Systems

¹ These practices are under the jurisdiction of ASTM Committee **B08** on Metallic and Inorganic Coatings and are the direct responsibility of Subcommittee **B08.12** on Materials for Porcelain Enamel and Ceramic-Metal Systems.

Current edition approved ~~April 1, 2010~~ May 1, 2015. Published ~~June 2010~~ June 2015. Originally approved in 1970. Last previous edition approved in 2005 ~~2010~~ as C660 – 81 – (2005) – (2010). DOI: ~~10.1520/C0660-81R10~~ 10.1520/C0660-81R15.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.