



Designation: ~~B 211-99~~ Designation: B 211 - 00

Standard Specification for Aluminum and Aluminum-Alloy Bar, Rod, and Wire¹

This standard is issued under the fixed designation B 211; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope*

1.1 This specification² covers rolled or cold-finished bar, rod, and wire in alloys (Note 1) and tempers as shown in ~~Table 1~~ Table 2.

NOTE 1—Throughout this specification use of the term *alloy* in the general sense includes aluminum as well as aluminum alloy.

NOTE 2—The term *cold finished* is used to indicate the type of surface finish, sharpness of angles, and dimensional tolerances produced by drawing through a die.

NOTE 3—See Specification B 221 for aluminum and aluminum-alloy extruded bars, rods, wire, shapes, and tubes; and Specification B 316 for aluminum and aluminum-alloy rivet and cold-heading wire and rods.

1.2 Alloy and temper designations are in accordance with ANSI H35.1. The equivalent UNS alloy designations are those of ~~Table 2~~ Table 1 preceded by A9, for example, A91100 for aluminum 1100 in accordance with Practice E 527E 527.

1.3 A complete metric companion to Specification B 211 has been developed—B 211M; therefore, no metric equivalents are presented in this specification.

1.4 For acceptance criteria for inclusion of new aluminum and aluminum alloys in this specification, see Annex A2.

2. Referenced Documents

2.1 The following documents of the issue in effect on date of material purchase form a part of this specification to the extent referenced herein:

2.2 *ASTM Standards:*

B 557 Test Methods of Tension Testing Wrought and Cast Aluminum- and Magnesium-Alloy Products³

B 594 Practice for Ultrasonic Inspection of Aluminum-Alloy Wrought Products for Aerospace Applications³

B 597 Practice for Heat Treatment of Aluminum Alloys³

B 660 Practices for Packaging/Packing of Aluminum and Magnesium Products³

B 666/B 666M Practice for Identification Marking of Aluminum Products³

E 29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications⁴ ~~sum-b211-00~~

E 34 Test Methods for Chemical Analysis of Aluminum and Aluminum-Base Alloys⁵

E 55 Practice for Sampling Wrought Nonferrous Metals and Alloys for Determination of Chemical Composition⁵

E 227 Test Method for Optical Emission Spectrometric Analysis of Aluminum and Aluminum Alloys by the Point-to-Plane Technique⁵

E 290 Test Methods for Bend Testing of Material for Ductility⁶

E 527 Practice for Numbering Metals and Alloys (UNS)⁷

E 607 Test Method for Optical Emission Spectrometric Analysis of Aluminum and Aluminum Alloys by the Point-to-Plane Technique, Nitrogen Atmosphere⁸

E 716 Practices for Sampling Aluminum and Aluminum Alloys for Spectrochemical Analysis⁸

E 1004 Test Method for Electromagnetic (Eddy-Current) Measurements of Electrical Conductivity⁹

¹ This specification is under the jurisdiction of ASTM Committee ~~B-7~~ B07 on Light Metals and Alloys and is the direct responsibility of Subcommittee B07.03 on Aluminum-Alloy Wrought Products.

Current edition approved May 10, ~~1999~~ 2000. Published ~~September 1999~~ August 2000. Originally published as B 211-46T. Last previous edition ~~B 211-95a~~ B 211-99.

² For ASME Boiler and Pressure Vessel Code applications see related Specification SB-211 in Section II of that Code.

³ *Annual Book of ASTM Standards*, Vol 02.02.

⁴ *Annual Book of ASTM Standards*, Vol 14.02.

⁵ *Annual Book of ASTM Standards*, Vol 03.05.

⁶ *Annual Book of ASTM Standards*, Vol 03.01.

⁷ *Annual Book of ASTM Standards*, Vol 01.01.

⁸ *Annual Book of ASTM Standards*, Vol 03.06.

⁹ *Annual Book of ASTM Standards*, Vol 03.03.

*A Summary of Changes section appears at the end of this standard.

E 1251 Test Method for Optical Emission Spectrometric Analysis of Aluminum and Aluminum Alloys by the Argon Atmosphere, Point-to-Plane, Unipolar Self Initiating Capacitor Discharge⁸

G 47 Test Method for Determining Susceptibility to Stress-Corrosion Cracking of 2XXX and 7XXX Aluminum-Alloy Products¹⁰

2.3 *ANSI Standards:*

H35.1 Alloy and Temper Designation Systems for Aluminum³

H35.2 Dimensional Tolerances for Aluminum Mill Products³

2.4 *Federal Standard:*

Fed. Std. No. 123 Marking for Shipment (Civil Agencies)¹¹

2.5 *Military Standard:*

MIL-STD-129 Marking for Shipment and Storage¹¹

TABLE 1 Chemical Composition Limits^{A,B,C}

Alloy	Silicon	Iron	Copper	Manganese	Magnesium	Chromium	Zinc	Bismuth	Lead	Titanium	Other Elements ^D		Aluminum
											Each	Total ^E	
1060	0.25	0.35	0.05	0.03	0.03	...	0.05	0.03	0.03 ^F	...	99.60 min ^G
1100	0.95 Si + Fe		0.05–0.20	0.05	0.10	0.05	0.15	99.00 min ^G
2011	0.40	0.7	5.0–6.0	0.30	0.20–0.6	0.20–0.6	...	0.05	0.15	remainder
2014	0.50–1.2	0.7	3.9–5.0	0.40–1.2	0.20–0.8	0.10	0.25	0.15	0.05	0.15	remainder
2017	0.20–0.8	0.7	3.5–4.5	0.40–1.0	0.40–0.8	0.10	0.25	0.15	0.05	0.15	remainder
2024	0.50	0.50	3.8–4.9	0.30–0.9	1.2–1.8	0.10	0.25	0.15	0.05	0.15	remainder
2219	0.20	0.30	5.8–6.8	0.20–0.40	0.02	...	0.10	0.02–0.10	0.05 ^H	0.15 ^H	remainder
3003	0.6	0.7	0.05–0.20	1.0–1.5	0.10	0.05	0.15	remainder
5052	0.25	0.40	0.10	0.10	2.2–2.8	0.15–0.35	0.10	0.05	0.15	remainder
5056	0.30	0.40	0.10	0.05–0.20	4.5–5.6	0.05–0.20	0.10	0.05	0.15	remainder
Alclad 5056	5056 alloy clad with 6253 alloy			
5154	0.25	0.40	0.10	0.10	3.1–3.9	0.15–0.35	0.20	0.20	0.05	0.15	remainder
6061	0.40–0.8	0.7	0.15–0.40	0.15	0.8–1.2	0.04–0.35	0.25	0.15	0.05	0.15	remainder
6110	0.7–1.5	0.8	0.20–0.7	0.20–0.7	0.50–1.1	0.04–0.25	0.30	0.15	0.05	0.15	remainder
6253 ^J		0.50	0.10	...	1.0–1.5	0.04–0.35	1.6–2.4	0.05	0.15	remainder
6262	0.40–0.8	0.7	0.15–0.40	0.15	0.8–1.2	0.04–0.14	0.25	0.40–0.7	0.40–0.7	0.15	0.05	0.15	remainder
7075	0.40	0.50	1.2–2.0	0.30	2.1–2.9	0.18–0.28	5.1–6.1	0.20	0.05	0.15	remainder

^A Limits are in mass percent maximum unless otherwise shown.

^B Analysis shall be made for the elements for which limits are shown in this table.

^C For purposes of determining conformance to these limits, an observed value or a calculated value obtained from analysis shall be rounded to the nearest unit in the last right-hand place of figures used in expressing the specified limit, in accordance with the rounding-off method of Practice E 29E 29.

^D *Others* includes listed elements for which no specific limit is shown as well as unlisted metallic elements. The producer may analyze samples for trace elements not specified in the specification. However, such analysis is not required and may not cover all metallic *Others* elements. Should any analysis by the producer or the purchaser establish that an *Others* element exceeds the limit of *Each* or that the aggregate of several *Others* elements exceeds the limit of *Total*, the material shall be considered non-conforming.

^E *Other elements*—Total shall be the sum of unspecified metallic elements 0.010 % or more each, rounded to the second decimal before determining the sum.

^F Vanadium 0.05 % max.

^G The aluminum content is the difference between 100.00 % and the sum of all other metallic elements and silicon present in amounts of 0.010 % or more each, rounded to the second decimal before determining the sum.

^H Vanadium 0.05–0.15 % zirconium 0.10–0.25 %. The total for other elements does not include vanadium and zirconium.

^I Composition of cladding alloy as applied during the course of manufacture. Samples from finished wire shall not be required to conform to these limits.

^J 45 to 65 % of actual magnesium content.

2.6 *Aerospace Material Specification:*

AMS-H-6088 Heat Treatment of Aluminum Alloys¹²

3. Terminology

3.1 *Definitions:* Definitions:

3.1.1 *alclad wire*—wire having on its surface a metallurgically bonded aluminum or aluminum-alloy coating that is anodic to the core alloy to which it is bonded, thus electrolytically protecting the core alloy against corrosion.

3.1.2 *bar*—a solid product that is long in relation to cross section which is square or rectangular (excluding plate and flattened wire) with sharp or rounded corners or edges, or is a regular hexagon or octagon, and in which at least one perpendicular distance between parallel faces is 0.375 in. or greater.

¹⁰ Annual Book of ASTM Standards, Vol 03.02.

¹¹ This specification is under the jurisdiction of ASTM Committee B07 on Light Metals and Alloys and is the direct responsibility of Subcommittee B07.03 on Aluminum-Alloy Wrought Products.

Current edition approved May 10, 2000. Published August 2000. Originally published as B 211–46T. Last previous edition B 211–99.

¹² Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

3.1.3 *cold-finished bar*—bar brought to final dimensions by cold working to obtain improved surface finish and dimensional tolerances.

3.1.4 *cold-finished rod*—rod brought to final dimensions by cold working to obtain improved surface finish and dimensional tolerances.

3.1.5 *drawn wire*—wire brought to final dimensions by drawing through a die.

3.1.6 *flattened and slit wire*—flattened wire which has been slit to obtain square edges.

3.1.7 *flattened wire*—a solid section having two parallel flat surfaces and rounded edges produced by roll-flattening round wire.

3.1.8 *producer*—the primary manufacturer of the material.

3.1.9 *rod*—a solid product 0.375 in. or greater in diameter that is long in relation to cross section.

3.1.10 *supplier*—includes only the category of jobbers and distributors as distinct from producers.

3.1.11 *wire*—a solid section long in relation to its cross-sectional dimensions, having a cross section that is round, hexagonal, or octagonal and whose diameter, width, or greatest distance between parallel faces is less than 0.375 in., or having a symmetrical cross section that is square or rectangular (excluding flattened wire) with sharp or rounded corners or edges.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *capable of*—The term *capable of* as used in this specification means that the test need not be performed by the producer of the material. However, should subsequent testing by the purchaser establish that the material does not meet these requirements, the material shall be subject to rejection.

4. Ordering Information

4.1 Orders for material to this specification shall include the following information:

4.1.1 This specification designation (which includes the number, the year, and the revision letter, if applicable),

4.1.2 Quantity in pieces or pounds,

4.1.3 Alloy (Section 7),

4.1.4 Temper (Section 9),

4.1.5 *Product Form*—Rolled or cold finished bar, rolled or cold finished rod, or wire,

4.1.6 *Geometry and Dimensions*—Diameter for rounds; distance across flats for square-cornered squares, hexagons, or octagons; width and depth for square-cornered rectangles (orders for squares, hexagons, octagons, or rectangles with rounded corners usually require a drawing),

4.1.7 Length,

4.1.8 Tensile property limits and dimensional tolerances for sizes not covered in Table 1—Table 2 and in ANSI H35.2, respectively.

4.2 Additionally, orders for material to this specification shall include the following information when required by the purchaser:

4.2.1 Whether heat treatment in accordance with Practice B 597B 597 is required (8.2),

4.2.2 Whether 7075-O material is required to develop requirements for T73 temper (see 10.1.2),

4.2.3 Whether bend testing is required for 2017, 2024, or 3003 (Section 12),

4.2.4 When specified finish of bar and rod is not required (Section 16),

4.2.5 Whether marking for identification is required (Section 17),

4.2.6 Whether ultrasonic inspection is required (Section 18, Table 3),

4.2.7 Whether inspection or witness of inspection and tests by the purchaser's representative is required prior to material shipment (Section 20),

4.2.8 Whether certification is required (Section 22), and

4.2.9 Whether Practices B 660B 660 apply, and if so, the levels of preservation, packaging, and packing required (Section 23).

5. Manufacture

5.1 The products covered by this specification shall be produced either by hot extruding and cold finishing or by hot rolling with or without cold finishing, at the option of the producer.

6. Quality Assurance

6.1 *Responsibility for Inspection and Tests*—Unless otherwise specified in the contract or purchase order, the producer is responsible for the performance of all inspection and test requirements specified herein. The producer may use his own or any other suitable facilities for the performance of the inspection and test requirements specified herein, unless disapproved by the purchaser in the order or at the time of contract signing. The purchaser shall have the right to perform any of the inspections and tests set forth in this specification where such inspections are deemed necessary to ensure that material conforms to prescribed requirements.

6.2 *Lot Definition*—An inspection lot shall be defined as follows:

6.2.1 For heat-treated tempers, an inspection lot shall consist of an identifiable quantity of material of the same mill form, alloy, temper, and nominal dimensions traceable to a heat-treat lot or lots, and subjected to inspection at one time.

6.2.2 For nonheat-treated tempers, an inspection lot shall consist of an identifiable quantity of material of the same mill form,

alloy, temper, and nominal dimensions subjected to inspection at one time.

5.1 The products covered by this specification shall be produced either by hot extruding and cold finishing or by hot rolling with or without cold finishing, at the option of the producer.

TABLE 2 Mechanical Property Limits^A

Temper	Specified Diameter or Thickness, in.	Tensile Strength, ksi		Yield Strength ^B (0.2 % offset), min, ksi	Elonga- tion ^B in 2 in. or 4 × Diam- eter, min, %
		min	max		
Aluminum 1060					
O	0.124 and under	8.0
	0.125 and over	8.0	...	2.5	25
H14	0.374 and under	12.0	...	10.0	...
H18	0.374 and under	16.0	...	13.0	...
Aluminum 1100					
O	0.124 and under	11.0	15.5
	0.125 and over	11.0	15.5	3.0	25
H12	0.374 and under	14.0
H14	0.374 and under	16.0
H16	0.374 and under	19.0
H18	0.374 and under	22.0
H112	all	11.0	...	3.0	...
F	all	^C	...	^C	...
Alloy 2011					
T3	0.125–1.500	45.0	...	38.0	10
	1.501–2.000	43.0	...	34.0	12
	2.001–3.500	42.0	...	30.0	12
T4 and T451 ^D	0.125–8.000	40.0	...	18.0	16
T8	0.125–3.250	54.0	...	40.0	10
Alloy 2014 ^E					
O	0.124 and under	...	35.0
	0.125–8.000	...	35.0	...	12
T4, T42 ^F , and T451 ^D	0.124 and under	55.0
	0.125–8.000 ^G	55.0	...	32.0	16
T6, T62 ^F , and T651 ^D	0.124 and under	65.0
	0.125–8.000 ^G	65.0	...	55.0	8
Alloy 2017 ^E					
O	0.124 and under	...	35.0
	0.125–8.000	...	35.0	...	16
T4, T42 ^F , and T451 ^D	0.124 and under	55.0
	0.125–8.000 ^H	55.0	...	32.0	12
Alloy 2024 ^E					
O	0.124 and under	...	35.0
	0.125–8.000	...	35.0	...	16
T36	0.124 and under	69.0
	0.125–0.375	69.0	...	52.0	10
T4 ^I	0.124 and under	62.0
	0.125–0.499	62.0	...	45.0 ^I	10
	0.500–4.500 ^G	62.0	...	42.0 ^I	10
	4.501–6.500 ^J	62.0	...	40.0	10
	6.501–8.000 ^J	58.0	...	38.0	10
T42 ^F	0.124 and under	62.0
	0.125–1.000	62.0	37.0	...	40.0
	1.001–6.500 ^G	62.0	...	40.0	10
T351 ^D	0.500–6.500 ^G	62.0	...	45.0	10
T6	0.124 and under	62.0
	0.125–6.500 ^G	62.0	...	50.0	5
T62 ^F	0.124 and under	60.0
	0.125–6.500 ^G	60.0	...	46.0	5
T851 ^D	0.500–6.500 ^G	66.0	...	58.0	5
Alloy 2219					
T851 ^D	0.500–2.000	58.0	...	40.0	4
	2.001–4.000	57.0	...	39.0	4
Alloy 3003					
O	all	14.0	19.0	5.0	25
H12	0.374 and under	17.0
H14	0.374 and under	20.0

TABLE *Continued*

Temper	Specified Diameter or Thickness, in.	Tensile Strength, ksi		Yield Strength ^B (0.2 % offset), min, ksi	Elonga- tion ^E in 2 in. or 4 × Diam- eter, min, %
		min	max		
H16	0.374 and under	24.0
H18	0.374 and under	27.0
H112	all	14.0	...	5.0	...
F	all	^C	...	^C	...
Alloy 5052					
O	0.124 and under	...	32.0
	0.125 and over	25.0	32.0	9.5	25
H32	0.124 and under	31.0
	0.125–0.374	31.0	...	23.0	...
H34	0.374 and under	34.0	...	26.0	...
H36	0.124 and under	37.0
	0.125–0.374	37.0	...	29.0	...
H38	0.374 and under	39.0
F	all	^C	...	^C	...
Alloy 5056					
O	0.124 and under	...	46.0
	0.125 and over	...	46.0	...	20
H111	0.374 and under	44.0
H12	0.374 and under	46.0
H32	0.374 and under	44.0
H14	0.374 and under	52.0
H34	0.374 and under	50.0
H18	0.374 and under	58.0
H38	0.374 and under	55.0
H192	0.374 and under	60.0
H392	0.374 and under	58.0
Alclad Alloy 5056					
H192	0.374 and under	52.0
H392	0.374 and under	50.0
H393	0.120–0.192	54.0	...	47.0	...
Alloy 5154					
O	all	30.0	41.0	11.0	25
H32	0.374 and under	36.0
H34	0.374 and under	39.0
H36	0.374 and under	42.0
H38	0.374 and under	45.0
H112	all	30.0	...	11.0	...
Alloy 6061 ^E					
O	0.124 and under	...	22.0
	0.125–8.000	...	22.0	...	18
T4 and T451 ^D	0.124 and under	30.0
	0.125–8.000 ^H	30.0	...	16.0	18
T42 ^F	0.125–8.000 ^H	30.0	...	14.0	18
T6, T62 ^F , and T651 ^D	0.124 and under	42.0
	0.125–8.000 ^H	42.0	...	35.0	10
T89 and T94	0.374 and under	54.0	...	47.0	...
Alloy 6110					
T9	0.374 and under	65.0	...	63.0	2
Alloy 6262					
T6 and T651 ^D	0.125–8.000 ^G	42.0	...	35.0	10
T9	0.125–2.000	52.0	...	48.0	5
	2.001–3.000	50.0	...	46.0	5
Alloy 7075 ^E					
O	0.124 and under	...	40.0
	0.125–8.000	...	40.0	...	10
T6, T62	0.124 and under	77.0	...	66.0	...
	0.125–4.000 ^K	77.0	...	66.0	7
T651	0.124 and under	77.0	...	66.0	...
	0.125–4.000 ^K	77.0	...	66.0	7
	4.001–6.000	75.0	...	64.0	7
	6.001–7.000	73.0	...	62.0	7
T73 and T7351 ^D	0.124 and under	68.0
	0.125–4.000	68.0	...	56.0	10

TABLE *Continued*

Temper	Specified Diameter or Thickness, in.	Tensile Strength, ksi		Yield Strength ^B (0.2 % offset), min, ksi	Elonga- tion ^B in 2 in. or 4 × Diam- eter, min, %
		min	max		
	4.001–5.000	66.0		55.0	8
Temper	Specified Diameter or Thickness, in.			Bend Diameter Factor, N	
Alloy 2017					
T4, T42, and T451		0.124 and under		3 ^L	
		0.125–8.000 ^H		6 ^L	
Alloy 2024					
O		0.124 and under		1	
T351, T4, T42		0.124 and under		3	
		0.125–6.500		6	
Alloy 3003					
O		all		0	
H12		0.374 and under		2	
H14		0.374 and under		2	
H16		0.374 and under		8	

^A To determine conformance to this specification, each value for tensile strength and for yield strength shall be rounded to the nearest 0.1 ksi and each value for elongation to the nearest 0.5 %, both in accordance with the rounding-off method of Practice E 29E 29. The basis for establishment of tensile property limits is shown in Annex A1.

^B The measurement of yield strength and elongation is not required for wire less than 0.125 in. in thickness or diameter.

^C There are no tensile requirements for material in the F temper but it usually can be expected that material 1½ in. or less in thickness or diameter (except sections over 4 in. in width) will have a strength about equivalent to the H14 or H34 temper. As size increases the strength decreases to nearly that of the O temper.

^D For stress-relieved tempers, characteristics and properties other than those specified may differ somewhat from the corresponding characteristics and properties of material in the basic tempers.

^E Also available in the F temper for which no properties are specified and no tension tests are performed but for which tests are performed for confirmation of heat-treat response as required by Section 10.

^F Material in the T42 or T62 tempers is not available from the materials producers. These properties can usually be obtained by the user when material is properly solution heat treated or solution and precipitation heat treated from the O or F temper. These properties also apply to samples of material in the O or F temper that are solution heat treated or solution and precipitation heat treated by the producer to determine that the material will respond to proper heat treatment. Properties attained by the user, however, may be lower than those listed if the material has been formed or otherwise cold or hot worked, particularly in the O temper, prior to solution heat treatment.

^G Properties listed for this full size increment are applicable to rod. Properties listed are also applicable to square, rectangular, hexagonal, or octagonal bar having a maximum thickness of 4 in. and a maximum cross-sectional area of 36 in.².

^H For bar, maximum cross-sectional area is 50 in.².

^I Minimum yield strength of coiled 2024 T4 wire and rod 0.125 in. and larger in thickness or diameter is 40.0 ksi. Minimum yield strength for 2024-T4 wire and rod 0.125 in. and larger in thickness or diameter, produced in coil form for both straight length and coiled products, is 40.0 ksi.

^J Properties listed for this size increment are applicable to rod only.

^K For rounds, maximum diameter is 4 in.; for square, hexagonal, or octagonal bar, maximum thickness is 3½ in.; for rectangular bar, maximum thickness is 3 in. with corresponding maximum width of 6 in.; for rectangular bar less than 3 in. in thickness, maximum width is 10 in.

^L Bend diameter factor values stated for this full size increment apply to T4 product only. Values listed also apply to T451 product in the 0.500–8.000 in. size range.

6. Quality Assurance

6.1 Responsibility for Inspection and Tests—Unless otherwise specified in the contract or purchase order, the producer is responsible for the performance of all inspection and test requirements specified herein. The producer may use his own or any other suitable facilities for the performance of the inspection and test requirements specified herein, unless disapproved by the purchaser in the order or at the time of contract signing. The purchaser shall have the right to perform any of the inspections and tests set forth in this specification where such inspections are deemed necessary to ensure that material conforms to prescribed requirements.

6.2 Lot Definition—An inspection lot shall be defined as follows:

6.2.1 For heat-treated tempers, an inspection lot shall consist of an identifiable quantity of material of the same mill form, alloy, temper, and nominal dimensions traceable to a heat-treat lot or lots, and subjected to inspection at one time.

6.2.2 For nonheat-treated tempers, an inspection lot shall consist of an identifiable quantity of material of the same mill form, alloy, temper, and nominal dimensions subjected to inspection at one time.

7. Chemical Composition

7.1 Limits—The bars, rods, and wire shall conform to the chemical composition limits specified in Table 2Table 1. Conformance shall be determined by the producer by analyzing samples taken at the time the ingots are cast, or samples taken from the finished or semifinished product. If the producer has determined the chemical composition of the material during the course of manufacture, sampling and analysis of the finished product shall not be required.

NOTE 4—It is standard practice in the United States aluminum industry to determine conformance to the chemical composition limits prior to further processing of ingots into wrought products. Due to the continuous nature of the process, it is not practical to keep a specific ingot analysis identified with a specific quantity of finished material.

7.2 Number of Samples—The number of samples taken for determination of chemical composition shall be as follows: