



Designation: D7470 – 08 (Reapproved 2015)

# Standard Practice for Evaluating Elevated Temperature Performance of End- Jointed Lumber Studs<sup>1</sup>

This standard is issued under the fixed designation D7470; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This practice is to be used to evaluate the elevated temperature performance of end-jointed lumber studs.

1.2 A symmetric wall assembly containing end-jointed lumber studs is exposed to a standard fire exposure specified in Test Methods E119.

1.3 End-jointed lumber studs are deemed qualified if the wall assembly resists a standard fire exposure specified in Test Methods E119 for a period of 60 min or more. Qualification of end-jointed lumber studs are restricted to the joint configuration and adhesive tested.

1.4 This practice is used to evaluate the performance of end-jointed lumber studs to heat and flame under controlled conditions, but does not by itself incorporate all factors required for fire hazard or fire risk assessment under actual fire conditions.

1.5 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.

1.6 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

- C1396/C1396M Specification for Gypsum Board
- D4688 Test Method for Evaluating Structural Adhesives for Finger Jointing Lumber
- D6513 Practice for Calculating the Superimposed Load on

<sup>1</sup> This practice is under the jurisdiction of ASTM Committee D07 on Wood and is the direct responsibility of Subcommittee D07.02 on Lumber and Engineered Wood Products.

Current edition approved May 1, 2015. Published June 2015. Originally approved in 2008. Last previous edition approved in 2008 as D7470 – 08. DOI: 10.1520/D7470-08R15.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

Wood-frame Walls for Standard Fire-Resistance Tests  
E119 Test Methods for Fire Tests of Building Construction  
and Materials

F1667 Specification for Driven Fasteners: Nails, Spikes, and  
Staples

2.2 *Other Standards:*

NDS National Design Specification for Wood Construction<sup>3</sup>

## 3. Terminology

3.1 *Definitions:*

3.1.1 *end-jointed lumber*—Lumber containing one or more end-joints.

3.1.2 *end-joints*—a joint formed by bonding two pieces of lumber end-to-end, often by machining a set of interlocking “fingers” (finger-joint) into each end of adjoining pieces, using an adhesive to form an adhesive bonded joint.

3.1.3 *qualified agency*—an organization, hereafter referred to as the agency, that has trained personnel and procedures to ensure the grades comply with all applicable requirements of this practice. The agency shall have no financial interest in, nor shall be financially dependent upon, any single company manufacturing the product being inspected or tested; and shall not be owned, operated, or controlled by any such company.

## 4. Summary of Practice

4.1 This practice shall be used to evaluate end-jointed lumber studs manufactured with a specific joint configuration and adhesive. This practice is intended to be limited to the evaluation of end-jointed lumber studs with a specific joint configuration, adhesive, and limited design properties. The results are only applicable to end-jointed lumber studs using a joint configuration with the same number of fingers and a finger length of at least equal length as qualified in 7.1.2 and shall have assigned design properties no greater than the grade level qualified in 7.1.2.

## 5. Significance and Use

5.1 End-jointed lumber studs used in fire resistance-rated assemblies shall be able to support the superimposed design

<sup>3</sup> Available from American Wood Council (AWC), 1111 Nineteenth Street, NW, Suite 800, Washington, DC 20036, <http://www.awc.org>.