



**SLOVENSKI STANDARD**  
**SIST ISO 3671:1996**

**01-junij-1996**

---

**Polimerni materiali - Aminoplasti za oblikovanje - Določanje hlapnih komponent**

Plastics -- Aminoplastic moulding materials -- Determination of volatile matter

Matières plastiques -- Matière à mouler aminoplastes -- Détermination des matières volatiles

**(standards.iteh.ai)**

**Ta slovenski standard je istoveten z: ISO 3671:1976**

<https://standards.iteh.ai/catalog/standards/sist/5d505e0f-842d-4b0f-ba25-33f7d559cc16/sist-iso-3671-1996>

**ICS:**

83.080.10      Duromeri      Thermosetting materials

**SIST ISO 3671:1996**

**en**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST ISO 3671:1996](#)

<https://standards.iteh.ai/catalog/standards/sist/5d505e0f-842d-4b0f-ba25-33f7d559ccf6/sist-iso-3671-1996>

INTERNATIONAL STANDARD



3671

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

ISO 3671:1976

SIST ISO 3671:1996

ITeH STANDARD PREVIEW  
(standard.itteh.ai)

[https://standards.iteh.ai/catalog/standards/sist/5d50780f-842d-4b0f-ba25-33f7d559ccfb/sist-iso-3671-1976](https://standards.iteh.ai/catalog/standards/sist/5d50780f-842d-4b0f-ba25-33f7d559ccfb/sist/5d50780f-842d-4b0f-ba25-33f7d559ccfb/sist-iso-3671-1976)

# Plastics — Aminoplastic moulding materials — Determination of volatile matter

*Matières plastiques — Matières à mouler aminoplastes — Détermination des matières volatiles*

First edition — 1976-09-30

UDC 678.652 : 543.713

Ref. No. ISO 3671-1976 (E)

**Descriptors :** plastics, aminoplasts, moulding materials, chemical tests, determination, volatile matter.

Price based on 1 page

## FOREWORD

ISO (the International Organization for Standardization) is a worldwide federation of national standards institutes (ISO Member Bodies). The work of developing International Standards is carried out through ISO Technical Committees. Every Member Body interested in a subject for which a Technical Committee has been set up has the right to be represented on that Committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work.

Draft International Standards adopted by the Technical Committees are circulated to the Member Bodies for approval before their acceptance as International Standards by the ISO Council.

International Standard ISO 3671 was drawn up by Technical Committee ISO/TC 61, *Plastics*, and was circulated to the Member Bodies in February 1975.

It has been approved by the Member Bodies of the following countries :

Belgium	Ireland	Spain
Brazil	Israel	Sweden
Canada	Japan	Switzerland
Chile	Netherlands	Turkey
France	Poland	United Kingdom
Hungary	Portugal	U.S.A.
India	Romania	U.S.S.R.
Iran	South Africa, Rep. of	Yugoslavia

The Member Body of the following country expressed disapproval of the document on technical grounds :

Germany

# Plastics – Aminoplastic moulding materials – Determination of volatile matter

## 1 SCOPE AND FIELD OF APPLICATION

This International Standard specifies a method for the determination of volatile matter (predominantly water) in aminoplastic moulding materials, by drying in an oven.

## 2 APPARATUS

**2.1 Two wide-mouthed weighing bottles**, of internal diameter 45 mm and depth 35 mm, provided with tight-fitting covers.

**2.2 Well-ventilated oven**, capable of being controlled at  $55 \pm 1$  °C.

**2.3 Balance**, with an accuracy of 0,001 g.

## 3 STORAGE OF SAMPLE

Store the sample in an airtight container prior to testing, to prevent the loss or gain of water or other volatile matter.

## 4 PROCEDURE

Weigh  $5 \pm 0,1$  g of the sample to the nearest 0,001 g into a clean dried weighing bottle (2.1) and spread evenly over the bottom of the weighing bottle. Conduct the test in duplicate.

Place the bottles, with covers removed, in the oven (2.2), controlled at  $55 \pm 1$  °C. After a period of 3 h, close the

weighing bottles, remove from the oven and place in a desiccator at room temperature. After a period of at least 1 h, ease the covers of the weighing bottles to equalize pressure, and reweigh the bottles.

## 5 EXPRESSION OF RESULTS

The volatile matter is given, as a percentage by mass, by the formula

$$\frac{m_1}{m_0} \times 100$$

where

$m_0$  is the original mass of the test portion;

$m_1$  is the loss in mass of the test portion.

Calculate the arithmetic mean of the two determinations.

## 6 TEST REPORT

The test report shall include the following particulars :

- reference to this International Standard;
- complete identification of the product tested;
- the volatile matter content as the arithmetic mean of the two determinations;
- the individual results of the two determinations.