



Designation: D4563 – 02 (Reapproved 2008) D4563 – 02 (Reapproved 2015)

Standard Test Method for Determination by Atomic Absorption Spectroscopy of Titanium Dioxide Content of Pigments Recovered From Whole Paint¹

This standard is issued under the fixed designation D4563; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the atomic absorption (AA) analysis of titanium dioxide content in pigments recovered from whole paint. It is applicable to quality control situations where the same type of product is repeatedly analyzed.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This standard does not purport to address the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* Specific hazard statements are given in Section 7.

2. Referenced Documents

2.1 *ASTM Standards:*²

D1193 Specification for Reagent Water

D1394 Test Methods for Chemical Analysis of White Titanium Pigments

E180 Practice for Determining the Precision of ASTM Methods for Analysis and Testing of Industrial and Specialty Chemicals (Withdrawn 2009)³

E288 Specification for Laboratory Glass Volumetric Flasks

3. Summary of Test Method

3.1 The specimen is prepared for analysis by ashing at 450°C followed by digestion with sulfuric acid and ammonium sulfate as in Test Methods D1394. The titanium content is determined by atomic absorption spectroscopy using a specimen similar to that previously analyzed by the Aluminum Reduction Method in Test Methods D1394.

3.2 By utilizing the pigment analyzed in Test Methods D1394 as an atomic absorption standard, several hundred TiO₂ determinations can be made. The AA technique is much faster than the technique in Test Methods D1394 for multiple determinations and uses only acids. This keeps reagents and time to a minimum.

4. Significance and Use

4.1 This test method may be used in quality control laboratories when the repeated analysis of titanium dioxide in similar paints may be required. Reagents and time are kept to a minimum when this test method is used in place of wet chemical analysis such as in Test Methods D1394. However, reproducibility and repeatability are not as good as in Test Methods D1394.

5. Apparatus

5.1 *Atomic Absorption Spectrophotometer*, consisting of

5.1.1 Atomizer and nitrous oxide burner,

5.1.2 Gas-pressure regulator and metering devices for nitrous oxide and acetylene,

5.1.3 Titanium hollow cathode lamp with regulated constant-current supply,

¹ This test method is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.21 on Chemical Analysis of Paints and Paint Materials.

Current edition approved Feb. 1, 2008; June 1, 2015. Published February 2008. Originally approved in 1986. Last previous edition approved in 2002 as D4563 – 02: D4563 – 02 (2008). DOI: 10.1520/D4563-02R08.10.1520/D4563-02R15.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

- 5.1.4 Monochromator and associated optics,
- 5.1.5 Photosensitive detector connected to an electronic amplifier,
- 5.1.6 Readout device.
- 5.2 *Muffle Furnace*, capable of maintaining $450 \pm 25^{\circ}\text{C}$.
- 5.3 *Circulating Oven*, maintained at $105 \pm 2^{\circ}\text{C}$.
- 5.4 *Porcelain Dishes*, 90-mm diameter.
- 5.5 *Plastic Disposable Syringe*, 10-mL capacity.
- 5.6 *Agate Mortar and Pestle*, 95-mm outside diameter.
- 5.7 *Wide-Mouth Erlenmeyer Flask*, 500-mL capacity.
- 5.8 *Hot Plate*, with variable surface temperature control from 10°C above ambient to 370°C accurate to within $\pm 5^{\circ}\text{C}$.
- 5.9 *Burner*.
- 5.10 *Volumetric Flask*, 1000 mL, plastic (see Specification E288).
- 5.11 *Paint Shaker*.
- 5.12 *Weighing Bottles*, wide-mouth, with an external-fitting cap, and no larger than necessary for required amount of sample.
- 5.13 *Desiccator*.

6. Reagents

6.1 *Purity of Reagents*—Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents shall conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society, where such specifications are available.⁴ Other grades may be used, provided it is first ascertained that the reagent is of sufficient high purity to permit its use without reducing the accuracy of the determination.

6.2 *Purity of Water*—Unless otherwise indicated, references to water shall be understood to mean reagent water conforming to Type II of Specification D1193.

6.3 *Ammonium Hydroxide* (sp gr 0.90)—Concentrated ammonium hydroxide (NH_4OH).

6.4 *Ammonium Sulfate* ($\text{NH}_4)_2\text{SO}_4$).

6.5 *Hydrochloric Acid* (sp gr 1.19)—Concentrated hydrochloric acid (HCl).

6.6 *Hydrofluoric Acid* (HF)—Approximately 49 %.

6.7 *Standard Pigment Solution*.

6.7.1 Following the procedure in Section 9 recover the pigment from a paint that is similar to the unknown specimen. Analyze the extracted pigment for TiO_2 content in accordance with the Aluminum Reduction Method in Test Methods D1394 and record the percent TiO_2 found in the pigment.

6.7.2 Following the procedure in 12.1 – 12.5 take a specimen of the pigment extracted in 6.7.1 into solution. Store this solution for no more than 3 months in a plastic bottle marked with the percent TiO_2 as determined in 6.7.1.

6.8 *Sulfuric Acid* (sp gr 1.84), concentrated sulfuric acid (H_2SO_4).

6.9 *Toluene*.

7. Hazards

7.1 *Concentrated Hydrofluoric Acid*—Make certain to observe manufacturer's recommended precautions for handling.

7.2 **Warning**—Nitrous oxide and acetylene can cause explosions, if not used properly. See the supplier's manual of instructions for the atomic absorption instrument for proper operation with these gases.

8. Calibration and Standardization

8.1 Operational instructions for atomic absorption spectrophotometers vary with different models. Consult the manufacturer's literature for establishing optimum conditions for the specific instrument used.

8.2 Turn the instrument on and set the wavelength to the 365.3-nm titanium line. Apply the recommended current to the titanium hollow cathode lamp. Allow the instrument to warm up for about 15 min and set the proper slit width. Adjust the gas pressures and ignite the burner in accordance with instructions for using nitrous oxide and acetylene.

⁴ *Reagent Chemicals, American Chemical Society Specifications*, American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see *Analar Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeia and National Formulary*, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD.