



Designation: **C836/C836M—12 C836/C836M – 15**

# Standard Specification for High Solids Content, Cold Liquid-Applied Elastomeric Waterproofing Membrane for Use with Separate Wearing Course<sup>1</sup>

This standard is issued under the fixed designation C836/C836M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This specification describes the required properties and test methods for a cold liquid-applied elastomeric-type membrane, one- or two-component, for waterproofing building decks and walls subject to hydrostatic pressure in building areas to be occupied by personnel, vehicles, or equipment. This specification applies only to a membrane system that will be covered with a separate wearing course, traffic course, or backfill.

NOTE 1—See Guide **C898** and Guide **C1471** for proper application of membrane.

1.2 There are no ISO standards similar or equivalent to this ASTM standard.

1.3 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

**E717** Terminology of Building Seals and Sealants

**C794** Test Method for Adhesion-in-Peel of Elastomeric Joint Sealants

**C898** Guide for Use of High Solids Content, Cold Liquid-Applied Elastomeric Waterproofing Membrane with Separate Wearing Course

**E1250** Test Method for Nonvolatile Content of Cold Liquid-Applied Elastomeric Waterproofing Membranes (Withdrawn 2015)<sup>3</sup>

**C1305** Test Method for Crack Bridging Ability of Liquid-Applied Waterproofing Membrane

**C1375** Guide for Substrates Used in Testing Building Seals and Sealants

**C1471** Guide for the Use of High Solids Content Cold Liquid-Applied Elastomeric Waterproofing Membrane on Vertical Surfaces

**C1522** Test Method for Extensibility After Heat Aging of Cold Liquid-Applied Elastomeric Waterproofing Membranes

**D1079** Terminology Relating to Roofing and Waterproofing

**D2240** Test Method for Rubber Property—Durometer Hardness

**D6511** Test Methods for Solvent Bearing Bituminous Compounds

## 3. Terminology

3.1 *Definitions*—Refer to Terminology **E717**/**D1079** for definitions of the terms used in this specification.

## 4. Classification

4.1 *Types:*

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee **D08** on Roofing and Waterproofing and is the direct responsibility of Subcommittee **D08.22** on Waterproofing and Dampproofing Systems.

Current edition approved May 1, 2012; June 1, 2015. Published May 2012; June 2015. Originally approved in 1976. Last previous edition approved in 2011 as **C836/C836M—11**; **C836/C836M—12**. DOI: 10.1520/C0836-12.10.1520/C0836\_C0836M-15.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.



4.1.1 *Type I*—A one-component, cold liquid-applied waterproofing material suitable for immediate application after mixing. Type I products may be used with an accelerator that is beneficial but not essential for curing of the membrane.

4.1.2 *Type II*—A two-component, cold liquid-applied waterproofing material. Combining two components is essential for curing of the membrane.

## 5. Physical Requirements

5.1 *Material*—Membrane materials shall cure, after application by spreading or spraying, to form an elastomeric film capable of maintaining a seal against liquid water.

5.2 The physical, mechanical, and performance properties of the membrane shall conform to the requirements described in Table 1.

## 6. Test Methods

6.1 *Standard Conditions*—Standard conditions for all tests shall be  $23 \pm 2^\circ\text{C}$  [ $73.4 \pm 3.6^\circ\text{F}$ ] and  $50 \pm 5\%$  relative humidity.

6.2 *Conditioning/Mixing*:

6.2.1 Store all membrane materials to be tested in an unopened container at standard conditions for at least 24 h before any test specimens are prepared.

6.2.2 Follow the manufacturer's instructions for mixing and preparing membrane materials for testing. Thoroughly mix one-component samples before using. Mix two-component compounds in the ratio recommended by the manufacturer.

6.3 *Test Surfaces*—In addition to the mortar test surfaces specified, use other test surfaces when required by the specifier.

6.4 *Primer*—When required by the manufacturer, use a primer as directed by the manufacturer on all substrate materials in test assemblies.

6.5 *Hardness*:

6.5.1 Following the manufacturer's instructions, apply a film of membrane,  $1.5 \pm 0.1$  mm [ $60 \pm 5$  mils] thick, on a 100 by 150-mm [4 by 6-in.] piece of polyethylene film-coated paper and allow the membrane to cure for 14 days at standard conditions. If more than one application is required, the total time for film application shall not exceed 48 h.

6.5.2 After curing, strip the film from the coated paper, cut into pieces, and lay the pieces one upon another to provide a test specimen meeting the requirements of Test Method D2240.

6.5.3 Using a Type 00 hardness gauge, obtain an instantaneous reading of the film hardness as specified in Test Method D2240.

6.6 *Weight Loss*:

6.6.1 Test in compliance with the requirements of Test Method C1250/D6511<sup>A</sup>, Section 7; utilize a forced draft oven controlled to  $70 \pm 2^\circ\text{C}$  [ $158 \pm 3.6^\circ\text{F}$ ] for 72 hours. Remove the specimens from the oven and allow to cool at standard conditions for 30 minutes prior to weighing samples.

6.7 *Low-Temperature Crack Bridging*:

6.7.1 Test in compliance with the requirements of Test Method C1305.

6.8 *Film Thickness on Vertical Surface*:

6.8.1 Prepare mortar test blocks 152 by 76 by 25 mm [6 by 3 by 1 in.] as described in Guide C1375.

TABLE 1 High Solids Content, Cold Liquid-Applied Elastomeric Waterproofing Membrane Physical Requirements

Property	Requirement	Test Method <sup>A</sup>
Hardness, Type 00, min	50	D2240 as modified in section 6.5 of this specification
Hardness, Type 00, min	50	D2240 as modified in section 6.5
Weight loss, max, %	20	C1250
Weight loss, max, %	20	D6511 as modified in 6.6.1
Nonvolatile, min, %	80	
Low temperature crack bridging	no cracking	C1305
Film thickness (vertical surface), — min, mm [mils]	$1.5 \pm 0.1$ [60 $\pm$ 5]	See section 6.8 of this specification <sup>A</sup>
Film thickness (vertical surface), — min, mm [mils]	$1.5 \pm 0.1$ [60 $\pm$ 5]	See section 6.8
Adhesion-in-Peel after water immersion, N [lbf]	4.4 [1]	C794 as modified in section 6.9 of this specification
Adhesion-in-Peel after water immersion, N [lbf]	4.4 [1]	C794 as modified in section 6.9
Extensibility after heat aging, min, mm [in.]	6.4 [ $\frac{1}{4}$ ], no cracking	C1522
Stability, min, months	6	See section 6.11 of this specification.
Stability, min, months	6	See section 6.11

<sup>A</sup> Numbers refer to portions of the Test Methods section, Section 6, of this specification.