



Designation: **C1318 – 95 (Reapproved 2009)^{ε1} C1318 – 15**

Standard Test Method for Determination of Total Neutralizing Capability and Dissolved Calcium and Magnesium Oxide in Lime for Flue Gas Desulfurization (FGD)¹

This standard is issued under the fixed designation C1318; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

^{ε1} NOTE—A units statement was added editorially as new paragraph 1.4 and subsequent paragraphs were renumbered in June 2009.

1. Scope

1.1 This test method covers analysis of magnesian, dolomitic and high-calcium limes for total neutralizing capability and dissolved major oxides. Dissolved calcium and magnesium are the major species that neutralize acid under the conditions of the test.

1.2 The test conditions are chosen to measure the acid-neutralizing capacity of both calcium hydroxide and magnesium hydroxide contained in slaked lime. By controlling the neutralization pH at 6, magnesium hydroxide and magnesium oxide are titrated in addition to calcium hydroxide fraction.

1.3 This test method also determines the fraction of Mg ions present in the lime that will dissolve under lime flue gas desulfurization (FGD) conditions. Because the Mg⁺⁺ ion alters FGD performance, it is important to know its concentration.

1.4 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[C25 Test Methods for Chemical Analysis of Limestone, Quicklime, and Hydrated Lime](#)

[C50 Practice for Sampling, Sample Preparation, Packaging, and Marking of Lime and Limestone Products](#)

[C51 Terminology Relating to Lime and Limestone \(as used by the Industry\)](#)

[C110 Test Methods for Physical Testing of Quicklime, Hydrated Lime, and Limestone](#)

[C1301 Test Method for Major and Trace Elements in Limestone and Lime by Inductively Coupled Plasma-Atomic Emission Spectroscopy \(ICP\) and Atomic Absorption \(AA\)](#)

[E11 Specification for Woven Wire Test Sieve Cloth and Test Sieves](#)

3. Terminology

3.1 *Definitions*—Unless otherwise specified, for definitions of terms used in these test methods refer to Terminology [C51](#).

4. Summary of Test Method

4.1 Lime is slaked by boiling and is reacted with acid at a pH and residence time similar to those found in full-scale FGD reaction tanks.

4.2 A sample of lime is titrated with 1N hydrochloric acid, maintaining a pH of 6 for 30 min. After 30 min, the acid consumption is recorded. The total neutralizing capacity is calculated from the acid consumption and reported as CaO. Dissolved magnesium is determined by atomic absorption spectrometry or by EDTA titration and reported as percent dissolved Magnesium Oxide (as MgO).

¹ This test method is under the jurisdiction of ASTM Committee [C07](#) on Lime and Limestone and is the direct responsibility of Subcommittee [C07.05](#) on Chemical Tests. Current edition approved June 1, 2009; June 1, 2015. Published September 2009; June 2015. Originally approved in 1995. Last previous edition approved in 2004 as C1318 – 95 (2009)^{ε1} (2001). DOI: 10.1520/C1318-95R09E01; 10.1520/C1318-15.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

5. Significance and Use

5.1 There are existing lime-based flue gas desulfurization units in operation that require a method to measure the oxides available for sulfur dioxide absorption. Dissolved magnesium oxide varies among limes depending on the limestone sources and calcination conditions.

6. Interferences

6.1 Any substance reacting with acid under the conditions of the test will contribute to the total oxide and dissolved oxide values.

6.2 Magnesium in forms other than MgO, which dissolve under test conditions, may affect the dissolved MgO and total oxide value.

7. Apparatus

7.1 *Digital Readout pH Meter*, with combination electrode readable to 0.01 pH units, or an autotitrator with an automatic temperature compensator capable of titrating to a preset endpoint (**Note 1**).

NOTE 1—Use of an automatic titrator is recommended.

7.2 *Stirrers and Stir Bars*.

7.3 *Inductively Coupled Plasma Spectrometer or Atomic Absorption Spectrometer*, if not using EDTA titration.

7.4 *Filtering Funnel*, Type AE glass fiber paper, volumetric flasks (size as needed), 500 mL volumetric flasks, and various Class A pipettes.

8. Reagents

8.1 *1.0 Normal Hydrochloric Acid*, standardize using procedures in the section on Available Lime Index in Test Methods **C25**, Section 28.

8.2 *Deionized or Distilled Water*, CO₂ free.

8.3 *Calcium and Magnesium Standard Solutions* (commercially available or use methods in the procedures in the section on Calcium and Magnesium Oxide (Alternative EDTA Titration Method) in Test Methods **C25**, Section 31).

8.4 *EDTA Standard Solution (0.4 %)*, standardize according to Test Methods the procedure **C25**, Section 31.5, Standardization of EDTA in the section on Calcium and Magnesium Oxide (Alternative EDTA Titration Method) in Test Methods **C25**.

9. Sample Preparation

9.1 The sampling and grinding of any lime sample shall be carried out as rapidly as possible, so that the absorption of moisture and carbon dioxide is held to a minimum.

9.2 The sample as received at the laboratory shall be thoroughly mixed and a representative sample with minimum weight of 100 g shall be taken and pulverized to pass a ~~No. 50 mesh~~ 300 μm (No. 50) sieve for analysis. Conduct the sieve analysis in accordance with Test Methods **C110**.

9.3 The prepared sample shall be stored in a tightly capped container.

10. Procedure

10.1 *Slaking of Lime Sample:*

10.1.1 Weigh rapidly 1.402 g of the finely pulverized sample and brush carefully into a 250 mL Erlenmeyer flask containing about 50 mL of CO₂ free deionized or distilled water and immediately stopper the flask.

10.1.2 Remove the stopper. Swirl the flask, place on a hot plate and boil actively 1 min for complete slaking. Remove from the hot plate, stopper the flask loosely and place in a cold-water bath to cool to room temperature.

10.2 *Titration of Sample:*

10.2.1 Set the pH electrode, burette tip, and temperature sensing device in place, while maintaining agitation.

10.2.2 Begin the titration by adding standard 1.0 normal hydrochloric acid solution. Titrate to and maintain a pH of 6 within 0.4 pH units for 30 min (**Note 2**). Time begins from initial addition of acid.

NOTE 2—When doing a manual titration, the increment of acid addition may require the use of partial drops (suspend a small amount of titrant on the buret tip and wash into the titration flask with CO₂ free deionized or distilled water) to avoid exceeding the 0.4 unit limit of pH 6.

10.2.3 Record the amount of acid consumed after 30 min.

10.2.4 Filter the solution and rinse the flask thoroughly with CO₂ free deionized or distilled water.

10.2.5 Carefully transfer the solution to an appropriately sized volumetric flask, add approximately 10 mL of 1:1 hydrochloric acid, and dilute to volume.